



Standard Specification for Smooth-Wall Coilable Polyethylene (PE) Conduit (Duct) for Preassembled Wire and Cable¹

This standard is issued under the fixed designation D 3485; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers materials, dimensions, and workmanship, and performance tests for medium-density and high-density smooth-wall coilable polyethylene (PE) conduit (duct) containing electrical wires or cables, or both, preassembled by the manufacturer.

NOTE 1—The end user may elect to assemble the conduit and the wire or cable system in the field.

1.2 The values stated in inch-pound units are the standard, except in cases where SI units are more appropriate. The values in parentheses are for information only.

2. Referenced Documents

2.1 ASTM Standards:

- D 638 Test Method for Tensile Properties of Plastics²
- D 746 Test Method for Brittleness Temperature of Plastics and Elastomers by Impact²
- D 1238 Test Method for Flow Rates of Thermoplastics by Extrusion Plastometer²
- D 1248 Specification for Polyethylene Plastics Molding and Extrusion Materials²
- D 1693 Test Method for Environmental Stress-Cracking of Ethylene Plastics²
- D 2951 Test Method for Resistance of Types III and IV Polyethylene Plastics to Thermal Stress-Cracking³
- D 6070 Test Methods for Physical Properties of Smooth-Wall, Coilable, Polyethylene (PE) Conduit (Duct) for Preassembled Wire and Cable⁴

2.2 Other Document:

National Electrical Code⁵

3. Significance and Use

3.1 PE duct must have smooth surfaces to facilitate the installation and removal of electrical wire and cable. It must be capable of being manufactured and coiled (reeled) in continuous lengths, transported, and subsequently uncoiled for installation or further processing, or both, without affecting its properties or performance.

4. Application and Installation

4.1 PE duct is suitable for underground electrical distribution systems utilizing insulations suitable for use at conductor temperatures not exceeding 90°C (190°F) for normal operation. The minimum recommended installation temperature for the PE duct is -25°C (-13°F), however, depending on the type of wire or cable installed in the duct, a higher installation temperature may be required.

5. Extrusion Compounds

5.1 The PE-extrusion compounds shall be either medium-density Type II, Class C, or high-density Type III, Class C, as described in Specification D 1248, and in addition meet the requirements shown in Table 1. Remove the electrical wires or cables, or both, from the duct before testing.

6. Finished PE Duct

6.1 *Workmanship*—Coilable PE duct shall be free of visible cracks, holes, foreign inclusions, or other physical defects that would detract from its performance. It shall be as uniform as practicable in dimensions, smoothness, density, and other physical properties.

6.2 *Dimensions*—Smooth-wall coilable PE duct shall have the dimensions prescribed in Table 2.

7. Duct Size Selection

7.1 Use this section only as a guide. Actual duct sizes must be agreed to between the seller and the purchaser.

7.1.1 *Percent Fill*—Article 347 (Paragraph 11) of the National Electrical Code limits the maximum percentage fill of electrical duct to the figures shown in Table 3.

7.1.2 *Cross-Sectional Area*—Table 4 gives cross-sectional area for the various duct sizes.

7.1.3 *Calculations of Duct Size*:

¹ This specification is under the jurisdiction of ASTM Committee D-9 on Electrical and Electronic Insulating Materials and is the direct responsibility of Subcommittee D09.18 on Solid Insulations, Non-Metallic Shieldings, and Coverings for Electrical and Telecommunications Wires and Cables.

Current edition approved Jan. 10, 1997. Published February 1998. Originally published as D 3485 – 76. Last previous edition D 3485 – 89.

² *Annual Book of ASTM Standards*, Vol 08.01.

³ *Annual Book of ASTM Standards*, Vol 08.02.

⁴ *Annual Book of ASTM Standards*, Vol 10.02.

⁵ Available from the National Fire Protection Assn., 470 Atlantic Ave., Boston, MA 02210.