



Standard Specification for Track-Resistant Black Crosslinked Polyethylene Insulation for Wire and Cable¹

This standard is issued under the fixed designation D 3555; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers a black track-resistant crosslinked polyethylene insulation, the base polymer which consists substantially of polyethylene or its copolymers. This insulation shall be carbon black pigmented.

1.2 This insulation is suitable for use on wire or in cable used for power transmission in overhead spaced-line service, installed at temperatures above -25° and exposed to sunlight and other atmospheric environments between -55 and $+75^{\circ}\text{C}$.

1.3 Whenever two sets of values are presented, in different units, the values in the first set are the standard, while those in parentheses are for information only.

2. Referenced Documents

2.1 ASTM Standards:

- D 470 Test Methods for Crosslinked Insulations and Jackets for Wire and Cable²
- D 1711 Terminology Relating to Electrical Insulation²
- D 2132 Test Method for Dust-and-Fog Tracking and Erosion Resistance of Electrical Insulating Materials²
- D 2633 Methods of Testing Thermoplastic Insulations and Jackets for Wire and Cable³
- D 2765 Test Methods for Determination of Gel Content and Swell Ratio of Crosslinked Ethylene Plastics⁴

3. Terminology

3.1 *Definitions:* For definitions of terms used in this specification refer to Terminology D 1711.

3.2 *Definition of Term Specific to This Standard:*

3.2.1 *aging, (act of), n*—exposure of materials to air at a temperature of 121°C for 168 h.

4. Physical Properties

4.1 When tested for physical and aging requirements, heat distortion, cold bend, U-bend discharge, surface resistivity, and track resistance in accordance with Test Methods D 470 and for solvent extraction in Test Methods D 2765, the track-resistant black crosslinked polyethylene insulation shall meet the requirements specified in Table 1.

5. Electrical Requirements

5.1 Subject cable specimens to a 5 min ac or dc voltage withstand test at voltages which are based on the nominal thickness of the insulation. Conduct tests in accordance with Methods D 2633 using 125 V/mil (5 kV/mm) for ac tests or 375 V/mil (15 kv/mm) for dc tests.

6. Sampling

6.1 Sample the insulation in accordance with Test Methods D 470 and D 2765.

7. Test Methods

7.1 Test the insulation in accordance with Test Methods D 470, D 2132, and D 2765, modified as noted in Table 1.

8. Keywords

8.1 ac test; cold bend; crosslinked polyethylene; dc test; elongation; environmental cracking; heat distortion. surface resistivity; tensile strength; track-resistant; u-bend discharge

¹ This specification is under the jurisdiction of ASTM Committee D-9 on Electrical and Electronic Insulating Materials and is the direct responsibility of Subcommittee D09.18 on Solid Insulations, Nonmetallic Shieldings, and Coverings for Electrical and Telecommunications Wires and Cables.

Current edition approved Oct. 10, 1998. Published February 1999. Originally published as D 3555 – 77. Last previous edition D 3555 – 93.

² *Annual Book of ASTM Standards*, Vol 10.01.

³ *Annual Book of ASTM Standards*, Vol 10.02.

⁴ *Annual Book of ASTM Standards*, Vol 08.02.