



Standard Specification for Molybdenum Flattened Wire for Electron Tubes ¹

This standard is issued under the fixed designation F 364; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers two types of molybdenum flattened wire up to 0.050 in. (1.27 mm) thick and up to 0.375 in. (9.52 mm) wide, specifically for use in electron tubes. The two grades have UNS numbers R03604 and R03603.

1.2 The values stated in inch-pound units are to be regarded as the standard. The values given in parentheses are for information only.

1.3 The following *safety hazards caveat* pertains only to the test method described in this specification (see 10.2). *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:

- E 18 Test Methods for Rockwell Hardness and Rockwell Superficial Hardness of Metallic Materials ²
- E 315 Test Methods for Chemical Analysis of Molybdenum ³
- E 384 Test Method for Microhardness of Materials ²

3. Classification

3.1 Two types of molybdenum flattened wire are covered by this specification:

3.1.1 *Type I, UNS R03604*—This type shall have the composition limits prescribed in Table 1.

3.1.2 *Type II, UNS R03603*—This type shall be a high-recrystallization-temperature material having the composition limits prescribed in Table 1 and shall be capable of retaining its ductility after firing at a temperature of 2375 ± 25°F (1300 ± 14°C) for at least 20 min.

4. Ordering Information

4.1 Orders for material under this specification shall include the following information:

¹ This specification is under the jurisdiction of ASTM Committee F-1 on Electronics and is the direct responsibility of Subcommittee F01.03 on Metallic Materials.

Current edition approved June 10, 1996. Published August 1996. Originally published as F 364 – 73 T. Last previous edition F 364– 77 (1991).

² *Annual Book of ASTM Standards*, Vol 03.01.

³ *Annual Book of ASTM Standards*, Vol 03.01.

TABLE 1 Chemical Composition

Element	Composition, max, ppm	
	Type I UNS R03604	Type II UNS R03603
Carbon	50	15
Oxygen	80	175
Nitrogen	20	10
Hydrogen	10	10
Aluminum	150	150
Calcium	50	50
Silicon	100	350
Iron	100	100
Tungsten	200	200
Potassium	150	150
Tin	25	25
Other elements, each	50	50
	min % by difference	
Molybdenum	99.90	99.90

- 4.1.1 Quantity of each size,
- 4.1.2 Dimensions or size (see 8.1),
- 4.1.3 Edgewise curvature (camber) if required (see 8.2),
- 4.1.4 Type (see 3.1),
- 4.1.5 Temper (see 7.1), and
- 4.1.6 How furnished (coils, spools, etc.).

5. Materials and Manufacture

5.1 The molybdenum wires covered by this specification shall be made by any appropriate process.

NOTE 1—It has been found that molybdenum wire made by the powder metallurgy process will meet the requirements of this specification.

6. Chemical Composition

6.1 Type I and Type II molybdenum wire shall conform to the chemical compositions prescribed in Table 1.

6.2 The materials shall be analyzed in accordance with Test Methods E 315 or other appropriate ASTM methods when available. Other methods, as mutually agreed upon between seller and purchaser, may be employed.

7. Physical Properties

7.1 *Temper*—Material under this specification shall be supplied in one of the following classifications of temper:

7.1.1 *Hard*—As-rolled, not stress-relieved, suitable for spring applications, or

7.1.2 *Stress-Relieved*—Suitable for bending or winding.

7.2 The hardness test (see 10.1) is to be used as the criterion for identifying hard and stress-relieved materials in accordance with Table 2.