

INTERNATIONAL
STANDARD

ISO
10545-1

First edition
1995-11-15

Ceramic tiles —

Part 1:

Sampling and basis for acceptance

iTeh STANDARD PREVIEW

(standards.iteh.ai)

Carreaux et dalles céramiques —

Partie 1: Échantillonnage et conditions de réception

<https://standards.iteh.ai/catalog/standards/sist/e0b0919f-7146-4a6b-83ae-b0c4e7a380c4/iso-10545-1-1995>



Reference number
ISO 10545-1:1995(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

International Standard ISO 10545-1 was prepared by Technical Committee ISO/TC 189, *Ceramic tile*.

ISO 10545 consists of the following parts, under the general title *Ceramic tiles*:

- *Part 1: Sampling and basis for acceptance*
- *Part 2: Determination of dimensions and surface quality*
- *Part 3: Determination of water absorption, apparent porosity, apparent relative density and bulk density*
- *Part 4: Determination of modulus of rupture and breaking strength*
- *Part 5: Determination of impact resistance by measurement of coefficient of restitution*
- *Part 6: Determination of resistance to deep abrasion for unglazed tiles*
- *Part 7: Determination of resistance to surface abrasion for glazed tiles*
- *Part 8: Determination of linear thermal expansion*

© ISO 1995

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

International Organization for Standardization
Case Postale 56 • CH-1211 Genève 20 • Switzerland

Printed in Switzerland

- *Part 9: Determination of resistance to thermal shock*
- *Part 10: Determination of moisture expansion*
- *Part 11: Determination of crazing resistance for glazed tiles*
- *Part 12: Determination of frost resistance*
- *Part 13: Determination of chemical resistance*
- *Part 14: Determination of resistance to stains*
- *Part 15: Determination of lead and cadmium given off by glazed tiles*
- *Part 16: Determination of small colour differences*
- *Part 17: Determination of coefficient of friction*

iTeh STANDARD PREVIEW **(standards.iteh.ai)**

[ISO 10545-1:1995](https://standards.iteh.ai/catalog/standards/sist/e0b0919f-7146-4a6b-83ae-b0c4e7a380c4/iso-10545-1-1995)

<https://standards.iteh.ai/catalog/standards/sist/e0b0919f-7146-4a6b-83ae-b0c4e7a380c4/iso-10545-1-1995>

iTeh STANDARD PREVIEW
This page intentionally left blank
(standards.iteh.ai)

[ISO 10545-1:1995](https://standards.iteh.ai/catalog/standards/sist/e0b0919f-7146-4a6b-83ae-b0c4e7a380c4/iso-10545-1-1995)

<https://standards.iteh.ai/catalog/standards/sist/e0b0919f-7146-4a6b-83ae-b0c4e7a380c4/iso-10545-1-1995>

Ceramic tiles —

Part 1: Sampling and basis for acceptance

1 Scope

This part of ISO 10545 specifies rules for batching, sampling, inspection and acceptance/rejection of ceramic tiles.

2 Definitions

For the purposes of this part of ISO 10545, the following definitions apply.

2.1 order: Quantity of tiles ordered at one time. An order may consist of one or more consignments.

2.2 consignment: Quantity of tiles delivered during a period of 2 days.

2.3 homogeneous (sub)consignment: (Sub) consignment that consists of tiles from one manufacturer, produced under conditions and with properties that are presumed uniform.

2.4 inspection lot: Quantity of tiles submitted for inspection manufactured by one manufacturer under conditions and with properties that are presumed uniform.

2.5 sample: Specified number of tiles taken from an inspection lot.

2.6 sample size: Number of tiles to be tested for each property.

2.7 requirement: Required characteristic as specified for the property in the relevant product standard.

2.8 non-conforming unit: Tile that does not meet the requirement for the property concerned.

3 Principle

This part of ISO 10545 provides for a sampling inspection system with a double sampling plan, partly for the method of inspection by attributes (individual values) and partly for a method of inspection by average values (variables).

The number of tiles to be tested varies for each property (see table 1).

4 Constitution of inspection lots

An inspection lot may consist of one or more homogeneous consignments or subconsignments.

Any consignment which is not homogeneous shall be divided into subconsignments which are assumed to be homogeneous and which may then constitute inspection lots.

If non-homogeneity is not relevant to the properties to be tested, by agreement between the supplier and consumer, the consignment can be treated as homogeneous.

NOTE 1 For example, a consignment of tiles, of the same type with different glazes, can be homogeneous with regard to dimensions and water absorption and non-homogeneous with regard to surface quality. In the same way, accessories which differ only in shape from the remaining tiles in the sample may be considered homogeneous with respect to the other properties.

5 Extent of the inspection

The choice of properties to be considered for inspection shall be subject to agreement between the

iTeh STANDARD PREVIEW
(standards.iteh.ai)

<https://standards.iteh.ai/catalog/standards/sist/e0b0919f-7146-4a6b-83ac-b0e477280410/iso-10545-1-1995>

supplier and consumer and may depend on the size of the inspection lot.

NOTE 2 In principle, a complete range of tests shall only be executed for inspection lots of more than 5 000 m² of tiles. Testing is usually not considered to be necessary for inspection lots of less than 1 000 m² of tiles.

The number of inspection lots to be drawn for testing shall be subject to agreement between the parties concerned.

6 Sampling

6.1 The sampling location shall be subject to agreement between the supplier and consumer.

6.2 One or more representatives of each party concerned may be present at the time the sample is taken.

Samples shall be taken at random from the inspection lot.

Two samples shall be taken. It may not be necessary to test the second sample.

Each sample shall be packed separately and shall be sealed and marked as agreed by the parties concerned.

6.3 For each property, the number of tiles to be tested is indicated as "sample size" in column 2 of table 1.

7 Inspection

7.1 The tiles in the sample shall be tested according to the test methods specified in the relevant product standards.

7.2 The test results shall be evaluated according to clause 8.

8 Determination of acceptability of inspection lots

8.1 Inspection by attributes

8.1.1 When the number of non-conforming units found in the initial sample is less than or equal to the acceptance number Ac_1 indicated in column 3 of table 1, the inspection lot from which the sample was drawn shall be considered acceptable.

8.1.2 When the number of non-conforming units found in the initial sample is greater than or equal to the rejection number Re_1 indicated in column 4 of table 1, this justifies rejection of the inspection lot.

8.1.3 When the number of non-conforming units found in the initial sample lies between the acceptance number and the rejection number (columns 3 and 4 of table 1), a second sample of the same size as the initial sample shall be taken and tested.

8.1.4 The number of non-conforming units found in the initial and second samples shall be totalled.

8.1.5 If the total number of non-conforming units is less than or equal to the acceptance number Ac_2 indicated in column 5 of table 1, the inspection lot shall be considered acceptable.

8.1.6 If the total number of non-conforming units is greater than or equal to the second rejection number Re_2 indicated in column 6 of table 1, this justifies rejection of the inspection lot.

8.1.7 When the relevant product standard calls for more than one property to be tested, the second sample taken (see 8.1.3) shall only be inspected in accordance with those tests which, at the time of inspection of the initial sample, gave numbers of non-conforming units between the acceptance number Ac_1 and the rejection number Re_1 .

8.2 Inspection by the average value

8.2.1 If the average value (\bar{x}_1) of the test results of the initial sample meets the requirements, the inspection lot shall be considered acceptable (column 7 of table 1).

8.2.2 If the average value \bar{x}_1 does not meet the requirements, a second sample of the same size as the initial sample shall be taken (column 8 of table 1).

8.2.3 If the average value (\bar{x}_2) of the test results of the combined initial and second samples meets the requirements, the inspection lot shall be considered acceptable (column 9 of table 1).

8.2.4 If the average value \bar{x}_2 does not meet the requirements, this justifies rejection of the inspection lot (column 10 of table 1).

9 Acceptance report

The acceptance report shall include the following information:

- a) reference to this part of ISO 10545;
- b) a description of the tiles;
- c) the sampling procedure;
- d) the constitution of the inspection lot;
- e) the determination of acceptability for each of the properties tested.

iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 10545-1:1995

<https://standards.iteh.ai/catalog/standards/sist/e0b0919f-7146-4a6b-83ae-b0c4e7a380c4/iso-10545-1-1995>

Table 1 — Sampling procedure

1 Properties	2 Sample size		3 Inspection by attribute, if required				4 Inspection by average value, if required				10 Rejection justified if	11 Test method
			Initial sample		Initial + second sample		Initial sample		Initial + second sample			
			Acceptance number Ac ₁	Rejection number Re ₁	Acceptance number Ac ₂	Rejection number Re ₂	Acceptable if	Second sample to be drawn if	Acceptable if	Rejection justified if		
Dimensions ¹⁾	10	10	0	2	1	2	—	—	—	—	2	
Surface quality ²⁾	30	30	1	3	3	4	—	—	—	—	—	
	40	40	1	4	4	5	—	—	—	—	—	
	50	50	2	5	5	6	—	—	—	—	—	
	60	60	2	5	6	7	—	—	—	—	—	
	70	70	3	6	6	8	—	—	—	—	2	
	80	80	3	7	8	9	—	—	—	—	—	
	90	90	4	8	9	10	—	—	—	—	—	
	100	100	4	9	10	11	—	—	—	—	—	
	1 m ²	1 m ²	4	9	5	> 5 %	—	—	—	—	—	
Water absorption ³⁾	5 4)	5 4)	0	2	1	2	$\bar{x}_1 > L 5)$ $\bar{x}_1 < U 6)$	$\bar{x}_2 > L$ $\bar{x}_2 < U$	$\bar{x}_2 < L$ $\bar{x}_2 > U$	3		
Modulus of rupture ³⁾	7 7)	7 7)	0	2	1	2	$\bar{x}_1 > L$	$\bar{x}_1 < L$	$\bar{x}_2 < L$	4		
Breaking strength ³⁾	7 7)	7 7)	0	2	1	2	$\bar{x}_1 > L$	$\bar{x}_1 < L$	$\bar{x}_2 < L$	4		
Deep abrasion UGL	5	5	0	2 8)	1 8)	2 8)	—	—	—	6		
Coefficient of linear thermal expansion	2	2	0	2 9)	1 9)	2 9)	—	—	—	8		
Crazing resistance	5	5	0	2	1	2	—	—	—	11		
Chemical resistance ¹⁰⁾	5	5	0	2	1	2	—	—	—	13		
Stain resistance ¹⁰⁾	5	5	0	2	1	2	—	—	—	14		
Frost resistance ¹¹⁾	10	—	0	1	—	—	—	—	—	12		
Thermal shock resistance	5	5	0	2	1	2	—	—	—	9		
Moisture expansion	5	—	—	—	—	—	Attribution by manufacturer's declaration				10	
Resistance to abrasion G11)	11	—	—	—	—	—	Attribution by manufacturer's declaration				7	
Coefficient of friction	—12)	—	—	—	—	—	Attribution by manufacturer's declaration				17	
Colour differences	5	—	—	—	—	—	Attribution by manufacturer's declaration				16	
Impact resistance	5	—	—	—	—	—	Attribution by manufacturer's declaration				5	
Lead and cadmium release	5	—	—	—	—	—	Attribution by manufacturer's declaration				15	

- 1) Only for tiles with individual areas $\geq 4 \text{ cm}^2$.
- 2) At least 1 m^2 with a minimum of 30 tiles. Whatever the number of tiles in 1 m^2 , the test sample should be rounded to the nearest 10 tiles above. Conformity to acceptable quality level (AQL) 2,5 % in accordance with ISO 2859-1:1989, *Sampling procedures for inspection by attributes — Part 1: Sampling plans indexed by acceptable quality level (AQL) for lot-by-lot inspection* or ISO 3951:1989, *Sampling procedures and charts for inspection by variables for percent nonconforming* is an acceptable alternative to the procedure in table 1.
- 3) The sample size depends on the size of the tile.
- 4) Only for tiles with individual surface areas $\geq 0,04 \text{ m}^2$. In the case of tiles with a mass $< 50 \text{ g}$, a sufficient number shall be taken so as to form five test specimens, each weighing between 50 g and 100 g.
- 5) *L*: Lower specification limit.
- 6) *U*: Upper specification limit.
- 7) Only for tiles with lengths $\geq 48 \text{ mm}$.
- 8) Number of measurements.
- 9) Number of test specimens.
- 10) Per test solution.
- 11) There is no double sampling test procedure for these properties.
- 12) The sample size varies with the test method.

iteh STANDARD PREVIEW
(standards.iteh.ai)

<https://standards.iteh.ai/catalog/standards/sist/e0b0919f-7146-4a6b-83ac-b0c4e7a380c4/iso-10545-1-1995>

<https://standards.iteh.ai/catalog/standards/sist/e0b0919f-7146-4a6b-83ac-b0c4e7a380c4/iso-10545-1-1995>