



SLOVENSKI STANDARD
SIST EN 23312:2000
01-december-2000

Sintered metal materials and hardmetals - Determination of Young modulus (ISO 3312:1987)

Sintered metal materials and hardmetals - Determination of Young modulus (ISO 3312:1987)

Sintermetall und Hartmetalle - Ermittlung des Elastizitätsmoduls (ISO 3312:1987)

Matériaux métalliques frittés et métaux-durs - Détermination du module de Young (ISO 3312:1987)

iTeh STANDARD PREVIEW
(standards.itteh.ai)

[SIST EN 23312:2000](https://standards.itteh.ai/catalog/standards/sist/24e921bf-31d2-4411-a2bb-a42d1a4496f0/sist-en-23312-2000)

Ta slovenski standard je istoveten z: EN 23312:1993

ICS:

77.040.10	Mehansko preskušanje kovin	Mechanical testing of metals
77.160	Metalurgija prahov	Powder metallurgy

SIST EN 23312:2000

en

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN 23312:2000](#)

<https://standards.iteh.ai/catalog/standards/sist/24e921bf-31d2-4411-a2bb-a42dfa4496f0/sist-en-23312-2000>

EUROPEAN STANDARD

EN 23312:1993

NORME EUROPÉENNE

EUROPÄISCHE NORM

April 1993

UDC 621.762.5:669-492.2:669.018.25:620.1:539.382

Descriptors: Powder metallurgy, sintered products, hard metals, modulus of elasticity, vibration tests

English version

**Sintered metal materials and hardmetals -
Determination of Young modulus
(ISO 3312:1987)**

Matériaux métalliques frittés et métaux-durs -
Détermination du module de Young
(ISO 3312:1987)

Sintermetall und Hartmetalle - Ermittlung des
Elastizitätsmoduls (ISO 3312:1987)

(standards.iteh.ai)

SIST EN 23312:2000

<https://standards.iteh.ai/catalog/standards/sist/24e921bf-31d2-4411-a2bb-a42dfa4496f0/sist-en-23312-2000>

This European Standard was approved by CEN on 1993-04-02. CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

The European Standards exist in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.

CEN

European Committee for Standardization
Comité Européen de Normalisation
Europäisches Komitee für Normung

Central Secretariat: rue de Stassart, 36 B-1050 Brussels

Page 2
EN 23312:1993

Foreword

In 1992 ISO 3312:1987 "Sintered metal materials and hardmetals - Determination of Young modulus" was submitted to the CEN Primary Questionnaire procedure.

Following the positive result of the CEN/CS Proposal ISO 3312:1987 was submitted to the CEN Formal Vote. The result of the Formal Vote was positive.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by October 1993, and conflicting national standards shall be withdrawn at the latest by October 1993.

According to the Internal Regulations of CEN/CENELEC, the following countries are bound to implement this European Standard :

Austria, Belgium, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.

iTeh STANDARD PREVIEW (standards.iteh.ai)

Endorsement notice

SIST EN 23312:2000

The text of the International Standard ISO 3312:1987 was approved by CEN as a European Standard without any modification.

NOTE: The European references to international publications are given in annex ZA (normative).

Annex ZA (normative)
Normative references to international publications
with their relevant European publications

This European Standard incorporates by dated or undated reference, provisions from other publications. These normative references are cited at the appropriate places in the text and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of any of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies (including amendments).

<u>Publication</u>	<u>Year</u>	<u>Title</u>	<u>EN/HD</u>	<u>Year</u>
ISO 2738		Permeable sintered metal materials - Determination of density, oil content and open porosity	-----	----

(standards.iteh.ai)

[SIST EN 23312:2000](https://standards.iteh.ai/catalog/standards/sist/24e921bf-31d2-4411-a2bb-a42dfa4496f0/sist-en-23312-2000)

<https://standards.iteh.ai/catalog/standards/sist/24e921bf-31d2-4411-a2bb-a42dfa4496f0/sist-en-23312-2000>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN 23312:2000](#)

<https://standards.iteh.ai/catalog/standards/sist/24e921bf-31d2-4411-a2bb-a42dfa4496f0/sist-en-23312-2000>

INTERNATIONAL STANDARD

ISO
3312

Second edition
1987-07-15



INTERNATIONAL ORGANIZATION FOR STANDARDIZATION
ORGANISATION INTERNATIONALE DE NORMALISATION
МЕЖДУНАРОДНАЯ ОРГАНИЗАЦИЯ ПО СТАНДАРТИЗАЦИИ

Sintered metal materials and hardmetals — Determination of Young modulus

iTeh STANDARD PREVIEW

Matériaux métalliques frittés et métaux-durs — Détermination du module de Young
(standards.iteh.ai)

SIST EN 23312:2000

<https://standards.iteh.ai/catalog/standards/sist/24e921bf-31d2-4411-a2bb-a42dfa4496f0/sist-en-23312-2000>

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work.

Draft International Standards adopted by the technical committees are circulated to the member bodies for approval before their acceptance as International Standards by the ISO Council. They are approved in accordance with ISO procedures requiring at least 75 % approval by the member bodies voting.

International Standard ISO 3312 was prepared by Technical Committee ISO/TC 119, *Powder metallurgy*.

This second edition cancels and replaces the first edition (ISO 3312:1975), of which it constitutes a minor revision.

Users should note that all International Standards undergo revision from time to time and that any reference made herein to any other International Standard implies its latest edition, unless otherwise stated.

Sintered metal materials and hardmetals — Determination of Young modulus

1 Scope and field of application

This International Standard specifies a method for the determination of the dynamic (adiabatic) Young modulus by longitudinal oscillations of sintered metal materials and hardmetals.

2 Reference

ISO 2738, *Permeable sintered metal materials — Determination of density, oil content and open porosity.*

3 Principle

Excitation of ultrasonic longitudinal oscillations in a test piece and determination of the resonance frequency of its natural oscillations.

4 Symbols and units

Symbol	Designation	Unit
L	Length of test piece	mm
ρ	Density	g/cm ³
f	Frequency of natural oscillations	Hz
E	Young modulus	N/mm ²

5 Apparatus

5.1 Fixture, for mounting test piece.

5.2 Ultrasonic oscillator, having a continuous control of frequencies in the range from 20 to 100 kHz.

5.3 Device, for determining resonance frequency.

6 Preparation of test pieces

6.1 The test pieces shall be at least 60 mm long and may have either a round or a rectangular cross-section. The test piece with round cross-section shall be $6 \pm 0,2$ mm in diameter. The cross-section of the rectangular test piece shall be $(6 \pm 0,2)$ mm \times $(8 \pm 0,2)$ mm.

6.2 The surface layer shall be removed to a depth of at least 0,1 mm. The surface roughness shall be $R_a < 1,25$ μ m.

6.3 The ends of the test piece shall be ground and shall be parallel to within 0,02 mm.

6.4 The test piece shall be free of surface cracks or other structural defects and shall be cleaned immediately before being tested.

7 Procedure

7.1 Determine the density of the test piece to the nearest 0,01 g/cm³ according to ISO 2738.

7.2 Measure the length of the test piece to the nearest 0,1 mm.

7.3 Mount the test piece in the apparatus. Smoothly increase the frequency of the oscillator until the lowest frequency of the natural longitudinal oscillations of the test piece is obtained. Determine the resonance frequency to the nearest 50 Hz.

8 Expression of results

8.1 Young modulus is given by the following equation:

$$E = 4 \times 10^{-9} \times L^2 \times \rho \times f^2$$

8.2 Report the result rounded to the nearest 5×10^3 N/mm².