

---

**Metallic powders - Determination of acid insoluble content in iron, copper, tin and bronze powders (ISO 4496:1978)**

Metallic powders - Determination of acid insoluble content in iron, copper, tin and bronze powders (ISO 4496:1978)

Metallpulver - Bestimmung der säureunlöslichen Bestandteile in Eisen-, Kupfer-, Zinn- und Bronzepulvern (ISO 4496:1978)

Poudres métalliques - Détermination de la teneur en insolubles dans les acides pour les poudres de fer, de cuivre, d'étain et de bronze (ISO 4496:1978)

[https://standards.iteh.ai/catalog/standards/sist/cc64a95f-ce4b-475a-ab60-](https://standards.iteh.ai/catalog/standards/sist/cc64a95f-ce4b-475a-ab60-b68d97a6e526/sist-en-24496-2000)

**Ta slovenski standard je istoveten z: EN 24496:1993**

---

**ICS:**

77.160            Metalurgija prahov            Powder metallurgy

**SIST EN 24496:2000**            **en**

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

SIST EN 24496:2000

<https://standards.iteh.ai/catalog/standards/sist/cc64a95f-ce4b-475a-ab60-b68d97a6e526/sist-en-24496-2000>

EUROPEAN STANDARD

EN 24496:1993

NORME EUROPÉENNE

EUROPÄISCHE NORM

April 1993

UDC 621.762:669-492.2:620.1:543.726

Descriptors: Powder metallurgy, metallic powder, iron, copper, tin, bronzes, chemical analysis, determination of content, acids, insoluble matter

English version

**Metallic powders - Determination of acid insoluble  
content in iron, copper, tin and bronze powders  
(ISO 4496:1978)**

**ITeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

Poudres métalliques - Détermination de la teneur en insolubles dans les acides pour les poudres de fer, de cuivre, d'étain et de bronze (ISO 4496:1978)

Metallpulver - Bestimmung der säureunlöslichen Bestandteile in Eisen-, Kupfer-, Zinn- und Bronzepulvern (ISO 4496:1978)

[SIST EN 24496:2000](https://standards.iteh.ai/catalog/standards/sist/cc64a95f-ce4b-475a-ab60-b68d97a6e526/sist-en-24496-2000)

<https://standards.iteh.ai/catalog/standards/sist/cc64a95f-ce4b-475a-ab60-b68d97a6e526/sist-en-24496-2000>

This European Standard was approved by CEN on 1993-04-02. CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

The European Standards exist in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.

**CEN**

European Committee for Standardization  
Comité Européen de Normalisation  
Europäisches Komitee für Normung

Central Secretariat: rue de Stassart, 36 B-1050 Brussels

## Foreword

In 1992 ISO 4496:1978 "Metallic powders - Determination of acid insoluble content in iron, copper, tin and bronze powders" was submitted to the CEN Primary Questionnaire procedure.

Following the positive result of the CEN/CS Proposal ISO 4496:1978 was submitted to the CEN Formal Vote. The result of the Formal Vote was positive.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by October 1993, and conflicting national standards shall be withdrawn at the latest by October 1993.

According to the Internal Regulations of CEN/CENELEC, the following countries are bound to implement this European Standard :

Austria, Belgium, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.

## iTeh STANDARD PREVIEW (standards.iteh.ai)

### Endorsement notice

[SIST EN 24496:2000](https://standards.iteh.ai/standards/ISO/4496:1978/CEN/25F/1993/EN/24496:1993)

The text of the International Standard ISO 4496:1978 was approved by CEN as a European Standard without any modification.

---

**INTERNATIONAL STANDARD****4496**

---

INTERNATIONAL ORGANIZATION FOR STANDARDIZATION • МЕЖДУНАРОДНАЯ ОРГАНИЗАЦИЯ ПО СТАНДАРТИЗАЦИИ • ORGANISATION INTERNATIONALE DE NORMALISATION

---

## **Metallic powders — Determination of acid-insoluble content in iron, copper, tin and bronze powders**

*Poudres métalliques — Détermination de la teneur en insolubles dans les acides pour les poudres de fer,  
de cuivre, d'étain et de bronze*

**iTeh STANDARD PREVIEW**

First edition — 1978-08-01

**(standards.iteh.ai)**

[SIST EN 24496:2000](https://standards.iteh.ai/catalog/standards/sist/cc64a95f-ce4b-475a-ab60-b68d97a6e526/sist-en-24496-2000)

[https://standards.iteh.ai/catalog/standards/sist/cc64a95f-ce4b-475a-ab60-  
b68d97a6e526/sist-en-24496-2000](https://standards.iteh.ai/catalog/standards/sist/cc64a95f-ce4b-475a-ab60-b68d97a6e526/sist-en-24496-2000)

---

UDC 621.762 : 669-492.2 : 543.726

Ref. No. ISO 4496-1978 (E)

**Descriptors** : metallic powder, iron, copper, tin, bronzes, chemical analysis, determination of content, insoluble matter, acids.

**FOREWORD**

ISO (the International Organization for Standardization) is a worldwide federation of national standards institutes (ISO member bodies). The work of developing International Standards is carried out through ISO technical committees. Every member body interested in a subject for which a technical committee has been set up has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work.

Draft International Standards adopted by the technical committees are circulated to the member bodies for approval before their acceptance as International Standards by the ISO Council.

International Standard ISO 4496 was developed by Technical Committee ISO/TC 119, *Powder metallurgical materials and products*, and was circulated to the member bodies in June 1977.

**(standards.iteh.ai)**

It has been approved by the member bodies of the following countries :

Australia	Germany	Sweden
Austria	Italy	Turkey
Bulgaria	Mexico	United Kingdom
Canada	Poland	U.S.A.
Chile	Portugal	U.S.S.R.
Czechoslovakia	Romania	Yugoslavia
Egypt, Arab Rep. of	South Africa, Rep. of	
France	Spain	

No member body expressed disapproval of the document.

# Metallic powders – Determination of acid-insoluble content in iron, copper, tin and bronze powders

## 1 SCOPE

This International Standard specifies methods for determining, in iron, copper, tin and bronze powders, the approximate content of non-metallic materials which are insoluble in the ordinary mineral acids.

The insoluble matter referred to is generally considered to be acid-insoluble silica and silicates, carbides, alumina, clays or other refractory oxides which are either present in the raw material from which the powders are manufactured or introduced during the manufacturing process.

## 2 FIELD OF APPLICATION

The methods are applicable to lubricant-free metallic powders of iron, copper, tin, alloy bronze and elemental mixtures of copper and tin.

## 3 REAGENTS

During the analysis, use only reagents of recognized analytical grade, and only distilled water or water of equivalent purity.

See the table for the reagents required.

## 4 APPARATUS

Ordinary laboratory apparatus and

**4.1 Laboratory balance** of sufficient capacity and capable of weighing to an accuracy of  $\pm 0,000$  1 g.

**4.2 Glass filter funnel**, diameter approximately 70 mm.

**4.3 Filter paper** for medium precipitates, diameter approximately 110 mm.

**4.4 Furnace**, capable of operating between 900 and 1 000 °C.

**4.5 Fused silica or porcelain crucibles**, pretreated to constant mass at 900 to 1 000 °C and stored in a desiccator.

## 5 SAMPLING

**5.1** Determine the content of insoluble matter on two test portions.

**5.2** The mass of the test portion shall be approximately 5 g.

Type of powder	Reagent	Density, $\rho$ g/ml	Concentration of solution
Iron	Hydrochloric acid (3.1)	1,19	1 + 1
	Hydrochloric acid (3.2)	1,19	1 + 25
	Potassium thiocyanate (3.3)		5 %
	Nitric acid (3.4)	1,42	concentrated
Copper Tin Bronze	Hydrochloric acid (3.5)	1,19	concentrated
	Nitric acid (3.6)	1,42	1 + 1
	Hydrogen peroxide (3.7)		30 %
	Ammonium acetate (3.8)		200 g/l
Copper Bronze	Sodium diethyldithiocarbamate (3.9)		4 %
Tin	Sodium sulphide (3.10)		
	Hydrogen sulphide (3.11)		

## ISO 4496-1978 (E)

## 6 PROCEDURE

## 6.1 Iron powder

**6.1.1** Weigh, to the nearest 0,000 1 g, a test portion of approximately 5 g of the test sample (mass  $m_1$ ) and transfer it to a glass beaker.

**6.1.2** Carefully add 100 ml of hydrochloric acid (3.1) and cover the beaker with a watch glass. Allow the solution to stand at room temperature until the reaction is completed (no further evolution of hydrogen).

NOTE — If it is desired to exclude carbides as a part of the insoluble matter, add 20 ml of nitric acid (3.4) to the hydrochloric acid (3.1) used according to 6.1.2. Then proceed according to 6.1.3 to 6.1.6.

**6.1.3** Place the glass beaker on a hot-plate and heat the solution to boiling. Maintain boiling for about 1 min. Then add 150 ml of water, reheat to boiling and maintain for about 1 min. Allow the solution to cool and settle for 5 min.

**6.1.4** Filter the solution through the medium filter paper and wash the residue alternately with hot water and hot hydrochloric acid (3.2). Repeat the washing until iron salts cannot be detected in the washing water, for example by means of potassium thiocyanate (3.3).

**6.1.5** Weigh a crucible to the nearest 0,000 1 g (mass  $m_2$ ) and place in it the filter paper with the residue. Place the crucible on a hot-plate to dry and char the paper. Heat in the furnace at a temperature between 900 and 1 000 °C until the difference between two consecutive weighings of the crucible with the residue after cooling is not greater than 0,000 1 g. Allow the crucible to cool completely in a desiccator.

**6.1.6** Determine the mass of the crucible with the residue to the nearest 0,000 1 g (mass  $m_3$ ).

## 6.2 Tin, copper and bronze powders

**6.2.1** Weigh, to the nearest 0,000 1 g, a test portion of approximately 5 g of the test sample (mass  $m_1$ ) and transfer it to a glass beaker.

**6.2.2** Carefully add 50 ml of hydrochloric acid (3.5), cover with a watch glass, place on the edge of a hot-plate and digest at low temperature for a minimum of 30 min.

**6.2.3** Remove the beaker, cool slightly, cautiously add 50 ml of nitric acid (3.6) and wait for the initial reaction, which starts after about 10 min. After the reaction is completed, add a further 50 ml of nitric acid (3.6).

**6.2.4** Place the beaker on a hot-plate and heat the solution to boiling. Maintain boiling until the volume is reduced to one-half.

NOTE — If the residue is black, remove the beaker from the hot-

plate, cautiously add a few millilitres of hydrogen peroxide (3.7), and boil for 2 min. Repeat the treatment with hydrogen peroxide (3.7) until no black residue is left.

**6.2.5** Slowly add 50 ml of hot water and reheat to boiling. Maintain boiling for about 1 min. Allow the solution to cool and settle for 5 min.

**6.2.6** Filter the solution through a medium filter paper and wash the residue first with hot hydrochloric acid (3.5) and finally with hot water. Repeat the washing with water until

— in the case of copper and bronze powders, copper salts in the washing water cannot be detected, for example by sodium diethyldithiocarbamate (3.9);

— in the case of tin powder, tin salts in the washing water cannot be detected, for example by sodium sulphide (3.10) or hydrogen sulphide (3.11).

NOTE — If the presence of lead sulphate is suspected, wash once or twice with a hot solution of ammonium acetate (3.8) and then with water.

**6.2.7** Weigh a crucible to the nearest 0,000 1 g (mass  $m_2$ ) and in it place the filter paper with the residue. Place the crucible on a hot-plate to dry and char the paper. Heat in the furnace at a temperature between 900 and 1 000 °C until the difference between two consecutive weighings of the crucible with the residue after cooling is not greater than 0,000 1 g. Allow the crucible to cool completely in a desiccator.

**6.2.8** Determine the mass of the crucible with the residue to the nearest 0,000 1 g (mass  $m_3$ ).

## 7 EXPRESSION OF RESULTS

**7.1** The acid-insoluble content, AIC, expressed as a percentage by mass, is given by the formula

$$\text{AIC} = \frac{m_3 - m_2}{m_1} \times 100$$

where

$m_1$  is the mass, in grams, of the test portion;

$m_2$  is the mass, in grams, of the dry, pretreated empty crucible;

$m_3$  is the mass, in grams, of the crucible with the residue.

**7.2** Calculate the result of each determination to the nearest 0,01 %.

**7.3** The maximum permissible difference between the two determinations shall not exceed 10 % of the mean value or 0,02 % in absolute value, whichever is greater.