Standard Specification for Wrought 18 Chromium-14 Nickel-2.5 Molybdenum Stainless Steel Surgical Fixation Wire (UNS S31673)¹

This standard is issued under the fixed designation F 1350; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

- 1.1 This specification covers the requirements for the manufacture of stainless steel surgical fixation wire.
- 1.2 The values stated in metric units are to be regarded as standard. The inch-pound equivalents may be approximate.

2. Referenced Documents

- 2.1 ASTM Standards:
- A 262 Practices for Detecting Susceptibility to Intergranular Attack in Austenitic Stainless Steels²
- A 370 Test Methods and Definitions for Mechanical Testing of Steel Products²
- A 555 Specification for General Requirements for Stainless and Heat-Resisting Steel Wire and Wire Rods²
- E 45 Practice for Determining the Inclusion Content of Steel³
- F 86 Practice for Surface Preparation and Marking of Metallic Surgical Implants⁴
- F 138 Specification for Stainless Steel Bar and Wire for Surgical Implants (Special Quality)⁴
- 2.2 USP Standards:

Nonabsorbable Surgical Suture, U.S. Pharmacopoeia

3. Materials and Manufacture

- 3.1 Surgical fixation wire shall conform to the specified chemical composition of Specification F 138, Grade 2 material. Conformance with this specification shall be so identified by suitable packaging or labeling, or both.
- 3.2 The microcleanliness of the steel as determined by Practice E 45, Method A shall conform to Specification F 138. Microcleanliness conformance shall be stated on the material certification.
- 3.3 The steel shall be capable of passing the intergranular corrosion susceptibility test in accordance with Practices A 262, Practice E as specified in Specification F 138. Conform-

ance shall be stated on material certification.

3.4 Surgical fixation wire shall be furnished in the bright annealed condition and finish.

4. Mechanical Properties

- 4.1 Surgical fixation wire shall conform to the appropriate mechanical properties specified in Table 1.
- 4.2 Mechanical testing shall be performed in accordance with Methods A 370 using a 254 mm (10 inch) gage length and cross-head speed of 254 mm/min (10 inches/min).
- 4.3 The wire shall meet the requirements of USP for Nonabsorbable Surgical Sutures, (latest revision) when tested in accordance with 4.2.

5. Dimensional Requirements

5.1 Surgical fixation wire shall be fabricated in accordance with the dimensions and tolerances specified in Table 1.

6. Surface Condition and Handling

- 6.1 The surface of surgical fixation wire conforming to this specification shall be free of imperfections such as toolmarks, nicks, scratches, cracks, cavities, spurs, and other defects that would impair the serviceability of the wire. The surface shall be free of embedded or deposited finishing materials and other undesirable contaminants.
- 6.2 The wire may be subjected to a passivation process if requested by the customer. Such passivation process shall be performed in accordance with Practice F 86.
- 6.3 Surgical fixation wire shall be handled with care and packaged adequately to prevent damage and contamination of the surface.

7. General Requirements

- 7.1 In addition to the requirements of this specification, all requirements of the current editions of Specifications A 555 and F 138 shall apply.
- 7.2 In cases of conflict between this specification and those listed in 2.1, this specification shall take precedence.

8. Keywords

8.1 fixation; mechanical properties; stainless steel; surgical implant; suture; tolerances; wire

¹ This specification is under the jurisdiction of ASTM Committee F04 on Medical and Surgical Materials and Devicesand is the direct responsibility of Subcommittee F04.21 on Osteosynthesis.

Current edition approved April 10, 1996. Published June 1996. Originally published as F1350-91. Last previous edition F1350-91.

² Annual Book of ASTM Standards, Vol 01.03.

³ Annual Book of ASTM Standards, Vol 03.01.

⁴ Annual Book of ASTM Standards, Vol 13.01.