

INTERNATIONAL STANDARD

NORME INTERNATIONALE

Electrical insulating materials – Thermal endurance properties –
Part 8: Instructions for calculating thermal endurance characteristics using
simplified procedures

Matériaux isolants électriques – Propriétés d'endurance thermique –
Partie 8: Instructions pour le calcul des caractéristiques d'endurance thermique
en utilisant des procédures simplifiées



THIS PUBLICATION IS COPYRIGHT PROTECTED

Copyright © 2013 IEC, Geneva, Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester.

If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

Droits de reproduction réservés. Sauf indication contraire, aucune partie de cette publication ne peut être reproduite ni utilisée sous quelque forme que ce soit et par aucun procédé, électronique ou mécanique, y compris la photocopie et les microfilms, sans l'accord écrit de la CEI ou du Comité national de la CEI du pays du demandeur.

Si vous avez des questions sur le copyright de la CEI ou si vous désirez obtenir des droits supplémentaires sur cette publication, utilisez les coordonnées ci-après ou contactez le Comité national de la CEI de votre pays de résidence.

IEC Central Office
3, rue de Varembe
CH-1211 Geneva 20
Switzerland

Tel.: +41 22 919 02 11
Fax: +41 22 919 03 00
info@iec.ch
www.iec.ch

About the IEC

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

About IEC publications

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigenda or an amendment might have been published.

Useful links:

IEC publications search - www.iec.ch/searchpub

The advanced search enables you to find IEC publications by a variety of criteria (reference number, text, technical committee,...).

It also gives information on projects, replaced and withdrawn publications.

IEC Just Published - webstore.iec.ch/justpublished

Stay up to date on all new IEC publications. Just Published details all new publications released. Available on-line and also once a month by email.

Electropedia - www.electropedia.org

The world's leading online dictionary of electronic and electrical terms containing more than 30 000 terms and definitions in English and French, with equivalent terms in additional languages. Also known as the International Electrotechnical Vocabulary (IEV) on-line.

Customer Service Centre - webstore.iec.ch/csc

If you wish to give us your feedback on this publication or need further assistance, please contact the Customer Service Centre: csc@iec.ch.

A propos de la CEI

La Commission Electrotechnique Internationale (CEI) est la première organisation mondiale qui élabore et publie des Normes internationales pour tout ce qui a trait à l'électricité, à l'électronique et aux technologies apparentées.

A propos des publications CEI

Le contenu technique des publications de la CEI est constamment revu. Veuillez vous assurer que vous possédez l'édition la plus récente, un corrigendum ou amendement peut avoir été publié.

Liens utiles:

Recherche de publications CEI - www.iec.ch/searchpub

La recherche avancée vous permet de trouver des publications CEI en utilisant différents critères (numéro de référence, texte, comité d'études,...).

Elle donne aussi des informations sur les projets et les publications remplacées ou retirées.

Just Published CEI - webstore.iec.ch/justpublished

Restez informé sur les nouvelles publications de la CEI. Just Published détaille les nouvelles publications parues. Disponible en ligne et aussi une fois par mois par email.

Electropedia - www.electropedia.org

Le premier dictionnaire en ligne au monde de termes électroniques et électriques. Il contient plus de 30 000 termes et définitions en anglais et en français, ainsi que les termes équivalents dans les langues additionnelles. Egalement appelé Vocabulaire Electrotechnique International (VEI) en ligne.

Service Clients - webstore.iec.ch/csc

Si vous désirez nous donner des commentaires sur cette publication ou si vous avez des questions contactez-nous: csc@iec.ch.

INTERNATIONAL STANDARD

NORME INTERNATIONALE

**Electrical insulating materials – Thermal endurance properties –
Part 8: Instructions for calculating thermal endurance characteristics using
simplified procedures**

**Matériaux isolants électriques – Propriétés d'endurance thermique –
Partie 8: Instructions pour le calcul des caractéristiques d'endurance thermique
en utilisant des procédures simplifiées**

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

COMMISSION
ELECTROTECHNIQUE
INTERNATIONALE

PRICE CODE
CODE PRIX

R

ICS 17.220.99; 29.035.01

ISBN 978-2-83220-679-9

**Warning! Make sure that you obtained this publication from an authorized distributor.
Attention! Veuillez vous assurer que vous avez obtenu cette publication via un distributeur agréé.**

CONTENTS

FOREWORD.....	3
INTRODUCTION.....	5
1 Scope.....	6
2 Normative references	6
3 Terms, definitions, symbols and abbreviations.....	7
3.1 Terms and definitions	7
3.2 Symbols and abbreviations.....	8
4 Thermal endurance test procedure	9
4.1 General.....	9
4.2 Number of test specimens	9
4.3 Preparation of test specimens	10
4.4 Preparation of ageing processes	11
5 Simplified numerical and graphical evaluation procedures	12
5.1 Outline description of procedures	12
5.2 Simplified calculation procedures	13
5.2.1 Validity of simplified calculations	13
5.2.2 Times to end-point.....	13
5.2.3 Calculation of the regression line.....	14
5.2.4 Calculation of deviation from linearity	15
5.2.5 Temperature index and halving interval.....	15
5.3 Data rescue.....	16
5.4 Determination of RTI	16
5.5 Test report.....	18
Bibliography.....	19
Figure 1 – Determination of the time to reach the end-point at each temperature – Property variation (according to IEC 60216-1).....	14
Figure 2 – Thermal endurance graph – Temperature index – Halving interval	16
Figure 3 – Thermal endurance graph – Relative temperature index.....	17
Table 1 – Suggested exposure temperatures and times for TI corresponding to 20 000 h	12

INTERNATIONAL ELECTROTECHNICAL COMMISSION

**ELECTRICAL INSULATING MATERIALS –
THERMAL ENDURANCE PROPERTIES –**
**Part 8: Instructions for calculating thermal endurance
characteristics using simplified procedures**

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

International Standard IEC 60216-8 has been prepared by IEC technical committee 112: Evaluation and qualification of electrical insulating materials and systems.

The text of this standard is based on the following documents:

FDIS	Report on voting
112/236/FDIS	112/244/RVD

Full information on the voting for the approval of this standard can be found in the report on voting indicated in the above table.

This publication has been drafted in accordance with the ISO/IEC Directives, Part 2.

A list of all parts in the IEC 60216 series, published under the general title *Electrical insulating materials – Thermal endurance properties*, can be found on the IEC website.

The committee has decided that the contents of this publication will remain unchanged until the stability date indicated on the IEC web site under "http://webstore.iec.ch" in the data related to the specific publication. At this date, the publication will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[IEC 60216-8:2013](https://standards.iteh.ai/catalog/standards/sist/7f96c4c8-fd11-4d1b-b2a0-315c4db15ae0/iec-60216-8-2013)

<https://standards.iteh.ai/catalog/standards/sist/7f96c4c8-fd11-4d1b-b2a0-315c4db15ae0/iec-60216-8-2013>

INTRODUCTION

The designation 'thermal endurance' is used here to refer to the test of thermal stress in air, excluding any other influence or stress applied to the test specimens. Thermal endurance properties evaluated in different environments and/or with different stresses applied to the test specimens require different test procedures.

In this part of IEC 60216, the study of the thermal ageing of materials is based solely on the change in certain properties resulting from a period of exposure to elevated temperature. The properties studied are always measured after the temperature has returned to ambient.

Properties of materials change at various rates on thermal ageing. To enable comparisons to be made of the thermal ageing of different materials, the criteria for judgment depend on the type of property to be studied and its acceptable limiting value.

iTeh STANDARD PREVIEW **(standards.iteh.ai)**

[IEC 60216-8:2013](https://standards.iteh.ai/catalog/standards/sist/7f96c4c8-fd11-4d1b-b2a0-315c4db15ae0/iec-60216-8-2013)

<https://standards.iteh.ai/catalog/standards/sist/7f96c4c8-fd11-4d1b-b2a0-315c4db15ae0/iec-60216-8-2013>

ELECTRICAL INSULATING MATERIALS – THERMAL ENDURANCE PROPERTIES –

Part 8: Instructions for calculating thermal endurance characteristics using simplified procedures

1 Scope

This part of IEC 60216 specifies the general ageing conditions and simplified procedures to be used for deriving thermal endurance characteristics, which are shown by temperature index (TI) and/or relative temperature index (RTI) and the halving interval (HIC).

The procedures specify the principles for evaluating the thermal endurance properties of materials exposed to elevated temperature for long periods.

In the application of this standard, it is assumed that a practically linear relationship exists between the logarithm of the time required to cause the predetermined property change and the reciprocal of the corresponding absolute temperature (Arrhenius relationship).

For the valid application of the standard, no transition, in particular no first-order transition should occur in the temperature range under study.

Throughout the rest of this standard the designation "insulating materials" is always taken to mean "insulating materials and simple combinations of such materials".

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60085, *Electrical insulation – Thermal evaluation and designation*

IEC 60216-1:2013, *Electrical insulating materials – Thermal endurance properties – Part 1: Ageing procedures and evaluation of test results*¹

IEC 60216-2, *Electrical insulating materials - Thermal endurance properties - Part 2: Determination of thermal endurance properties of electrical insulating materials - Choice of test criteria*

IEC 60216-3, *Electrical insulating materials – Thermal endurance properties – Part 3: Instructions for calculating thermal endurance characteristics*

IEC 60216-4-1, *Electrical insulating materials – Thermal endurance properties – Part 4-1: Ageing ovens – Single-chamber ovens*

¹ A sixth edition is due to be published shortly.

IEC 60216-5, *Electrical insulating materials – Thermal endurance properties – Part 5: Determination of relative thermal endurance index (RTE) of an insulating material*

ISO 291, *Plastics – Standard atmospheres for conditioning and testing*

3 Terms, definitions, symbols and abbreviations

For the purposes of this document, the following terms, definitions, symbols and abbreviations apply.

3.1 Terms and definitions

3.1.1

temperature index

TI

numerical value of the temperature in degrees Celsius derived from the thermal endurance relationship at a time of 20 000 h (or other specified time)

3.1.2

halving interval

HIC

numerical value of the temperature interval in Kelvin which expresses the halving of the time to end-point taken at the temperature equal to TI

[SOURCE: IEC 60050-212:2010 [1]², definition 212-12-13, modified – omission of reference to "relative temperature index"]

3.1.3

thermal endurance graph

graph in which the logarithm of the time to reach a specified end-point in a thermal endurance test is plotted against the reciprocal thermodynamic test temperature

[SOURCE: IEC 60050-212:2010, definition 212-12-10]

3.1.4

thermal endurance graph paper

graph paper having a logarithmic time scale as the ordinate, graduated in powers of ten (from 10 h to 100 000 h is often a convenient range) and values of the abscissa are proportional to the reciprocal of the thermodynamic (absolute) temperature

Note 1 to entry: The abscissa is usually graduated in a non-linear (Celsius) temperature scale oriented with temperature increasing from left to right.

3.1.5

degrees of freedom

number of data values minus the number of parameter values

3.1.6

end-point

limit for a diagnostic property value based on which the thermal endurance is evaluated.

² Figures in square brackets refer to the Bibliography.

3.1.7**time to end-point**

failure time

time to reach the end point or conventional failure

3.1.8**square of the correlation coefficient** r^2

fraction of the variation in one variable that may be explained by the other variable

Note 1 to entry: r^2 is a square of correlation coefficient which explains the ratio of all data deviation on the regression line.

3.1.9**destructive test**

diagnostic property test, where the test specimen is irreversibly changed by the property measurement, in a way which precludes a repeated measurement on the same specimen

3.1.10**non-destructive test**

diagnostic property test, where the properties of the test specimen are not permanently changed by the measurement, so that a further measurement on the same specimen may be made after appropriate treatment

3.1.11**proof test**

diagnostic property test, where each test specimen is, at the end of each ageing cycle, subjected to a specified stress, further ageing cycles being conducted until the specimen fails on testing

iTeh STANDARD PREVIEW
(standards.iteh.ai)

<https://standards.iteh.ai/catalog/standards/sist/796c4c8-fd11-4d1b-b2a0-315c4db15ae0/iec-60216-8-2013>

3.1.12**temperature group**

temperature group of specimens

number of specimens being exposed together to the same temperature ageing in the same oven

Note 1 to entry: Where there is no risk of ambiguity, either temperature groups or test groups may be referred to simply as groups.

3.1.13**test group**

test group of specimens

number of specimens removed together from a temperature group (as above) for destructive testing

3.1.14**relative temperature index****RTI**

numerical value of the temperature in degrees Celsius at which the estimated time to endpoint of the candidate material is the same as the estimated time to endpoint of the reference material at a temperature equal to its assessed temperature index

3.2 Symbols and abbreviations a, b Regression coefficients $n_{a,b,c,d}$ Numbers of specimens for destructive tests n Number of y-values

N	Total number of test specimens
r	Correlation coefficient
F	Fisher distributed stochastic variable
x	Reciprocal thermodynamic temperature ($1/\Theta$)
y	Logarithm of time to end-point
ϑ	Temperature, °C
Θ	Temperature, thermodynamic (Kelvin)
Θ_0	Value in Kelvin of 0 °C (273,15 K)
τ	Time (to end-point)
TI	Temperature index
HIC	Halving interval at temperature equal to TI
RTI	Relative temperature index

4 Thermal endurance test procedure

4.1 General

Simplified procedures, which do not test the data dispersion but only deviations from linear behaviour, are described.

It is possible, with some limitations, to evaluate the thermal endurance data graphically. In this case, statistical assessment of data dispersion is not possible, but it is considered important to evaluate any deviation of the data from the linear relationship.

Since the temperature is very often the dominant ageing factor affecting an electrical insulating material (EIM) certain basic thermal classes are useful and have been recognized as such internationally (see IEC 60085).

4.2 Number of test specimens

The accuracy of endurance test results depends largely on the number of specimens aged at each temperature. Generally, the following instructions, which influence the testing procedure, apply.

- a) For a criterion requiring non-destructive testing, in most cases a group of five test specimens for each exposure temperature is adequate.

Where the test criterion for non-destructive or proof tests is based upon the initial value of the property, this should be determined from a group of specimens of at least twice the number of specimens in each temperature group

- b) For proof-test criteria, a group of at least 11 and possibly 21 specimens will be required for each exposure temperature.

The dimensions and method of preparation of the test specimens shall be in accordance with the specifications given for the relevant test method.

- c) For a criterion requiring a destructive test, the minimum total number (N) of test specimens needed is derived as follows:

$$N = n_a \times n_b \times n_c + n_d \quad (1)$$

where

- n_a is the number of specimens in a test group undergoing identical treatment at one temperature and one treatment time and discarded after determination of the property (usually five);
- n_b is the number of treatments, i.e. exposure lengths, at one temperature;
- n_c is the number of exposure temperature levels;
- n_d is the number of specimens in the group used to establish the initial value of the property. Normal practice is to select $n_d = 2n_a$ when the diagnostic criterion is a percentage change of the property from its initial level. When the criterion is an absolute property level, n_d is usually given the value of zero, unless reporting of the initial value is required.

NOTE When there is a large number of specimens to be tested, it may be possible in certain cases to deviate from the relevant test specifications and to reduce this number. However, it should be recognized that the precision of the test result depends to a large extent on the number of specimens tested. In contrast, when the individual results are too scattered, an increase in the number of specimens may be necessary in order to obtain satisfactory precision. It is advisable to make an approximate assessment, by means of preliminary tests, of the number and duration of the ageing tests required.

4.3 Preparation of test specimens

The specimens used for the ageing test should constitute a random sample from the population investigated and are to be treated uniformly.

The material specifications or the test standards will contain all necessary instructions for the preparation of specimens.

The thickness of specimens is in some cases specified in the list of property measurements for the determination of thermal endurance (see IEC 60216-2); otherwise the thickness shall be reported. Some physical properties are sensitive even to minor variations of specimen thickness. In such cases, the thickness after each ageing period may need to be determined and reported if required in the relevant specification.

The thickness is also important because the rate of ageing may vary with thickness. Ageing data of materials with different thicknesses are not always comparable. Consequently, a material may be assigned more than one thermal endurance characteristic derived from the measurement of properties at different thicknesses.

The tolerances of specimen dimensions should be the same as those normally used for general testing; where specimen dimensions need smaller tolerances than those normally used, these special tolerances should be given. Screening measurements ensure that specimens are of uniform quality and typical of the material to be tested.

Since processing conditions may significantly affect the ageing characteristics of some materials, it shall be ensured that, for example, sampling, cutting sheet from the supply roll, cutting of anisotropic material in a given direction, moulding, curing, pre-conditioning, are performed in the same manner for all specimens.

It is good practice to keep an adequate number of test specimens separately as a reserve of the original material batch from which such specimens may subsequently be prepared. In this way, any required ageing of additional specimens in case of unforeseen complications will introduce a minimum risk of producing systematic differences between groups of specimens. Such complications may arise, for example, if the thermal endurance relationship turns out to be non-linear, or if specimens are lost due to thermal runaway of an oven. Moreover they can be used:

- for cases in which the accuracy requires heat ageing at an additional temperature;
- as reference specimens.

They shall be stored in an appropriately controlled atmosphere (see ISO 291).

Thermosetting materials shall be conditioned for 48 h at the lowest exposure temperature of the range selected.

If necessary, thermoplastic materials should be annealed for 48 h at the lowest exposure temperature of the range selected.

4.4 Preparation of ageing processes – exposure temperature and cycle time

For TI determinations, test specimens should be exposed to not less than three, preferably at least four, temperatures covering a sufficient range to demonstrate a linear relationship between logarithms of time to end-point and reciprocal thermodynamic (absolute) temperature.

To reduce the uncertainties in calculating the appropriate thermal endurance characteristic, the overall temperature range of thermal exposure needs to be carefully selected, observing the following requirements:

- a) the lowest exposure temperature shall be one which will result in a mean or median time to end-point more than 1/4 of the extrapolation time (which is generally 20 000 h) when determining TI;

NOTE 1 The mean time corresponding to TI is generally 20 000 h, thus the lowest exposure temperature corresponds to a mean time $\geq 5\,000$ h.

- b) the extrapolation necessary to establish TI shall not be more than 25 K;

- c) the highest exposure temperature shall be one which will result in a mean or median time to end-point of more than 100 h.

NOTE 2 For some materials, it may not be possible to achieve a time to end-point of less than 500 h while retaining satisfactory linearity. However, it is important that a smaller range of mean times to end-point will lead to a larger confidence interval of the result for the same data dispersion.

Table 1 gives guidance in making initial selections.

A number of recommendations and suggestions useful in establishing times and temperatures can be found in IEC 60216-1:2013, Annex B.

Before the heat-ageing procedure is started, an initial test shall be made at room temperature with the required number of specimens conditioned and tested in accordance with the chosen test method.

Selection of adequate exposure temperatures requires previously determined information on the material under test. If such information is not available, exploratory tests may help in selecting exposure temperatures which are suitable for evaluating the thermal endurance characteristics.

For heat ageing, ovens shall be used that meet the requirements specified in IEC 60216-4-1, in particular with respect to the temperature tolerances and ventilation rates of air exchange.

Place the required number of specimens in each of the ovens maintained at the selected temperatures.

If there is a risk of cross-contamination between test specimens originating from different materials, use separate ovens for each material.

At the end of each heat-ageing period, the required number of test specimens is removed from the oven and conditioned, if necessary, under the appropriately controlled atmosphere (see ISO 291). The test, in accordance with the selected test criterion, shall be carried out at room temperature.