

INTERNATIONAL STANDARD

**Optical fibres –
Part 1-54: Measurement methods and test procedures – Gamma irradiation**

IEC 60793-1-54:2012
<https://standards.iteh.ai/catalog/standards/sist/5659a399-5ab6-46ad-8887-e3e225160258/iec-60793-1-54-2012>

Withhold



THIS PUBLICATION IS COPYRIGHT PROTECTED
Copyright © 2012 IEC, Geneva, Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester.
If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

IEC Central Office
3, rue de Varembe
CH-1211 Geneva 20
Switzerland

Tel.: +41 22 919 02 11
Fax: +41 22 919 03 00
info@iec.ch
www.iec.ch

About the IEC

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

About IEC publications

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigenda or an amendment might have been published.

Useful links:

IEC publications search - www.iec.ch/searchpub

The advanced search enables you to find IEC publications by a variety of criteria (reference number, text, technical committee,...).

It also gives information on projects, replaced and withdrawn publications.

IEC Just Published - webstore.iec.ch/justpublished

Stay up to date on all new IEC publications. Just Published details all new publications released. Available on-line and also once a month by email.

Electropedia - www.electropedia.org

The world's leading online dictionary of electronic and electrical terms containing more than 30 000 terms and definitions in English and French, with equivalent terms in additional languages. Also known as the International Electrotechnical Vocabulary (IEV) on-line.

Customer Service Centre - webstore.iec.ch/csc

If you wish to give us your feedback on this publication or need further assistance, please contact the Customer Service Centre: csc@iec.ch.

[https://standards.iteh.ai/catalog/standards/sist/5659a399-5ab6-46ad-8887-e3e225160258/iec-](https://standards.iteh.ai/catalog/standards/sist/5659a399-5ab6-46ad-8887-e3e225160258/iec-60793-1-54-2012)

60793-1-54-2012

INTERNATIONAL STANDARD

**Optical fibres –
Part 1-54: Measurement methods and test procedures – Gamma irradiation**

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

PRICE CODE

M

ICS 33.180.10

ISBN 978-2-83220-400-9

Warning! Make sure that you obtained this publication from an authorized distributor.

CONTENTS

FOREWORD.....	3
1 Scope.....	5
2 Normative references	5
3 Apparatus.....	6
3.1 Radiation source	6
3.1.1 Testing of environmental background radiation	6
3.1.2 Testing of adverse nuclear environments.....	6
3.2 Optical source	6
3.3 Optical filters/monochromators	6
3.4 Cladding mode stripper	6
3.5 Fibre support and positioning apparatus	6
3.6 Optical splitter	6
3.7 Input launch conditions.....	7
3.7.1 Class A, category A1 fibres (graded index multimode fibres)	7
3.7.2 Class B fibres (single-mode fibres).....	7
3.7.3 Class A, category A2 fibres (quasi-step and step index fibres).....	7
3.8 Detector – Signal detection electronics.....	7
3.9 Optical power meter	7
3.10 Radiation dosimeter	7
3.11 Temperature controlled container.....	7
3.12 Test reel.....	7
4 Sampling and specimens.....	7
4.1 Specimens	7
4.1.1 Fibre specimen	7
4.1.2 Cable specimen.....	8
4.2 Specimen for environmental background radiation test	8
4.3 Specimen for testing adverse nuclear environments	8
4.4 Test reel.....	8
4.5 Ambient light shielding	8
5 Procedure.....	8
5.1 General	8
5.2 Calibration of radiation source	8
5.3 Preparation and pre-conditioning.....	8
5.4 Attenuation measurement for environmental background radiation	9
5.5 Attenuation measurement for adverse nuclear environment.....	9
6 Calculations	10
6.1 Change in optical attenuation Δa (environmental background radiation test).....	10
6.2 Change in optical transmittance, a (adverse nuclear environmental radiation test)	10
6.3 Normalization of the results	10
7 Results	11
7.1 Information to be provided with each measurement	11
7.2 Information available upon request.....	11
8 Specification information	11
Bibliography.....	12

INTERNATIONAL ELECTROTECHNICAL COMMISSION

OPTICAL FIBRES –

**Part 1-54: Measurement methods and test procedures –
Gamma irradiation**

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

International Standard IEC 60793-1-54 has been prepared by subcommittee 86A: Fibres and cables, of IEC technical committee 86: Fibre optics.

This second edition cancels and replaces the first edition, published in 2003. It constitutes a technical revision.

This edition includes the following significant technical changes with respect to the previous edition:

- launching conditions and optical sources have been reviewed and are better defined.

The text of this standard is based on the following documents:

CDV	Report on voting
86A/1413/CDV	86A/1433/RVC

Full information on the voting for the approval of this standard can be found in the report on voting indicated in the above table.

This publication has been drafted in accordance with the ISO/IEC Directives, Part 2.

A list of all parts of the IEC 60793 series can be found, under the general title *Optical Fibres*, on the IEC website.

The committee has decided that the contents of this publication will remain unchanged until the stability date indicated on the IEC web site under "<http://webstore.iec.ch>" in the data related to the specific publication. At this date, the publication will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

A bilingual version of this publication may be issued at a later date.

OPTICAL FIBRES –

Part 1-54: Measurement methods and test procedures – Gamma irradiation

1 Scope

This part of IEC 60793 outlines a method for measuring the steady state response of optical fibres and optical cables exposed to gamma radiation. It can be employed to determine the level of radiation induced attenuation produced in Class B single-mode or Class A, category A1 and A2 multimode optical fibres, in either cabled or uncabled form, due to exposure to gamma radiation.

The attenuation of cabled and uncabled optical fibres generally increases when exposed to gamma radiation. This is primarily due to the trapping of radiolytic electrons and holes at defect sites in the glass (i.e. the formation of “colour centres”). This test procedure focuses on two regimes of interest: the low dose rate regime suitable for estimating the effect of environmental background radiation, and the high dose rate regime suitable for estimating the effect of adverse nuclear environments. The testing of the effects of environmental background radiation is achieved with an attenuation measurement approach similar to IEC 60793-1-40 Method A, cut-back. The effects of adverse nuclear environments are tested by monitoring the power before, during and after exposure of the test sample to gamma radiation. The depopulation of colour centres by light (photo bleaching) or by heat causes recovery (lessening of radiation induced attenuation). Recovery may occur over a wide range of time which depends on the irradiation time and annealing temperature. This complicates the characterization of radiation induced attenuation since the attenuation depends on many variables including the temperature of the test environment, the configuration of the sample, the total dose and the dose rate applied to the sample and the light level used to measure it.

This test is not a material test for the non-optical material components of a fibre optic cable. If degradation of cable materials exposed to irradiation is to be studied, other test methods will be required.

This test method is written to contain a clear, concise listing of instructions. The background knowledge that is necessary to perform correct, relevant and expressive irradiation tests as well as to limit measurement uncertainty is presented separately in IEC/TR 62283.

Attention is drawn to the fact that strict regulations and suitable protective facilities are to be adopted in the laboratory for this test. Carefully selected trained personnel shall be used to perform this test. It can be extremely hazardous to test personnel if it is improperly performed or without qualified conditions.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60793-1-40, *Optical Fibres – Part 1-40: Measurement methods and test procedures – Attenuation*

IEC 60793-1-44, *Optical fibres – Part 1-44: Measurement methods and test procedures – Cut-off wavelength*

IEC 60793-1-46, *Optical fibres – Part 1-46: Measurement methods and test procedures – Monitoring of changes in optical transmittance*

IEC 61280-4-1, *Fibre-optic communication subsystem test procedures – Part 4-1: Installed cable plant – Multimode attenuation measurement*

3 Apparatus

3.1 Radiation source

3.1.1 Testing of environmental background radiation

A ^{60}Co or equivalent ionising source shall be used to deliver gamma radiation. This environment is characterised by relatively low total dose and dose rate.

3.1.2 Testing of adverse nuclear environments

A ^{60}Co or equivalent ionizing source(s) shall be used to deliver gamma radiation. This environment is characterised by higher total dose and dose rate.

3.2 Optical source

An optical source such as a lamp, laser or light emitting diode emitting at wavelengths compatible with the optical fibres under test shall be used.

The optical source shall be stable in intensity over a time period sufficient to perform the measurement. The power coupled from the source into the test sample shall be < -30 dBm (1,0 μW) or as specified in the detail specification. The optical source shall be modulated with a pulsed signal at a 50 % duty cycle.

NOTE If a source that couples more than 1,0 μW is used, photo bleaching may occur.

3.3 Optical filters/monochromators

Unless otherwise specified, wavelength tolerances of ± 20 nm shall be obtained by filtering the optical source with a set of optical filters or a monochromator. The 3 dB optical bandwidth of the filters shall be less than or equal to 25 nm.

3.4 Cladding mode stripper

When necessary, a device that extracts cladding modes shall be employed at the input end and output end of the test sample. If the fibre coating materials are designed to strip cladding modes, a cladding mode stripper is not required.

3.5 Fibre support and positioning apparatus

A means of stable support for the input end of the test sample, such as a vacuum chuck, shall be arranged. This support shall be mounted on a positioning device so that the end of the test sample can be repeatedly positioned in the input beam.

3.6 Optical splitter

An optical splitter shall divert a small portion of the input light to a reference detector. The reference path shall be used to monitor system fluctuations for the duration of the test.

3.7 Input launch conditions

3.7.1 Class A, category A1 fibres (graded index multimode fibres)

An equilibrium mode simulator shall be used to attenuate higher order propagation modes and to establish a steady-state mode condition near the input end of the fibre. The requirements for the launch conditions for sub-category A1a graded index multimode fibre measurements are defined in IEC 61280-4-1.

3.7.2 Class B fibres (single-mode fibres)

An optical lens system or fibre pigtail may be employed to excite the test fibre. The power coupled into the test sample shall be stable for the duration of the test. If an optical lens system is used, a method of making the positioning of the fibre less sensitive is to overfill the fibre end spatially and angularly. If a pigtail is used, it may be necessary to use index matching material to eliminate interference effects. A high order mode filter shall be employed to remove high order propagating modes in the wavelength range greater than or equal to the cut-off wavelength of the test fibre. The test condition specified in IEC 60793-1-44, Method C satisfies this requirement.

3.7.3 Class A, category A2 fibres (quasi-step and step index fibres)

Launch conditions shall be created as specified in the detail specification.

3.8 Detector – Signal detection electronics

An optical detector which is linear and stable over the range of intensities that are encountered shall be used. A typical system might include a photovoltaic mode photodiode amplified by a current input preamplifier, with synchronous detection by a lock-up amplifier.

3.9 Optical power meter

A suitable optical power meter shall be used to determine that the power coupled from the optical source into the test sample is less than or equal to 1,0 μ W or the level specified in the detail specification.

3.10 Radiation dosimeter

Thermo luminescent LiF or CaF crystal detectors (TLDs) or an ion chamber detector shall be used to measure the total radiation dose received by the specimen fibre.

3.11 Temperature controlled container

Unless otherwise specified, the temperature controlled container shall have the capability of maintaining the specified temperatures to within ± 2 °C.

3.12 Test reel

The test reel shall not act as a shield or sink for the radiation used in this test. Reels of wood, plastic or similar non-conducting materials would, in principle, act as transparent to the radiation. The additional absorption shall be taken into account for exact measurements.

4 Sampling and specimens

4.1 Specimens

4.1.1 Fibre specimen

The test specimen shall be a representative sample of the fibre specified in the detail specification.

4.1.2 Cable specimen

The test specimen shall be a representative sample of the cable described in the detail specification and shall contain at least one of the specified fibres.

4.2 Specimen for environmental background radiation test

Unless otherwise specified in the detail specification, the length of the test sample shall be $(3\,000 \pm 30)$ m. (Where reactor constraints dictate smaller lengths, the length of the test sample may be $(1\,100 \pm 20)$ m.) A minimum length at the ends of the test sample (typically 5 m) shall reside outside of the test chamber and be used to connect the optical source to the detector. The irradiated length of the test sample shall be reported.

4.3 Specimen for testing adverse nuclear environments

Unless otherwise specified in the detail specification, the length of the test sample shall be $(250 \pm 2,5)$ m. (When test conditions require a high total dose and dose rate a shorter test sample length may be necessary). A minimum length at the ends of the test sample (typically 5 m) shall remain outside of the test chamber and be used to connect the optical source to the detector. The irradiated length of the test sample shall be reported.

4.4 Test reel

The test sample shall be spooled onto a reel with a drum diameter that is specified in the detail specification. Allowance shall be made for the unspooling of a measured length of the test sample from each end of the reel to allow for attachment to the optical measurement equipment. An alternative deployment method allows the fibre to be loosely wound in a coil of specified diameter.

4.5 Ambient light shielding

The test sample shall be shielded from ambient light to prevent external photo bleaching.

5 Procedure

5.1 General

The radiation tests differ in exposure dose, dose rate, exposure time and temperature. The tests are environmental background radiation test and adverse nuclear radiation test.

5.2 Calibration of radiation source

Calibration of the radiation source for dose uniformity and level shall be made prior to the test sample being set up in the chamber. Four TLDs shall be placed in the area of exposure and the centre of the TLDs shall be placed where the axis of the test reel will be placed. (Four TLDs are used to get a representative average value.) A dose equal to or greater than the actual test dose shall be used to calibrate the system. To maintain the highest possible accuracy in measuring the test dose, the TLDs shall not be used more than once.

5.3 Preparation and pre-conditioning

The test sample shall be preconditioned in the temperature chamber at (25 ± 5) °C for 1 h prior to testing, or at the test temperature for a preconditioned time as specified in the detail specification.

The input end of the short test length shall be placed in the positioning device and aligned in the test set to obtain maximum optical power as measured with a calibrated power meter.