

INTERNATIONAL STANDARD

NORME INTERNATIONALE

Flexible insulating sleeves –
STANDARD PREVIEW
Part 3: Specifications for individual types of sleeves –
Sheet 285: Heat-shrinkable polyolefin sleeves, for medium voltage joint
insulation

[IEC 60684-3-285:2014](#)

<https://standards.iteh.ai/catalog/standards/sist/d3d9e40f-f00f-4816-99f5-22f9abd71ff0/iec-60684-3-285-2014>

Gaines isolantes souples –
Partie 3: Spécifications pour types particuliers de gaines –
Feuille 285: Gaines thermorétractables en polyoléfine, pour isolation de jonction
moyenne tension





THIS PUBLICATION IS COPYRIGHT PROTECTED

Copyright © 2014 IEC, Geneva, Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester. If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

Droits de reproduction réservés. Sauf indication contraire, aucune partie de cette publication ne peut être reproduite ni utilisée sous quelque forme que ce soit et par aucun procédé, électronique ou mécanique, y compris la photocopie et les microfilms, sans l'accord écrit de l'IEC ou du Comité national de l'IEC du pays du demandeur. Si vous avez des questions sur le copyright de l'IEC ou si vous désirez obtenir des droits supplémentaires sur cette publication, utilisez les coordonnées ci-après ou contactez le Comité national de l'IEC de votre pays de résidence.

IEC Central Office
3, rue de Varembé
CH-1211 Geneva 20
Switzerland

Tel.: +41 22 919 02 11
Fax: +41 22 919 03 00
info@iec.ch
www.iec.ch

About the IEC

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

About IEC publications

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigenda or an amendment might have been published.

IEC Catalogue - webstore.iec.ch/catalogue

The stand-alone application for consulting the entire bibliographical information on IEC International Standards, Technical Specifications, Technical Reports and other documents. Available for PC, Mac OS, Android Tablets and iPad.

Electropedia - www.electropedia.org

The world's leading online dictionary of electronic and electrical terms containing more than 30 000 terms and definitions in English and French, with equivalent terms in 15 additional languages. Also known as the International Electrotechnical Vocabulary (IEV) online.

IEC publications search - www.iec.ch/searchpub

The advanced search enables to find IEC publications by a variety of criteria (reference number, text, technical committee,...). It also gives information on projects, replaced and withdrawn publications.

IEC Glossary - std.iec.ch/glossary

More than 60 000 electrotechnical terminology entries in English and French extracted from the Terms and Definitions clause of IEC publications issued since 2002. Some entries have been collected from earlier publications of IEC TC 37, 77, 86 and CISPR.

IEC Just Published - webstore.iec.ch/justpublished

Stay up to date on all new IEC publications. Just Published details all new publications released. Available online and also once a month by email.

IEC Customer Service Centre - webstore.iec.ch/csc

If you wish to give us your feedback on this publication or need further assistance, please contact the Customer Service Centre: csc@iec.ch.

A propos de l'IEC

La Commission Electrotechnique Internationale (IEC) est la première organisation mondiale qui élabore et publie des Normes internationales pour tout ce qui a trait à l'électricité, à l'électronique et aux technologies apparentées.

A propos des publications IEC

Le contenu technique des publications IEC est constamment revu. Veuillez vous assurer que vous possédez l'édition la plus récente, un corrigendum ou amendement peut avoir été publié.

Catalogue IEC - webstore.iec.ch/catalogue

Application autonome pour consulter tous les renseignements bibliographiques sur les Normes internationales, Spécifications techniques, Rapports techniques et autres documents de l'IEC. Disponible pour PC, Mac OS, tablettes Android et iPad.

Electropedia - www.electropedia.org

Le premier dictionnaire en ligne de termes électroniques et électriques. Il contient plus de 30 000 termes et définitions en anglais et en français, ainsi que les termes équivalents dans 15 langues additionnelles. Egalement appelé Vocabulaire Electrotechnique International (IEV) en ligne.

Recherche de publications IEC - www.iec.ch/searchpub

La recherche avancée permet de trouver des publications IEC en utilisant différents critères (numéro de référence, texte, comité d'études,...). Elle donne aussi des informations sur les projets et les publications remplacées ou retirées.

Glossaire IEC - std.iec.ch/glossary

Plus de 60 000 entrées terminologiques électrotechniques, en anglais et en français, extraites des articles Termes et Définitions des publications IEC parues depuis 2002. Plus certaines entrées antérieures extraites des publications des CE 37, 77, 86 et CISPR de l'IEC.

IEC Just Published - webstore.iec.ch/justpublished

Restez informé sur les nouvelles publications IEC. Just Published détaille les nouvelles publications parues. Disponible en ligne et aussi une fois par mois par email.

Service Clients - webstore.iec.ch/csc

Si vous désirez nous donner des commentaires sur cette publication ou si vous avez des questions contactez-nous: csc@iec.ch.



IEC 60684-3-285

Edition 1.0 2014-10

INTERNATIONAL STANDARD

NORME INTERNATIONALE

Flexible insulating ~~sleeving~~ **STANDARD PREVIEW**

Part 3: Specifications for individual types of sleeving –

Sheet 285: Heat-shrinkable polyolefin sleeving, for medium voltage joint
insulation

[IEC 60684-3-285:2014](https://standards.iteh.ai/catalog/standards/sist/d3d9e40f-f00f-4816-99f5-22f9abd71ff0/iec-60684-3-285-2014)

<https://standards.iteh.ai/catalog/standards/sist/d3d9e40f-f00f-4816-99f5-22f9abd71ff0/iec-60684-3-285-2014>

Gaines isolantes souples –

Partie 3: Spécifications pour types particuliers de gaines –
Feuille 285: Gaines thermorétractables en polyoléfine, pour isolation de jonction
moyenne tension

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

COMMISSION
ELECTROTECHNIQUE
INTERNATIONALE

ICS 29.035.20

ISBN 978-2-8322-2978-1

Warning! Make sure that you obtained this publication from an authorized distributor.

Attention! Veuillez vous assurer que vous avez obtenu cette publication via un distributeur agréé.

CONTENTS

FOREWORD.....	3
INTRODUCTION.....	5
1 Scope	6
2 Normative references	6
3 Designation	6
4 Conditions of test	7
5 Requirements	7
6 Sleeving conformance	7
Bibliography.....	10
Table 1 – Property requirements	8
Table 2 – Requirements for breakdown voltage.....	9

iTeh STANDARD PREVIEW (standards.iteh.ai)

[IEC 60684-3-285:2014](#)

<https://standards.iteh.ai/catalog/standards/sist/d3d9e40f-f00f-4816-99f5-22f9abd71ff0/iec-60684-3-285-2014>

INTERNATIONAL ELECTROTECHNICAL COMMISSION

FLEXIBLE INSULATING SLEEVING –

**Part 3: Specifications for individual types of sleeving –
Sheet 285: Heat-shrinkable polyolefin sleeving,
for medium voltage joint insulation**

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

International Standard IEC 60684-3-285 has been prepared by IEC technical committee 15: Solid electrical insulating materials.

This bilingual version (2015-10) corresponds to the English version, published in 2014-10.

The text of this standard is based on the following documents:

CDV	Report on voting
15/694/CDV	15/727/RVC

Full information on the voting for the approval of this standard can be found in the report on voting indicated in the above table.

The French version of this standard has not been voted upon.

This publication has been drafted in accordance with the ISO/IEC Directives, Part 2.

A list of all parts in the IEC 60684 series, published under the general title *Flexible insulating sleeving*, can be found on the IEC website.

The committee has decided that the contents of this publication will remain unchanged until the stability date indicated on the IEC website under "http://webstore.iec.ch" in the data related to the specific publication. At this date, the publication will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[IEC 60684-3-285:2014](#)

<https://standards.iteh.ai/catalog/standards/sist/d3d9e40f-f00f-4816-99f5-22f9abd71ff0/iec-60684-3-285-2014>

INTRODUCTION

This International Standard is one of a series which deals with flexible insulating sleeving for electrical purposes.

The series consists of three parts:

- Part 1: Definitions and general requirements (IEC 60684-1)
- Part 2: Methods of test (IEC 60684-2)
- Part 3: Specifications for individual types of sleeving (IEC 60684-3)

This standard gives one of the sheets comprising Part 3, as follows:

Sheet 285: Heat-shrinkable polyolefin sleeving, for medium voltage joint insulation.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[IEC 60684-3-285:2014](#)

<https://standards.iteh.ai/catalog/standards/sist/d3d9e40f-f00f-4816-99f5-22f9abd71ff0/iec-60684-3-285-2014>

FLEXIBLE INSULATING SLEEVING –

Part 3: Specifications for individual types of sleeving – Sheet 285: Heat-shrinkable polyolefin sleeving, for medium voltage joint insulation

1 Scope

This part of IEC 60684 gives the requirements for heat-shrinkable sleeving for medium voltage joint insulation, with a range of shrink ratios.

This sleeving has been found suitable up to temperatures of 100 °C.

These sleeveings are normally supplied in colour, red or brown.

Since this type of sleeveings covers a significantly large range of sizes and wall thicknesses, the actual size will be agreed between the purchaser and supplier.

Materials which conform to this standard meet established levels of performance. However, the selection of a material by a user for a specific application should be based on the actual requirements necessary for adequate performance in that application and not based on this standard alone. This sleeving is designed to be used in medium voltage cable accessories and as such electrical performance will be proven as part of the assembly. Examples of this are described in HD 629 and IEC 60502. [IEC 60684-3-285:2014](#)

<https://standards.iteh.ai/catalog/standards/sist/d3d9e40f-f00f-4816-99f5-22f9abd71ff0/iec-60684-3-285-2014>

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60684-1:2003, *Flexible insulating sleeving – Part 1: Definitions and general requirements*

IEC 60684-2:2011, *Flexible insulating sleeving – Part 2: Methods of test*

IEC 60757:1983, *Code for designation of colours*

3 Designation

The sleeving shall be identified by the following designation:

Description	IEC publication number	IEC part number	IEC sheet number	Size (Expanded and recovered internal diameter in mm)	Colour
Sleeving	IEC 60684	- 3	- 285	- 75,0/30,0	- RD

Any colour abbreviation shall comply with IEC 60757, where applicable. Non-standard colours shall be written out in full.

NOTE This information is for packaging labelling only in accordance with IEC 60684-1.

4 Conditions of test

Unless otherwise specified, the sleeving shall be shrunk in a forced air circulation oven for (20 ± 1) min at $200^{\circ}\text{C} \pm 3\text{ K}$ prior to testing.

5 Requirements

In addition to the general requirements given in IEC 60684-1, the sleeving shall comply with the requirements of Tables 1 and 2.

6 Sleeving conformance

Conformance to the requirements of this standard shall normally be based on the results from typical sizes.

Recovered ID 25 mm – 30 mm

**iTeh STANDARD PREVIEW
(standards.iteh.ai)**

[IEC 60684-3-285:2014](#)

<https://standards.iteh.ai/catalog/standards/sist/d3d9e40f-f00f-4816-99f5-22f9abd71ff0/iec-60684-3-285-2014>

Table 1 – Property requirements

Property	IEC 60684-2:2011 Clause or Subclause	Units	Max. or Min.	Requirements	Remarks
Dimensions	3				
Internal diameter	3.1.2	mm	Min.	To be agreed between purchaser and supplier	
Wall thickness	3.3.2	mm	Min.	60	
Concentricity expanded recovered	3.3.3	%	Min.	85	
Heat shock	6				
Tensile strength	19.1 and 19.2	MPa	Min.	5	
Elongation at break	19.1 and 19.2	%	Min.	200	Heat at 200 °C ± 5 K
Longitudinal change	9	%	Max.	– 10 + 5	Heat expanded sleeving at 200 °C ± 3 K for (20 ± 1) min
Bending at low temperature	14 https://standards.iteh.ai/catalog/standards/sist/d3d9e40f-f00f-4816-99f5-229abd71ff0/iec-60684-3-285-2014	IEC 60684-3-285:2014		No cracking shall be visible	Test at -20 °C For strips, the mandrel shall be between 20 and 22 times the wall thickness. Full section sleeving is tested unfilled and the mandrel shall be between 20 and 22 times the outer diameter.
Dimensional stability on storage	16	–	–	The dimensions shall remain as agreed.	See Clause 1 (Scope)
Tensile strength	19.1 and 19.2	MPa	Min.	8	
Elongation at break	19.1 and 19.2	%	Min.	400	Rate of jaw separation shall be 100 mm/min.
Secant modulus at 2 % elongation	19.5	MPa	Max.	175	
Breakdown voltage	21	kV	Min.	See Table 2.	
Volume resistivity at room temperature	23 23.5.2	Ω·m	Min.	10 ¹²	
Heat ageing	39				
Tensile strength	19.1 and 19.2	MPa	Min.	5	
Elongation at break	19.1 and 19.2	%	Min.	200	Heat at 135 °C ± 3 K

Table 2 – Requirements for breakdown voltage

Expanded wall thickness (mm)	Electric strength ^a Min.	
	Expanded wall thickness/mm <u>Type B</u>	Electric strength kV/mm
All dimensions	< 1	12
	1 to 1,5	10
	> 1,5	8

^a Measure the expanded wall thickness and calculate the electric strength by dividing the breakdown voltage by this value.

The breakdown voltage shall be determined by the method described in 21.4 of IEC 60684-2:2011. The central value shall comply with the minimum value in the above Table 2.

The sleeving shall be tested in the expanded condition.

The rate of application of the voltage shall be 500 V/s.

Care should be taken in selection of sizes based on these values. Refer to the manufacturer for actual values on installed conditions.
iTeh STANDARD PREVIEW
(standards.iteh.ai)

[IEC 60684-3-285:2014](https://standards.iteh.ai/catalog/standards/sist/d3d9e40f-f00f-4816-99f5-22f9abd71ff0/iec-60684-3-285-2014)
<https://standards.iteh.ai/catalog/standards/sist/d3d9e40f-f00f-4816-99f5-22f9abd71ff0/iec-60684-3-285-2014>