

INTERNATIONAL STANDARD

NORME INTERNATIONALE



Safety of primary and secondary lithium cells and batteries during transport

Sécurité des piles et des accumulateurs au lithium pendant le transport

[IEC 62281-2012](https://standards.iteh.ai/catalog/standards/sist/758ebbb7-1c11-4eae-ac16-3574fdd840b3/iec-62281-2012)

<https://standards.iteh.ai/catalog/standards/sist/758ebbb7-1c11-4eae-ac16-3574fdd840b3/iec-62281-2012>



THIS PUBLICATION IS COPYRIGHT PROTECTED

Copyright © 2012 IEC, Geneva, Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester. If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

Droits de reproduction réservés. Sauf indication contraire, aucune partie de cette publication ne peut être reproduite ni utilisée sous quelque forme que ce soit et par aucun procédé, électronique ou mécanique, y compris la photocopie et les microfilms, sans l'accord écrit de l'IEC ou du Comité national de l'IEC du pays du demandeur. Si vous avez des questions sur le copyright de l'IEC ou si vous désirez obtenir des droits supplémentaires sur cette publication, utilisez les coordonnées ci-après ou contactez le Comité national de l'IEC de votre pays de résidence.

IEC Central Office
3, rue de Varembe
CH-1211 Geneva 20
Switzerland

Tel.: +41 22 919 02 11
Fax: +41 22 919 03 00
info@iec.ch
www.iec.ch

About the IEC

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

About IEC publications

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigenda or an amendment might have been published.

IEC Catalogue - webstore.iec.ch/catalogue

The stand-alone application for consulting the entire bibliographical information on IEC International Standards, Technical Specifications, Technical Reports and other documents. Available for PC, Mac OS, Android Tablets and iPad.

IEC publications search - www.iec.ch/searchpub

The advanced search enables to find IEC publications by a variety of criteria (reference number, text, technical committee,...). It also gives information on projects, replaced and withdrawn publications.

IEC Just Published - webstore.iec.ch/justpublished

Stay up to date on all new IEC publications. Just Published details all new publications released. Available online and also once a month by email.

Electropedia - www.electropedia.org

The world's leading online dictionary of electronic and electrical terms containing more than 30 000 terms and definitions in English and French, with equivalent terms in 14 additional languages. Also known as the International Electrotechnical Vocabulary (IEV) online.

IEC Glossary - std.iec.ch/glossary

More than 55 000 electrotechnical terminology entries in English and French extracted from the Terms and Definitions clause of IEC publications issued since 2002. Some entries have been collected from earlier publications of IEC TC 37, 77, 86 and CISPR.

IEC Customer Service Centre - webstore.iec.ch/csc

If you wish to give us your feedback on this publication or need further assistance, please contact the Customer Service Centre: csc@iec.ch.

A propos de l'IEC

La Commission Electrotechnique Internationale (IEC) est la première organisation mondiale qui élabore et publie des Normes internationales pour tout ce qui a trait à l'électricité, à l'électronique et aux technologies apparentées.

A propos des publications IEC

Le contenu technique des publications IEC est constamment revu. Veuillez vous assurer que vous possédez l'édition la plus récente, un corrigendum ou amendement peut avoir été publié.

Catalogue IEC - webstore.iec.ch/catalogue

Application autonome pour consulter tous les renseignements bibliographiques sur les Normes internationales, Spécifications techniques, Rapports techniques et autres documents de l'IEC. Disponible pour PC, Mac OS, tablettes Android et iPad.

Recherche de publications IEC - www.iec.ch/searchpub

La recherche avancée permet de trouver des publications IEC en utilisant différents critères (numéro de référence, texte, comité d'études,...). Elle donne aussi des informations sur les projets et les publications remplacées ou retirées.

IEC Just Published - webstore.iec.ch/justpublished

Restez informé sur les nouvelles publications IEC. Just Published détaille les nouvelles publications parues. Disponible en ligne et aussi une fois par mois par email.

Electropedia - www.electropedia.org

Le premier dictionnaire en ligne de termes électroniques et électriques. Il contient plus de 30 000 termes et définitions en anglais et en français, ainsi que les termes équivalents dans 14 langues additionnelles. Egalement appelé Vocabulaire Electrotechnique International (IEV) en ligne.

Glossaire IEC - std.iec.ch/glossary

Plus de 55 000 entrées terminologiques électrotechniques, en anglais et en français, extraites des articles Termes et Définitions des publications IEC parues depuis 2002. Plus certaines entrées antérieures extraites des publications des CE 37, 77, 86 et CISPR de l'IEC.

Service Clients - webstore.iec.ch/csc

Si vous désirez nous donner des commentaires sur cette publication ou si vous avez des questions contactez-nous: csc@iec.ch.

INTERNATIONAL STANDARD

NORME INTERNATIONALE



Safety of primary and secondary lithium cells and batteries during transport

Sécurité des piles et des accumulateurs au lithium pendant le transport

<https://standards.iteh.ai/catalog/standards/sist/758ebb7-1c11-4eae-ac16-3574fdd840b3/iec-62281-2012>

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

COMMISSION
ELECTROTECHNIQUE
INTERNATIONALE

PRICE CODE
CODE PRIX

T

ICS 29.220.10

ISBN 978-2-8322-1333-9

**Warning! Make sure that you obtained this publication from an authorized distributor.
Attention! Veuillez vous assurer que vous avez obtenu cette publication via un distributeur agréé.**

CONTENTS

FOREWORD.....	4
INTRODUCTION.....	6
1 Scope.....	7
2 Normative references.....	7
3 Terms and definitions.....	7
4 Requirements for safety.....	10
4.1 General considerations.....	10
4.2 Quality plan.....	11
4.3 Packaging.....	11
5 Type testing, sampling and re-testing.....	11
5.1 Type testing.....	11
5.2 Battery assemblies.....	12
5.2.1 Secondary batteries for use in battery assemblies.....	12
5.2.2 Small battery assemblies.....	12
5.2.3 Large battery assemblies.....	12
5.3 Sampling.....	12
5.4 Re-testing.....	13
6 Test methods and requirements.....	13
6.1 General.....	13
6.1.1 Safety notice.....	13
6.1.2 Ambient temperature.....	14
6.1.3 Parameter measurement tolerances.....	14
6.1.4 Pre-discharge and pre-cycling.....	14
6.2 Evaluation of test criteria.....	14
6.2.1 Shifting.....	14
6.2.2 Distortion.....	14
6.2.3 Short-circuit.....	14
6.2.4 Excessive temperature rise.....	14
6.2.5 Leakage.....	14
6.2.6 Venting.....	15
6.2.7 Fire.....	15
6.2.8 Rupture.....	15
6.2.9 Explosion.....	15
6.3 Tests and requirements – Overview.....	15
6.4 Transport tests.....	16
6.4.1 Test T-1: Altitude.....	16
6.4.2 Test T-2: Thermal cycling.....	16
6.4.3 Test T-3: Vibration.....	17
6.4.4 Test T-4: Shock.....	17
6.4.5 Test T-5: External short-circuit.....	18
6.4.6 Test T-6: Impact/crush.....	18
6.5 Misuse tests.....	20
6.5.1 Test T-7: Overcharge.....	20
6.5.2 Test T-8: Forced discharge.....	20
6.6 Packaging test.....	20
Test P-1: Drop test.....	20

6.7	Information to be given in the relevant specification	21
6.8	Evaluation and report	21
7	Information for safety.....	22
7.1	Packaging	22
7.2	Handling of battery cartons.....	22
7.3	Transport	22
7.3.1	General	22
7.3.2	Air transport	22
7.3.3	Sea transport.....	22
7.3.4	Land transport.....	22
7.3.5	Classification.....	22
7.4	Display and storage.....	22
8	Instructions for packaging and handling during transport – Quarantine	23
9	Marking	23
9.1	Marking of primary and secondary (rechargeable) cells and batteries.....	23
9.2	Marking of the packaging and shipping documents.....	23
	Bibliography.....	25
	Figure 1 – Example of a test set-up for the impact test.....	19
	Figure 2 – Example for the marking of packages with primary or secondary (rechargeable) lithium cells or batteries	24
	Table 1 – Number of primary test cells and batteries for type testing	12
	Table 2 – Number of secondary test cells and batteries for type testing	13
	Table 3 – Number of packages with primary or secondary test cells and batteries.....	13
	Table 4 – Mass loss limits.....	15
	Table 5 – Transport and packaging tests and requirements	16
	Table 6 – Vibration profile (sinusoidal).....	17
	Table 7 – Shock parameters	18

INTERNATIONAL ELECTROTECHNICAL COMMISSION

SAFETY OF PRIMARY AND SECONDARY LITHIUM CELLS AND BATTERIES DURING TRANSPORT

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

International Standard IEC 62281 has been prepared jointly by IEC technical committee 35: Primary cells and batteries and by subcommittee 21A: Secondary cells and batteries containing alkaline or other non-acid electrolytes, of IEC technical committee 21: Secondary cells and batteries.

This second edition cancels and replaces the first edition, published in 2004, and constitutes a technical revision.

This edition includes the following significant technical changes with respect to the previous edition:

- a) distinction between small and large cell or battery by gross mass rather than by lithium content or Watt-hour rating ("nominal" energy);
- b) combination of the no mass loss (NM) and no leakage (NL) criteria into one criteria (NL);
- c) extension of an acceptable mass loss of 0,2 % from 5 g to 75 g mass of a cell or battery;
- d) reduction of large batteries to be tested under tests T-1 to T-5 and T-8 from 4 to 2 samples;

- e) reduction of test samples required for small battery assemblies (5.2.2);
- f) reduction of the vibration amplitude to 2 g for large batteries in T-3 vibration test method;
- g) replacement of the impact test by the crush test for prismatic, pouch, button, and coin cells as well as cylindrical cells with no more than 20 mm in diameter.

This bilingual version (2014-01) corresponds to the monolingual English version, published in 2012-12.

The text of this standard is based on the following documents:

FDIS	Report on voting
35/1303/FDIS	35/1307/RVD

Full information on the voting for the approval of this standard can be found in the report on voting indicated in the above table.

The French version of this standard has not been voted upon.

This publication has been drafted in accordance with the ISO/IEC Directives, Part 2.

The committee has decided that the contents of this publication will remain unchanged until the stability date indicated on the IEC web site under "<http://webstore.iec.ch>" in the data related to the specific publication. At this date, the publication will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

IMPORTANT – The 'colour inside' logo on the cover page of this publication indicates that it contains colours which are considered to be useful for the correct understanding of its contents. Users should therefore print this document using a colour printer.

INTRODUCTION

Primary lithium cells and batteries were first introduced in military applications in the 1970s. At that time, little commercial interest and no industrial standards existed. Consequently, the United Nations (UN) Committee of Experts on the Transport of Dangerous Goods, although usually referring to industrial standards for testing and criteria, introduced a sub-section in the Manual of tests and criteria concerning safety tests relevant to transport of primary lithium cells and batteries. Meanwhile, commercial interest in primary and secondary (rechargeable) lithium cells and batteries has grown and several industrial standards exist. However, the existing IEC standards are manifold, not completely harmonized, and not necessarily relevant to transport. They are not suitable to be used as a source of reference in the UN Model Regulations. Therefore this group safety standard has been prepared to harmonize the tests and requirements relevant to transport.

This International Standard applies to primary and secondary (rechargeable) lithium cells and batteries containing lithium in any chemical form: lithium metal, lithium alloy or lithium-ion. Lithium-metal and lithium alloy primary electrochemical systems use metallic lithium and lithium alloy, respectively, as the negative electrode. Lithium-ion secondary electrochemical systems use intercalation compounds (intercalated lithium exists in an ionic or quasi-atomic form within the lattice of the electrode material) in the positive and in the negative electrodes.

This International Standard also applies to lithium polymer cells and batteries, which are considered either as primary lithium-metal cells and batteries or as secondary lithium-ion cells and batteries, depending on the nature of the material used in the negative electrode.

The history of transporting primary and secondary lithium cells and batteries is worth noting. Since the 1970s, over ten billion primary lithium cells and batteries have been transported, and since the early 1990s, over one billion secondary (rechargeable) lithium cells and batteries utilizing a lithium-ion system have been transported. As the number of primary and secondary lithium cells and batteries to be transported is increasing, it is appropriate to also include in this standard the safety testing of packaging used for the transportation of these products.

This International Standard specifically addresses the safety of primary and secondary lithium cells and batteries during transport and also the safety of the packaging used.

The UN Manual of Tests and Criteria [1]¹ distinguishes between lithium metal and lithium alloy cells and batteries on the one hand, and lithium ion and lithium polymer cells and batteries on the other hand. While it defines that lithium metal and lithium alloy cells and batteries can be either primary (non-rechargeable) or rechargeable, it always considers lithium ion cells and batteries as rechargeable. However, test methods in the UN Manual of Tests and Criteria are the same for both secondary lithium metal and lithium alloy cells and batteries and lithium ion and lithium polymer cells and batteries. The concept is only needed to distinguish between small and large battery assemblies. Battery assemblies assembled from (primary or secondary) lithium metal and lithium alloy batteries are distinguished by the aggregate lithium content of all anodes (measured in grams), while battery assemblies assembled from lithium ion or lithium polymer batteries are distinguished by their “nominal” energy (measured in Watt-hours).

¹ Numbers in square brackets refer to the Bibliography

SAFETY OF PRIMARY AND SECONDARY LITHIUM CELLS AND BATTERIES DURING TRANSPORT

1 Scope

This International Standard specifies test methods and requirements for primary and secondary (rechargeable) lithium cells and batteries to ensure their safety during transport other than for recycling or disposal. Requirements specified in this standard do not apply in those cases where special provisions given in the relevant regulations, listed in 7.3, provide exemptions.

NOTE Different standards may apply for lithium-ion traction battery systems used for electrically propelled road vehicles.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 61960, *Secondary cells and batteries containing alkaline or other non-acid electrolytes – Secondary lithium cells and batteries for portable applications*

IEC 62133, *Secondary cells and batteries containing alkaline or other non-acid electrolytes – Safety requirements for portable sealed secondary cells, and for batteries made from them, for use in portable applications*

IEC 62660-1, *Secondary lithium-ion cells for the propulsion of electric road vehicles – Part 1: Performance testing*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

aggregate lithium content

total lithium content of the cells comprising a battery

3.2

battery

one or more cells electrically connected and fitted in a case, with terminals, markings and protective devices etc., as necessary for use

Note 1 to entry: This definition is different from the definition used in the UN Manual of Tests and Criteria [1]. The standard was, however, carefully prepared so that the test set-up for each test is harmonized with the UN Manual.

[SOURCE: IEC 60050-482:2004 [2], 482-01-04, modified – reference to "electrically connected" has been added]

3.3

battery assembly

battery comprising two or more batteries

3.4

button (cell or battery)

coin (cell or battery)

small round cell or battery where the overall height is less than the diameter, e.g. in the shape of a button or a coin

[SOURCE: IEC 60050-482:2004, 482-02-40, modified – the term "small round cell or battery" replaces the original "cell with a cylindrical shape"]

3.5

cell

basic functional unit, consisting of an assembly of electrodes, electrolyte, container, terminals and, usually, separators that is a source of electric energy obtained by direct conversion of chemical energy

[SOURCE: IEC 60050-482:2004, 482-01-01]

3.6

component cell

cell contained in a battery

3.7

cycle (of a secondary (rechargeable) cell or battery)

set of operations that is carried out on a secondary (rechargeable) cell or battery and is repeated regularly in the same sequence

Note 1 to entry: These operations may consist of a sequence of a discharge followed by a charge or a charge followed by a discharge under specified conditions. This sequence may include rest periods.

[SOURCE: IEC 60050-482:2004, 482-05-28, modified – the words "secondary (rechargeable" have been added]

3.8

cylindrical (cell or battery)

round cell or battery in which the overall height is equal to or greater than the diameter

[SOURCE: IEC 60050-482:2004, 482-02-39, modified – the words "round cell or battery" replace the original "cell with a cylindrical shape"]

3.9

depth of discharge

DOD

percentage of rated capacity discharged from a battery

3.10

first cycle

initial cycle of a secondary (rechargeable) cell or battery following completion of all manufacturing, formation and quality control processes

3.11

fully charged

state of charge of a secondary (rechargeable) cell or battery corresponding to 0 % depth of discharge

3.12

fully discharged

state of charge of a cell or battery corresponding to 100 % depth of discharge

3.13**large battery**

battery with a gross mass of more than 12 kg

3.14**large cell**

cell with a gross mass of more than 500 g

3.15**lithium cell (primary or secondary (rechargeable))**

cell containing a non-aqueous electrolyte and a negative electrode of lithium or containing lithium

Note 1 to entry: Depending on the design features chosen, a lithium cell may be primary or secondary (rechargeable).

[SOURCE: IEC 60050-482:2004, 482-01-06, modified – the notion of "primary or secondary (rechargeable)" has been added]

3.16**lithium content**

mass of lithium in the negative electrode of a lithium metal or lithium alloy cell or battery in the undischarged or fully charged state

3.17**lithium ion cell or battery**

rechargeable non-aqueous cell or battery in which the positive and negative electrodes are both intercalation compounds constructed with no metallic lithium in either electrode

Note 1 to entry: Intercalated lithium exists in an ionic or quasi-atomic form with the lattice of the electrode material.

Note 2 to entry: A lithium polymer cell or battery that uses lithium ion chemistries, as described herein, is considered as a lithium ion cell or battery.

3.18**nominal energy**

energy value of a cell or battery determined under specified conditions and declared by the manufacturer

Note 1 to entry: The nominal energy is calculated by multiplying the nominal voltage by rated capacity.

Note 2 to entry: The term "rated energy" could be more appropriate.

3.19**nominal voltage**

suitable approximate value of the voltage used to designate or identify a cell, a battery or an electrochemical system

[SOURCE: IEC 60050-482:2004, 482-03-31]

3.20**open-circuit voltage**

voltage across the terminals of a cell or battery when no external current is flowing

[SOURCE: IEC 60050-482:2004, 482-03-32, modified – "when no external current is flowing" replaces "when the discharge current is zero"]

3.21**primary (cell or battery)**

cell or battery that is not designed to be electrically recharged

[SOURCE: IEC 60050-482:2004, 482-01-02, modified – addition of "or battery"]

3.22

prismatic (cell or battery)

cell or battery having rectangular sides and bases

[SOURCE: IEC 60050-482:2004, 482-02-38, modified – omission of "having the shape of a parallelepiped"]

3.23

protective devices

devices such as fuses, diodes or other electric or electronic current limiters designed to interrupt the current flow, block the current flow in one direction or limit the current flow in an electrical circuit

3.24

rated capacity

capacity value of a cell or battery determined under specified conditions and declared by the manufacturer

Note 1 to entry: The following IEC standards provide guidance and methodology for determining the rated capacity: IEC 61960, IEC 62133, IEC 62660-1.

[SOURCE: IEC 60050-482:2004, 482-03-15, modified – inclusion of "a cell or battery", addition of Note to entry]

3.25

secondary (rechargeable) cell or battery

cell or battery which is designed to be electrically recharged

[SOURCE: IEC 60050-482:2004, 482-01-03, modified – addition of "rechargeable" and "or battery"]

3.26

small battery

battery with a gross mass of not more than 12 kg

3.27

small cell

cell with a gross mass of not more than 500 g

3.28

type (for cells or batteries)

particular electrochemical system and physical design of cells or batteries

3.29

undischarged

state of charge of a primary cell or battery corresponding to 0 % depth of discharge

4 Requirements for safety

4.1 General considerations

Lithium cells and batteries are categorized by their chemical composition (electrodes, electrolyte) and internal construction (bobbin, spiral). They are available in various shapes. It is necessary to consider all relevant safety aspects at the battery design stage, recognizing the fact that they may differ considerably, depending on the specific lithium system, power output and battery configuration.

The following design concepts for safety are common to all lithium cells and batteries:

- a) Abnormal temperature rise above the critical value defined by the manufacturer shall be prevented by design.
- b) Temperature increases in the cell or battery shall be controlled by the design e.g. by limiting the current flow.
- c) Lithium cells and batteries shall be designed to relieve excessive internal pressure or to preclude a violent rupture under conditions of transport.
- d) Lithium cells and batteries shall be designed so as to prevent a short-circuit under normal conditions of transport and intended use.
- e) Lithium batteries containing cells or strings of cells connected in parallel shall be equipped with effective means, as may be necessary, to prevent dangerous reverse current flow (e.g., diodes, fuses, etc.).

4.2 Quality plan

The manufacturer shall implement a documented quality plan (i.e. quality reports, inspection records, management structure) defining the procedures for the inspection of materials, components, cells and batteries during the course of manufacture, to be applied to the total process of producing a specific type of battery. Manufacturers should understand their process capabilities and should institute the necessary process controls as they relate to product safety and reliability.

4.3 Packaging

Lithium cells and batteries shall be packaged so as to prevent an external short-circuit under normal transport conditions.

NOTE Additional requirements for packaging of dangerous goods are given in UN Model Regulations:2011 [10], section 6.1. See also regulations mentioned in 7.3.

5 Type testing, sampling and re-testing

5.1 Type testing

Lithium metal and lithium ion cells or batteries which differ from a tested type by

- a) for primary cells and batteries, a change of more than 0,1 g or 20 % by mass, whichever is greater, to the electrodes or to the electrolyte, or
- b) for rechargeable cells and batteries, a change in nominal energy (in Wh) of more than 20 % or an increase in nominal voltage of more than 20 %, or
- c) a change that would lead to failure of any of the tests,

shall be considered a different type and shall be subject to the required tests.

NOTE The type of change that might be considered to differ from a tested type, such that it might lead to failure of any of the test results, may include, but is not limited to

- 1) a change in the material of the anode, the cathode, the separator or the electrolyte,
- 2) a change of protective devices, including hardware and software,
- 3) a change of safety design in cells or batteries, such as a venting valve,
- 4) a change in the number of component cells, and
- 5) a change in connecting mode of component cells.

5.2 Battery assemblies

5.2.1 Secondary batteries for use in battery assemblies

Secondary batteries not equipped with overcharge protection that are designed for use only in a battery assembly, which affords such protection, are not subject to the requirements of test T-7.

5.2.2 Small battery assemblies

When testing a battery assembly in which the aggregate lithium content of all anodes, when fully charged, is not more than 500 g, or in the case of a lithium ion battery, with a nominal energy of not more than 6 200 Wh, assembled from batteries that have passed all applicable tests, one battery assembly in a fully charged state shall be tested under tests T-3, T-4 and T-5, and, in addition, test T-7 in the case of a secondary battery assembly. For a secondary battery assembly, the assembly shall have been cycled for at least 25 cycles.

5.2.3 Large battery assemblies

A battery assembly with an aggregate lithium content of more than 500 g, or in the case of a lithium ion battery, with a nominal energy of more than 6 200 Wh, does not need to be tested if

- a) it is formed by electrically connecting batteries that have passed all applicable tests, and
- b) it is equipped with a system capable of
 - monitoring the battery assembly,
 - preventing short-circuits and over-discharge between the batteries in the assembly, and
 - preventing any overheat or overcharge of the battery assembly.

5.3 Sampling

Each different type shall be tested by taking random samples. The number of samples for testing primary cells and batteries is given in Table 1. The number of samples for testing secondary cells and batteries is given in Table 2. The number of samples for testing packages of primary and secondary cells and batteries is given in Table 3.

Table 1 – Number of primary test cells and batteries for type testing

Tests	Discharge state	Cells or single cell batteries ^a	Multi-cell batteries
Tests T-1 to T-5	Undischarged	10	4
	Fully discharged	10	4
Test T-6	Undischarged	5	5 component cells
	Fully discharged	5	5 component cells
Test T-8	Fully discharged	10	10 component cells
Total for all tests		40	8 batteries and 20 component cells

^a Single cell batteries consisting of tested component cells do not require retesting.

Table 2 – Number of secondary test cells and batteries for type testing

Tests	Cycles and discharge state	Cells	Single cell batteries ^a		Multi-cell batteries	
			Small	Large	Small	Large
Tests T-1 to T-5	At first cycle, fully charged	10	10	10	4	2
	After 25 cycles, fully charged	N/A ^b	N/A ^b	N/A ^b	N/A ^b	2
	After 50 cycles, fully charged	N/A ^b	N/A ^b	N/A ^b	4	N/A ^b
Test T-6	At first cycle, at 50 % DOD	5	5	5	5 component cells	5 component cells
Test T-7	At first cycle, fully charged	N/A ^b	4 ^c	2 ^c	4 ^c	2 ^c
	After 25 cycles, fully charged	N/A ^b	N/A ^b	2 ^c	N/A ^b	2 ^c
	After 50 cycles, fully charged	N/A ^b	4 ^c	N/A ^b	4 ^c	N/A ^b
Test T-8	At first cycle, fully discharged	10	10	10	10 component cells	10 component cells
	After 50 cycles, fully discharged	10	10	10	10 component cells	10 component cells
Total for all tests		35	43	39	16 batteries and 25 component cells	8 batteries and 25 component cells

^a Single cell batteries consisting of tested component cells shall be subject to T7 testing only.

^b N/A = not applicable.

^c Applies only to batteries equipped with overcharge protection.

Table 3 – Number of packages with primary or secondary test cells and batteries

Number of samples for test P-1	1 package as supplied for transport
--------------------------------	-------------------------------------

5.4 Re-testing

In the event that a primary or secondary lithium cell or battery type does not meet the test requirements, steps shall be taken to correct the deficiency or deficiencies that caused the failure before such a cell or battery type is re-tested.

6 Test methods and requirements

6.1 General

6.1.1 Safety notice

WARNING – These tests call for the use of procedures which may result in injury if adequate precautions are not taken.

The execution of these tests shall only be conducted by appropriately qualified and experienced technicians using adequate protection.