



Designation: E 1731 – 95<sup>ε1</sup>

## Standard Test Method for Gravimetric Determination of Nonvolatile Residue from Cleanroom Gloves<sup>1</sup>

This standard is issued under the fixed designation E 1731; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

<sup>ε1</sup> NOTE—To bring Subcommittee E21.05's existing standards into compliance with Part H of ASTM's Form and Style Manual, the M designation has been editorially removed in July 2000.

### 1. Scope

1.1 This test method covers the determination of solvent extractable nonvolatile residue (NVR) from gloves used in cleanrooms where spacecraft are assembled, cleaned, or tested.

1.2 The values stated in SI units are to be regarded as standard.

1.3 The NVR of interest is that which can be extracted from gloves using a specified solvent that has been selected for its extracting qualities, or because it is representative of solvents used in the particular facility. Alternative solvents may be used, but since their use may result in different values being generated, they must be identified in the procedure data sheet.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

### 2. Referenced Documents

#### 2.1 ASTM Standards:

D 1193 Specification for Reagent Water<sup>2</sup>

F 24 Test Method for Measuring and Counting Particulate Contamination on Surfaces<sup>3</sup>

F 50 Practice for Continuous Sizing and Counting of Airborne Particles in Dust-Controlled Areas and Cleanrooms Using Instruments Capable of Detecting Single Submicrometre and Larger Particles<sup>4</sup>

G 120 Test Method for Determination of Soluble Residual Contamination in Materials and Components by Soxhlet Extraction<sup>5</sup>

#### 2.2 Military Standards<sup>6</sup>:

Air Force T.O. 00-25-203 Contamination Control of Aerospace Facilities

Mil-F-51068F Filters, Particulate (High Efficiency, Fire Resistant)

Mil-P-27401 Propellant, Pressurizing Agent, Nitrogen

Mil-Std-105D Sampling Procedures and Tables for Inspection by Attributes

Mil-Std-1246B Product Cleanliness Levels and Contamination Control Program

#### 2.3 Federal Standards<sup>6</sup>:

Fed Spec O-E-00760 Ethyl Alcohol

Fed Std 209E Airborne Particulate Classes for Cleanrooms and Clean Zones

#### 2.4 Other Documents:

IES-RP-CC005.2 Gloves and Finger Cots Used in Cleanrooms and Other Controlled Environments

Industrial Ventilation, A Manual of Recommended Practice

### 3. Terminology

#### 3.1 Definitions:

3.1.1 *contamination, n*—unwanted molecular or particulate matter that could affect or degrade the performance of the components upon which they are deposited.

3.1.2 *contamination, n*—a process of contaminant transport or accretion, or both.

3.1.3 *environmentally controlled area, n*—cleanrooms, clean facilities, controlled work areas, and other enclosures that are designed to protect hardware from contamination. Cleanliness is achieved by controlling airborne particulate matter, temperature, relative humidity, materials, garments, and personnel activities. Guidelines for controlled areas can be found in Air Force T.O. 00-25-203 Table 3-1.

3.1.4 *high efficiency particulate air (HEPA), n*—a term describing filters having an efficiency of 99.97 % for removal of 0.3- $\mu\text{m}$  and larger particles. For this application, filters shall meet the requirements of 2.3 and 6.1 of this test method.

3.1.5 *molecular contaminant (nonparticulate), n*—may be in a gaseous, liquid, or solid state. It may be uniformly or nonuniformly distributed or be in the form of droplets. Molecular contaminants account for most of the NVR.

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee E-21 on Space Simulation and Applications of Space Technology and is the direct responsibility of Subcommittee E21.05 on Contamination.

Current edition approved Aug. 15, 1995. Published October 1995.

<sup>2</sup> *Annual Book of ASTM Standards*, Vol 11.01.

<sup>3</sup> Discontinued. See 1992 *Annual Book of ASTM Standards*, Vol 10.05.

<sup>4</sup> *Annual Book of ASTM Standards*, Vol 15.03.

<sup>5</sup> *Annual Book of ASTM Standards*, Vol 14.02.

<sup>6</sup> Available from Standardization Documents Order Desk, Bldg. 4 Section D, 700 Robbins Ave., Philadelphia, PA 19111-5094, Attn: NPODS.

3.1.6 *NVR, n*—that quantity of molecular matter remaining after the filtration of a solvent containing contaminants, and evaporation of the solvent at a specified temperature.

3.1.7 *particle (particulate contaminant), n*—a piece of matter in a solid state, with observable length, width, and thickness. The size of a particle is defined by its greatest dimension and is expressed in micrometres.

#### 4. Summary of Test Method

4.1 A glove to be tested is cut into several standard-sized pieces. The pieces are placed in a clean blanked container and a measured volume of solvent is added to the container. (See Note 1.)

4.2 The container is placed in a heated ultrasonic cleaner, or a heated water bath, and heated (and agitated if in an ultrasonic bath) for a specific length of time, after which the pieces of glove are removed from the container.

4.3 The solvent in the container is filtered into another clean container and allowed to evaporate to a low volume.

4.4 The solvent is transferred to a clean preweighed weighing dish and evaporated to a constant weight.

4.5 The results are expressed in mg/sq cm of glove surface area or in mg/unit mass of glove sections.

4.6 A controlled blank shall be run on all solvents, filtration components, and all other equipment associated with the analysis. In the event that more than one determination is run the same day, additional blanks will not be necessary, but will rely on the value from the first test.

4.7 *NVR* samples thus obtained may be used for analysis such as IR or FTIR if required.

NOTE 1—Some cleanroom gloves are of a coated or layered construction or have different textures applied to the inside and outside surfaces. Because the inside and outside surfaces of these gloves may release different quantities of nonvolatile residue, results using this method may not reflect the actual potential or transfer of contamination from this type of glove to hardware surfaces.

#### 5. Significance and Use

5.1 The *NVR* obtained by this test method is that amount which is available for release by the gloves onto handled surfaces.

5.2 Evaporation of solvent at the stated temperature is to quantify the *NVR* that can be expected to exist at room temperature, since the slight difference between room temperature and the test temperature is not likely to result in significant variances.

5.3 Various other methods exist for determining *NVR*, for example Test Method G 120 and IES-RP-CC005.2. This test is not intended to replace test methods used for other purposes.

#### 6. Apparatus and Materials

6.1 *Unidirectional Airflow Work Station*, 100 % exhaust, for handling solvents. Must meet the particulate air cleanliness class M3.5 (100) or better in accordance with Fed-Std-209. HEPA filters in the work station must not have been tested with Di-Octyl Phthalate (DOP) at any time. Temperature shall be controlled within a range of 20 to 25°C and relative humidity to less than 60 %.

6.2 *Solvent*, Acetone.

6.3 *Solvent*, Ethanol.

6.4 *Analytical Balance*, 0.01-mg readability, 0.1-mg precision. Capacity to be determined by the user.

6.5 *Vacuum Filtration System*, 25-mm diameter, consisting of a membrane filter funnel and vacuum pump that will provide a pressure of 250 torr (20 in. Hg vac.). Other size filters may be used as needed. All items that will come in contact with solvents during analysis shall be made of glass, stainless steel, or other materials that will not affect the analysis via induced contamination. Any house vacuum system may be used.

6.6 *Solvent-Resistant Membrane Filters*, Fluorocarbon, 25-mm diameter, 0.2- $\mu$ m nominal pore size. The use of supported membrane filters is not recommended because of possible adverse effects of the solvent on support media.

6.7 *Teflon-Coated Tweezers, or Hemostat*, unserrated tips.

6.8 *Beakers*, low form glass, 500 mL.

6.9 *Laboratory Detergent*, liquid.

6.10 *Methanol*, Reagent grade, A.C.S.

6.11 *Acetone*, Reagent grade, A.C.S.

6.12 *Deionized Water*, organic free, Type II per Specification D 1193, with a minimum resistivity of 1.0 megohm-cm.

6.13 *Gloves*, barrier type, low particle-generating, low outgassing, per IES-RP-CC005.2.

6.14 *NVR Solvent*, acetone. Must be verified to contain no more than 0.35-mg *NVR* per 300-mL solvent (0.12 mg/100 mL) when tested in accordance with Section 8 of this test method.

NOTE 2—Other solvents may be used if they are more representative of service conditions, but the actual solvent used must be reported per Section 11 of this test method.

6.15 *Ultrasonic Tank*, 5.7-L capacity nominal, with heater capable of maintaining a temperature of  $35 \pm 2^\circ\text{C}$ , and cover to position beakers in tank. Other convenient sizes may be used.

6.16 *Evaporating Dishes*, aluminum foil, 43-mm diameter.

6.17 *Drying Oven*, stainless steel interior.

#### 7. Preparation of Equipment

7.1 All operation shall be performed in the work station per 6.1.

7.2 Wash all glassware, filter funnels, weighing dishes, and the associated tools (see Note 3). Rinse with deionized water for a period of 1 min followed by rinsing with acetone or methanol, then with acetone (or other *NVR* solvent) as described in 6.14. Dry in a cleaned oven for 1 h at 35 to 40°C, remove and store in a dessicator until used.

7.3 All items, such as glassware, funnels, and so forth, that will come in contact with the *NVR* solvent during analysis, will be blanked per Section 8 of this test method before use.

NOTE 3—A 3 % solution of liquid detergent in deionized water has been found to be effective.

#### 8. *NVR* and System Blank

8.1 The *NVR* of the solvent, and all glassware and other items that will come in contact with the solvent during the analysis, shall be determined before use. The only exception is when several tests are to be run consecutively, in which case, the blank only needs to be determined once for a batch. It must