



Designation: F 693 – 95

Standard Practice for Sealing Seams of Resilient Sheet Flooring Products by Use of Liquid Seam Sealers¹

This standard is issued under the fixed designation F 693; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This practice covers the instructions and precautions to be observed to ensure satisfactory performance of seams in sheet resilient flooring sealed with liquid seam sealers.

1.2 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*

F 141 Terminology Relating to Resilient Floor Coverings²

3. Terminology

3.1 For definitions of terms used in this practice refer to Terminology F 141.

4. Significance and Use

4.1 Seams in some sheet resilient flooring are sealed to prevent openings from forming between cut edges and prevent penetrations of dirt, liquids, etc., into the seams.

¹ This practice is under the jurisdiction of ASTM Committee F-6 on Resilient Floor Coverings and is the direct responsibility of Subcommittee F06.40 on Special Properties.

Current edition approved Feb. 15, 1995. Published April 1995. Originally published as F 693 – 80. Last previous edition F 693 – 84 (1990) ^{ϵ 1}.

² *Annual Book of ASTM Standards*, Vol 15.04.

The American Society for Testing and Materials takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, 100 Barr Harbor Drive, West Conshohocken, PA 19428.

This standard is copyrighted by ASTM, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (<http://www.astm.org>).

5. Instructions

5.1 Flooring shall be installed in accordance with the manufacturer's instructions.

5.2 Particular attention shall be paid to proper cutting of the seams so that there are no gaps or overlaps.

5.3 In making up the seam, care shall be taken to prevent any flooring adhesive used to bond the floor covering to the substrate from getting between the cut edges of seam. It is almost impossible to remove such adhesive, and the seam sealer will not bond properly in those areas and may result in discoloration.

5.4 The proper seam sealer and applicator as recommended by the resilient flooring manufacturer shall be used. Follow the resilient flooring manufacturer's instructions as to the method of application for the specific product being installed.

6. Hazards

6.1 Most of the seam sealers contain solvents that are flammable, and all cautions on the label shall be observed.

6.2 Protect the sealed seam from dirt and traffic for the period specified by the flooring manufacturer to prevent discoloration.

7. Keywords

7.1 applicator; bead; flammable; seam sealers; seams; sheet flooring