

# TECHNICAL REPORT

**HV polymeric insulators for indoor and outdoor use tracking and erosion testing  
by wheel test and 5 000h test**  
**(standards.iteh.ai)**

IEC TR 62730:2012

<https://standards.iteh.ai/catalog/standards/sist/6163e854-a2c4-45fc-a743-2cdd120fd7bd/iec-tr-62730-2012>



**THIS PUBLICATION IS COPYRIGHT PROTECTED**  
**Copyright © 2012 IEC, Geneva, Switzerland**

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester.  
If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

IEC Central Office  
3, rue de Varembe  
CH-1211 Geneva 20  
Switzerland

Tel.: +41 22 919 02 11  
Fax: +41 22 919 03 00  
[info@iec.ch](mailto:info@iec.ch)  
[www.iec.ch](http://www.iec.ch)

### About the IEC

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

### About IEC publications

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigenda or an amendment might have been published.

#### Useful links:

IEC publications search - [www.iec.ch/searchpub](http://www.iec.ch/searchpub)

The advanced search enables you to find IEC publications by a variety of criteria (reference number, text, technical committee,...).

It also gives information on projects, replaced and withdrawn publications.

IEC Just Published - [webstore.iec.ch/justpublished](http://webstore.iec.ch/justpublished)

Stay up to date on all new IEC publications. Just Published details all new publications released. Available on-line and also once a month by email.

Electropedia - [www.electropedia.org](http://www.electropedia.org)

The world's leading online dictionary of electronic and electrical terms containing more than 30 000 terms and definitions in English and French, with equivalent terms in additional languages. Also known as the International Electrotechnical Vocabulary (IEV) on-line.

Customer Service Centre - [webstore.iec.ch/csc](http://webstore.iec.ch/csc)

If you wish to give us your feedback on this publication or need further assistance, please contact the Customer Service Centre: [csc@iec.ch](mailto:csc@iec.ch).

<https://standards.iteh.ai/catalog/standards/sist/6163e854-a2c4-45fc-a743-2cdd120fd7bd/iec-tr-62730-2012>

# TECHNICAL REPORT

---

**HV polymeric insulators for indoor and outdoor use tracking and erosion testing  
by wheel test and 5 000h test**

**STANDARD PREVIEW**  
(standards.iteh.ai)  
<https://standards.iteh.ai/catalog/standards/sist/6163e854-a2c4-45fc-a743-2cdd120fd7bd/iec-tr-62730-2012>

INTERNATIONAL  
ELECTROTECHNICAL  
COMMISSION

PRICE CODE

R

ICS 29.080.10

ISBN 978-2-8322-0070-4

**Warning! Make sure that you obtained this publication from an authorized distributor.**

## CONTENTS

FOREWORD.....	3
INTRODUCTION.....	5
1 Scope and object.....	6
2 Normative references .....	6
3 Terms and definitions .....	6
4 Background to the tracking and erosion tests .....	8
4.1 Difference between the tracking and erosion and accelerated ageing tests on polymeric insulators .....	8
4.2 The wheel test.....	8
4.3 The 5 000h multiple stress test.....	9
5 Classification of tests .....	10
6 General requirements for insulator test specimens .....	10
7 The tests .....	10
7.1 Wheel test.....	10
7.1.1 Test specimens .....	10
7.1.2 Procedure.....	10
7.1.3 Test conditions .....	12
7.1.4 Acceptance criteria.....	12
7.2 5 000 hour test (test at multiple stresses).....	12
7.2.1 Test specimen .....	12
7.2.2 Procedure.....	12
7.2.3 Test conditions .....	13
7.2.4 Voltage.....	15
7.2.5 Solar simulation.....	15
7.2.6 Artificial rain .....	15
7.2.7 Dry heat .....	16
7.2.8 Humidity .....	16
7.2.9 Pollution .....	16
7.2.10 Salt fog calibration.....	16
7.2.11 Acceptance criteria.....	18
Bibliography.....	19
Figure 1 – Test arrangement of the tracking wheel test.....	11
Figure 2 – Typical layout of the test specimens in the chamber and main dimensions of the chamber.....	13
Figure 3 – Multiple stress cycle.....	14
Figure 4 – Typical layout of the rain and salt fog spray systems and the xenon lamp .....	14
Figure 5 – Spectrum of xenon arc lamp and solar spectrum .....	15
Figure 6 – Reference porcelain insulator.....	17

## INTERNATIONAL ELECTROTECHNICAL COMMISSION

## HV POLYMERIC INSULATORS FOR INDOOR AND OUTDOOR USE TRACKING AND EROSION TESTING BY WHEEL TEST AND 5 000H TEST

### FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

The main task of IEC technical committees is to prepare International Standards. However, a technical committee may propose the publication of a technical report when it has collected data of a different kind from that which is normally published as an International Standard, for example "state of the art".

IEC 62730, which is a technical report, has been prepared by IEC technical committee 36: Insulators.

The text of this technical report is based on the following documents:

Enquiry draft	Report on voting
36/305/DTR	36/316A/RVC

Full information on the voting for the approval of this technical report can be found in the report on voting indicated in the above table.

This publication has been drafted in accordance with the ISO/IEC Directives, Part 2.

The committee has decided that the contents of this publication will remain unchanged until the stability date indicated on the IEC web site under "<http://webstore.iec.ch>" in the data related to the specific publication. At this date, the publication will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

A bilingual version of this publication may be issued at a later date.

## **iTeh STANDARD PREVIEW (standards.iteh.ai)**

[IEC TR 62730:2012](#)

<https://standards.iteh.ai/catalog/standards/sist/6163e854-a2c4-45fc-a743-2cdd120fd7bd/iec-tr-62730-2012>

## INTRODUCTION

IEC 62217 [1]<sup>1</sup> included three different tracking and erosion tests. One, the 1 000 hour salt-fog test, was included in the main text as a default test and two others, the 5 000 hour test and the tracking wheel test, were given in annexes as alternative tests.

Following a decision by TC 36 it was decided that it was desirable to have a single standardised test in IEC 62217; hence a study of the usage and effectiveness of all three tests was undertaken by Working Group 12 of TC 36. The results of this study indicated that, while the 5 000h and the tracking wheel tests each had their advantages, only the 1 000 hour salt fog test was adapted to all insulator types and was more economical to perform.

It was decided by TC 36 to adopt the 1 000 hour salt-fog test as the only standardised test. It was also decided to draft this Technical Report to reproduce the 5 000 hour and the tracking wheel test procedures in order to keep the information on the test methods and parameters available for those wishing to use those tests for research or other purposes.

The tracking and erosion tests given in this technical report are considered as screening tests intended to reject materials or designs which are inadequate. These tests are not intended to predict long-term performance for insulator designs under cumulative service stresses.

Composite insulators are used in both a.c. and d.c. applications. In spite of this fact a specific tracking and erosion test procedure for d.c. applications as a design test has not yet been defined and accepted.

IEC Guide 111 has been followed during preparation of this technical report wherever possible.

[IEC TR 62730:2012](https://standards.iteh.ai/catalog/standards/sist/6163e854-a2c4-45fc-a743-2cdd120fd7bd/iec-tr-62730-2012)

<https://standards.iteh.ai/catalog/standards/sist/6163e854-a2c4-45fc-a743-2cdd120fd7bd/iec-tr-62730-2012>

---

<sup>1</sup> Numbers in square brackets refer to the Bibliography.

# HV POLYMERIC INSULATORS FOR INDOOR AND OUTDOOR USE TRACKING AND EROSION TESTING BY WHEEL TEST AND 5 000H TEST

## 1 Scope and object

This technical report is applicable to polymeric insulators whose insulating body consists of one or various organic materials. Polymeric insulators covered by this technical report include both solid core and hollow insulators. They are intended for use on overhead lines and in indoor and outdoor equipment with a rated voltage greater than 1 000 V.

The object of this technical report is:

- to define the common terms used;
- to give the background behind the development and use of the 5 000 h multiple stress test and the tracking wheel test;
- to describe the test methods for the 5 000 h multiple stress test and the tracking wheel tests on polymeric insulators;
- to describe possible acceptance or failure criteria, if applicable;

These tests, criteria and recommendations are intended to give a common basis for the 5 000h multiple stress test and the tracking wheel test when they are used for research or required as a supplementary design test. These tests are not mandatory and their use is subject to prior agreement between the interested parties.

## 2 Normative references

[IEC TR 62730:2012](https://standards.iteh.ai/catalog/standards/sist/6163e854-a2c4-45fc-a743-2cdd120fd7bd/iec-tr-62730-2012)

<https://standards.iteh.ai/catalog/standards/sist/6163e854-a2c4-45fc-a743-2cdd120fd7bd/iec-tr-62730-2012>

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60050-47:2007, *International Electrotechnical Vocabulary – Part 471: Insulators*

IEC 60060-1, *High-voltage test techniques – Part 1: General definitions and test requirements.*

IEC 60507, *Artificial pollution tests on high-voltage insulators to be used on a.c. systems*

IEC 60815-2, *Selection and dimensioning of high-voltage insulators intended for use in polluted conditions – Part 2: Ceramic and glass insulators for a.c. systems*

## 3 Terms and definitions

For the purposes of this document the terms and definitions given in IEC 60050 (471) and the following apply:

### 3.1

#### **polymeric insulator**

insulator whose insulating body consists of at least one organic based material. Coupling devices may be attached to the ends of the insulating body

Note 1 to entry: Polymeric insulators are also known as non-ceramic insulators.

[SOURCE: IEC 60050-471:2007, 471-01-13, modified]



### 3.2

#### **core**

central insulating part of an insulator which provides the mechanical characteristics

Note 1 to entry: The housing and sheds are not part of the core.

[SOURCE: IEC 60050-471:2007, 471-01-03]

### 3.3

#### **insulator trunk**

central insulating part of an insulator from which the sheds project.

Note 1 to entry: Also known as shank on smaller insulators.

[SOURCE: IEC 60050-471:2007, 471-01-11]

### 3.4

#### **housing**

external insulating part of a composite insulator providing the necessary creepage distance and protects the core from the environment

Note 1 to entry: An intermediate sheath made of insulating material may be part of the housing.

[SOURCE: IEC 60050-471:2007, 471-01-09]

### 3.5

#### **shed**

insulating part, projecting from the insulator trunk, intended to increase the creepage distance.

Note 1 to entry: The shed can be with or without ribs.

[SOURCE: IEC 60050-471:2007, 471-01-15]

### 3.6

#### **creepage distance**

shortest distance or the sum of the shortest distances along the surface on an insulator between two conductive parts which normally have the operating voltage between them

Note 1 to entry: The surface of cement or of any other non-insulating jointing material is not considered as forming part of the creepage distance.

Note 2 to entry: If a high resistance coating is applied to parts of the insulating part of an insulator, such parts are considered to be effective insulating surfaces and the distance over them is included in the creepage distance.

[SOURCE: IEC 60050-471:2007, 471-01-04]

### 3.7

#### **interfaces**

surface between the different materials. Various interfaces occur in most composite insulators, e.g.:

- between housing and fixing devices;
- between various parts of the housing; e.g. between sheds, or between sheath and sheds;
- between core and housing;

### 3.8

#### **tracking**

process which forms irreversible degradation by formation of conductive paths (tracks) starting and developing on the surface of an insulating material. These paths are conductive even under dry conditions

### **3.9 erosion**

irreversible and non-conducting degradation of the surface of the insulator that occurs by loss of material. This can be uniform, localized or tree-shaped.

Note 1 to entry: Light surface traces, commonly tree-shaped, can occur on composite insulators as on ceramic insulators, after partial flashover. These traces are not considered to be objectionable as long as they are non-conductive. When they are conductive they are classified as tracking.

### **3.10 crack**

any internal fracture or surface fissure of depth greater than 0,1 mm

### **3.11 puncture**

permanent loss of dielectric strength due to a disruptive discharge passing through the solid insulating material of an insulator

[SOURCE: IEC 60050-471:2007, 471-01-14, modified]

## **4 Background to the tracking and erosion tests**

### **4.1 Difference between the tracking and erosion and accelerated ageing tests on polymeric insulators**

Although this Technical Report describes tracking and erosion tests which often may be referred to in the literature as “ageing tests” it is important to note that they are not accelerated ageing tests in the sense that these tests do not simulate exactly real life degradation conditions nor do they accelerate them to give a life-equivalent test in a short time. Rather they use continuous, cyclic or combined stresses to try to detect potential weaknesses which could compromise the insulators performance in service.

The tests are better described as screening tests, which can be used to reject materials, designs, or combinations thereof which are inadequate.

The ageing mechanisms on a polymeric insulator generally do not cause a progressive reduction of easily measurable ageing-induced properties with time. The transition from “good condition” to “end of life” is frequently rapid with no forewarning and might be observed by, for instance, erosion to depths comparable to those obtained in the 1 000 hour salt fog test defined in IEC 62217 or deep UV-initiated cracks in the surfaces. The time and speed of this transition depends on multiple parameters, both of the insulator material and design and of the operating environment. Hence the use of such ageing tests for true “end of life” prediction is only possible when relevant data on damage and degradation is available for the same or similar insulators in the same or similar environments.

Therefore these tests are used to give a general indication of the quality of the design and materials with respect to the stresses arising in relatively harsh but not extreme environments.

For further information, see [2].

### **4.2 The wheel test**

The tracking wheel test was originally developed in Canada and introduced in the Canadian Electrical Association Light Weight Insulator Working Group CEA LWIWG-01 – Dead-end suspension composite insulator standard in 1991. It was named Tracking Wheel # 2.

The # 1 version was a spray system rather than a dip system.

The original concept was to energize, at 35 V/mm of creepage, the insulator sample which had been dipped in a NaCl solution of 1,40 g/l of water and allowed to drip. It was continuous for the duration of the 30 000 cycles. The original acceptance criteria were: no tracking, no erosion to the core and no shed or housing puncture. Every unit was then tested with a steep front impulse and a power frequency voltage test.

The wheel test was not deemed to be an ageing test by the CEA. Although there were discussions 20 years ago to correlate the aspects of the tested insulators with insulators in the field and to estimate an aging factor, such correlation was never implied in the standard. There was also consideration to modify the test parameters to reflect different pollution severities. This was never introduced.

In the LWIWG-01-1996 version, the description of the test was modified to describe the de-ionized water and introduce a rest period of 24 hours where the dip tank is empty. It was observed during the first part of the 1990s that silicone-based housings did not perform well when the test was uninterrupted. This corresponds to the concept of hydrophobicity recovery which had gained popularity by that time.

In 2010, the test in the standard was re-affirmed in CSA C411.5 with basically the same parameters.

In this IEC version, there are no provisions for a rest period, nor impulse and flashover tests following the 30 000 cycles. There is allocation for test interruptions and a requirement to change the dip tank solution weekly. The IEC version gives precise guidelines as to the acceptable erosion depth.

This test is mandatory in the CSA insulator standards. For more than 20 years, this test has been considered able to detect insulator designs that are not suitable for use on overhead transmission lines. It is not meant as an ageing test with an estimated acceleration factor.

[https://standards.iteh.ai/catalog/standards/sist/6163e854-a2c4-45fc-a743-](https://standards.iteh.ai/catalog/standards/sist/6163e854-a2c4-45fc-a743-311120fd7bd/iec-tr-62730-2012)

#### 4.3 The 5 000h multiple stress test

The 5 000h multiple stress test was initially developed by CIGRE WG 22.10 which was set up in 1978 to establish a technical basis for minimum requirements for composite insulators. Their work was published in 1983 [3] and included a proposal for a multi-stress 5 000 hour test combining cycles of humidity, heating, rain, salt fog and solar radiation on energised insulators. The intention of the test was to reproduce any synergy between the multiple stresses seen by insulators in service that might not be present in a single stress test. Later work by EDF in France using the same “CIGRE” cycles reported varying acceleration factors with respect to different test station environments [4] and classed the test as an accelerated ageing test.

A similar, but not identical, test cycle was used in Italy as an accelerated ageing test and it was deemed necessary to “fix” the test parameters by including it in IEC 61109:1992 [5]. At this point it was given as an alternative to the 1 000h salt-fog test for insulators intended for extreme conditions. IEC 61109:1992 did not mention any acceleration factors.

When it was decided to group common tests for composite insulators into IEC 62217:2005, the test was included an alternative tracking and erosion test, not an accelerated ageing test. The version of the test in 62217:2005 had been revised by IEC TC 36 WG12 on the basis of work between Sweden and France to improve the reproducibility of the test which had been shown to be problematic [6]. The main improvement involved calibration of the salt-fog cycle by using standard dummy insulators at each test position to set up fog distribution and flow rate.

The procedure included in this Technical Report includes some minor alterations to further improve reproducibility.