



SLOVENSKI STANDARD

SIST ISO 11437-1:1996

01-avgust-1996

B]`^j Yn`hjbY!`I [cHj `Ub^XYjYg`YXcj b]`YYa Ybhcj `n'a YhcXc
YY_hfchfa] bYUca g_YUVgcfDWg_YgdY_hfca Yfj^Y!`%`XY.`Gd`cýbYnU hYj Y]b
fUhUd`Ub^j ncfWU

Nickel alloys -- Determination of trace-element content by electrothermal atomic absorption spectrometric method -- Part 1: General requirements and sample dissolution

iTeh STANDARD PREVIEW

(standards.iteh.ai)

Alliages de nickel -- Dosage des éléments-traces -- Méthode par spectrométrie d'absorption atomique à excitation électrothermique -- Partie 1: Caractéristiques générales et mise en solution de l'échantillon

<https://standards.iteh.ai/catalog/standards/sist/caf2cb93-4573-4576-b4ed-36e75fa139fc/sist-iso-11437-1-1996>

Ta slovenski standard je istoveten z: ISO 11437-1:1994

ICS:

77.120.40	Nikelj, krom in njune zlitine	Nickel, chromium and their alloys
-----------	-------------------------------	-----------------------------------

SIST ISO 11437-1:1996

en

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST ISO 11437-1:1996

<https://standards.iteh.ai/catalog/standards/sist/eaf2cb93-4573-4576-b4ed-36e75fa139fc/sist-iso-11437-1-1996>

INTERNATIONAL STANDARD

ISO
11437-1

First edition
1994-12-01

Nickel alloys — Determination of trace-element content by electrothermal atomic absorption spectrometric method —

iTeh STANDARD PREVIEW

(standards.iteh.ai)

Part 1:
General requirements and sample dissolution

[SIST ISO 11437-1:1996](https://standards.iteh.ai/catalog/standards/sist/eaf2cb93-4573-4576-b4ed-36e75fa139fc/sist-iso-11437-1-1996)

[https://standards.iteh.ai/catalog/standards/sist/eaf2cb93-4573-4576-b4ed-](https://standards.iteh.ai/catalog/standards/sist/eaf2cb93-4573-4576-b4ed-36e75fa139fc/sist-iso-11437-1-1996)

[36e75fa139fc/sist-iso-11437-1-1996](https://standards.iteh.ai/catalog/standards/sist/eaf2cb93-4573-4576-b4ed-36e75fa139fc/sist-iso-11437-1-1996)

*Alliages de nickel — Dosage des éléments-traces — Méthode par
spectrométrie d'absorption atomique à excitation électrothermique —*

Partie 1: Caractéristiques générales et mise en solution de l'échantillon



Reference number
ISO 11437-1:1994(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

International Standard ISO 11437-1 was prepared by Technical Committee ISO/TC 155, *Nickel and nickel alloys*, Subcommittee SC 4, *Analysis of nickel alloys*.

<https://standards.iteh.ai/catalog/standards/sist/eaf2cb93-4573-4576-b4ed-10258199905a-iso-11437-1-1996>

ISO 11437 consists of the following parts, under the general title: *Nickel alloys — Determination of trace-element content by electrothermal atomic absorption spectrometric method*:

- Part 1: *General requirements and sample dissolution*
- Part 2: *Determination of lead content*
- Part 3: *Determination of bismuth content*
- Part 4: *Determination of silver content*

Annex A forms an integral part of this part of ISO 11437. Annex B is for information only.

Introduction

This part of ISO 11437 is to be used in conjunction with the other parts which specify methods for the determination of individual trace elements in nickel alloys by electrothermal atomic absorption spectrometry.

Although the analytical methods are specified in independent International Standards, it is possible to determine more than one element on a single test solution.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST ISO 11437-1:1996](https://standards.iteh.ai/catalog/standards/sist/caf2cb93-4573-4576-b4ed-36e75fa139fc/sist-iso-11437-1-1996)

<https://standards.iteh.ai/catalog/standards/sist/caf2cb93-4573-4576-b4ed-36e75fa139fc/sist-iso-11437-1-1996>

iTeh STANDARD PREVIEW

This page intentionally left blank
(standards.iteh.ai)

SIST ISO 11437-1:1996

<https://standards.iteh.ai/catalog/standards/sist/eaf2cb93-4573-4576-b4ed-36e75fa139fc/sist-iso-11437-1-1996>

Nickel alloys — Determination of trace-element content by electrothermal atomic absorption spectrometric method —

Part 1:

General requirements and sample dissolution

1 Scope

1.1 ISO 11437 specifies electrothermal atomic absorption methods for the determination of trace elements in nickel alloys, in the concentration ranges given in clause 1 of other parts of ISO 11437. Other elements may be added in subsequent parts of ISO 11437. Typical compositions of some nickel alloys are given in annex B.

1.2 This part of ISO 11437 specifies the general requirements for analysis by electrothermal atomic absorption spectrometry, preparation and dissolution of the test sample, method of calculation and the procedures used for the evaluation of the repeatability and reproducibility of the individual methods specified in other parts of ISO 11437.

2 Normative references

The following standards contain provisions which, through reference in this text, constitute provisions of this part of ISO 11437. At the time of publication, the editions indicated were valid. All standards are subject to revision, and parties to agreements based on this part of ISO 11437 are encouraged to investigate the possibility of applying the most recent editions of the standards indicated below. Members of IEC and ISO maintain registers of currently valid International Standards.

ISO 385-1:1984, *Laboratory glassware — Burettes — Part 1: General requirements.*

ISO 648:1977, *Laboratory glassware — One-mark pipettes.*

ISO 1042:1983, *Laboratory glassware — One-mark volumetric flasks.*

ISO 5725:1986, *Precision of test methods — Determination of repeatability and reproducibility for a standard test method by inter-laboratory tests.*

3 Principle

Dissolution of a test portion in a mixture of dilute nitric acid and hydrofluoric acid.

Dilution of the test solution to a known volume and transfer of an aliquot to a plastics vial.

Addition of a modifier and/or diluent, where necessary, and injection of a small volume of the test solution into an electrothermal atomizer.

Measurement of the absorption of the resonance line energy from the spectrum of the element being determined and comparison with that of calibration solutions containing the same element.

4 Reagents

During the analysis, unless otherwise stated, use only

reagents of recognized analytical grade and only distilled water or water of equivalent purity.

4.1 High purity metals, 99,9 % (*m/m*) minimum, as specified in the relevant part of ISO 11437.

4.2 Nitric acid, $\rho_{20} = 1,41$ g/ml, diluted 1+1.

4.3 Hydrofluoric acid, $\rho_{20} = 1,13$ g/ml.

WARNING — Hydrofluoric acid is extremely irritating and corrosive to skin and mucous membranes, producing severe skin burns which are slow to heal. In the case of contact with skin, wash well with water and seek medical advice.

4.4 Acid mixture for dissolution.

Carefully add 150 ml of nitric acid ($\rho_{20} = 1,41$ g/ml) and 150 ml of the hydrofluoric acid (4.3) to 150 ml of water. Mix and store in a plastics bottle.

4.5 Modifiers.

Prepare separately for each metal as specified in the appropriate part of ISO 11437.

4.6 Standard reference solutions, 100 mg/l of metal.

Prepare separately for each metal as specified in the relevant part of ISO 11437.

5 Apparatus

Ordinary laboratory apparatus, and

5.1 Atomic absorption spectrometer.

5.1.1 The atomic absorption spectrometer used in this method shall be fitted with an electrothermal atomizer and shall meet the performance criteria given in annex A.

5.1.2 The spectrometer shall be equipped with a background corrector and a rapid recording system capable of measuring peak heights and peak areas. The electrothermal atomizer shall be fitted with a pyrolytic graphite tube and L'vov platform, or a normal graphite tube as specified in the relevant part of ISO 11437.

5.1.3 The spectrometer should be capable of using single-element hollow cathode lamps or electrodeless discharge lamps operated at currents recommended by the manufacturer.

5.2 Polytetrafluoroethylene (PTFE) beakers, of capacity 100 ml.

5.3 Plastics vials, of capacity 5 ml.

5.4 Plastics volumetric flasks, of capacities 50 ml and 100 ml.

5.5 Glass volumetric flasks, of capacities 100 ml, 500 ml and 1 000 ml, in accordance with ISO 1042, Class A.

5.6 Burettes, of capacities 10 ml (graduated in divisions of 0,02 ml) and 25 ml (graduated in divisions of 0,1 ml), in accordance with ISO 385-1, Class A.

5.7 Pipettes, in accordance with ISO 648, Class A.

5.8 Mechanical micropipettes, of capacities 10 μ l to 100 μ l.

5.9 Variable mechanical pipette, of capacity 2,0 μ l to 10,0 μ l, fitted with plastics positive displacement tips.

6 Sampling and sample preparation

6.1 Sampling and preparation of the laboratory sample shall be carried out by normal agreed procedures or, in case of dispute, by the relevant International Standard.

6.2 The laboratory sample normally is in the form of turnings, millings or drillings and no further mechanical preparation of the sample is necessary.

6.3 The laboratory sample shall be cleaned by washing with pure acetone and drying in air.

6.4 If brazed alloy tools are used in the preparation of the laboratory sample, the sample shall be further cleaned by pickling in dilute nitric acid for a few minutes. The sample shall then be washed several times with distilled water followed by several washings with acetone, and air dried.

7 Procedure

7.1 Preparation of test solution — General method

7.1.1 Weigh, to the nearest 0,001 g, 0,500 g of the laboratory sample and transfer to the 100 ml PTFE beaker (5.2). Add 20 ml of the acid mixture for dissolution (4.4). Apply sufficient heat to initiate and maintain the reaction until dissolution is complete.

7.1.2 Cool the solution and proceed as directed in the relevant part of ISO 11437.

NOTE 1 It may be difficult to dissolve certain alloys in the nitric acid-hydrofluoric acid mixture. In such cases, the proportions of the dissolving mixture may be adjusted, but a corresponding blank test is necessary.

7.2 Blank test

Carry out a blank test in parallel with the determination, following the same procedure and using the same quantities of all the reagents.

7.3 Preparation of calibration solutions

Proceed as directed in the relevant part of ISO 11437.

7.4 Calibration and determination

7.4.1 Atomic absorption measurements

7.4.1.1 The spectral lines for each element, the type of graphite tube and the measurement mode (peak height or peak area integration) to be used in the analysis are specified in the relevant part of ISO 11437. Condition new graphite tubes as instructed by the manufacturer.

7.4.1.2 Establish the optimum furnace temperature programme in accordance with the instructions given in annex A.

7.4.1.3 The volume injected into the furnace shall be between 10 μ l and 50 μ l, depending on the sensitivity of the analyte.

7.4.1.4 Starting with the calibration solutions, atomize the preselected volume (10 μ l to 50 μ l). Record three absorbance measurements for each of the calibration solutions.

7.4.1.5 Atomize the preselected volume (10 μ l to 50 μ l) for the blank solution. Record three absorbance measurements.

7.4.1.6 Check the calibration slope by atomizing the preselected volume (10 μ l to 50 μ l) of the zero and highest calibration solutions. Record three measurements for each of the solutions.

7.4.1.7 Atomize the preselected volume (10 μ l to 50 μ l) for two of the test solutions. Record three absorbance measurements.

7.4.1.8 Repeat the instructions in 7.4.1.6 and 7.4.1.7 until all of the test solutions are measured.

7.4.1.9 Calculate the means of the three absorbance measurements obtained in 7.4.1.4 to 7.4.1.8.

7.4.2 Preparation of calibration graphs

7.4.2.1 Subtract the mean absorbance value obtained for the 0 μ g/l calibration solution from the mean absorbance values obtained for the remaining calibration solutions.

7.4.2.2 Construct a graph relating the mean absorbance values obtained for the calibration solutions (7.4.2.1) to their analyte concentrations (in micrograms per litre).

8 Expression of results

8.1 Calculation

8.1.1 Using the mean absorbance obtained for the blank test solution (7.4.1.5), determine the analyte concentration of the blank test solution from the calibration curve (7.4.2.2).

8.1.2 If the calibration check measurement obtained in 7.4.1.6 shows that the calibration curve has drifted significantly, adjust the calibration curve accordingly.

8.1.3 Using the mean absorbance values obtained in 7.4.1.7, determine the analyte concentration of two of the test solutions.

8.1.4 Repeat the instructions given in 8.1.2 and 8.1.3 until the analyte concentrations of the remaining test solutions are obtained.

8.1.5 Subtract the analyte concentration of the blank test solution (8.1.1) from the analyte concentration of the test solutions found in 8.1.3 and 8.1.4.