

# INTERNATIONAL STANDARD

# NORME INTERNATIONALE

Specifications for particular types of winding wires –  
Part 0-1: General requirements – Enamelled round copper wire  
(standards.iteh.ai)

Spécifications pour types particuliers de fils de bobinage –  
Partie 0-1: Exigences générales – Fil de section circulaire en cuivre émaillé

<https://standards.iteh.ai/catalog/standards/sist/60317-0-1/iec-60317-0-1-2013>  
5787a8272211/iec-60317-0-1-2013



**THIS PUBLICATION IS COPYRIGHT PROTECTED**  
**Copyright © 2013 IEC, Geneva, Switzerland**

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester.  
If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

Droits de reproduction réservés. Sauf indication contraire, aucune partie de cette publication ne peut être reproduite ni utilisée sous quelque forme que ce soit et par aucun procédé, électronique ou mécanique, y compris la photocopie et les microfilms, sans l'accord écrit de la CEI ou du Comité national de la CEI du pays du demandeur.  
Si vous avez des questions sur le copyright de la CEI ou si vous désirez obtenir des droits supplémentaires sur cette publication, utilisez les coordonnées ci-après ou contactez le Comité national de la CEI de votre pays de résidence.

IEC Central Office  
3, rue de Varembe  
CH-1211 Geneva 20  
Switzerland

Tel.: +41 22 919 02 11  
Fax: +41 22 919 03 00  
[info@iec.ch](mailto:info@iec.ch)  
[www.iec.ch](http://www.iec.ch)

### About the IEC

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

### About IEC publications

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigenda or an amendment might have been published.

#### Useful links:

IEC publications search - [www.iec.ch/searchpub](http://www.iec.ch/searchpub)

The advanced search enables you to find IEC publications by a variety of criteria (reference number, text, technical committee,...).

It also gives information on projects, replaced and withdrawn publications.

IEC Just Published - [webstore.iec.ch/justpublished](http://webstore.iec.ch/justpublished)

Stay up to date on all new IEC publications. Just Published details all new publications released. Available on-line and also once a month by email.

Electropedia - [www.electropedia.org](http://www.electropedia.org)

The world's leading online dictionary of electronic and electrical terms containing more than 30 000 terms and definitions in English and French, with equivalent terms in additional languages. Also known as the International Electrotechnical Vocabulary (IEV) on-line.

Customer Service Centre - [webstore.iec.ch/csc](http://webstore.iec.ch/csc)

If you wish to give us your feedback on this publication or need further assistance, please contact the Customer Service Centre: [csc@iec.ch](mailto:csc@iec.ch).

---

### A propos de la CEI

La Commission Electrotechnique Internationale (CEI) est la première organisation mondiale qui élabore et publie des Normes internationales pour tout ce qui a trait à l'électricité, à l'électronique et aux technologies apparentées.

### A propos des publications CEI

Le contenu technique des publications de la CEI est constamment revu. Veuillez vous assurer que vous possédez l'édition la plus récente, un corrigendum ou amendement peut avoir été publié.

#### Liens utiles:

Recherche de publications CEI - [www.iec.ch/searchpub](http://www.iec.ch/searchpub)

La recherche avancée vous permet de trouver des publications CEI en utilisant différents critères (numéro de référence, texte, comité d'études,...).

Elle donne aussi des informations sur les projets et les publications remplacées ou retirées.

Just Published CEI - [webstore.iec.ch/justpublished](http://webstore.iec.ch/justpublished)

Restez informé sur les nouvelles publications de la CEI. Just Published détaille les nouvelles publications parues. Disponible en ligne et aussi une fois par mois par email.

Electropedia - [www.electropedia.org](http://www.electropedia.org)

Le premier dictionnaire en ligne au monde de termes électroniques et électriques. Il contient plus de 30 000 termes et définitions en anglais et en français, ainsi que les termes équivalents dans les langues additionnelles. Egalement appelé Vocabulaire Electrotechnique International (VEI) en ligne.

Service Clients - [webstore.iec.ch/csc](http://webstore.iec.ch/csc)

Si vous désirez nous donner des commentaires sur cette publication ou si vous avez des questions contactez-nous: [csc@iec.ch](mailto:csc@iec.ch).



IEC 60317-0-1

Edition 4.0 2013-10

# INTERNATIONAL STANDARD

## NORME INTERNATIONALE

Specifications for particular types of winding wires –  
Part 0-1: General requirements – Enamelled round copper wire

Spécifications pour types particuliers de fils de bobinage –  
Partie 0-1: Exigences générales – Fil de section circulaire en cuivre émaillé

INTERNATIONAL  
ELECTROTECHNICAL  
COMMISSION

COMMISSION  
ELECTROTECHNIQUE  
INTERNATIONALE

PRICE CODE  
CODE PRIX



ICS 29.060.10

ISBN 978-2-8322-1150-2

**Warning! Make sure that you obtained this publication from an authorized distributor.  
Attention! Veuillez vous assurer que vous avez obtenu cette publication via un distributeur agréé.**

## CONTENTS

FOREWORD.....	4
INTRODUCTION.....	6
1 Scope.....	7
2 Normative references.....	7
3 Terms, definitions, general notes and appearance.....	7
3.1 Terms and definitions .....	7
3.2 General notes .....	8
3.2.1 Methods of test .....	8
3.2.2 Winding wire.....	9
3.3 Appearance .....	9
4 Dimensions.....	9
4.1 Conductor diameter .....	9
4.2 Out of roundness of conductor (nominal conductor diameters over 0,063 mm).....	13
4.3 Minimum increase in diameter due to the insulation and the bonding layer (nominal conductor diameters over 0,063 mm).....	13
4.3.1 Enamelled wires without a bonding layer .....	13
4.3.2 Enamelled wires with a bonding layer .....	13
4.3.3 Intermediate nominal conductor diameters .....	13
4.4 Maximum overall diameter.....	13
4.4.1 Enamelled wires without a bonding layer .....	13
4.4.2 Enamelled wires with a bonding layer .....	14
5 Electrical resistance.....	14
6 Elongation .....	15
7 Springiness.....	15
7.1 Nominal conductor diameters from 0,080 mm up to and including 1,600 mm .....	15
7.2 Nominal conductor diameters over 1,600 mm.....	15
8 Flexibility and adherence .....	17
8.1 Mandrel winding test (nominal conductor diameters up to and including 1,600 mm).....	17
8.2 Stretching test (nominal conductor diameters over 1,600 mm).....	17
8.3 Jerk test (nominal conductor diameters up to and including 1,000 mm) .....	17
8.4 Peel test (nominal conductor diameters over 1,000 mm) .....	17
9 Heat shock .....	18
9.1 Nominal conductor diameters up to and including 1,600 mm.....	18
9.2 Nominal conductor diameters over 1,600 mm.....	18
10 Cut-through .....	19
11 Resistance to abrasion .....	19
12 Resistance to solvents .....	19
13 Breakdown voltage .....	19
13.1 General .....	19
13.2 Nominal conductor diameters up to and including 0,100 mm.....	19
13.3 Nominal conductor diameters over 0,100 mm up to and including 2,500 mm.....	21
13.4 Nominal conductor diameters over 2,500 mm.....	23
14 Continuity of insulation (nominal conductor diameters up to and including 1,600 mm).....	24
15 Temperature index.....	24

16 Resistance to refrigerants .....	24
17 Solderability .....	24
18 Heat or solvent bonding .....	24
19 Dielectric dissipation factor .....	24
20 Resistance to transformer oil .....	24
21 Loss of mass .....	24
23 Pin hole test .....	25
30 Packaging .....	25
Annex A (informative) Dimensions for intermediate nominal conductor diameters (R 40) .....	26
Annex B (informative) Method for the calculation of linear resistance .....	30
Annex C (informative) Resistance .....	32
Bibliography .....	34
Table 1 – Dimensions of enamelled wires (R 20) – Preferred nominal conductor diameters (1 of 2) .....	10
Table 2 – Dimensions of enamelled wires with a bonding layer (R 20) – Preferred nominal conductor diameters (1 of 2) .....	12
Table 3 – Electrical resistance .....	14
Table 4 – Elongation .....	15
Table 5 – Springiness .....	16
Table 6 – Mandrel winding .....	17
Table 7 – Heat shock .....	18
Table 8 – Breakdown voltage – Preferred nominal conductor diameters (R 20) (0,018 mm up to and including 0,100 mm) .....	20
Table 9 – Breakdown voltage – Intermediate nominal conductor diameters (R 40) (0,019 mm up to and including 0,095 mm) .....	21
Table 10 – Breakdown voltage – Preferred nominal conductor diameters (R 20) (0,112 mm up to and including 2,500 mm) .....	22
Table 11 – Breakdown voltage – Intermediate nominal conductor diameters (R 40) (0,106 mm up to and including 0,950 mm) .....	23
Table 12 – Breakdown voltage – Nominal conductor diameters over 2,500 mm .....	23
Table 13 – Continuity of insulation .....	24
Table 14 – Maximum number of pin holes .....	25
Table A.1 – Dimensions of enamelled wires (R 40) – Intermediate nominal conductor diameters (1 of 2) .....	26
Table A.2 – Dimensions of enamelled wires with a bonding layer (R 40) – Intermediate nominal conductor diameters (1 of 2) .....	28
Table B.1 – Ratios .....	31
Table C.1 – Electrical resistances – Nominal conductor diameters over 0,063 mm up to and including 1,000 mm (1 of 2) .....	32

## INTERNATIONAL ELECTROTECHNICAL COMMISSION

**SPECIFICATIONS FOR PARTICULAR TYPES  
OF WINDING WIRES –****Part 0-1: General requirements –  
Enamelled round copper wire**

## FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as “IEC Publication(s)”). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.  
<https://standards.iteh.ai/catalog/standards/sist/fb1c42ed-45aa-4c16-84ed-48272719c006>
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

International Standard IEC 60317-0-1 has been prepared by IEC technical committee 55: Winding wires.

This fourth edition cancels and replaces the third edition published in 2008. This edition constitutes a technical revision.

This edition includes the following significant technical changes with respect to the previous edition:

- revision to the definition of nominal conductor dimension;
- new subclause containing general notes on winding wire, formerly a part of the scope;
- revision to elongation requirements in Table 4;
- revisions to Clause 13, Breakdown voltage, to include new requirements for intermediate wire diameters;

- revision to continuity of insulation requirements in Table 13;
- revision to the introduction of Annex A;
- revision to B.2 of Annex B;
- revision to Table C.1 of Annex C.

This standard is to be read in conjunction with the IEC 60851 series. The clause numbers used in this part of IEC 60317 are identical with the respective test numbers of the IEC 60851 series.

In case of inconsistencies between IEC 60851 and this part of IEC 60317, the latter prevails.

The text of this standard is based on the following documents:

FDIS	Report on voting
55/1409/FDIS	55/1430/RVD

Full information on the voting for the approval of this standard can be found in the report on voting indicated in the above table.

This publication has been drafted in accordance with the ISO/IEC Directives, Part 2.

A list of all parts in the IEC 60317 series, published under the general title *Specifications for particular types of winding wires*, can be found on the IEC website.

The committee has decided that the contents of this publication will remain unchanged until the stability date indicated on the IEC web site under "<http://webstore.iec.ch>" in the data related to the specific publication. At this date, the publication will be

[IEC 60317-0-1:2013](#)

- reconfirmed, <https://standards.iteh.ai/catalog/standards/sist/fb1c42ed-45aa-4c16-84ed-5787a8272211/iec-60317-0-1-2013>
- withdrawn,
- replaced by a revised edition, or
- amended.

## INTRODUCTION

This part of IEC 60317 is one of a series which deals with insulated wires used for windings in electrical equipment. The series has three groups describing:

- 1) Winding wires – Test methods (IEC 60851);
- 2) Specifications for particular types of winding wires (IEC 60317);
- 3) Packaging of winding wires (IEC 60264).

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[IEC 60317-0-1:2013](https://standards.iteh.ai/catalog/standards/sist/fb1c42ed-45aa-4c16-84ed-5787a8272211/iec-60317-0-1-2013)

<https://standards.iteh.ai/catalog/standards/sist/fb1c42ed-45aa-4c16-84ed-5787a8272211/iec-60317-0-1-2013>



## SPECIFICATIONS FOR PARTICULAR TYPES OF WINDING WIRES –

### Part 0-1: General requirements – Enamelled round copper wire

#### 1 Scope

This part of IEC 60317 specifies general requirements of enamelled round copper winding wires with or without bonding layer.

The range of nominal conductor diameters is given in the relevant specification sheet.

#### 2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

iTeh STANDARD PREVIEW

IEC 60172, *Test procedure for the determination of the temperature index of enamelled winding wires*

IEC 60851 (all parts), *Winding wires – Test methods*

ISO 3, *Preferred numbers – Series of preferred numbers*

#### 3 Terms, definitions, general notes and appearance

For the purposes of this document, the following terms and definitions apply.

##### 3.1 Terms and definitions

###### 3.1.1

###### **bonding layer**

material which is deposited on an enamelled wire and which has the specific function of bonding wires together

###### 3.1.2

###### **class**

thermal performance of a wire expressed by the temperature index and the heat shock temperature

###### 3.1.3

###### **coating**

material which is deposited on a conductor or wire by a suitable means and then dried and/or cured

###### 3.1.4

###### **conductor**

bare metal after removal of the insulation

**3.1.5**

**crack**

opening in the insulation which exposes the conductor to view at the stated magnification

**3.1.6**

**dual coating**

insulation composed of two different materials, an underlying and a superimposed coating

**3.1.7**

**enamelled wire**

wire coated with an insulation of cured resin

**3.1.8**

**grade**

range of thickness of the insulation of a wire

**3.1.9**

**insulation**

coating or covering on the conductor with the specific function of withstanding voltage

**3.1.10**

**nominal conductor dimension**

designation of the conductor size in accordance with the IEC 60317 series

**iTeh STANDARD PREVIEW**

**3.1.11**

**normal vision**

20/20 vision, with corrective lenses, if necessary

**(standards.iteh.ai)**

[IEC 60317-0-1:2013](https://standards.iteh.ai/catalog/standards/sist/fb1c42ed-45aa-4c16-84ed-5787a8272211/iec-60317-0-1-2013)

**3.1.12**

**sole coating**

insulation composed of one material

<https://standards.iteh.ai/catalog/standards/sist/fb1c42ed-45aa-4c16-84ed-5787a8272211/iec-60317-0-1-2013>

**3.1.13**

**winding wire**

wire used for winding a coil to provide a magnetic field

**3.1.14**

**wire**

conductor coated or covered with an insulation

**3.2 General notes**

**3.2.1 Methods of test**

All methods of test to be used for this part of IEC 60317 are given in the IEC 60851 series.

The clause numbers used in this standard are identical to the corresponding test numbers in the IEC 60851 series of standards.

In case of inconsistencies between the publication on methods of test and this standard, IEC 60317-0-1 shall prevail.

Where no specific range of nominal conductor diameters is given for a test, the test applies to all nominal conductor diameters covered by the specification sheet.

Unless otherwise specified, all tests shall be carried out at a temperature from 15 °C to 35 °C and a relative humidity from 45 % to 75 %. Before measurements are made, the specimens

shall be preconditioned under these atmospheric conditions for a time sufficient to allow the specimens to reach stability.

The wire to be tested shall be removed from the packaging in such a way that the wire will not be subjected to tension or unnecessary bends. Before each test, sufficient wire should be discarded to ensure that any damaged wire is not included in the test specimens.

### 3.2.2 Winding wire

See the relevant specification sheet.

In addition, when reference is made to a winding wire according to a standard of the IEC 60317 series mentioned under Clause 2, the following information is given in the description:

- reference to IEC specification;
- nominal conductor diameter in millimetres;
- grade.

EXAMPLE IEC 60317-1 – 0,500 Grade 2

### 3.3 Appearance

The film coating shall be essentially smooth and continuous, free from streaks, blisters and foreign material when examined with normal vision, as wound on the original spool or reel.

When agreed upon between the user and supplier, examination using 6× to 10× magnification shall be used for wires with a nominal diameter less than 0,1 mm.

## 4 Dimensions

<https://standards.iteh.ai/catalog/standards/sist/fb1c42ed-45aa-4c16-84ed-5787a8272211/iec-60317-0-1-2013>

### 4.1 Conductor diameter

The series of preferred nominal conductor diameters shall correspond to series R 20 according to ISO 3. The actual values and their tolerances are given in Tables 1 and 2.

The series of intermediate diameters from which the user may select intermediate nominal conductor diameters, when required for technical reasons, shall correspond to series R 40 according to ISO 3. The actual values and their tolerances are given in Annex A.

The conductor diameter shall not differ from the nominal diameter by more than the limit given in Tables 1 or 2.

**Table 1 – Dimensions of enamelled wires (R 20) – Preferred nominal conductor diameters (1 of 2)**

Nominal conductor diameter mm	Conductor tolerance ± mm	Minimum increase due to the insulation mm			Maximum overall diameter mm		
		Grade 1	Grade 2	Grade 3	Grade 1	Grade 2	Grade 3
0,018		0,002	0,004	0,006	0,022	0,024	0,026
0,020		0,002	0,004	0,007	0,024	0,027	0,030
0,022		0,002	0,005	0,008	0,027	0,030	0,033
0,025		0,003	0,005	0,008	0,031	0,034	0,037
0,028		0,003	0,006	0,009	0,034	0,038	0,042
0,032		0,003	0,007	0,010	0,039	0,043	0,047
0,036		0,004	0,008	0,011	0,044	0,049	0,053
0,040		0,004	0,008	0,012	0,049	0,054	0,058
0,045		0,005	0,009	0,013	0,055	0,061	0,066
0,050		0,005	0,010	0,014	0,060	0,066	0,072
0,056		0,006	0,011	0,015	0,067	0,074	0,081
0,063		0,006	0,012	0,017	0,076	0,083	0,090
0,071	0,003	0,007	0,012	0,018	0,084	0,091	0,098
0,080	0,003	0,007	0,014	0,020	0,094	0,101	0,108
0,090	0,003	0,008	0,015	0,022	0,105	0,113	0,120
0,100	0,003	0,008	0,016	0,023	0,117	0,125	0,132
0,112	0,003	0,009	0,017	0,026	0,130	0,139	0,147
0,125	0,003	0,010	0,019	0,028	0,144	0,154	0,163
0,140	0,003	0,011	0,021	0,030	0,160	0,171	0,181
0,160	0,003	0,012	0,023	0,033	0,182	0,194	0,205
0,180	0,003	0,013	0,025	0,036	0,204	0,217	0,229
0,200	0,003	0,014	0,027	0,039	0,226	0,239	0,252
0,224	0,003	0,015	0,029	0,043	0,252	0,266	0,280
0,250	0,004	0,017	0,032	0,048	0,281	0,297	0,312
0,280	0,004	0,018	0,033	0,050	0,312	0,329	0,345
0,315	0,004	0,019	0,035	0,053	0,349	0,367	0,384
0,355	0,004	0,020	0,038	0,057	0,392	0,411	0,428
0,400	0,005	0,021	0,040	0,060	0,439	0,459	0,478
0,450	0,005	0,022	0,042	0,064	0,491	0,513	0,533
0,500	0,005	0,024	0,045	0,067	0,544	0,566	0,587

Table 1 (2 of 2)

Nominal conductor diameter mm	Conductor tolerance ± mm	Minimum increase due to the insulation mm			Maximum overall diameter mm		
		Grade 1	Grade 2	Grade 3	Grade 1	Grade 2	Grade 3
0,560	0,006	0,025	0,047	0,071	0,606	0,630	0,653
0,630	0,006	0,027	0,050	0,075	0,679	0,704	0,728
0,710	0,007	0,028	0,053	0,080	0,762	0,789	0,814
0,800	0,008	0,030	0,056	0,085	0,855	0,884	0,911
0,900	0,009	0,032	0,060	0,090	0,959	0,989	1,018
1,000	0,010	0,034	0,063	0,095	1,062	1,094	1,124
1,120	0,011	0,034	0,065	0,098	1,184	1,217	1,248
1,250	0,013	0,035	0,067	0,100	1,316	1,349	1,381
1,400	0,014	0,036	0,069	0,103	1,468	1,502	1,535
1,600	0,016	0,038	0,071	0,107	1,670	1,706	1,740
1,800	0,018	0,039	0,073	0,110	1,872	1,909	1,944
2,000	0,020	0,040	0,075	0,113	2,074	2,112	2,148
2,240	0,022	0,041	0,077	0,116	2,316	2,355	2,392
2,500	0,025	0,042	0,079	0,119	2,578	2,618	2,656
2,800	0,028	0,043	0,081	0,123	2,880	2,922	2,961
3,150	0,032	0,045	0,084	0,127	3,233	3,276	3,316
3,550	0,036	0,046	0,086	0,130	3,635	3,679	3,721
4,000	0,040	0,047	0,089	0,134	4,088	4,133	4,176
4,500	0,045	0,049	0,092	0,138	4,591	4,637	4,681
5,000	0,050	0,050	0,094	0,142	5,093	5,141	5,186

NOTE Minimum overall diameter up to and inclusive of 0,060 mm is calculated from the maximum resistance value for each corresponding diameter of Table 3, then adding the minimum increase due to the insulation.

**Table 2 – Dimensions of enamelled wires with a bonding layer (R 20) – Preferred nominal conductor diameters (1 of 2)**

Nominal conductor diameter mm	Conductor tolerance ± mm	Minimum increase underlying coating mm		Minimum increase bonding layer mm	Maximum overall diameter mm	
		Grade 1B	Grade 2B		Grade 1B	Grade 2B
0,020		0,002	0,004	0,002	0,026	0,029
0,022		0,002	0,005	0,002	0,030	0,033
0,025		0,003	0,005	0,002	0,034	0,037
0,028		0,003	0,006	0,003	0,038	0,042
0,032		0,003	0,007	0,003	0,044	0,048
0,036		0,004	0,008	0,003	0,050	0,055
0,040		0,004	0,008	0,003	0,055	0,060
0,045		0,005	0,009	0,003	0,062	0,068
0,050		0,005	0,010	0,003	0,068	0,074
0,056		0,006	0,011	0,003	0,075	0,082
0,063		0,006	0,012	0,005	0,085	0,092
0,071	0,003	0,007	0,012	0,005	0,094	0,101
0,080	0,003	0,007	0,014	0,005	0,105	0,112
0,090	0,003	0,008	0,015	0,005	0,117	0,125
0,100	0,003	0,008	0,016	0,005	0,129	0,137
0,112	0,003	0,009	0,017	0,008	0,143	0,152
0,125	0,003	0,010	0,019	0,009	0,158	0,168
0,140	0,003	0,011	0,021	0,010	0,175	0,186
0,160	0,003	0,012	0,023	0,010	0,197	0,209
0,180	0,003	0,013	0,025	0,010	0,220	0,233
0,200	0,003	0,014	0,027	0,011	0,243	0,256
0,224	0,003	0,015	0,029	0,012	0,270	0,284
0,250	0,004	0,017	0,032	0,013	0,300	0,316
0,280	0,004	0,018	0,033	0,013	0,331	0,348
0,315	0,004	0,019	0,035	0,014	0,369	0,387
0,355	0,004	0,020	0,038	0,015	0,413	0,432
0,400	0,005	0,021	0,040	0,016	0,461	0,481
0,450	0,005	0,022	0,042	0,016	0,514	0,536
0,500	0,005	0,024	0,045	0,017	0,568	0,590
0,560	0,006	0,025	0,047	0,017	0,630	0,654

Table 2 (2 of 2)

Nominal conductor diameter mm	Conductor tolerance ± mm	Minimum increase underlying coating mm		Minimum increase bonding layer mm	Maximum overall diameter mm	
		Grade 1B	Grade 2B		Grade 1B	Grade 2B
0,630	0,006	0,027	0,050	0,018	0,704	0,729
0,710	0,007	0,028	0,053	0,019	0,788	0,815
0,800	0,008	0,030	0,056	0,020	0,882	0,911
0,900	0,009	0,032	0,060	0,020	0,987	1,017
1,000	0,010	0,034	0,063	0,021	1,091	1,123
1,120	0,011	0,034	0,065	0,022	1,214	1,247
1,250	0,013	0,035	0,067	0,022	1,346	1,379
1,400	0,014	0,036	0,069	0,023	1,499	1,533
1,600	0,016	0,038	0,071	0,023	1,702	1,738
1,800	0,018	0,039	0,073	0,024	1,905	1,942
2,000	0,020	0,040	0,075	0,025	2,108	2,146

NOTE Minimum overall diameter up to and inclusive of 0,060 mm is calculated from the maximum resistance value for each corresponding diameter of Table 3, then adding the minimum increase due to the insulation, plus minimum increase due to the bonding layer.

IEC 60317-0-1:2013

#### 4.2 Out of roundness of conductor (nominal conductor diameters over 0,063 mm)

The difference between the minimum and maximum diameter, at any one point, shall not be more than the figure given in column 2 of Table 1 or Table 2.

#### 4.3 Minimum increase in diameter due to the insulation and the bonding layer (nominal conductor diameters over 0,063 mm)

##### 4.3.1 Enamelled wires without a bonding layer

The minimum increase in diameter due to the insulation shall not be less than the values given in Table 1.

##### 4.3.2 Enamelled wires with a bonding layer

The minimum increase in diameter due to the insulation including the bonding layer shall not be less than the values given in Table 2.

##### 4.3.3 Intermediate nominal conductor diameters

For intermediate nominal conductor diameters, the minimum increase figure corresponding to the next larger nominal conductor diameter in Table 1 or Table 2 shall apply.

#### 4.4 Maximum overall diameter

##### 4.4.1 Enamelled wires without a bonding layer

The maximum overall diameter shall not exceed the values given in Table 1.