

# INTERNATIONAL STANDARD

## NORME INTERNATIONALE

Specifications for winding wires –  
**Part 47: Aromatic polyimide enamelled rectangular copper wire, class 240**  
([standards.iec.ch](https://standards.iec.ch/catalog-standards/sis/8c00960dd-5541-4537-8e02-a7fa3bce788b/iec-60317-47-2013))

Spécifications pour types particuliers de fils de bobinage –  
**Partie 47: Fil de section rectangulaire en cuivre émaillé avec polyimide**  
aromatique, classe 240 [IEC 60317-47-2013](https://standards.iec.ch/catalog-standards/sis/8c00960dd-5541-4537-8e02-a7fa3bce788b/iec-60317-47-2013)  
<https://standards.iec.ch/catalog-standards/sis/8c00960dd-5541-4537-8e02-a7fa3bce788b/iec-60317-47-2013>





## THIS PUBLICATION IS COPYRIGHT PROTECTED

Copyright © 2013 IEC, Geneva, Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester.

If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

Droits de reproduction réservés. Sauf indication contraire, aucune partie de cette publication ne peut être reproduite ni utilisée sous quelque forme que ce soit et par aucun procédé, électronique ou mécanique, y compris la photocopie et les microfilms, sans l'accord écrit de la CEI ou du Comité national de la CEI du pays du demandeur.

Si vous avez des questions sur le copyright de la CEI ou si vous désirez obtenir des droits supplémentaires sur cette publication, utilisez les coordonnées ci-après ou contactez le Comité national de la CEI de votre pays de résidence.

IEC Central Office  
3, rue de Varembé  
CH-1211 Geneva 20  
Switzerland

Tel.: +41 22 919 02 11  
Fax: +41 22 919 03 00  
[info@iec.ch](mailto:info@iec.ch)  
[www.iec.ch](http://www.iec.ch)

### About the IEC

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

### About IEC publications

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigenda or an amendment might have been published.

#### Useful links:

IEC publications search - [www.iec.ch/searchpub](http://www.iec.ch/searchpub)

The advanced search enables you to find IEC publications by a variety of criteria (reference number, text, technical committee,...).

It also gives information on projects, replaced and withdrawn publications. <https://standards.iteh.ai/catalog/standards/sist/8c0060dd-5341-4537-8c05-5f8bce788b/iec-60317-47-201>

IEC Just Published - [webstore.iec.ch/justpublished](http://webstore.iec.ch/justpublished)

Stay up to date on all new IEC publications. Just Published details all new publications released. Available on-line and also once a month by email.

Electropedia - [www.electropedia.org](http://www.electropedia.org)

The world's leading online dictionary of electronic and electrical terms containing more than 30 000 terms and definitions in English and French, with equivalent terms in additional languages. Also known as the International Electrotechnical Vocabulary (IEV) on-line.

Customer Service Centre - [webstore.iec.ch/csc](http://webstore.iec.ch/csc)

If you wish to give us your feedback on this publication or need further assistance, please contact the Customer Service Centre: [csc@iec.ch](mailto:csc@iec.ch).

### A propos de la CEI

La Commission Electrotechnique Internationale (CEI) est la première organisation mondiale qui élabore et publie des Normes internationales pour tout ce qui a trait à l'électricité, à l'électronique et aux technologies apparentées.

### A propos des publications CEI

Le contenu technique des publications de la CEI est constamment revu. Veuillez vous assurer que vous possédez l'édition la plus récente, un corrigendum ou amendement peut avoir été publié.

#### Liens utiles:

Recherche de publications CEI - [www.iec.ch/searchpub](http://www.iec.ch/searchpub)

La recherche avancée vous permet de trouver des publications CEI en utilisant différents critères (numéro de référence, texte, comité d'études,...).

Elle donne aussi des informations sur les projets et les publications remplacées ou retirées.

Just Published CEI - [webstore.iec.ch/justpublished](http://webstore.iec.ch/justpublished)

Restez informé sur les nouvelles publications de la CEI. Just Published détaille les nouvelles publications parues. Disponible en ligne et aussi une fois par mois par email.

Electropedia - [www.electropedia.org](http://www.electropedia.org)

Le premier dictionnaire en ligne au monde de termes électriques et électroniques. Il contient plus de 30 000 termes et définitions en anglais et en français, ainsi que les termes équivalents dans les langues additionnelles. Egalement appelé Vocabulaire Electrotechnique International (VEI) en ligne.

Service Clients - [webstore.iec.ch/csc](http://webstore.iec.ch/csc)

Si vous désirez nous donner des commentaires sur cette publication ou si vous avez des questions contactez-nous: [csc@iec.ch](mailto:csc@iec.ch).

# INTERNATIONAL STANDARD

# NORME INTERNATIONALE

Specifications for particular types of winding wires –  
**iTech STANDARD REVIEW**  
Part 47: Aromatic polyimide enamelled rectangular copper wire, class 240  
(standards.iec.ch)

Spécifications pour types particuliers de fils de bobinage –  
**Partie 47: Fil de section rectangulaire en cuivre émaillé avec polyimide  
aromatique, classe 240**

INTERNATIONAL  
ELECTROTECHNICAL  
COMMISSION

COMMISSION  
ELECTROTECHNIQUE  
INTERNATIONALE

PRICE CODE  
CODE PRIX

J

ICS 29.060.10

ISBN 978-2-8322-1137-3

**Warning! Make sure that you obtained this publication from an authorized distributor.**  
**Attention! Veuillez vous assurer que vous avez obtenu cette publication via un distributeur agréé.**

## CONTENTS

FOREWORD .....	3
INTRODUCTION .....	5
1 Scope .....	6
2 Normative reference .....	6
3 Terms, definitions, general notes, and appearance .....	6
3.1 Terms and definitions .....	6
3.2 General notes .....	6
3.2.1 Methods of test .....	6
3.2.2 Winding wire .....	6
3.3 Appearance .....	7
4 Dimensions .....	7
5 Electrical resistance .....	7
6 Elongation .....	7
7 Springiness .....	7
8 Flexibility and adherence .....	7
9 Heat shock .....	7
10 Cut-through .....	7
11 Resistance to abrasion .....	7
12 Resistance to solvents .....	7
13 Breakdown voltage .....	7
14 Continuity of insulation .....	8
IEC 60317-47:2013 <a href="https://standards.iteh.ai/catalog/standards/sist/8c0060dd-5341-4537-8e05-a71a3bce788b/iec-60317-47-2013">https://standards.iteh.ai/catalog/standards/sist/8c0060dd-5341-4537-8e05-a71a3bce788b/iec-60317-47-2013</a>	8
15 Temperature index .....	8
16 Resistance to refrigerants .....	8
17 Solderability .....	8
18 Heat or solvent bonding .....	8
19 Dielectric dissipation factor .....	8
20 Resistance to transformer oil .....	8
21 Loss of mass .....	8
23 Pin hole test .....	8
30 Packaging .....	8
Bibliography .....	9

## INTERNATIONAL ELECTROTECHNICAL COMMISSION

**SPECIFICATIONS FOR PARTICULAR TYPES OF WINDING WIRES –****Part 47: Aromatic polyimide enamelled rectangular copper wire, class 240****FOREWORD**

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.

- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.  
IEC 60317-47-2013  
http://www.itchai.org/standards/sist/8c0060dd-5341-4537-8e05-  
7831iec7881iec60317-47-2013
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

International Standard IEC 60317-47 has been prepared by IEC technical committee 55: Winding wires.

This second edition cancels and replaces the first edition published in 1997. This edition constitutes a technical revision.

This edition includes the following significant technical changes with respect to the previous edition:

- deletion of the "in some countries" statement in the scope;
- new subclause containing general notes on winding wire, formerly a part of the scope;
- new subclause containing requirements for appearance;
- revision to the notes in Clause 19, Dielectric dissipation factor;
- new Clause 23, Pin hole test.

The text of this standard is based on the following documents:

FDIS	Report on voting
55/1421/FDIS	55/1442/RVD

Full information on the voting for the approval of this standard can be found in the report on voting indicated in the above table.

This publication has been drafted in accordance with the ISO/IEC Directives, Part 2.

This International standard is to be read in conjunction with IEC 60317-0-2:2013.

The numbering of clauses in this standard is not continuous from Clauses 20 and 30 in order to reserve space for possible future wire requirements prior to those for wire packaging.

A list of all parts in the IEC 60317 series, published under the general title *Specifications for particular types of winding wires*, can be found on the IEC website.

The committee has decided that the contents of this publication will remain unchanged until the stability date indicated on the IEC web site under "http://webstore.iec.ch" in the data related to the specific publication. At this date, the publication will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[IEC 60317-47:2013](#)  
<https://standards.iteh.ai/catalog/standards/sist/8c0060dd-5341-4537-8e05-a7fa3bce788b/iec-60317-47-2013>

## INTRODUCTION

This part of IEC 60317 is one of a series of standards which deals with insulated wires used for windings in electrical equipment. The series has three groups describing:

- 1) Winding wires – Test methods (IEC 60851);
- 2) Specifications for particular types of winding wires (IEC 60317);
- 3) Packaging of winding wires (IEC 60264).

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[IEC 60317-47:2013](#)

<https://standards.iteh.ai/catalog/standards/sist/8c0060dd-5341-4537-8e05-a7fa3bce788b/iec-60317-47-2013>

## SPECIFICATIONS FOR PARTICULAR TYPES OF WINDING WIRES –

### Part 47: Aromatic polyimide enamelled rectangular copper wire, class 240

#### 1 Scope

This part of IEC 60317 specifies the requirements of enamelled rectangular copper winding wire of class 240 with a sole coating of aromatic polyimide resin.

The range of nominal conductor dimensions covered by this standard is:

- width: min. 2,0 mm max. 16,0 mm;
- thickness: min. 0,80 mm max. 5,60 mm.

Wires of grade 1 and grade 2 are included in this specification and apply to the complete range of conductors.

The specified combinations of width and thickness, as well as the specified width/thickness ratio, are given in IEC 60317-0-2.

#### iTeh STANDARD PREVIEW

#### 2 Normative reference

#### (standards.iteh.ai)

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.  
a7fa3bce788b/iec-60317-47-2013

IEC 60317-0-2:2013, *Specifications for particular types of winding wires – Part 0-2: General requirements – Enamelled rectangular copper wire*

#### 3 Terms, definitions, general notes, and appearance

##### 3.1 Terms and definitions

Subclause 3.1 of IEC 60317-0-2:2013 applies.

##### 3.2 General notes

###### 3.2.1 Methods of test

Subclause 3.2.1 of IEC 60317-0-2:2013 applies. In case of inconsistencies between IEC 60317-0-2: 2013 and this standard, the latter shall prevail.

###### 3.2.2 Winding wire

Class 240 is a thermal class that requires a minimum temperature index of 240 and heat shock temperature of at least 260 °C.

The temperature in degrees Celsius corresponding to the temperature index is not necessarily that at which it is recommended that the wire be used, and this will depend on many factors, including the type of equipment involved.

### **3.3 Appearance**

Subclause 3.3 of IEC 60317-0-2:2013 applies.

### **4 Dimensions**

Clause 4 of IEC 60317-0-2:2013 applies.

### **5 Electrical resistance**

Clause 5 of IEC 60317-0-2:2013 applies.

### **6 Elongation**

Clause 6 of IEC 60317-0-2:2013 applies.

### **7 Springiness**

Clause 7 of IEC 60317-0-2:2013 applies.

## **8 Flexibility and adherence *iTeh STANDARD PREVIEW (standards.iteh.ai)***

Clause 8 of IEC 60317-0-2:2013 applies. For 8.2, the wire for the adherence test shall be stretched by 10 %.

[IEC 60317-47:2013](#)

<https://standards.iteh.ai/catalog/standards/sist/8c0060dd-5341-4537-8e05-a7fa3bce788b/iec-60317-47-2013>

### **9 Heat shock**

Clause 9 of IEC 60317-0-2:2013 applies. The minimum heat shock temperature shall be 260 °C.

### **10 Cut-through**

Clause 10 of IEC 60317-0-2:2013 applies.

### **11 Resistance to abrasion**

Test inappropriate.

### **12 Resistance to solvents**

Clause 12 of IEC 60317-0-2:2013 applies.

### **13 Breakdown voltage**

Clause 13 of IEC 60317-0-2:2013 applies. The elevated temperature shall be 240 °C.

## **14 Continuity of insulation**

Test inappropriate.

## **15 Temperature index**

Clause 15 of IEC 60317-0-2:2013 applies. The minimum temperature index shall be 240.

## **16 Resistance to refrigerants**

Test inappropriate.

## **17 Solderability**

Test inappropriate.

## **18 Heat or solvent bonding**

Test inappropriate.

# iTeh STANDARD PREVIEW

## **19 Dielectric dissipation factor**

**(standards.iteh.ai)**

The dielectric dissipation factor  $\tan \delta$  shall not exceed  $60 \times 10^{-4}$  at a frequency of 1 000 Hz.

[IEC 60317-47:2013](#)

NOTE Test under consideration [standards.iteh.ai/catalog/standards/sist/8c0060dd-5341-4537-8e05-a7fa3bce788b/iec-60317-47-2013](#)

## **20 Resistance to transformer oil**

Test appropriate, but no requirements specified.

## **21 Loss of mass**

Test appropriate, but no requirements specified.

## **23 Pin hole test**

Test inappropriate.

## **30 Packaging**

Clause 30 of IEC 60317-0-2:2013 applies.

## Bibliography

IEC 60264 (all parts), *Packaging of winding wires*

IEC 60317 (all parts), *Specifications for particular types of winding wires*

IEC 60851 (all parts), *Winding wires – Test methods*

---

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[IEC 60317-47:2013](#)

<https://standards.iteh.ai/catalog/standards/sist/8c0060dd-5341-4537-8e05-a7fa3bce788b/iec-60317-47-2013>