
**Paints and varnishes — Exposure of
coatings to artificial weathering —
Exposure to fluorescent UV and water**

*Peintures et vernis — Exposition des revêtements au vieillissement
artificiel — Exposition au rayonnement UV fluorescent et à l'eau*

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 11507:1997

[https://standards.iteh.ai/catalog/standards/sist/4a3b54da-0b01-4d19-9640-
c424fa6fcc4b/iso-11507-1997](https://standards.iteh.ai/catalog/standards/sist/4a3b54da-0b01-4d19-9640-c424fa6fcc4b/iso-11507-1997)



Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

International Standard ISO 11507 was prepared by Technical Committee ISO/TC 35, *Paints and varnishes*, Subcommittee SC 9, *General test methods for paints and varnishes*.

Annex A forms an integral part of this International Standard.

iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 11507:1997

<https://standards.iteh.ai/catalog/standards/sist/4a3b54da-0b01-4d19-9640-c424fa6fcc4b/iso-11507-1997>

© ISO 1997

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

International Organization for Standardization
Case postale 56 • CH-1211 Genève 20 • Switzerland
Internet central@iso.ch
X.400 c=ch; a=400net; p=iso; o=isocs; s=central

Printed in Switzerland

Introduction

Coatings from paints, varnishes and similar materials are weathered in the laboratory, in order to simulate ageing processes occurring during natural weathering. Generally, valid correlations between ageing during artificial and natural weathering cannot be expected because of the large number of influencing factors. Certain relationships can only be expected if the effect of the important parameters (spectral distribution of the irradiance in their photochemically relevant range, temperature of the specimen, type of wetting, wetting cycle relative humidity) on the coating is known. However, unlike natural weathering, testing in the laboratory is carried out taking into consideration a limited number of variables which can be controlled and therefore the results are more reproducible.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[ISO 11507:1997](https://standards.iteh.ai/catalog/standards/sist/4a3b54da-0b01-4d19-9640-c424fa6fcc4b/iso-11507-1997)

<https://standards.iteh.ai/catalog/standards/sist/4a3b54da-0b01-4d19-9640-c424fa6fcc4b/iso-11507-1997>

iTeh STANDARD PREVIEW
This page intentionally left blank
(standards.iteh.ai)

ISO 11507:1997

<https://standards.iteh.ai/catalog/standards/sist/4a3b54da-0b01-4d19-9640-c424fa6fcc4b/iso-11507-1997>

Paints and varnishes — Exposure of coatings to artificial weathering — Exposure to fluorescent UV and water

1 Scope

This International Standard is one of a series of standards dealing with the sampling and testing of paints, varnishes and related products.

It specifies a test method for determining the resistance of paint coatings to artificial weathering in apparatus including fluorescent UV lamps and condensation or water spray.

NOTE 1 - The ultraviolet light produced by the fluorescent tubes simulates only part of the UV region of the natural sunlight and consequently the test pieces are subjected to a small but destructive portion of the spectrum.

Due to the lack of energy of visible and infra-red radiation compared to sunlight the test piece is not heated above the temperature of the surrounding air which takes place in practical use.

2 Normative references

The following standards contain provisions which, through reference in this text, constitute provisions of this International Standard. At the time of publication, the editions indicated were valid. All standards are subject to revision, and parties to agreements based on this International Standard are encouraged to investigate the possibility of applying the most recent editions of the standards indicated below. Members of IEC and ISO maintain registers of currently valid International Standards.

ISO 1512 : 1991, Paints and varnishes - Sampling of products in liquid or paste form.

ISO 1513 : 1992, Paints and varnishes - Examination and preparation of samples for testing.

ISO 1514 : 1983, Paints and varnishes - Standard panels for testing.

ISO 2808 : —1) , Paints and varnishes - Determination of film thickness.

ISO 2813 : 1994 , Paints and varnishes - Determination of specular gloss of non-metallic paint films at 20°, 60° and 85°.

ISO 3668 : 1976, Paints and varnishes - Visual comparison of the colour of paints.

ISO 3696 : 1987, Water for analytical laboratory use - Specification and test method.

ISO 4628-1 : 1982, Paints and varnishes - Evaluation of degradation of paint coatings - Designation of intensity, quantity and size of common types of defect - Part 1: General principles and rating schemes.

ISO 4628-2 : 1982, Paints and varnishes - Evaluation of degradation of paint coatings - Designation of intensity, quantity and size of common types of defect - Part 2: Designation of degree of blistering.

ISO 4628-3 : 1982, Paints and varnishes - Evaluation of degradation of paint coatings - Designation of intensity, quantity and size of common types of defect - Part 3: Designation of degree of rusting.

ISO 4628-4 : 1982, Paints and varnishes - Evaluation of degradation of paint coatings - Designation of intensity, quantity and size of common types of defect - Part 4: Designation of degree of cracking.

ISO 4628-5 : 1982, Paints and varnishes - Evaluation of degradation of paint coatings - Designation of intensity, quantity and size of common types of defect - Part 5: Designation of degree of flaking.

ISO 4628-6 : 1990, Paints and varnishes - Evaluation of degradation of paint coatings - Designation of intensity, quantity and size of common types of defect - Part 6: Rating of degree of chalking by tape method.

ISO 4892-1 : 1994, Plastics - Methods of exposure to laboratory light sources - Part 1: General guidance.

ISO 7724-1 : 1984, Paints and varnishes - Colorimetry - Part 1: Principles.

ISO 7724-2 : 1984, Paints and varnishes - Colorimetry - Part 2: Colour measurement.

ISO 7724-3 : 1984, Paints and varnishes - Colorimetry - Part 3: Calculation of colour differences.

ISO 11341 : 1994, Paints and varnishes - Artificial weathering and exposure to artificial radiation - Exposure to filtered xenon-arc radiation.

1) To be published. (Revision of ISO 2808:1991)

3 Definitions

For the purpose of this International Standard, the following definitions apply:

3.1 ageing criterion: A given degree of ageing, corresponding to a specified or agreed degree of change in a selected property of the coating under test. [ISO 11341]

3.2 ageing behaviour: The change in properties of a coating during artificial weathering or exposure to artificial radiation until a certain ageing criterion (see 3.1) is satisfied.

NOTE 2 - One measure of ageing is the radiant exposure H in the wavelength range below 400 nm or at a specified wavelength, e.g. 340 nm. The ageing behaviour of coatings exposed to artificial weathering, or to artificial radiation, depends on the type of coating, the conditions of exposure of the coating, the property selected for monitoring the progress of the ageing process and the degree of change of this property. [ISO 11341]

3.3 Irradiance, E : Radiant flux/area for a specified wavelength range expressed in watts per square metre.

3.4 radiant exposure, H : A measure of the radiant energy to which a test panel has been exposed, given by the formula

$$H = \int E dt$$

where

E is the irradiance, in watts per square metre;

t is the exposure time, in seconds.

H is therefore expressed in joules per square metre.

If the irradiance E is constant throughout the whole exposure time, the radiant exposure H is given simply by the product of E and t . [ISO 11341]

4 Principle

Artificial weathering of coatings using fluorescent UV lamps and condensation or water spray is carried out in order to produce a certain radiant exposure or mutually agreed total number of operation hours, a given degree of a change in a property or properties. The properties of the exposed coatings are compared with those of unexposed coatings, prepared from the same coating materials under identical conditions, or with coatings whose degradation properties are known. These properties are evaluated by criteria agreed in advance between the interested parties, these criteria usually being of a subjective nature.

Radiation, temperature and humidity all contribute to the ageing process. Therefore, apparatus specified in this standard simulates all three factors.

The results obtained by the use of this method do not necessarily related directly to the results obtained under natural exposure conditions. The relationship between these results needs to be established before the method can be used to predict performance.

5 Required supplementary information

For any particular application, the test method specified in this International Standard needs to be

completed by supplementary information. The items of supplementary information are given in annex A.

6 Apparatus

6.1 Test chamber

The test chamber consists essentially of a conditioned enclosure made from corrosion resistant material in which are housed the lamps, a heated water-tray or spray nozzles and test panel racks.

6.1.1 Lamps

UV lamps emit UV light from a low pressure mercury arc. The required spectral distribution is achieved by a careful selection of the type of phosphor coating on the inner surface of the lamp and the nature of the glass used in the construction of the tubes.

Unless otherwise specified or mutually agreed the lamp shall be one of the three types listed below:

Type 1: This lamp emits a significant amount of radiation at wavelengths below 300 nm which is not present in the sun's radiation. Due to the higher quantum energy of this radiation, photochemical ageing processes may be initiated which do not take place in natural weathering. Therefore this type of fluorescent lamp is suitable for use only for aerospace technology, or when specially agreed between the parties concerned.

This lamp, commonly called UVB (313), has a peak emission at 313 nm and the following relative spectral irradiance:

ITeH STANDARD PREVIEW
(standards.iteh.ai)

Wavelength, λ nm	Relative spectral irradiance*) %
$270 < \lambda \leq 400$	100
$\lambda \leq 270$	0
$270 < \lambda \leq 280$	$0,3 \pm 0,03$
$280 < \lambda \leq 300$	$16,2 \pm 1,6$
$300 < \lambda \leq 320$	$41,6 \pm 4,2$
$320 < \lambda \leq 340$	$29,4 \pm 2,9$
$340 < \lambda \leq 360$	$9,1 \pm 0,9$
$360 < \lambda \leq 380$	$3,0 \pm 0,3$
$380 < \lambda \leq 400$	$0,4 \pm 0,04$

*) The spectral irradiance between 270 nm and 400 nm is defined as 100 %.

Type 2: This lamp, commonly called UVA (340), has a peak emission at 340 nm and the following relative spectral irradiance:

Wavelength, λ nm	Relative spectral irradiance*) %
$270 < \lambda \leq 400$	100
$\lambda \leq 270$	0
$270 < \lambda \leq 280$	0
$280 < \lambda \leq 300$	0
$300 < \lambda \leq 320$	$7,8 \pm 0,8$
$320 < \lambda \leq 340$	$29,6 \pm 3,0$
$340 < \lambda \leq 360$	$34,4 \pm 3,4$
$360 < \lambda \leq 380$	$20,9 \pm 2,1$
$380 < \lambda \leq 400$	$7,3 \pm 0,7$

*) The spectral irradiance between 270 nm and 400 nm is defined as 100 %.

Type 3: This lamp, commonly called UVA (351), has a peak emission at 351 nm and the following relative spectral irradiance:

Wavelength, λ nm	Relative spectral irradiance*) %
$270 < \lambda \leq 400$	100
$\lambda \leq 270$	0
$270 < \lambda \leq 280$	0
$280 < \lambda \leq 300$	0
$300 < \lambda \leq 320$	$2,1 \pm 0,2$
$320 < \lambda \leq 340$	$19,4 \pm 1,9$
$340 < \lambda \leq 360$	$43,4 \pm 4,3$
$360 < \lambda \leq 380$	$28,2 \pm 2,8$
$380 < \lambda \leq 400$	$6,9 \pm 0,7$

*) The spectral irradiance between 270 nm and 400 nm is defined as 100 %.

If the lamps are of the same type, they shall be fixed in banks of at least four. It is not recommended, but when combinations of lamps with different spectral emissions are used, provision shall be made to ensure uniformity of the spectral irradiance at the surface of the specimens, e.g., by changing the positions of the specimens at intervals. Since the spectral output deteriorates with age, the lamps shall be renewed or rotated according to the apparatus manufacturers' recommendation.

6.1.2 Device for wetting the test panels

The test panels shall be wetted by condensation from the heated water tray or by spray. Water to ISO 3696 grade 2 shall be used.

6.1.3 Test panel racks

The design of the racks shall be such that when the test panels are mounted in place there will be sufficient free access of air to cool the back of the panel and produce condensation on the front.