

INTERNATIONAL STANDARD

NORME INTERNATIONALE



**Measurement procedures for materials used in photovoltaic modules –
Part 1-6: Encapsulants – Test methods for determining the degree of cure
in Ethylene-Vinyl Acetate**

**Procédures de mesure des matériaux utilisés dans les modules
photovoltaïques –
Partie 1-6: Encapsulants – Méthodes d'essai pour déterminer le degré
de durcissement dans l'éthylène-acétate de vinyle**



THIS PUBLICATION IS COPYRIGHT PROTECTED

Copyright © 2020 IEC, Geneva, Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester. If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

Droits de reproduction réservés. Sauf indication contraire, aucune partie de cette publication ne peut être reproduite ni utilisée sous quelque forme que ce soit et par aucun procédé, électronique ou mécanique, y compris la photocopie et les microfilms, sans l'accord écrit de l'IEC ou du Comité national de l'IEC du pays du demandeur. Si vous avez des questions sur le copyright de l'IEC ou si vous désirez obtenir des droits supplémentaires sur cette publication, utilisez les coordonnées ci-après ou contactez le Comité national de l'IEC de votre pays de résidence.

IEC Central Office
3, rue de Varembe
CH-1211 Geneva 20
Switzerland

Tel.: +41 22 919 02 11
info@iec.ch
www.iec.ch

About the IEC

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

About IEC publications

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigendum or an amendment might have been published.

IEC publications search - webstore.iec.ch/advsearchform

The advanced search enables to find IEC publications by a variety of criteria (reference number, text, technical committee,...). It also gives information on projects, replaced and withdrawn publications.

IEC Just Published - webstore.iec.ch/justpublished

Stay up to date on all new IEC publications. Just Published details all new publications released. Available online and once a month by email.

IEC Customer Service Centre - webstore.iec.ch/csc

If you wish to give us your feedback on this publication or need further assistance, please contact the Customer Service Centre: sales@iec.ch.

Electropedia - www.electropedia.org

The world's leading online dictionary on electrotechnology, containing more than 22 000 terminological entries in English and French, with equivalent terms in 16 additional languages. Also known as the International Electrotechnical Vocabulary (IEV) online.

IEC Glossary - std.iec.ch/glossary

67 000 electrotechnical terminology entries in English and French extracted from the Terms and definitions clause of IEC publications issued between 2002 and 2015. Some entries have been collected from earlier publications of IEC TC 37, 77, 86 and CISPR.

A propos de l'IEC

La Commission Electrotechnique Internationale (IEC) est la première organisation mondiale qui élabore et publie des Normes internationales pour tout ce qui a trait à l'électricité, à l'électronique et aux technologies apparentées.

A propos des publications IEC

Le contenu technique des publications IEC est constamment revu. Veuillez vous assurer que vous possédez l'édition la plus récente, un corrigendum ou amendement peut avoir été publié.

Recherche de publications IEC -

webstore.iec.ch/advsearchform

La recherche avancée permet de trouver des publications IEC en utilisant différents critères (numéro de référence, texte, comité d'études,...). Elle donne aussi des informations sur les projets et les publications remplacées ou retirées.

IEC Just Published - webstore.iec.ch/justpublished

Restez informé sur les nouvelles publications IEC. Just Published détaille les nouvelles publications parues. Disponible en ligne et une fois par mois par email.

Service Clients - webstore.iec.ch/csc

Si vous désirez nous donner des commentaires sur cette publication ou si vous avez des questions contactez-nous: sales@iec.ch.

Electropedia - www.electropedia.org

Le premier dictionnaire d'électrotechnologie en ligne au monde, avec plus de 22 000 articles terminologiques en anglais et en français, ainsi que les termes équivalents dans 16 langues additionnelles. Egalement appelé Vocabulaire Electrotechnique International (IEV) en ligne.

Glossaire IEC - std.iec.ch/glossary

67 000 entrées terminologiques électrotechniques, en anglais et en français, extraites des articles Termes et définitions des publications IEC parues entre 2002 et 2015. Plus certaines entrées antérieures extraites des publications des CE 37, 77, 86 et CISPR de l'IEC.

INTERNATIONAL STANDARD

NORME INTERNATIONALE



**Measurement procedures for materials used in photovoltaic modules –
Part 1-6: Encapsulants – Test methods for determining the degree of cure
in Ethylene-Vinyl Acetate**

**Procédures de mesure des matériaux utilisés dans les modules
photovoltaïques –
Partie 1-6: Encapsulants – Méthodes d'essai pour déterminer le degré
de durcissement dans l'éthylène-acétate de vinyle**

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

COMMISSION
ELECTROTECHNIQUE
INTERNATIONALE

ICS 27.160

ISBN 978-2-8322-8421-6

**Warning! Make sure that you obtained this publication from an authorized distributor.
Attention! Veuillez vous assurer que vous avez obtenu cette publication via un distributeur agréé.**

REDLINE VERSION

VERSION REDLINE



**Measurement procedures for materials used in photovoltaic modules –
Part 1-6: Encapsulants – Test methods for determining the degree of cure
in Ethylene-Vinyl Acetate**

**Procédures de mesure des matériaux utilisés dans les modules
photovoltaïques –
Partie 1-6: Encapsulants – Méthodes d'essai pour déterminer le degré
de durcissement dans l'éthylène-acétate de vinyle**

CONTENTS

FOREWORD	4
1 Scope	6
2 Normative references	6
3 Terms and definitions	7
4 Principle	8
5 DSC secondary method	8
5.1 Instrument and equipment for the secondary method	8
5.1.1 General	8
5.1.2 Electronic balance	8
5.1.3 Differential scanning calorimeter	8
5.1.4 Instrument calibration	9
5.2 Specimen preparation for the secondary method	9
5.2.1 Sampling and storage	9
5.2.2 Preparation procedures	9
5.3 Test requirements for the secondary method	10
5.3.1 Environment requirements	10
5.3.2 Parameter settings (residual enthalpy method)	10
5.3.3 Parameter settings (melt/freeze method)	10
5.3.4 Parameter settings (combined enthalpy and melt/freeze method)	10
5.4 Test procedure for the secondary method	11
5.5 Calculation and expression of the results for the secondary method	11
5.5.1 Enthalpy method	11
5.5.2 Melt/freeze method	12
5.6 Uncertainty of measurements for the secondary method	16
6 The primary method	16
6.1 Principle for the primary method	16
6.2 Instrument and equipment for the primary method	17
6.2.1 Electronic balance	17
6.2.2 Soxhlet extractor	17
6.2.3 Thimble	17
6.2.4 Heating apparatus	17
6.2.5 Handling apparatus	18
6.2.6 Solvent	18
6.3 Specimen preparation for the primary method	18
6.3.1 Sampling and storage	18
6.3.2 Preparation procedures	18
6.4 Test requirements for the primary method – Environment requirements	19
6.5 Test procedure for the primary method	19
6.6 Calculation and expression of the results for the primary method	19
7 Test report	19
8 Indentation secondary method	20
8.1 General	20
8.2 Principle	21
8.3 Instrument and equipment for the indentation method	21
8.4 Instrument calibration	22

8.5	Correlation of the degree of cure.....	22
8.6	Specimen preparation for the indentation method	22
8.7	Test procedure for the indentation method	23
Annex A (informative) Limitations of the primary and secondary measurement methods.....		24
Bibliography.....		26
Figure 1 – Example result for the DSC residual enthalpy method		12
Figure 2 – Location of temperatures and temperature ranges used in the melt/freeze DSC method		13
Figure 3 – Example of the temperature bounds applied for an automated software integration algorithm		15
Figure 4 – Representation of the measurement profile for an EVA test specimen.....		16
Figure 5 – Example of the correlation applied between G_i (indentation) and $G_{\%}$ (gel content)		22
Table 1 – Summary of the results for the example measurements shown in Figure 2		14

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[IEC 62788-1-6:2017](https://standards.iteh.ai/catalog/standards/sist/c72b255e-dbc4-40b3-9122-d578b4ce87ba/iec-62788-1-6-2017)

<https://standards.iteh.ai/catalog/standards/sist/c72b255e-dbc4-40b3-9122-d578b4ce87ba/iec-62788-1-6-2017>

INTERNATIONAL ELECTROTECHNICAL COMMISSION

**MEASUREMENT PROCEDURES FOR MATERIALS USED
IN PHOTOVOLTAIC MODULES –**

**Part 1-6: Encapsulants – Test methods for determining
the degree of cure in Ethylene-Vinyl Acetate**

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

This consolidated version of the official IEC Standard and its amendment has been prepared for user convenience.

IEC 62788-1-6 edition 1.1 contains the first edition (2017-01) [documents 82/1197/FDIS and 82/1231/RVD] and its amendment 1 (2020-05) [documents 82/1691/FDIS and 82/1720/RVD].

In this Redline version, a vertical line in the margin shows where the technical content is modified by amendment 1. Additions are in green text, deletions are in strikethrough red text. A separate Final version with all changes accepted is available in this publication.

International Standard IEC 62788-1-6 has been prepared by IEC technical committee 82: Solar photovoltaic energy systems.

This document has been drafted in accordance with the ISO/IEC Directives, Part 2.

A list of all parts in the IEC 62788 series, published under the general title *Measurement procedures for materials used in photovoltaic modules*, can be found on the IEC website.

The committee has decided that the contents of the base publication and its amendment will remain unchanged until the stability date indicated on the IEC web site under "<http://webstore.iec.ch>" in the data related to the specific publication. At this date, the publication will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

IMPORTANT – The 'colour inside' logo on the cover page of this publication indicates that it contains colours which are considered to be useful for the correct understanding of its contents. Users should therefore print this document using a colour printer.

ITEH STANDARD PREVIEW
(standards.iteh.ai)

[IEC 62788-1-6:2017](https://standards.iteh.ai/catalog/standards/sist/c72b255e-dbc4-40b3-9122-d578b4ce87ba/iec-62788-1-6-2017)

<https://standards.iteh.ai/catalog/standards/sist/c72b255e-dbc4-40b3-9122-d578b4ce87ba/iec-62788-1-6-2017>

MEASUREMENT PROCEDURES FOR MATERIALS USED IN PHOTOVOLTAIC MODULES –

Part 1-6: Encapsulants – Test methods for determining the degree of cure in Ethylene-Vinyl Acetate

1 Scope

This part of IEC 62788 defines the terminology, test equipment, test environment, specimen preparation, test procedures, and test report for measuring the degree of cure of Ethylene-Vinyl Acetate (EVA) encapsulation sheet used in photovoltaic (PV) modules. The differential scanning calorimetry (both residual enthalpy and melt/freeze protocols) and gel content methods are included herein. This procedure can be used by material- or module-manufacturers to verify that the cross-linking additive is present and is active. The procedure can also be used to verify the module manufacturing (lamination) process for the purposes of quality- and process-control. The procedure can also be used to assess the uniformity of the EVA formulation within a roll as well as to compare variation of the EVA formulation from roll to roll. This procedure can be applied to uncured or recently cured EVA sheet as well as uncured or recently cured EVA from PV modules.

This test procedure can also be applied to cross-linking ethylenic co-polymers other than EVA. The temperatures identified for the calorimetry measurements in this procedure have been optimized for EVA. Therefore, if the test procedure is applied to other encapsulation materials, the range of the test temperatures can have to be adjusted based on the active temperature of the curing agent and/or the melt/freeze temperature of the base material.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 61215-1, *Terrestrial photovoltaic (PV) modules – Design qualification and type approval – Part 1: Test requirements*

ISO/IEC 17025:2005, *General requirements for the competence of testing and calibration laboratories*

ISO 291:2008, *Plastics – Standard atmospheres for conditioning and testing*

ISO 6427:2013, *Plastics – Determination of matter extractable by organic solvents (conventional methods)*

ISO 6721-1, *Plastics – Determination of dynamic mechanical properties – Part 1: General principles*

ISO 11357-1:2009, *Plastics – Differential scanning calorimetry (DSC) – Part 1: General principles*

ISO 10147:2011, *Pipes and fittings made of crosslinked polyethylene (PE-X) – Estimation of the degree of cross-linking by determination of the gel content*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in IEC TS 61836 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

NOTE Calculations related to these definitions are given in 5.5.

3.1 degree of cure

G

unitless parameter that characterizes the extent of cross-linking within EVA

Note 1 to entry: Unlike the cross-link density, which is a physical quantity defined by the theory of rubber elasticity, the degree of cure in a polymer may be assessed by any experimental method that distinguishes partially cured specimens with respect to one another or with respect to a reference material. The degree of cure can be correlated to the gel content, which is the mass percentage of insoluble material (assumed to be cross-linked) within the specimen.

3.2 heat flow

Q

thermal flux across a specified area in the direction of a temperature gradient, W

Note 1 to entry: The specific heat flow, q , is defined as the thermal flux per unit mass of the specimen, W g⁻¹.

3.3 differential scanning calorimetry

DSC

thermoanalytical technique described in ISO 11357-1, in which the difference in the amount of heat flow required to change the temperature of a material specimen and a reference is measured as a function of temperature or time

Note 1 to entry: Both the specimen and reference are maintained at nearly the same temperature during DSC characterization. DSC may be applied to quantify the amount of heat generated or absorbed during the processing (curing) of EVA. The effects of cross-linking, which occur from changes in the molecular structure of the EVA, may also be examined using DSC at the phase transitions (glass transition, melting point, and crystallization temperature). The determination of the phase transition temperatures is described in ISO 11357-2 and ISO 11357-3.

3.4 differential scanning calorimeter

instrument used to measure the heat flow difference between the test crucible (containing the specimen) and reference (typically empty) crucible

3.5 gel content

percentage of mass content of polymer insoluble in a specified solvent after extraction according to the specified test conditions

Note 1 to entry: The gel is typically composed of insoluble cross-linked material.

3.6 degree of cure

G_i

<indentation method> parameter that correlates with the extent of cross-linking within the EVA using the indentation method

Note 1 to entry: Unit: dimensionless.

4 Principle

The degree of cure of EVA may be quickly inferred using a "secondary method", such as differential scanning calorimetry (DSC, ISO 11357-1), described in Clause 5. Established alternative secondary methods, as identified in Annex A, or specialized equipment may also be used directly for the purpose of manufacturing and quality control. When the results of the secondary method are to be compared between different institutions, they shall be calibrated using a slower, more universal "primary" method, the gel content test as described in Clause 6, similar to the procedures described in ISO 6427, ISO 10147 and ASTM D2765. The primary method may also be applied for research and development when the results of the secondary method are to be compared between formulations of EVA. A test procedure for the primary method is described in Clause 6. The results of the primary or secondary methods may be correlated to the module qualification tests (IEC 61215 series) or additional field durability data to identify the minimum degree of cure necessary. Examples correlating between the secondary and primary methods may be found in the bibliography of Annex A.

The DSC measurements for EVA may be interpreted based on the enthalpy of the cross-linking reaction or the characteristics of the melt/freeze transition as described in 5.5. Because the melt/freeze transition does not depend on the concentration of residual peroxide, the DSC melt/freeze method may be applied to specimens obtained from fielded modules. Limitations of the primary and secondary methods are discussed in Annex A.

5 DSC secondary method

5.1 Instrument and equipment for the secondary method

5.1.1 General

References for the application of the DSC method are provided in Annex A.

5.1.2 Electronic balance

The micro balance should have a measurement resolution of at least 0,01 mg, and a maximum range of at least 20 mg.

5.1.3 Differential scanning calorimeter

5.1.3.1 The calorimeter should have a temperature accuracy of at least $\pm 0,1$ °C, temperature precision of at least 0,01 °C, calorimetric accuracy of at least $\pm 0,5$ % (or 0,2 mW), calorimetric sensitivity of at least 2 μ W, and calorimetric repeatability of at least $\pm 0,5$ %.

5.1.3.2 The oven heating/cooling rate should be adjustable between 5 °C min⁻¹ and 30 °C min⁻¹ measured with a thermometric accuracy of at least $\pm 0,1$ °C min⁻¹.

5.1.3.3 The baseline drift (absolute value of signal change between the two integration limit, for an empty cell) should be less than 50 μ W, for the temperature range from –50 °C to 250 °C.

5.1.3.4 The baseline curvature (the biggest deviation from the integration baseline) should be less than 50 μ W, for the temperature range from –50 °C to 250 °C.

5.1.4 Instrument calibration

The instrument should be calibrated routinely according to the instrument manufacturer's specification, using the instrument supplier's recommended calibration methods. Accuracy calibration should be performed using standard substances, for example, indium or tin, as the temperature and heat-flow verification material. Sapphire may be used to quantify the baseline (curvature) of the instrument drift. The instrument should specifically be recalibrated if the test rate, type of pan, or test atmosphere has been changed before DSC measurements.

NOTE The importance, performance, and considerations related to DSC instrument calibration are described further in D. Chen, A. Green, D. Dollimore, "DSC: the Importance of Baseline Calibration", *Thermochimica Acta*, 284 (2), 1996, 429–433.

5.2 Specimen preparation for the secondary method

5.2.1 Sampling and storage

5.2.1.1 Because the results for the secondary method may depend on the make of EVA, test results may only be directly compared for the same formulation of EVA. Therefore, test specimens should come from the same manufacturer(s) ~~and fabrication batch~~ for the same fabrication lay-up configuration (backsheet/EVA combination). Changes in the encapsulant that affect the curing process, including but not limited to a change of the material supplier, would require validating the correlation between $G_{\%}$ and the degree of cure. For example, if the percentage vinyl acetate content in the EVA resin changes, a new correlation between $G_{\%}$ and the degree of cure (from a secondary method) should be obtained because the percentage vinyl acetate content is known to significantly affect the viscoelastic-dependent cure characteristics of the encapsulant.

5.2.1.2 Additional experimentation shall be performed using uncured EVA to establish a baseline for the uncured state (for both the DSC residual enthalpy and melt/freeze methods) and a previously cured ("maximum cured") EVA used to establish a baseline for the final cured state (for the melt/freeze method).

If the experiment is intended to monitor a production process, the "maximum cured" samples should be taken from a laminated module or test sample subjected to the thermal history used in lamination. If the experiment is intended to monitor the complete consumption of peroxide (which often does not occur during the lamination of a PV module), additional processing (time or temperature) may be required.

5.2.1.3 Operators should wear clean gloves when preparing and handling samples.

5.2.1.4 When storage is required, the EVA should be packaged in a marked, sealed bag for later use.

5.2.1.5 Specimens should be kept dry (stored at below 50 % relative humidity), maintained at ambient temperature, and not exposed to light.

It is recommended to verify that the results of the secondary method do not change with storage time.

5.2.2 Preparation procedures

5.2.2.1 Weigh the empty specimen crucible and empty reference crucibles.

The use of aluminium crucibles is recommended for use with EVA.

5.2.2.2 Prepare EVA specimens 5 mg to 9 mg in size (or of a size recommended by the DSC instrument manufacturer), obtained from a single sheet of material. The accuracy of the measurement of the specimen mass should be at least 1 %.

5.2.2.3 A minimum of 2 samples shall be used from each roll of EVA for process control.

5.2.2.4 Place each specimen in a separate crucible, and seal the crucible with a lid.

A non-hermetic aluminium crucible meets the requirement for this test.

The final geometry, specifically the flatness of bottom surface of the crucible, can affect its thermal contact to the instrument, which is critical to the measurement. If the crucible geometry is compromised during preparation, the specimen should be discarded.

If the specimen or lid is not well seated relative to the crucible, it will affect the measurement, and the specimen should be discarded.

5.2.2.5 Record the measured mass of each specimen and its crucible.

5.3 Test requirements for the secondary method

5.3.1 Environment requirements

The recommended laboratory environment of $(25 \pm 2) ^\circ\text{C}$ and the relative humidity of $(50 \pm 5) \%$ shall be used, as in ISO 291.

DSC tests should be performed using a dry inert carrier gas, such as nitrogen, in the DSC instrument. The gas flow rate shall be specified by the user, for example, $(50 \pm 5) \text{ ml}\cdot\text{min}^{-1}$. The purity of gas should be at least 99,99 %.

5.3.2 Parameter settings (residual enthalpy method)

The following test parameters are recommended for use during the DSC residual enthalpy method:

Data acquisition rate: 5 Hz ($0,2 \text{ s}\cdot\text{point}^{-1}$);

Initial temperature: 25 °C;

End temperature: 225 °C;

Heating rate: 10 °C·min⁻¹.

The completion of the peroxide reaction may be verified using a second thermal cycle (cool to 25 °C and reheat to 225 °C). The residual enthalpy for maximum cured EVA should be $< 0,1 \text{ J}\cdot\text{g}^{-1}$ during this second thermal cycle.

5.3.3 Parameter settings (melt/freeze method)

The following test procedure is recommended for use during the DSC melt/freeze method:

Data acquisition rate: 5 Hz ($0,2 \text{ s}\cdot\text{point}^{-1}$);

Initial temperature: 25 °C;

Heat to 100 °C at the rate of 10 °C·min⁻¹;

Cool to -20 °C at the rate of 10 °C·min⁻¹.

Care should be taken to ensure that the heating used to melt the specimen and erase structure-related effects is limited to temperatures less than that capable of activating the peroxide. If a reaction is evident in the data profile for heating, a temperature less than 100 °C should be used.

5.3.4 Parameter settings (combined enthalpy and melt/freeze method)

The following test procedure (with no dwell time occurring between the separate steps) is recommended for performing the DSC enthalpy and melt/freeze characterization on the same specimen, in a single test:

Data acquisition rate: 5 Hz ($0,2 \text{ s}\cdot\text{point}^{-1}$);

Initial temperature: 25 °C;
Heat to 100 °C at the rate of 10 °C·min⁻¹;
Cool to –20 °C at the rate of 10 °C·min⁻¹;
Heat to 225 °C at the rate of 10 °C·min⁻¹.

Additional data obtained after cooling from 225 °C, can be used for the "maximum cured" reference specimen required for the DSC melt/freeze method. To make use of the combined DSC method to also obtain data for the maximum cured reference specimen, cooling should be carried out to –20 °C at the rate of 10 °C·min⁻¹, so that the freeze transition is accurately characterized after thoroughly curing the test specimen in the calorimeter. If the maximum cured reference specimen is measured after the combined DSC characterization of a set of EVA specimens, the specimens with the greatest previous thermal history (temperature and time) should be used, to ensure that the EVA is thoroughly cured.

5.4 Test procedure for the secondary method

5.4.1 The DSC tests shall be carried out as follows.

5.4.2 The test parameters in 5.3.2 shall be used for the DSC residual enthalpy method; the test parameters in 5.3.3 shall be used for the DSC melt/freeze method; or the test parameters in 5.3.4 shall be used for the combined DSC residual enthalpy and melt/freeze methods.

5.4.3 Confirm the furnace (flange) temperature for the calorimeter is in a safe temperature range, and open the lid.

5.4.4 Place the specimen crucible and the empty reference crucible in the oven, and close the lid.

5.4.5 Specify the mass of the specimen and reference crucible to the calorimeter and initiate the test. An isothermal hold at the endpoints of the test segments within the method (i.e., initial, hot, or cold temperatures) shall not be used for the residual enthalpy, melt/freeze, or combined methods. In order to obtain the most consistent results, it is recommended to use the same test method (residual enthalpy, melt/freeze, or combined) for the purpose of process control or other sample comparison.

5.4.6 Remove the crucibles from the calorimeter at the end of test.

It is suggested that the specimen(s) be weighed after the test, which may be compared to the initial mass to verify the integrity of the crucible. The final weights of the specimen(s) may also be used to confirm the specimen identity.

5.4.7 Record test data, and calculate the degree of cure according to the method in 5.5.

5.5 Calculation and expression of the results for the secondary method

5.5.1 Enthalpy method

The degree of cure for the DSC residual enthalpy method shall be calculated using Formula (1):

$$G_e = \frac{h_u - h_t}{h_u} 100 \quad (1)$$

In the formula, G_e represents the degree of cure for the enthalpy method, %; h_u , the measured specific enthalpy of EVA of an uncured reference specimen, J·kg⁻¹; and h_t , the measured specific enthalpy of EVA of the test specimen, J·kg⁻¹.