



Standard Test Method for Determination of Residual Acetaldehyde in Polyethylene Terephthalate Bottle Polymer Using an Automated Static Head-Space Sampling Device and a Capillary GC with a Flame Ionization Detector¹

This standard is issued under the fixed designation F 2013; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers a gas chromatographic procedure for the determination of the ppm residual acetaldehyde (AA) present in poly(ethylene terephthalate) (PET) homopolymers and co-polymers which are used in the manufacture of beverage bottles. This includes sample types of both amorphous and solid-stated pellet and preform samples.

1.2 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:

D 4509 Test Method for Determining the 24-Hour Gas (Air) Space Acetaldehyde Content of Freshly Blown PET Bottles²

3. Terminology

3.1 The terms employed in this test method are commonly used in normal laboratory practice and require no special comment.

4. Summary of Test Method

4.1 A specified size (800 to 1000 μm) of granulated sample is weighed into a 20-mL head-space vial, sealed, and then heated at 150°C for 60 min. After heating, the gas above the sealed sample of PET polymer is injected onto a capillary GC column. The acetaldehyde is separated, and the ppm of acetaldehyde is calculated.

5. Significance and Use

5.1 This test method is of particular use as a quality control tool for a molding or synthesis operation. Acetaldehyde is a volatile degradation product generated during melt processing

of PET. Thus, it becomes trapped in the sidewalls of a molded article and desorbs slowly into the contents packaged therein. In some foods and beverages AA can impart an off-taste that is undesirable, thus, it is important to know its concentration in PET articles that are to be used in food contact applications.

5.2 The desorption conditions of 150 C for 60 min are such that no measurable AA is generated by the sample during the desorption process.

6. Sources of Error

6.1 A bias is known to exist if the ratio of sample mass (mg) to head-space vial volume (mL) exceeds a value of ten.

6.2 Acetaldehyde is very volatile and must be handled carefully to avoid sample loss during the calibration procedure. Storing the standard vials in a refrigerator is a must to minimize the error due to volatility.

6.3 Failure to achieve a tight seal on the head-space vial will result in the loss of acetaldehyde during storage and desorption, producing a false low value.

6.4 Failure to grind the sample to the appropriate particle size may lead to a false low value for residual AA due to the increased path length for desorption.

6.5 Samples submitted for 'residual AA measurement' should be stored in a freezer until they are tested. Failure to do so can result in lower than expected results.

6.6 Excessive grinding of samples can cause residual AA contained therein to be desorbed. Extensive excessive grinding can lead to actual melting of the polymer and AA generation. Samples which have been chilled in liquid nitrogen properly should only be in the grinder for ~30 s or less.

7. Apparatus

7.1 *Gas Chromatograph*, Hewlett-Packard 6890 series³

7.2 *Integrator*, Hewlett-Packard Model 6890 series, H-P ChemStation, H-P LAN.³

7.3 *Head-Space Sampler*, Hewlett-Packard 7694.³

¹ This test method is under the jurisdiction of ASTM Committee F02 on Flexible Barrier Materials and is the direct responsibility of Subcommittee F02.30 on Test Methods.

Current edition approved April 10, 2000. Published August 2000.

² *Annual Book of ASTM Standards*, Vol 08.03.

³ Hewlett-Packard apparatus, website: hewlett-packard.com, was used in the development of this standard. If you are aware of alternative suppliers, please provide this information to ASTM headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend.

7.4 *Column*, 30-m by 0.53-mm i.d. (megabore capillary column).⁴

7.5 *Vials*, 20-mL, head-space, with 20-mm septa, 20-mm aluminum caps, and crimper for 20-mm caps

7.5.1 *Vials*:

Perkin-Elmer Part Number 0105-0129⁵, or Kimble Glass Inc. Part Number 60827A-2375⁶, or Hewlett-Packard Part Number 5182-0837³.

7.5.2 *Septa*:

Pierce Part Number 12720, or Hewlett-Packard Part Number 9301-0807.³

7.5.3 *Caps*:

Pierce Part Number 13214, or Hewlett-Packard Part Number 9301-0721.³

7.6 *Crimper*, 20-mm, Wheaton Part Number 224303.⁷

7.7 *Decrimper*, 20-mm, Kimble Part Number 69903-20.⁶

7.8 *Wiley Mill*, equipped with an 800 to 1000 μm screen, or equivalent

7.9 *Syringe*, calibrated, with certificate of calibration.⁸

7.10 *Small Vacuum Cleaner*, with host attachment for cleaning.

7.11 *Analytical Balance*, capable of accurately weighing to at least ± 0.0001 g.

7.12 *Hammer*.

8. Reagents and Materials

8.1 *Acetaldehyde (AA)*, 500 ppm AA in water (or 1000 ppm), purchased certified standard.⁹

8.2 *Liquid Nitrogen*, plant grade (R-3, S-3).

9. Calibration and Standardization

NOTE 1—The following procedure should be performed and recorded once every three months.

9.1 Break open a certified AA standard ampule. (Ampules must be stored in a refrigerator.)

9.2 Using the syringe, fill it by placing the tip in the liquid standard and quickly moving the plunger up and down several times to evacuate any bubbles, then pull the plunger back past the 2.000- μL mark to 2.200 to 2.250 μL .

9.3 Wipe the syringe needle with a tissue.

⁴ J & W Scientific GS-Q (Catalogue Number 115-3435), available from 91 Blue Ravine Rd., Folsom, CA, website: JWscientific.com, was used in the development of this standard. If you are aware of alternative suppliers, please provide this information to ASTM headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend.

⁵ Available from Perkin-Elmer, website: perkin-elmer.com.

⁶ Available from Kimble/Kontes, Vineland, NJ, e-mail: cs@kimble-kontes.com.

⁷ Wheaton Part Number 224303, available from 1501 North 10th St., Millville, NJ 08332, website: algroupwheaton.com, was used in the development of this standard. If you are aware of alternative suppliers, please provide this information to ASTM headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend.

⁸ Hamilton Digital with 2- μL capacity, Model Number 7002KH, was used in the development of this standard. If you are aware of alternative suppliers, please provide this information to ASTM headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend.

⁹ Protocol Analytical Supplies, Inc., Middlesex, NJ 08846 (R-3, S-2). If you are aware of alternative suppliers, please provide this information to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend.

9.4 Depress the plunger until the digital readout is 2.000 μL .

9.5 Smear the excess liquid that is on the syringe tip on the OUTSIDE of the headspace vial.

9.6 Place the syringe inside of the vial so that the tip just touches the bottom of the vial.

9.7 Quickly inject the liquid standard into the vial and swirl the syringe tip around the inside of the vial to smear all liquid on the vial walls.

9.8 Remove the syringe and IMMEDIATELY cap the vial.

9.9 Calculate the weight of AA based on the standard's certified value and a 2.000- μL injection volume.

NOTE 2—Acetaldehyde is very volatile. The AA ampules must be stored in a refrigerator, and the standards prepared immediately after breaking open an ampule.

9.10 Analyze the working standard by the procedure described in Section 11, starting with 11.2.11.

9.11 Calculate an AA response factor for the standard using the following equation:

$$\text{response factor of AA} = \text{Wt of AA in } \mu\text{g/area of AA} \quad (1)$$

NOTE 3—Due to the error associated with the certified standard, 9.1-9.11 should be performed five times using five different standard ampules.

9.12 Average the five response factors obtained, and use this value for the sample analyses.

9.13 Manually enter the calculated response factor in the calibration list of the Hewlett-Packard 6890³ integrator or data system.

NOTE 4—During a series of sample analyses, a periodic check of instrument performance is recommended by placing a few liquid standard samples throughout the sample set. If these values fall out of the acceptable range as specified by the certificate of analysis, recalibration (9.1-9.12) should be performed.

10. Sample Preparation

10.1 *Parisons or Preforms or Plaques*—May be cryogenically ground whole, or can be broken into small pieces with a hammer (using liquid nitrogen) and then ground with the aid of grinding mill equipped with a 20 mesh or 850 μm screen. The grind should be thoroughly homogenized before sampling for AA. If the appropriate size screen is not available on the large grinding mill, then it is suggested that the sample be ground to 3 to 6 mm on the large mill and the sample thoroughly homogenized. A portion can then be taken to a smaller mill equipped with the 20 mesh or 850 μm screen and cryogenically ground again before analysis. Again the final sample should be thoroughly homogenized.

10.2 *Pellets*—May be cryogenically ground in a small grinding mill using liquid nitrogen. The final sample should be thoroughly homogenized before sampling for analysis.

NOTE 5—Samples, either preforms, plaques, or pellets, should be chilled in the liquid nitrogen for several minutes until the liquid nitrogen stops boiling and then dropped immediately into the grinder. Sample should be sufficiently ground in a few seconds. The grinder should not be allowed to operate more than 20 to 30 s as in such cases undesirable sample heating can occur.

11. Procedure

NOTE 6—Refer to the general operating manual for the Hewlett-Packard 6890³ gas chromatograph, the Hewlett-Packard 7694³ head-space

sampler, and the Hewlett-Packard 6890³ series integrator for instructions in performing steps in this procedure.

11.1 Adjust the H-P 6890³ gas chromatograph to the conditions specified in Appendix X1. Adjust the H-P 7694³ head-space sampler to the conditions in Appendix X2. Set the H-P 6890³ series integrator to the conditions in Appendix X3.

11.2 *Sample Analysis:*

11.2.1 Place 2 to 3 of polymer pellets (or crushed preform) into a small Dewar flask.

11.2.2 Cover the polymer with 20 to 40 mL of liquid nitrogen.

11.2.3 Allow the polymer to chill under the liquid nitrogen for approximately 3 min (or until most of the liquid N₂ has evaporated).

11.2.4 Turn on the Wiley mill equipped with a 800 to 1000 µm screen.

11.2.5 Slowly pour the remaining liquid nitrogen from the Dewar flask through the Wiley mill, followed by the chilled polymer sample (tapping the sample may be required).

11.2.6 Collect the ground polymer in a small glass jar or small manila envelope.

11.2.7 Turn off the Wiley mill and clean it with a vacuum cleaner.

11.2.8 Allow the ground polymer sample to come to room temperature (approximately 10 min).

11.2.9 Weigh approximately 0.2000 (± 0.0200) g, recorded to the nearest 0.0001 g, into a 20-mL head-space vial.

11.2.10 Place a septum (with Teflon side down towards the inside of the vial) on the vial. Place an aluminum cap on top of the septum, and crimp the cap with a crimper UNTIL THE CAP CANNOT BE TURNED. Remove the center piece of the aluminum cap (if it exists).

11.2.11 Place the vial in the appropriate position in the head-space sampler.

11.2.12 Press the “Vial Parameter” key on the H-P 7964³ head-space sampler, and enter the starting and stopping vial positions.

11.2.13 Press the “START” button on the H-P 7694³ head-space sampler.

11.2.14 The head-space sampler will heat the sample for 60 min at 150°C and then automatically inject the head-space gas and start the gas chromatograph and integrator.

11.2.15 The final report will appear on the H-P 6890³ integrator or the data system when the GC is finished. This report will give the micrograms of AA.

11.2.16 To determine the concentration in ppm of AA in the polymer sample, divide the micrograms of AA (reported in 11.2.15) by the sample weight in the vial (recorded in 11.2.9 as grams of polymer).

12. Calculation

12.1 The AA response factor is calculated as described in 9.11 and 9.12. The ppm of AA can be calculated manually by multiplying the response factor and the area of the AA peak, and then dividing this number by the sample weight in the vial (in grams).

13. Report

13.1 Report the ppm of AA to two decimal places.

14. Precision and Bias ¹⁰

14.1 To be written from work done in the International Society of Beverage Technologists subcommittee at a later date.

15. Keywords

15.1 acetaldehyde; carbonated soft drink; ground parison AA; PET bottles; 24 hours headspace; AA test; water

¹⁰ A research report is available from ASTM headquarters. Request RR:F02-1015.

APPENDIXES

(Nonmandatory Information)

X1. HEWLETT-PACKARD 6890³ SERIES GC CONDITIONS

TABLE X1.1 Hewlett-Packard 6890³ Series GC Conditions

Temp 1 Isothermal	90°C
Time 1	8.00 min
Injector Temperature	250°C
Detector Temperature	250°C
Head Pressure	10 psi
Column-Flow	12.2 mL/min Helium
Velocity	85 cm/s
Split Ratio	2.0
Detector Air Flow	300 mL/min
Detector Hydrogen Flow	30 mL/min
Detector Makeup Flow	20 mL/min helium

X2. HEWLETT-PACKARD 7694³ HEAD-SPACE SAMPLER CONDITIONS

TABLE X2.1 Hewlett-Packard 7694³ Head-Space Sampler Conditions

Oven Temp	150°C
Loop Temp	160°C
Transfer Line Temp	170°C
Carrier Pressure	11.5 psi
Vial Pressure	10.5 psi
Vial Eq. Time	60 min
Pressurize Time	0.2 min
Loop Fill Time	0.2 min
Loop Eq. Time	0.1 min
Inject Time	0.2 min
GC Cycle Time	9 min

X3. HEWLETT-PACKARD 6890 SERIES³ INTEGRATOR METHOD FILE

iTeh Standards
 (https://standards.iteh.ai)
 Document Preview

ASTM F2013-00

<https://standards.iteh.ai/catalog/standards/sist/a57c3987-f299-4a65-bdab-14bad4f5db8d/astm-f2013-00>