



SLOVENSKI STANDARD
SIST ISO 11534:2000
01-junij-2000

Železove rude -- Določitev vsebnosti svinec -- Metoda s plamensko atomsko absorpcijsko spektrometrijo

Iron ores -- Determination of tin content -- Flame atomic absorption spectrometric method

ITeH STANDARD PREVIEW

Minerais de fer -- Dosage de l'étain -- Méthode par spectrométrie d'absorption atomique dans la flamme

[SIST ISO 11534:2000](https://standards.iteh.ai/catalog/standards/sist/eb9d5ea-659f-482f-b25e-ca484556f468/sist-iso-11534-2000)

Ta slovenski standard je istoveten z: **ISO 11534:1998**

ICS:

73.060.10 Železove rude Iron ores

SIST ISO 11534:2000

en

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST ISO 11534:2000

<https://standards.iteh.ai/catalog/standards/sist/eb9d5ea-659f-482f-b25e-ca484556f468/sist-iso-11534-2000>

INTERNATIONAL
STANDARD

ISO
11534

First edition
1998-05-01

**Iron ores — Determination of tin content —
Flame atomic absorption spectrometric
method**

*Minerais de fer — Dosage de l'étain — Méthode par spectrométrie
d'absorption atomique dans la flamme*

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST ISO 11534:2000](https://standards.iteh.ai/catalog/standards/sist/eb9d5ea-659f-482f-b25e-ca484556f468/sist-iso-11534-2000)

[https://standards.iteh.ai/catalog/standards/sist/eb9d5ea-659f-482f-b25e-
ca484556f468/sist-iso-11534-2000](https://standards.iteh.ai/catalog/standards/sist/eb9d5ea-659f-482f-b25e-ca484556f468/sist-iso-11534-2000)



Reference number
ISO 11534:1998(E)

ISO 11534:1998(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

iTeh STANDARD PREVIEW

International Standard ISO 11534 was prepared by Technical Committee ISO/TC 102, *Iron ores*, Subcommittee SC 2, *Chemical analysis*.

Annex A forms an integral part of this International Standard. Annexes B and C are for information only. <https://standards.itih.ai/catalog/standards/sist/eb9d5ea-659f-482f-b25e-ca484556f468/sist-iso-11534-2000>

© ISO 1998

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

International Organization for Standardization
Case postale 56 • CH-1211 Genève 20 • Switzerland
Internet central@iso.ch
X.400 c=ch; a=400net; p=iso; o=isocs; s=central

Printed in Switzerland

Iron ores — Determination of tin content — Flame atomic absorption spectrometric method

WARNING—This International Standard may involve hazardous materials, operations and equipment. This International Standard does not purport to address all of the safety problems associated with its use. It is the responsibility of the user of this International Standard to establish appropriate health and safety practices and determine the applicability of regulatory limitations prior to use.

1 Scope

This International Standard specifies a flame atomic absorption spectrometric method for the determination of the tin content of iron ores.

This method is applicable to tin contents between 0,001% (*m/m*) and 0,015 % (*m/m*) in natural iron ores, iron ore concentrates and agglomerates, including sinter products.

2 Normative references

The following standards contain provisions which, through reference in this text, constitute provisions of this International Standard. At the time of publication, the editions indicated were valid. All standards are subject to revision, and parties to agreements based on this International Standard are encouraged to investigate the possibility of applying the most recent editions of the standards indicated below. Members of IEC and ISO maintain registers of currently valid International Standards.

ISO 648:1977, *Laboratory glassware — One-mark pipettes*.

ISO 1042:—¹⁾, *Laboratory glassware — One-mark volumetric flasks*.

ISO 3081:1986, *Iron ores — Increment sampling — Manual method*.

ISO 3082:1987, *Iron ores — Increment sampling and sample preparation — Mechanical method*.

ISO 3083:1986, *Iron ores — Preparation of samples — Manual method*.

ISO 3696:1987, *Water for analytical laboratory use — Specification and test methods*.

ISO 7764:1985, *Iron ores — Preparation of predried test samples for chemical analysis*.

¹⁾ To be published. (Revision of ISO 1042:1983)

3 Principle

Treatment of the test portion with sulfuric acid and hydrofluoric acid in a platinum crucible. Removal of silica by heating and evaporation. Fusion of the residue in sodium carbonate/sodium tetraborate flux, and dissolution of the cooled melt in hydrochloric acid.

Reduction of iron by ascorbic acid and potassium iodide, followed by extraction of tin with tri-*n*-octyl phosphine oxide (TOPO) in 4-methyl-2-pentanone (MIBK) solvent.

Aspiration of the tin TOPO-MIBK extract into a dinitrogen oxide-acetylene flame and measurement of absorbance of tin at 286,3 nm resonance line using a tin hollow cathode lamp. Comparison of the absorbance values obtained with those obtained from calibration solutions.

4 Reagents

During the analysis, use only reagents of recognized analytical grade and only water that conforms to grade 2 of ISO 3696:1987.

4.1 Sodium carbonate (Na_2CO_3), anhydrous.

4.2 Sodium tetraborate ($\text{Na}_2\text{B}_4\text{O}_7$), anhydrous.

4.3 Iron oxide (Fe_2O_3), of minimum purity 99,9% (*m/m*) and tin content < 0,000 2% (*m/m*).

4.4 Hydrochloric acid, ρ 1,16 g/ml to 1,19 g/ml.

4.5 Hydrochloric acid, ρ 1,16 g/ml to 1,19 g/ml, diluted 1 + 1.

4.6 Hydrochloric acid, ρ 1,16 g/ml to 1,19 g/ml, diluted 2 + 3.

Add 200 ml of hydrochloric acid (4.4) to 300 ml of water and mix.

4.7 Hydrofluoric acid, ρ 1,13 g/ml, 40% (*m/m*) or 1,19 g/ml, 48% (*m/m*).

4.8 Sulfuric acid, ρ 1,84 g/ml.

4.9 Sulfuric acid, ρ 1,84 g/ml, diluted 1 + 1.

4.10 Ascorbic acid solution, 200 g/l.

This solution shall be prepared freshly on the day of use.

4.11 Potassium iodide-ascorbic acid solution

Dissolve 90 g of potassium iodide in water, add 30 g of ascorbic acid and 30 ml of hydrochloric acid (4.4), and dilute with water to 200 ml. This solution shall be prepared freshly just prior to use.

4.12 Tri-*n*-octyl phosphine oxide (TOPO)-4-methyl-2 pentanone (MIBK) solution

Dissolve 1 g of TOPO in 100 ml of MIBK.

4.13 Tin standard solution, 200 μg Sn/ml.

Dissolve 0,1 g of tin metal [purity > 99,5 % (*m/m*)] in a platinum dish (with cover) with 5 ml of hydrochloric acid (4.4). After cooling, transfer the solution to a 500 ml one-mark volumetric flask, add 200 ml of hydrochloric acid (4.5), and dilute to volume with hydrochloric acid (4.5).

4.14 Tin standard solution, 40 µg Sn/ml.

Transfer 20 ml of tin standard solution (4.13) to a 100 ml one-mark volumetric flask, dilute to volume with hydrochloric acid (4.5) and mix.

4.15 Tin standard solution, 10 µg Sn/ml.

Transfer 5,0 ml of tin standard solution (4.13) to a 100 ml one-mark volumetric flask, dilute to volume with hydrochloric acid (4.5) and mix.

5 Apparatus

Ordinary laboratory apparatus, including one-mark pipettes and one-mark volumetric flasks complying with the specifications of ISO 648 and ISO 1042 respectively, and

5.1 Platinum crucible, 25 ml to 30 ml capacity.

5.2 Platinum rod.

5.3 Muffle furnace, suitable for heating at 1 000 °C to 1 020 °C.

5.4 Atomic absorption spectrometer, equipped with a dinitrogen oxide-acetylene burner.

WARNING—To avoid possible explosion hazards, follow the manufacturer's instructions for igniting and extinguishing the dinitrogen oxide-acetylene flame. Wear tinted safety glasses whenever the flame is burning.

The atomic absorption spectrometer used in this method shall meet the following criteria.

- a) Minimum sensitivity - the absorbance of the most concentrated calibration solution (see 7.4.5) shall be at least 0,13.
- b) Graph linearity - the slope of the calibration graph covering the top 20 % of the concentration range (expressed as a change in absorbance) shall be not less than 0,7 of the value of the slope for the bottom 20 % of the concentration range determined in the same way.
- c) Minimum stability - the standard deviation of the absorbance of the most concentrated calibration solution and that of the zero calibration solution, each being calculated from a sufficient number of repetitive measurements, shall be less than 1,5 % and 0,5 % respectively of the mean value of the absorbance of the most concentrated calibration solution.

NOTES

1 The use of a strip chart recorder and/or digital readout device is recommended to evaluate criteria a), b) and c) for all subsequent measurements.

2 Instrument parameters may vary with each instrument. The following parameters were successfully used in several laboratories and they can be used as guidelines. A dinitrogen oxide-acetylene flame was used.

Hollow cathode lamp, mA	12,5
Wavelength, nm	286,3
Dinitrogen oxide flow rate, l/min	6,6
Acetylene flow rate, l/min	4,5

In systems where the values shown above for gas flow rates do not apply, the ratio of the gas flow rates may still be a useful guideline.

6 Sampling and samples

6.1 Laboratory sample

For analysis, use a laboratory sample of minus 100 µm particle size which has been taken in accordance with ISO 3081 or ISO 3082 and prepared in accordance with ISO 3082 or ISO 3083. In the case of ores having significant contents of combined water or oxidizable compounds, use a particle size of minus 160 µm.

NOTE — A guideline on significant contents of combined water and oxidizable compounds is incorporated in ISO 7764.

6.2 Preparation of predried test samples

Thoroughly mix the laboratory sample and, taking multiple increments, extract a test sample in such a way that it is representative of the whole contents of the container. Dry the test sample at $105\text{ °C} \pm 2\text{ °C}$, in accordance with ISO 7764. (This is the predried test sample.)

7 Procedure

7.1 Number of determinations

Carry out the analysis at least in duplicate in accordance with annex A, independently, on one predried test sample.

NOTE — The expression "independently" means that the second and any subsequent result is not affected by the previous result(s). For the particular analytical method, this condition implies that the repetition of the procedure is carried out either by the same operator at a different time or by a different operator including, in either case, appropriate recalibration.

7.2 Test portion

Taking several increments, weigh, to the nearest 0,000 2 g, approximately 2 g of the predried test sample obtained in accordance with 6.2.

NOTE — The test portion should be taken and weighed quickly to avoid reabsorption of moisture.

7.3 Blank test and check test

In each run, one blank test and one analysis of a certified reference material of the same type of ore shall be carried out in parallel with the analysis of the ore sample(s) under the same conditions. A predried test sample of the certified reference material shall be prepared as specified in 6.2.

NOTE — The certified reference material should be of the same type as the sample to be analysed and the properties of the two materials should be sufficiently similar to ensure that in either case no significant changes in the analytical procedure will become necessary. Where a certified reference material is not available, a reference material may be used (see 8.2.4).

Where the analysis is carried out on several samples at the same time, the blank value may be represented by one test, provided that the procedure is the same and the reagents used are from the same reagent bottles.

Where the analysis is carried out on several samples of the same type of ore at the same time, the analytical value of one certified reference material may be used.

7.4 Determination

7.4.1 Decomposition of the test portion

Transfer the test portion (see 7.2) to a crucible (5.1), moisten with a few drops of water, add 2 ml of sulfuric acid (4.9) and 6 ml of hydrofluoric acid (4.7), mix well using a platinum rod (5.2) and wash the rod with water.

Using a gas burner, heat the crucible gently at first, then to white fumes and continue heating until no fumes are observed. Place the crucible in a muffle furnace (5.3) at 1 000 °C to 1 020 °C for 30 min.

NOTE 1 During the first heating, mix the contents periodically to facilitate the digestion of silica.

Cool the crucible and remove the residue on the crucible walls using a platinum rod. Add 1,6 g of sodium carbonate (4.1) and 0,8 g of sodium tetraborate (4.2), mix well with a platinum rod, and heat over a Meker burner for 5 min or until the mixture has partially melted. Add a further 1,6 g of sodium carbonate and 0,8 g of sodium tetraborate and repeat the heating until fusion is virtually complete, swirling the crucible to remove any residue on its inner walls. Remove from the heat source and swirl until the melt solidifies on the inner walls of the crucible. Place the crucible in a muffle furnace at 1 000 °C to 1 020 °C for 15 min. Cool and place the crucible in a 200 ml beaker. Add 50 ml of hydrochloric acid (4.6), cover the beaker with a watch glass and heat at 90 °C until dissolution of the melt is complete.

NOTES

2 A pressurized air burner or similar, capable of attaining a temperature of 900 °C or more, may be used instead of a Meker burner.

3 The crucible may need to be rolled to ensure complete dissolution of the fused melt.

Remove the crucible and rinse. Cool the solution.

7.4.2 Treatment of the test solution

Add 20 ml of ascorbic acid solution (4.10) and 4 ml of potassium iodide-ascorbic acid solution (4.11) to the test solution (see 7.4.1) and mix. Transfer the solution to a 200 ml separating funnel having a mark indicating 100 ml volume. Dilute to 100 ml with water and mix gently. Add 10 ml of TOPO-MIBK solution (4.12). Stopper the funnel and shake vigorously for 30 s. Allow the layers to separate.

Drain the lower aqueous layer. Using a dry filter paper, drain the organic layer into a 25 ml one-mark volumetric flask and stopper it. Reserve the solution for atomic absorption measurement. (This solution is the TOPO-MIBK extract.)

7.4.3 Adjustment of atomic absorption spectrometer

Aspirate MIBK between the TOPO-MIBK extracts of each calibration and test solution.

Ensure that the trap and the drain tube are compatible with the MIBK solvent.

After completion of the test work, drain off MIBK from the trap.

For normal work with aqueous aspirations, dry and fill with water.

Set the wavelength for tin (286,3 nm) to obtain minimum absorbance, and adjust the read-out to zero absorbance.

Taking account of appropriate safety precautions, light the dinitrogen oxide-acetylene flame. After 10 min preheating of the burner, aspirate the TOPO-MIBK extract of the calibration solution having highest tin content and carefully adjust the fuel flow and burner position to obtain maximum absorbance.

Check that the conditions for zero absorbance have been maintained while aspirating MIBK, and again aspirate the TOPO-MIBK extract for the solution having highest tin content to establish that the absorbance reading is not drifting. Set the reading for MIBK to zero absorbance.

NOTE — Water in the trap reservoir has to be emptied, dried and replaced with MIBK for aspirating the TOPO-MIBK extract into the flame.