



Designation: C 711 – 93 (Reapproved 1997)

## Standard Test Method for Low-Temperature Flexibility and Tenacity of One-Part, Elastomeric, Solvent-Release Type Sealants<sup>1</sup>

This standard is issued under the fixed designation C 711; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

### 1. Scope

1.1 This test method covers determination of the low-temperature flexibility and tenacity of one-part, elastomeric, solvent-release type sealants after cyclic high- and low-temperature aging.

1.2 *This standard does not purport to address all of the safety problems, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

### 2. Referenced Documents

- 2.1 *ASTM Standards:*  
C 717 Terminology of Building Seals and Sealants<sup>2</sup>

### 3. Terminology

3.1 *Definitions*—Refer to Terminology C 717 for definitions of the following terms used in this Test Method: elastomer, elastomeric, joint, sealant, solvent-release sealant.

### 4. Significance and Use

4.1 This test method is not intended to simulate an actual use condition but it will give some indication of the elastomeric properties or flexibility of a building joint sealant at low temperature. It can serve to differentiate between elastomer-based sealants and sealants based on nonelastic binders that can harden or embrittle on aging and crack or lose adhesion when flexed at low temperature. In addition, it can aid in identifying sealants that have poor flexibility because they are overextended and contain a very low level of elastomeric binder as well as those sealants having binders that will embrittle at low temperature.

### 5. Apparatus

5.1 *Aluminum Panels*, 3, thin, approximately 3 in. (76 mm) wide by 5 in. (127 mm) long by 0.012 in. (0.30 mm) thick.

5.2 *Spatula*, steel, with thin knife edge.

5.3 *Template*, rectangular, of steel or brass, 1/8 in. (3.2 mm) high, 1 by 3 3/4 in. (25 by 95 mm) inside and approximately 2 by 4 3/4 in. (51 by 121 mm) outside.

5.4 *Oven*, forced-draft type, having a temperature controlled at  $158 \pm 3.6^\circ\text{F}$  ( $70 \pm 2^\circ\text{C}$ ).

5.5 *Freezer Chest or Cold Box*, having a controlled temperature of  $-10 \pm 5^\circ\text{F}$  ( $-23 \pm 3^\circ\text{C}$ ).

5.6 *Mandrel or Rod*, with a diameter of 1/4 in. (6.4 mm), with a suitable holder or rack to support it.

5.7 *Methyl Ethyl Ketone*, or similar solvent.

### 6. Sampling

6.1 Take the test specimen from a previously unopened container as received from the sealant manufacturer.

### 7. Test Specimens

7.1 Prepare three test specimens as follows:

7.1.1 Condition the sealant sample in the original closed container for at least 5 h at  $73.4 \pm 3.6^\circ\text{F}$  ( $23 \pm 2^\circ\text{C}$ ) and  $50 \pm 5\%$  relative humidity.

7.1.2 Thoroughly clean template and aluminum panels with solvent.

7.1.3 Center the template on the aluminum panel and carefully fill it with compound, avoiding air pockets. Strike off the surface of the compound flat to a uniform 1/8-in. (3.2-mm) thickness.

7.1.4 With the thin knife edge of the spatula, cut all around the outside edge of the compound and lift the template straight up and off leaving the formed sealant on the plate.

### 8. Conditioning

8.1 Condition the specimens for at least 24 h at  $73.4 \pm 3.6^\circ\text{F}$  ( $23 \pm 2^\circ\text{C}$ ) and  $50 \pm 5\%$  relative humidity.

### 9. Procedure

9.1 Expose the conditioned specimens three times to the following temperature cycle:

$$\begin{aligned} &16 \text{ h at } 158 \pm 3.6^\circ\text{F} (70 \pm 2^\circ\text{C}) \\ &8 \text{ h at } -10 \pm 5^\circ\text{F} (-23 \pm 3^\circ\text{C}) \end{aligned} \quad (1)$$

9.2 At the end of the third cycle, while it is in the freezer at  $-10^\circ\text{F}$  ( $-23^\circ\text{C}$ ) bend the panel through  $180^\circ$  over the 1/4-in.

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee C24 on Building Seals and Sealants and is the direct responsibility of Subcommittee C24.20 on General Sealant Standards.

Current edition approved April 15, 1993. Published June 1993. Originally published as C 711 – 72. Last previous edition C 711 – 72 (1988).

<sup>2</sup> *Annual Book of ASTM Standards*, Vol 04.07.