



**SLOVENSKI STANDARD**  
**SIST ISO 1013:1998**

**01-februar-1998**

---

Številka: SIST ISO 1013:1998

Coke -- Determination of bulk density in a large container

Coke -- Détermination de la masse volumique en vrac dans un récipient de grandes dimensions

(standards.iteh.ai)

**Ta slovenski standard je istoveten z: ISO 1013:1995**

<https://standards.iteh.ai/catalog/standards/sist/473c785b-4c68-49ab-a325-78e3339a4c27/sist-iso-1013-1998>

**ICS:**

75.160.10      Trda goriva                      Solid fuels

**SIST ISO 1013:1998**                      **en**

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

SIST ISO 1013:1998

<https://standards.iteh.ai/catalog/standards/sist/473c785b-4c68-49ab-a325-78e3339a4c27/sist-iso-1013-1998>

INTERNATIONAL  
STANDARD

**ISO**  
**1013**

Second edition  
1995-07-01

---

---

**Coke — Determination of bulk density in a  
large container**

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

*Coke — Détermination de la masse volumique en vrac dans un récipient  
de grandes dimensions*

SIST ISO 1013:1998

<https://standards.iteh.ai/catalog/standards/sist/473c785b-4c68-49ab-a325-78e3339a4c27/sist-iso-1013-1998>



Reference number  
ISO 1013:1995(E)

**ISO 1013:1995(E)****Foreword**

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

International Standard ISO 1013 was prepared by Technical Committee ISO/TC 27, *Solid mineral fuels*, Subcommittee SC 3, *Coke*.

This second edition cancels and replaces the first edition (ISO 1013:1975), which has been technically revised.

ITC STANDARD PREVIEW

(standards.iteh.ai)

SIST ISO 1013:1998

<https://standards.iteh.ai/catalog/standards/sist/473-785b-4c68-49ab-a325-73c379a4c27/sist-iso-1013-1998>

© ISO 1995

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

International Organization for Standardization  
Case Postale 56 • CH-1211 Genève 20 • Switzerland

Printed in Switzerland

## Introduction

The bulk density of coke depends upon its physical characteristics, e.g. apparent relative density, shape and size of the coke particles, and upon the dimensions of the container. If the container is sufficiently large, its actual dimensions will have a negligible effect on the value obtained in a determination of bulk density. The method described in this International Standard is based on the use of any suitable large container, possibly that in which the coke is delivered, such as a wagon or skip. The determination of bulk density of coke in a small container (of specified dimensions) is described in ISO 567.

## iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST ISO 1013:1998](https://standards.iteh.ai/catalog/standards/sist/473c785b-4c68-49ab-a325-78e3339a4c27/sist-iso-1013-1998)

<https://standards.iteh.ai/catalog/standards/sist/473c785b-4c68-49ab-a325-78e3339a4c27/sist-iso-1013-1998>

**iTeh STANDARD PREVIEW**  
This page intentionally left blank  
**(standards.iteh.ai)**

SIST ISO 1013:1998

<https://standards.iteh.ai/catalog/standards/sist/473c785b-4c68-49ab-a325-78e3339a4c27/sist-iso-1013-1998>

# Coke — Determination of bulk density in a large container

## 1 Scope

This International Standard specifies a method for the determination of the bulk density of coke in a large container such as a wagon or skip.

## 2 Normative references

The following standards contain provisions which, through reference in this text, constitute provisions of this International Standard. At the time of publication, the editions indicated were valid. All standards are subject to revision, and parties to agreements based on this International Standard are encouraged to investigate the possibility of applying the most recent editions of the standards indicated below. Members of IEC and ISO maintain registers of currently valid International Standards.

ISO 567:1995, *Coke — Determination of bulk density in a small container*.

ISO 579:1981, *Coke — Determination of total moisture content*.

## 3 Definition

For the purposes of this International Standard, the following definition applies.

**3.1 bulk density:** The mass of a portion of a solid mineral fuel divided by the volume of the container which is filled by that portion under specified conditions.

## 4 Principle

A weighed container of known volume is filled with coke and the increase in mass is determined.

## 5 Apparatus

**5.1 Container**, such as a wagon or skip, capable of holding at least 3 t of the coke.

**5.2 Weighing machine**, capable of weighing the container and its contents to an accuracy of 0,2 %.

## 6 Procedure

Weigh the empty container (5.1) on the weighing machine (5.2). Measure the internal dimensions of the container to the nearest 1 cm and calculate its capacity.

NOTE 1 If the container is already fully charged, it should be weighed with the coke first, then be weighed empty and then be measured.

With the container on a level surface, carefully charge the coke into it until pieces of coke project above the top of the container across the whole surface.

Slide a straightedge across the top of the container and remove any pieces of coke which obstruct its passage. Weigh the charged container.

## 7 Expression of results

The bulk density in a large container ( $\rho_1$ ) of the coke, in kilograms per cubic metre, on a dry basis, is given by the equation:

$$\rho_1 = \frac{m_2 - m_1}{V} \times \frac{100 - M}{100}$$

where

$m_1$  is the mass, in kilograms, of the empty container;

- $m_2$  is the mass, in kilograms, of the container plus coke;
- $V$  is the capacity, in cubic metres, of the container;
- $M$  is the total moisture content of the coke, expressed as a percentage by mass, determined in accordance with ISO 579.

Report the result to three significant figures.

For calculation of the result on an "as sampled" basis, omit the correction factor for moisture, i.e. " $(100 - M)/100$ ", in the equation.

## 8 Precision

### 8.1 Repeatability limit

The results of two determinations, carried out at different times by the same operator with the same apparatus on samples from the same lot of coke, should not differ by more than  $10 \text{ kg/m}^3$ .

### 8.2 Reproducibility

No value for reproducibility can be quoted for determinations carried out on different sites because the transport of coke samples involves the risk of breakage and thus alteration of the size distribution and the bulk density.

## 9 Test report

The test report shall include the following:

- the method used by reference to this International Standard;
- a complete identification of the sample;
- the date of the test;
- the results expressed in accordance with clause 7;
- any unusual features noted during the determination;
- any operation not included in this International Standard, or regarded as optional.

iTeh STANDARD PREVIEW  
(standards.iteh.ai)

[SIST ISO 1013:1998](https://standards.iteh.ai/catalog/standards/sist/473c785b-4c68-49ab-a325-78e3339a4c27/sist-iso-1013-1998)

<https://standards.iteh.ai/catalog/standards/sist/473c785b-4c68-49ab-a325-78e3339a4c27/sist-iso-1013-1998>