



Designation: D 6072 – 96 (Reapproved 2002)

Standard Guide for Obtaining Samples of Geosynthetic Clay Liners¹

This standard is issued under the fixed designation D 6072; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This practice covers procedures for sampling geosynthetic clay liners (GCLs) for the purpose of laboratory testing. These procedures are designed to ensure that representative samples are obtained and properly packaged for submittal to a testing laboratory.

1.2 The procedures in this practice may be applied to samples of unhydrated GCLs obtained at the project site or at the production facility, prior to shipment to the project site.

1.3 It is assumed that the *number* of samples to be obtained has already been determined in the project specification, standard test method, or by prior agreement between the purchaser and seller. This practice covers only the methods for obtaining a pre-arranged number of samples and does not describe methods for obtaining individual specimens from the sample.

1.4 The values stated in SI units are to be regarded as the standard.

1.5 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:

- D 4354 Practice for Sampling of Geosynthetics for Testing²
- D 4439 Terminology for Geosynthetics²
- D 4873 Guide for Identification, Storage, and Handling of Geosynthetic Rolls and Samples²

3. Terminology

3.1 Definitions:

3.1.1 *geosynthetic clay liner (GCL), n*—a manufactured hydraulic barrier consisting of clay bonded to a layer or layers of geosynthetics.

3.1.2 *sample, n*—a portion of a material which is taken for testing or for record purposes (See Practice D 4354).

3.1.3 *specimen, n*—a specific portion of a material or laboratory sample upon which a test is performed or which is taken for that purpose (See Practice D 4354).

3.1.4 For definitions of other geosynthetic terms used in this practice, refer to Terminology D 4439.

4. Significance and Use

4.1 This practice provides a method by which samples of GCL may be obtained for laboratory testing. The practice applies to materials obtained either at a job site or at a production facility.

4.2 GCL samples obtained in accordance with this practice will be considered representative of the actual manufactured GCL.

4.3 The quantity of GCL received by the laboratory should be sufficient for the preparation of several representative test specimens for a variety of standardized physical, hydraulic, and mechanical tests commonly performed on GCLs.

4.4 The procedures in this practice should be used by plant and field personnel for obtaining GCL samples for laboratory testing.

5. Procedure

5.1 In accordance with the project specifications or with Practice D 4354, divide the shipment or other given quantity of GCL into lots, and select lot and laboratory samples. This will usually involve the selection of a certain number of finished GCL rolls from which samples will be cut.

5.2 Affix on the packaging of the GCL rolls to be sampled adhesive labels or other markings which clearly identify that the roll is to be sampled.

5.3 Record the label information from each roll to be sampled for future incorporation into within the quality assurance/quality control (QA/QC) documentation for the GCL.

5.4 Segregate the rolls identified for sampling. Refer to appropriate ASTM standard practices for the proper equipment and techniques for handling the GCL rolls.

5.5 Inspect the packaging of the selected GCL rolls for damage. Describe and record the damage, if any.

5.6 Remove the outer packaging from the GCL as carefully as possible, taking precautions not to damage the GCL and to preserve the packaging as much as possible for re-use after sampling is completed.

¹ This practice is under the jurisdiction of ASTM Committee D35 on Geosynthetics and is the direct responsibility of Subcommittee D35.04 on Geosynthetic Clay Liners.

Current edition approved December 10, 1996. Published December 1997.

² Annual Book of ASTM Standards, Vol 04.13.