



SLOVENSKI STANDARD

SIST EN 10155:1998

01-avgust-1998

Strukturalni jekli s izboljšano odpornostjo na atmosfersko korozijo - Tehnične pogoje dobave

Structural steels with improved atmospheric corrosion resistance - Technical delivery conditions

Wetterfeste Baustähle - Technische Lieferbedingungen

Aciers de construction à résistance améliorée à la corrosion atmosphérique - Conditions techniques de livraison

ITeH STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN 10155:1998](https://standards.iteh.ai/catalog/standards/sist/c7f340a4-0de7-4fb9-b11f-1cd4854961c/sist-en-10155-1998)

Ta slovenski standard je istoveten z: [EN 10155:1993](https://standards.iteh.ai/catalog/standards/sist/c7f340a4-0de7-4fb9-b11f-1cd4854961c/sist-en-10155-1998)

ICS:

77.140.10 Jekla za toplotno obdelavo Heat-treatable steels

SIST EN 10155:1998

en

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 10155:1998

<https://standards.iteh.ai/catalog/standards/sist/c7f340a4-0de7-4fb9-b11f-fcd4f854961c/sist-en-10155-1998>

EUROPEAN STANDARD

EN 10155:1993

NORME EUROPÉENNE

EUROPÄISCHE NORM

June 1993

UDC 669.14.018.29:669.018.821:620.1

Descriptors: Iron- and steel products, hot rolled products, structural steels, corrosion resistant steels, atmospheric corrosion, grades : quality, chemical composition, dimensions, delivery conditions, tests, inspection, marking

English version

**Structural steels with improved atmospheric
corrosion resistance - Technical delivery
conditions**

iTeh STANDARD PREVIEW

Aciers de construction à résistance améliorée à la corrosion atmosphérique - Conditions techniques de livraison (Standards.iteh.ai) Wetterfeste Baustähle - Technische Lieferbedingungen

SIST EN 10155:1998

<https://standards.iteh.ai/catalog/standards/sist/c7b40a4-0de7-4fb9-b11f-fcd4f854961c/sist-en-10155-1998>

This European Standard was approved by CEN on 1993-06-21. CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

The European Standards exist in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.

CEN

European Committee for Standardization
Comité Européen de Normalisation
Europäisches Komitee für Normung

Central Secretariat: rue de Stassart, 36 B-1050 Brussels

Contents list

	page
0 Foreword	4
1 Scope	5
2 Normative references	5
2.1 General standards	5
2.2 Standards on dimensions and tolerances	6
2.3 Standards on testing	7
3 Definitions	7
4 Information to be supplied by the purchaser	8
4.1 General	8
4.2 Options	8
5 Dimensions, mass and tolerances	8
5.1 Dimensions and tolerances	8
5.2 Mass of steel	9
6 Classification of grades and qualities; designation	9
6.1 Classification of grades and qualities	9
6.2 Designation	9
https://standards.iteh.ai/catalog/standards/sist/c7b40a4-0de7-4fb9-b11f-644854921654/sist-en-10155-1998	
7 Technical requirements	10
7.1 Steel manufacturing process	10
7.2 Delivery conditions	10
7.3 Chemical composition	11
7.4 Mechanical properties	12
7.5 Technological properties	13
7.6 Surface finish	13
8 Inspection and testing	14
8.1 General	14
8.2 Specific inspection and testing	14
8.3 Sampling	14
8.4 Test units	14
8.5 Verification of chemical composition	15
8.6 Mechanical tests	15
8.7 Test methods	16
8.8 Retests and resubmission for testing	17
8.9 Internal defects	17
8.10 Inspection documents	17
9 Marking for flat and long products	17
10 Complaints after delivery	18
11 Options	18
11.1 All products	18
11.2 Flat products	19



11.3	Long products	19
Annex A	(normative) Location of samples and test pieces (see EURONORM 18)	27
Annex B	(informative) Additional information for the use of steel with improved atmospheric corrosion resistance	30
Annex C	(informative) Notes on fabrication	31
Annex D	(informative) List of national standards which correspond with EURONORMS referenced	32
Annex E	(informative) List of corresponding former designations	34

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 10155:1998

<https://standards.iteh.ai/catalog/standards/sist/c7b340a4-0de7-4fb9-b11f-fcd4f854961c/sist-en-10155-1998>

Page 4
EN 10155:1993

Foreword

This European Standard has been drawn up by ECISS/TC 10 "Structural steel - qualities" whose secretariat is held by NNI.

This European Standard replaces EURONORM 155-80 "Weathering steels for structural purposes - Quality standard".

ECISS/TC 10 met 26 and 27 September 1991 in Brussels and agreed on the text for circulation for formal vote within CEN. The following countries were represented at that meeting: Belgium, Denmark, Finland, France, Germany, Italy, Luxembourg, Netherlands, Sweden and United Kingdom.

This standard was approved by CEN as a European Standard.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by December 1993, and conflicting national standards shall be withdrawn at the latest by December 1993.

In accordance with the CEN/CENELEC Internal Regulations, following countries are bound to implement this European Standard: Austria, Belgium, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.

SIST EN 10155:1998

<https://standards.iteh.ai/catalog/standards/sist/c7b40a4-0de7-4fb9-b11f-fcd4f854961c/sist-en-10155-1998>

1 Scope

1.1 This European Standard specifies requirements for long products and flat products of hot-rolled steels with improved atmospheric corrosion resistance (alloyed special steel according to EN 10020) in the grades and qualities given in tables 3 (chemical composition), 5 and 6 (mechanical properties) in the usual delivery condition as given in 7.2.

The thicknesses in which products of the steel grades and qualities specified in this European Standard may be supplied are given in table 2. The application of this standard to greater thicknesses shall be agreed at the time of the enquiry and order.

Option 1.

The steels specified in this European Standard are intended for use in welded, bolted and riveted components which shall have enhanced resistance to atmospheric corrosion, for service at ambient temperatures (subject to the restrictions described in 7.5.1).

They are not intended to be heat treated except products delivered in the delivery condition N. Stress relief annealing is permitted. Products delivered in the N condition may be normalized and hot formed after delivery (see clause 3). (standards.iteh.ai)

1.2 This European Standard does not apply to structural steels for use in the applications referred to in 1.1 for which specific Euronorms exist or European Standards dealing with steels for general structural applications are being prepared.

- non-alloy structural steels - (see EN 10025);
- steels for simple pressure vessels - (see EN 10207);
- non-alloy steel sheet and strip for pressure purposes - (see EN 10028 part 1 - 3);
- reinforcing bars (not for prestressing) - (see prEN 10080)¹⁾;
- weldable fine grain structural steel - (see EN 10113 part 1 - 3);
- hot finished structural hollow sections - (see EN 10210-1).

2 Normative references

This European Standard incorporates by dated or undated reference, provisions from other publications. These normative references are cited at the appropriate places in the text and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of any of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies.

2.1 General standards

EN 10020 Definition and classification of grades of steel

¹⁾ Draft is under discussion.

Page 6
EN 10155:1993

EN 10021		General technical delivery requirements for steel and iron products
EN 10025		Hot-rolled products of non-alloy structural steels -- Technical delivery conditions
EN 10027-1		Designation systems for steel -- Part 1: Steel names, principal symbols
EN 10027-2		Designation systems for steels -- Part 2: Numerical system
prEN 10052	¹⁾	Vocabulary of heat treatment terms for ferrous products
EN 10079		Definition of steel products
EN 10163		Delivery requirements for surface condition of hot-rolled steel plates, wide flats and sections -- Part 1: General requirements Part 2: Plate and wide flats Part 3: Sections
EN 10164		Steel products with improved deformation properties perpendicular to the surface of the product -- Technical delivery conditions
EN 10204		Metallic products -- Types of inspection documents
EURONORM 168 (1986)	²⁾	Iron and steel products -- Inspection documents -- Contents
ECISS IC 10		Designation systems for steel -- Additional symbols for steel names
2.2		https://standards.iteh.ai/catalog/standards/sist/c7b340a4-0de7-4fb9-b11f-10577698 Standards on dimensions and tolerances
EN 10029		Hot-rolled steel plates 3 mm thick or above -- Tolerances on dimensions, shape and mass
EN 10051		Continuously hot-rolled uncoated plate, sheet and strip of non-alloy and alloy steels -- Tolerances on dimensions and shape
prEN 10034	¹⁾	Structural steel I and H sections -- Tolerances on shape and dimensions
prEN 10056-2	¹⁾	Structural steel equal and unequal leg angles -- Part 2: Tolerances on shape and dimensions
EURONORM 19 (1957)	²⁾	IPE beams: parallel-flanged beams
EURONORM 24 (1962)	²⁾	Standard beams and channel sections -- Tolerances
EURONORM 48 (1984)	²⁾	Specification for hot-rolled narrow steel strip -- Tolerances on dimensions, shape and mass
EURONORM 53 (1962)	²⁾	Wide-flanged beams with parallel flanges
EURONORM 54 (1980)	²⁾	Small hot-rolled steel channels
EURONORM 55 (1980)	²⁾	Hot-rolled equal flange tees with radiused root and toes in steel

1) Draft is under discussion.

2) Until these EURONORMS are transformed into European Standards, they can either be implemented or reference made to the corresponding national standards, the list of which is given in Annex D to this European Standard.

EURONORM 56 (1977) ²⁾ ³⁾	Hot-rolled equal angles (with radiused root and toes)
EURONORM 57 (1978) ²⁾ ³⁾	Hot-rolled unequal angles (with radiused root and toes)
EURONORM 58 (1978) ²⁾	Hot-rolled flats for general purposes
EURONORM 59 (1978) ²⁾	Hot-rolled square bars for general purposes
EURONORM 60 (1977) ²⁾	Hot-rolled round bars for general purposes
EURONORM 91 (1981) ²⁾	Hot-rolled wide flats -- Tolerances on dimensions, shape and mass

2.3 Standards on testing

EN 10002-1	Metallic materials -- Tensile testing -- Part 1: method of test (at ambient temperature)
EN 10045-1	Metallic materials -- Charpy impact test -- Part 1: Test method
EURONORM 18 (1979) ²⁾	Selection and preparation of samples and test pieces for steel and iron and steel products
EURONORM 103 (1971) ²⁾	Microscopic determination of the ferritic and austenitic grain size of steel
ISO 2566/1 (1984)	Steel -- Conversion of elongation values -- Part 1: Carbon and low alloy steels

3 Definitions

SIST EN 10155:1998

For the purposes of this European Standard the following definitions apply.

- 3.1 Alloy special steel as defined in EN 10020,
- 3.2 Heat treatment terms as defined in prEN 10052.
- 3.3 Long products and flat products (plate, sheet, narrow strip, wide strip and wide flats) as defined in EN 10079.
- 3.4 Normalizing rolling: a rolling process in which the final deformation is carried out in a certain temperature range leading to a material condition equivalent to that obtained after normalizing so that the specified values of the mechanical properties are retained even after normalizing.
- The abbreviated form of this delivery condition is N.

2) Until these EURONORMS are transformed into European Standards, they can either be implemented or reference made to the corresponding national standards, the list of which is given in Annex D to this European Standard.

3) EURONORM 56 and 57 are added because they contain the nominal dimensions.

NOTE: In international publications for both the normalizing rolling, as well as the thermomechanical rolling, the expression "controlled rolling" may be found. However in view of the different applicability of the products a distinction of the terms is necessary.

3.5 **Steel with improved atmospheric corrosion resistance:** a steel in which a certain number of alloying elements, such as P, Cu, Cr, Ni, Mo, have been added in order to increase its resistance to atmospheric corrosion, by forming an auto-protective oxide layer on the base metal under the influence of weather conditions.

NOTE 1: Steel with improved atmospheric corrosion resistance is often called weathering steel.

NOTE 2: Additional information for the use of steel with improved atmospheric corrosion resistance is given in Annex B.

4 Information to be supplied by the purchaser

4.1 General

The following information shall be supplied by the purchaser at the time of enquiry and order:

- SIST EN 10155:1998
<https://standards.iteh.ai/catalog/standards/sist/c7f340a4-0de7-4fb9-b11f-fcd4f854961c/sist-en-10155-1998>
- a) details of the product form and relevant quantities;
 - b) reference to this European Standard;
 - c) nominal dimensions and tolerances (see 5.1);
 - d) the grade and quality of steel (see tables 3, 5 and 6);
 - e) whether products have to be submitted to inspection and testing and if inspection and testing is required which type of inspection and which inspection document is required (see 8.1.2);

Where no specific choice is made by the purchaser concerning points a, b, c and d the supplier shall refer back to the purchaser.

4.2 Options

A number of options are specified in clause 11. In the event that the purchaser does not indicate his wish to implement any of these options, the supplier shall supply in accordance with the basic specification.

5 Dimensions, mass and tolerances

5.1 Dimensions and tolerances

Dimensions and tolerances shall be in accordance with the relevant European Standards and EURONORMS (see 2.2).

5.2 *Mass of steel*

The calculated mass shall be determined using a volumetric mass of 7.85 kg/dm³.

6 **Classification of grades and qualities: designation**6.1 *Classification of grades and qualities*

This European Standard specifies the steel grades S235 and S355 (see table 5, which differ in their mechanical properties.

These steel grades may be supplied in qualities J0, J2, and K2. Products of grade S355 with quality J2 and K2 are subdivided into two qualities J2G1, J2G2, K2G1 and K2G2 (see 7.2). The qualities differ in weldability and specified impact values (see also 7.5.1).

Grade S355 is subdivided into the classes W and WP, which differ mainly in their carbon and phosphorus contents (see table 3) and availability (see table 2).

6.2 *Designation* (standards.iteh.ai)

6.2.1 For the steel grades covered by this European Standard the steel names are allocated in accordance with EN 10027-1 and ECIS IC 10; the steel numbers are allocated in accordance with EN 10027-2.

NOTE: For a list of corresponding former designations and the former designations from EURONORM 155 (1980) see Annex E, table E.1.

6.2.2 The designation shall consist of:

- the number of this European Standard (EN 10155);
- the symbol S;
- the indication of the minimum specified yield strength for thickness ≤ 16 mm expressed in N/mm²;
- the quality designation (see 6.1) in respect to the weldability and specified impact values;
- the letter W indicating that the steel has an improved atmospheric corrosion resistance;
- the letter P for the class with a greater phosphorus content (only in the case of grade S355);
- if applicable, the indication "+N" when the products shall be delivered in the condition N (see 3.4 and table 1).

EXAMPLE: Steel EN 10155-S355JOW

Page 10
EN 10155:1993

7 Technical requirements

7.1 Steel manufacturing process

7.1.1 The steel manufacturing process shall be at the manufacturer's option. If specified at the time of the enquiry and order the steel manufacturing process shall be reported to the purchaser.
Option 2.

7.1.2 The method of deoxidation shall be as given in table 3.

7.1.3 The deoxidation methods are indicated as follows:

FN Rimming steel not permitted

FF Fully killed steel containing nitrogen binding elements in amounts sufficient to bind the available nitrogen (for example min. 0,020 % Al). If other elements are used they shall be reported in the inspection document.

7.2 Delivery conditions

7.2.1 General

If an inspection document is required (see 8.1.2) and products are ordered and delivered in the condition N this shall be indicated in the document.

[SIST EN 10155:1998](https://standards.iteh.ai/catalog/standards/sist/c7b40a4-0de7-4fb9-b11f-cd4f854961c/sist-en-10155-1998)

<https://standards.iteh.ai/catalog/standards/sist/c7b40a4-0de7-4fb9-b11f-cd4f854961c/sist-en-10155-1998>

7.2.2 Flat products

7.2.2.1 Unless otherwise agreed flat products of qualities J0 shall be supplied in a delivery condition at the manufacturers discretion (see 7.4.1).
Option 10.

7.2.2.2 Flat products of qualities J2, J2G1 and K2G1 shall be supplied normalized or in an equivalent condition obtained by normalizing rolling as defined in 3.4.

7.2.2.3 Flat products of qualities J2G2 and K2G2 shall be supplied in a delivery condition at the manufacturers discretion.

7.2.3 Long products

7.2.3.1 Unless otherwise agreed long products of the qualities J0, J2, J2G1 and K2G1 shall be supplied in a delivery condition at the manufacturers discretion.
Option 14.

7.2.3.2 Long products of qualities J2G2 and K2G2 shall be supplied in a delivery condition at the manufacturers discretion.

7.2.4 The delivery conditions are summarized in table 1.