

SLOVENSKI STANDARD

SIST EN 10113-2:1997

01-december-1997

Jfc Yj U'Ub]nXY_]n'j Ufj j \XfcVbcnf bUf _cbgfi _W'g _\ 'Y_Y'!'&"XY.'8cVUj b]
dc[c'j nUbcfa U]n]fUbU#bcfa U]nUW'g_c'j U'UbU'Y'_U

Hot-rolled products in weldable fine grain structural steels - Part 2: Delivery conditions for normalized/normalized rolled steels

Warmgewalzte Erzeugnisse aus schweißgeeigneten Feinkornbaustählen - Teil 2:
Lieferbedingungen für normalgeglühte/normalisierend gewalzte Stähle

Produits laminés a chaud en aciers de construction soudable a grains fins - Partie 2:
Conditions de livraison des aciers a l'état normalisé/laminage normalisé

<https://standards.iteh.ai/catalog/standards/sist/08d8f6db-0f3b-4eb7-8879-97e374e29077/sist-en-10113-2-1997>

Ta slovenski standard je istoveten z: **EN 10113-2:1993**

ICS:

77.140.10 Jekla za toplotno obdelavo Heat-treatable steels

SIST EN 10113-2:1997

en

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 10113-2:1997

<https://standards.iteh.ai/catalog/standards/sist/08d8f6db-0f3b-4eb7-8879-97e374e29077/sist-en-10113-2-1997>

EUROPEAN STANDARD

EN 10113-2:1993

NORME EUROPÉENNE

EUROPÄISCHE NORM

March 1993

UDC 669.14.018.29.018.62-122.4-153.65-4:620.1

Descriptors: Iron and steel products, hot rolled products, structural steels, welded construction, delivery conditions, designation, quality classes, chemical composition, grades : quality, mechanical properties, inspection, tests

English version

**Hot-rolled products in weldable fine grain
structural steels - Part 2 : Delivery conditions for
normalized/normalized rolled steels**

iTeh STANDARD PREVIEW

Produits laminés à chaud en aciers de
construction soudable à grains fins - Partie 2:
Conditions de livraison des aciers à l'état
normalisé/laminage normalisé

(standards.iteh.ai)

Warmgewalzte Erzeugnisse aus schweißgeeigneten
Feinkornbaustählen - Teil 2: Lieferbedingungen
für normalgeglühte/normalisierend gewalzte
Stähle

SIST EN 10113-2:1997

<https://standards.iteh.ai/catalog/standards/sist/08d8fdb-0f3b-4eb7-8879-97e374e29077/sist-en-10113-2-1997>

This European Standard was approved by CEN on 1993-03-05. CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

The European Standards exist in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.

CEN

European Committee for Standardization
Comité Européen de Normalisation
Europäisches Komitee für Normung

Central Secretariat: rue de Stassart, 36 B-1050 Brussels

Contents list

0	Foreword	page 3
1	Scope	4
2	Normative references	4
3	Definitions	4
4	Information to be supplied by the purchaser	4
4.1	General	4
4.2	Options	4
5	Dimensions, mass and tolerances	5
5.1	Dimensions and tolerances	5
5.2	Mass of steel	5
6	Classification of qualities; designation	5
6.1	Classification of qualities	5
6.2	Designation	5
7	Technical requirements	5
7.1	Steel manufacturing process	5
7.2	Delivery condition	5
7.3	Chemical composition	5
7.4	Mechanical properties	6
7.5	Technological properties	6
7.6	Surface finish	7
7.7	Internal defects	7
8	Inspection and testing	8
8.1	General	8
8.2	Sampling	8
8.3	Test units	8
8.4	Verification of chemical composition	8
8.5	Mechanical tests	8
8.6	Test methods	8
8.7	Retests and resubmission for testing	8
8.8	Inspection documents	8
9	Marking for flat and long products	9
10	Complaints after delivery	9
11	Options	9
11.1	All products	9
11.2	Flat products	9
11.3	Long products	9



Foreword

This European Standard has been drawn up by ECISS/TC 10 "Structural steel - Qualities" whose secretariat is held by NNI.

This European Standard replaces EURONORM 113-72 "Special quality weldable structural steel grades and quality. General provisions".

The Technical Committee ECISS/TC 10 met in June 1991 in Brussels and agreed on the text for circulation for formal vote within CEN. The following countries were represented in that meeting: Austria, Belgium, Denmark, Finland, France, Germany, Italy, Luxembourg, Netherlands, Spain, Sweden and UK.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by September 1993, and conflicting national standards shall be withdrawn at the latest by September 1993.

This European Standard has been adopted and in accordance with the CEN/CENELEC Internal Regulations, following countries are bound to implement this European Standard: Austria, Belgium, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.

<https://standards.ichan.ch.cn/standards/sist/08d8fdb-0f3b-4eb7-8879-97e374e29077/sist-en-10113-2-1997>

1 Scope

Part 2 of this European Standard, in addition to part 1, specifies requirements for flat and long products of hot-rolled weldable fine grain structural steel in the normalized delivery condition in the grades and qualities given in table 1 (chemical composition) and tables 3, 4 and 5 (mechanical properties), in thickness ≤ 150 mm for grades S275, S355 and S420 and in thickness ≤ 100 mm for grade S460.

2 Normative references

The normative references as given in EN 10113 part 1 shall apply.

3 Definitions

The definitions given in EN 10113 part 1 shall apply.

4 Information to be supplied by the purchaser

4.1 General

The following information shall be supplied by the purchaser at the time of enquiry and order:

- a) details of the product form and relevant quantities;
- b) reference to this European Standard;
- c) nominal dimensions and tolerances (see 5.1);
- d) the grade and quality of the steel (see tables 1 - 5);
- e) the type of inspection document (see 8.8).

Where no specific choice is made by the purchaser concerning points a, b, c, d and e the supplier shall refer back to the purchaser.

4.2 Options

A number of options is specified in clause 11. In the event that the purchaser does not indicate his wish to implement any of these options, the supplier shall supply in accordance with the basic specification.

5 Dimensions, mass and tolerances

5.1 Dimensions and tolerances

The dimensions and tolerances shall be in accordance with the relevant European Standards and EURONORMS (see 2.2 of EN 10113 part 1).

5.2 Mass of steel

The mass of steel shall comply with EN 10113 part 1.

6 Classification of qualities; designation

6.1 Classification of qualities

The steel grades S275 and S355 of part 2 of this European Standard are non-alloy quality steels and the steel grades S420 and S460 of part 2 of this European Standard are alloy special steels according to EN 10020.

6.2 Designation

The designation shall be in accordance with EN 10113 part 1.

Example: Normalized steel with a specified minimum yield strength at ambient temperature of 355 N/mm², and with a specified minimum impact value at -50 °C:

Steel EN 10113-2 S355NL

7 Technical requirements

7.1 Steel manufacturing process

The steel manufacturing process shall be in accordance with EN 10113 part 1.
Option 1.

7.2 Delivery condition

The products shall be supplied normalized or in an equivalent condition obtained by normalizing rolling as defined in clause 3.

7.3 Chemical composition

7.3.1 The chemical composition determined by ladle analysis shall comply with the specified values of table 1.

7.3.2 The values for permissible deviations of the product analysis from the specified limits of the ladle

Page 6
EN 10113-2:1993

analysis are as specified in table 1 of EN 10113 part 1. The manufacturer shall inform the purchaser at the time of the enquiry and order which of the alloying elements appropriate to the steel grade required will be deliberately added to the material to be delivered.

7.3.3 If agreed at the time of the enquiry and order the maximum carbon equivalent values, based on the ladle analysis, given in table 2 shall apply.
Option 2.

7.4 Mechanical properties

7.4.1 General

Under the inspection and testing conditions as specified in clause 8 and in the delivery condition as specified in 7.2 as well as after normalizing by heat treatment after delivery the mechanical properties shall comply with the values given in tables 3 and 4.

7.4.2 Impact test

The verification of the impact energy value shall be carried out in accordance with EN 10113 part 1.

Option 4.

Option 5.

SIST EN 10113-2:1997

<https://standards.iteh.ai/catalog/standards/sist/08d8f6db-0f3b-4eb7-8879-97e374e29077/sist-en-10113-2-1997>

7.5 Technological properties

7.5.1 Weldability

Weldability shall be in accordance with EN 10113 part 1.

7.5.2 Formability

NOTE: Recommendations regarding hot and cold forming are laid down in ECCS IC 2.

7.5.2.1 Hot forming

The products shall comply with tables 3 and 4 if hot forming is carried out after delivery (see 7.4.1).

7.5.2.2 Cold forming

7.5.2.2.1 Flangeability

If specified at the time of the enquiry and order plate, sheet, strip and wide flats ordered and supplied in the normalized condition with a nominal thickness ≤ 16 mm shall be suitable for flanging without cracking with the following minimum bend radii:

- 2 times the nominal thickness with the axis of the bend in transverse direction and 2,5 times the nominal thickness in longitudinal direction for the steel grades S275 and S355;
- 4 times the nominal thickness with the axis of the bend in transverse direction and 5 times the nominal thickness in longitudinal direction for the steel grades S420 and S460.

Option 11.

7.5.2.2.2 Roll forming

If specified at the time of the enquiry and order plate and strip with a nominal thickness ≤ 8 mm shall be suitable for the production of sections through cold rolling (for example according to EURONORM 162), with the same minimum bend radii as given in 7.5.2.2.1.

Option 12.

NOTE: The products suitable for roll forming are also suitable for the manufacture of cold-finished square and rectangular hollow sections.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

7.5.3 Other requirements

7.5.3.1 If specified at the time of the enquiry and order the grades S275 and S355 shall be suitable for hot-dip zinc coating and shall comply with the relevant product quality requirements.

Option 7.

7.5.3.2 If agreed at the time of the enquiry and order the material shall be suitable for slitting of heavy sections.

Option 15.

7.6 Surface finish

The surface finish shall be in accordance with EN 10113 part 1.

Option 8.

7.7 Internal defects

The internal defects shall be in accordance with EN 10113 part 1.

Option 13 (for flat products).

Option 16 (for long products).