



# SLOVENSKI STANDARD

## SIST EN 10219-2:1998

01-avgust-1998

---

### Hladno oblikovani varjeni votli konstrukcijski profili iz nelegiranih in drobnnozrnatih jekel - 2. del: Mere, mejni odstopki in značilnosti profilov

Cold formed welded structural hollow sections of non-alloy and fine grain steels - Part 2: Tolerances, dimensions and sectional properties

Kaltgefertigte geschweißte Hohlprofile für den Stahlbau aus unlegierten Baustählen und aus Feinkornbaustählen Teil 2: Grenzabmaße, Maße und statische Werte

Profils creux pour la construction formés a froid en aciers de construction non-alliés et a grains fins - Partie 2: Tolérances, dimensions et caractéristiques du profil

<https://standards.iteh.ai/catalog/standards/sist/dc36f6f6-f1d8-451c-9a2d-d5122bd75ae3/sist-en-10219-2-1998>

Ta slovenski standard je istoveten z: EN 10219-2:1997

---

#### **ICS:**

77.140.45	Nelegirana jekla	Non-alloyed steels
77.140.70	Jekleni profili	Steel profiles

**SIST EN 10219-2:1998**

**en**

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

SIST EN 10219-2:1998

<https://standards.iteh.ai/catalog/standards/sist/dc36f6f6-f1d8-451c-9a2d-d5122bd75ae3/sist-en-10219-2-1998>

EUROPEAN STANDARD

EN 10219-2

NORME EUROPÉENNE

EUROPÄISCHE NORM

August 1997

ICS 77.140.70; 77.140.90; 91.080.10

Descriptors: steel construction, metal sections, hollow profiles, cold-working, structural steels, unalloyed steels, dimensions, dimensional tolerances, measurements, geometric characteristics, fine grain steels

English version

**Cold formed welded structural hollow sections of  
non-alloy and fine grain steels - Part 2:  
Tolerances, dimensions and sectional properties**

**iTeh STANDARD PREVIEW**

Profils creux pour la construction formés à froid en aciers de construction non-alliés et à grains fins - Partie 2: Tolérances, dimensions et caractéristiques du profil

Kaltgefertigte geschweißte Hohlprofile für den Stahlbau aus unlegierten Baustählen und aus Feinkornbaustählen - Teil 2: Grenzabmaße, Maße und statische Werte

[SIST EN 10219-2:1998](https://standards.iteh.ai/catalog/standards/sist/dc36f6f6-fl d8-451c-9a2d-d5122bd75ae3/sist-en-10219-2-1998)

<https://standards.iteh.ai/catalog/standards/sist/dc36f6f6-fl d8-451c-9a2d-d5122bd75ae3/sist-en-10219-2-1998>

This European Standard was approved by CEN on 1997-06-22. CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

The European Standards exist in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.

**CEN**

European Committee for Standardization  
Comité Européen de Normalisation  
Europäisches Komitee für Normung

Central Secretariat: rue de Stassart, 36 B-1050 Brussels

<b>Contents</b>	<b>Page</b>
<b>Foreword</b>	3
1 Scope	4
2 Normative references	4
3 Definitions	4
4 Symbols	4
5 Information to be supplied by the purchaser	6
6 Tolerances	7
7 Measurement of size and shape	7
8 Dimensions and sectional properties	9
<b>Annex</b>	
A (normative) Formulae for calculation of properties	35

**iTeh STANDARD PREVIEW**  
(standards.iteh.ai)

<https://standards.iteh.ai/catalog/standards/sist/dc36f6f6-11d8-451c-9a2d-d5122bd75ac3/sist-en-10219-2-1998>

SIST EN 10219-2:1998

## Foreword

This European Standard has been prepared by Technical Committee ECISS/TC 10 "Structural steels - Qualities", the secretariat of which is held by NNI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by February 1998, and conflicting national standards shall be withdrawn at the latest by February 1998.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and the United Kingdom.

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

SIST EN 10219-2:1998

<https://standards.iteh.ai/catalog/standards/sist/dc36f6f6-fl d8-451c-9a2d-d5122bd75ae3/sist-en-10219-2-1998>

## 1 Scope

This Part of this European Standard specifies the tolerances for cold formed welded circular, square and rectangular structural hollow sections and gives the dimensions and sectional properties for a range of standard sizes.

For the technical delivery requirements see EN 10219-1.

## 2 Normative references

This European Standard incorporates by dated or undated reference, provisions from other publications. These normative references are cited at the appropriate places in the text and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of any of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies.

EN 10219-1 Cold formed welded structural hollow sections of non-alloy and fine grain steels  
Part 1: Technical delivery conditions

**ITeH STANDARD PREVIEW**  
**(standards.iteh.ai)**

[SIST EN 10219-2:1998](https://standards.iteh.ai/catalog/standards/sist/dc36f6f6-f1d8-451c-9a2d-d5122bd75ae3/sist-en-10219-2-1998)

**3 Definitions** <https://standards.iteh.ai/catalog/standards/sist/dc36f6f6-f1d8-451c-9a2d-d5122bd75ae3/sist-en-10219-2-1998>

See EN 10219 - 1

## 4 Symbols

Symbols used in this standard are given in table 1.

Table 1: Symbols

Symbol	Unit	Definition
A	cm <sup>2</sup>	Cross-sectional area
A <sub>s</sub>	m <sup>2</sup> /m	Superficial area per metre length
B	mm	Nominal length of side of square hollow section. Nominal length of the shorter side of a rectangular hollow section.
C <sub>1</sub> / C <sub>2</sub>	mm	Length of corner region of a square or rectangular hollow section.
C <sub>t</sub>	cm <sup>3</sup>	Torsional modulus constant.
D	mm	Nominal outside diameter of a circular hollow section
D <sub>max</sub> /D <sub>min</sub>	mm	The maximum and minimum outside diameter of a circular hollow section measured in the same plane
e	mm	Deviation from straightness.
H	mm	Nominal length of the longer side of a rectangular hollow section.
I	cm <sup>4</sup>	Second moment of area.
I <sub>t</sub>	cm <sup>4</sup>	Torsional inertia constant (polar moment of inertia in the case of circular hollow sections only).
i	cm	Radius of gyration.
L	mm	Length.
M	kg/m	Mass per unit length.
O	%	Out-of-roundness
R	mm	External corner radius of a square or rectangular hollow section.
T	mm	Nominal thickness.
V	mm	Total measured twist.
V <sub>1</sub>	mm	Twist measured at one end of a section.

**Table 1: Symbols (concluded)**

Symbols	Unit	Definitions
$W_{el}$	cm <sup>3</sup>	Elastic section modulus
$W_{pl}$	cm <sup>3</sup>	Plastic section modulus
$x_1$	mm	Concavity of a side of a square or rectangular hollow section
$x_2$	mm	Convexity of a side of a square or rectangular hollow section
xx	-	Axis of cross-section, major axis of a rectangular hollow section
yy	-	Axis of cross-section, minor axis of a rectangular hollow section
$\theta$	Degrees	Angle between adjacent sides of a square or rectangular hollow section

**5 Information to be supplied by the purchaser**

The following mandatory information from this Part of this European Standard shall be supplied by the purchaser at the time of enquiry and order.

a) The type of length and the length range or length (see table 4)

b) The dimensions (see clause 8)

NOTE: This information is included in the list of information to be supplied by the purchaser contained in clause 5.1 of EN 10219-1.



## 6 Tolerances

6.1 Tolerances on the dimensions and mass of cold formed hollow sections shall not exceed the values given in table 2 for shape and mass, table 3 for external corner profiles, table 4 for length and table 5 for the height of the internal and external weld bead of submerged arc welded hollow sections.

6.2 The internal corners of square and rectangular hollow sections shall be rounded.

NOTE: The internal corner profile is not specified.

## 7 Measurement of size and shape

### 7.1 General

All external dimensions including out-of-roundness shall be measured at a distance from the end of the hollow section of not less than  $D$  for circular sections,  $B$  for square sections or  $H$  for rectangular sections, with a minimum of 100 mm.

### 7.2 Outside dimension

For circular hollow sections the diameter ( $D$ ) shall be measured either directly e.g. using a calliper gauge or by circumference tape at the discretion of the manufacturer.

The limiting cross-sectional positions for measuring  $B$  and  $H$  are shown in figure 1.

### 7.3 Thickness

The thickness ( $T$ ) shall be measured at a position not less than  $2T$  from the weld.

The limiting cross-sectional positions for measuring the thickness of square and rectangular hollow sections are shown in figure 1.

NOTE: Thickness is normally measured within a distance of half the outside diameter or half the longer side length from the end of the section.

#### 7.4 Out-of-roundness

The out-of-roundness (O) of a circular hollow section shall be calculated from the following equation.

$$O(\%) = \frac{D_{\max} - D_{\min}}{D} \times 100$$

#### 7.5 Concavity and convexity

The concavity ( $x_1$ ) or the convexity ( $x_2$ ) of the sides of a square or rectangular hollow section shall be measured as shown in figure 2.

The percentage concavity or convexity shall be calculated as follows:

$$\frac{x_1}{B} \times 100\% ; \frac{x_2}{B} \times 100\% ; \frac{x_1}{H} \times 100\% ; \frac{x_2}{H} \times 100\%$$

where B and H are the lengths of the sides containing the concavity  $x_1$  or the convexity  $x_2$ .

#### 7.6 Squareness of sides

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

The deviation from squareness of the sides of a square or rectangular hollow section shall be measured as the difference between  $90^\circ$  and  $\theta$  as shown in figure 3.

SIST EN 10219-2:1998  
<https://standards.iteh.ai/catalog/standards/sist/dc36f6f6-11d8-451c-9a2d-d5122bd75ae3/sist-en-10219-2-1998>

#### 7.7 External Corner Profile

The external corner profile of a square or rectangular hollow section shall be measured according to 7.7.1 or 7.7.2 at the discretion of the manufacturer.

**7.7.1** The corner arc shall be measured with a radius gauge.

**7.7.2** The distance between the intersection of the flat side and the corner arc and the intersection of the projections of the flat sides to the corner ( $C_1$  and  $C_2$  in figure 4) shall be measured.

#### 7.8 Twist

The twist (V) in a square or rectangular hollow section shall be determined in accordance with 7.8.1 or 7.8.2 at the discretion of the manufacturer.

**7.8.1** The hollow section shall be placed on a horizontal surface with one side at one end pressed flat against the surface. At the opposite end of the hollow section the difference in height of the two lower corners from a horizontal surface (see figure 5) shall be measured.

**7.8.2** The twist shall be measured with a spirit level and micrometer gauge (screw). The reference length of the spirit level shall be the distance between the intersection of the flat sides and the corner arcs (see figure 6). The twist  $V$  is the difference between the values  $V_1$  (see figure 6) measured at each end of the section.

### 7.9 Straightness

The deviation from straightness ( $e$ ) of the total length of a hollow section shall be measured at the point of maximum departure of the hollow section from a straight line connecting its two ends as shown in figure 7. The percentage deviation from straightness shall be calculated as follows:-

$$\frac{e}{L} \times 100 \%$$

## iTeh STANDARD PREVIEW

### 8 Dimensions and sectional properties (standards.iteh.ai)

The nominal section dimensions and sectional properties for a range of standard sizes of cold formed structural hollow section are given in table 6 for circular sections, table 7 for square sections and table 8 for rectangular sections. The sectional properties were calculated from the formulae given in annex A.

NOTE: Other sizes and thicknesses may be available by agreement with the manufacturer.

Table 2: Tolerances

Characteristic	Circular hollow sections	Square and rectangular hollow sections	
		Side length mm	Tolerance
Outside dimensions (D, B and H)	± 1 % with a minimum of  ± 0,5 mm and a maximum of ± 10 mm.		
		H,B < 100	± 1 % with a minimum of ± 0,5 mm
		100 ≤ H,B ≤ 200 H,B > 200	± 0,8 % ± 0,6 %
Thickness (T)	For D ≤ 406,4 mm T ≤ 5 mm: ± 10 % T > 5 mm: ± 0,50 mm	T ≤ 5 mm: ± 10 %	
	For D > 406,4 mm ± 10 % with a maximum of ± 2 mm	T > 5 mm: ± 0,50 mm	
Out-of-roundness (O)	2 % for hollow sections having a diameter to thickness ratio not exceeding 100 <sup>1)</sup>	-	
Concavity/Convexity <sup>2)</sup>	-	max 0,8 % with a minimum of 0,5 mm	
Squareness of Side	-	90 ° ± 1°	
External Corner Profile	-	See table 3	
Twist (V)	-	2 mm plus 0,5 mm/m length.	
Straightness	0,20 % of total length	0,15 % of total length	
Mass (M)	± 6 % on individual lengths		
<sup>1)</sup> Where the diameter to thickness ratio exceeds 100 the tolerance on out-of-roundness shall be agreed.			
<sup>2)</sup> The tolerance on convexity and concavity is independent of the tolerance on outside dimensions.			

**Table 3: External corner profile**

Thickness T mm	External corner profile C <sub>1</sub> , C <sub>2</sub> , or R <sup>1)</sup> mm
T ≤ 6	1,6T to 2,4T
6 < T ≤ 10	2,0T to 3,0T
10 < T	2,4T to 3,6T

<sup>1)</sup> The sides need not be tangential to the corner arcs.

**Table 4: Tolerances on length<sup>1)</sup>**

Type of length	Range in mm	Tolerance
Random length	4000 to 16000 with a range of 2000 per order item.	10 % of sections supplied may be below the minimum for the ordered range but not less than 75 % of the minimum of the range.
Approximate length	≥ 4000	+ 50 mm 0
Exact length	< 6000 ≥ 6000 to ≤ 10 000 > 10 000	+ 5 mm 0 + 15 mm 0 + 5 mm + 1 mm/m 0

<sup>1)</sup> The purchaser shall indicate in the enquiry and order the type of length required and the length range or length required.

**Table 5: Tolerance on height of internal and external weld bead for submerged arc welded hollow sections**

Thickness (T)	Maximum weld bead height mm
≤ 14,2	3,5
> 14,2	4,8