



SLOVENSKI STANDARD
SIST EN 10149-2:1998

01-avgust-1998

Vroče valjani ploščati izdelki za hladno preoblikovanje iz jekel z veliko napetostjo tečenja - 2. del: Dobavni pogoji za termomehansko valjana jekla

Hot-rolled flat products made of high yield strength steels for cold forming - Part 2: Delivery conditions for thermomechanically rolled steels

Warmgewalzte Flacherzeugnisse aus Stählen mit hoher Streckgrenze zum Kaltumformen - Teil 2: Lieferbedingungen für thermomechanisch gewalzte Stähle

Produits plats laminés a chaud en aciers a haute limite d'élasticité pour formage a froid - Partie 2: Conditions de livraison des aciers obtenus par laminage thermomécanique

[https://standards.iteh.ai/catalog/standards/sist/d5532910-9c7d-4467-8cf4-](https://standards.iteh.ai/catalog/standards/sist/d5532910-9c7d-4467-8cf4-23ebc9f2c97b/sist-en-10149-2-1998)

Ta slovenski standard je istoveten z: EN 10149-2:1995

ICS:

77.140.10	Jekla za toplotno obdelavo	Heat-treatable steels
77.140.50	Ploščati jekleni izdelki in polizdelki	Flat steel products and semi-products

SIST EN 10149-2:1998

en

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 10149-2:1998

<https://standards.iteh.ai/catalog/standards/sist/d5532910-9c7d-4467-8cf4-23ebc9f2c97b/sist-en-10149-2-1998>

EUROPEAN STANDARD

EN 10149-2

NORME EUROPÉENNE

EUROPÄISCHE NORM

September 1995

ICS 77.140.10; 77.140.50

Descriptors: iron and steel products, hot rolled products, high yield strength steels, cold-working, metal rolling, designation, classifications, grades:quality, chemical composition, delivery condition, mechanical properties, inspection, tests, marking

English version

Hot-rolled flat products made of high yield strength steels for cold forming - Part 2: Delivery conditions for thermomechanically rolled steels

iTeh STANDARD PREVIEW

Produits plats laminés à chaud en aciers à haute limite d'élasticité pour formage à froid - Partie 2: Conditions de livraison des aciers obtenus par laminage thermomécanique

Warmgewalzte Flacherzeugnisse aus Stählen mit hoher Streckgrenze zum Kaltumformen - Teil 2: Lieferbedingungen für thermomechanisch gewalzte Stähle

SIST EN 10149-2:1998

<https://standards.iteh.ai/catalog/standards/sist/d5532910-9c7d-4467-8c4f-23ebc9f2c97b/sist-en-10149-2-1998>

This European Standard was approved by CEN on 1995-08-06. CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

The European Standards exist in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.

CEN

European Committee for Standardization
Comité Européen de Normalisation
Europäisches Komitee für Normung

Central Secretariat: rue de Stassart, 36 B-1050 Brussels

Contents

	page
Foreword	3
1 Scope	4
2 Normative references	4
3 Definitions	4
4 Information to be supplied by the purchaser	4
4.1 General	4
4.2 Options	4
5 Dimensions, mass and tolerances	4
5.1 Dimensions and tolerances	4
5.2 Mass of steel	4
6 Classification and designation	5
6.1 Classification	5
6.2 Designation	5
7 Technical requirements	5
7.1 Steel/manufacturing process	5
7.2 Delivery condition	5
7.3 Chemical composition	5
7.4 Mechanical properties	5
7.5 Technological properties	6
7.6 Surface finish	6
7.7 Internal soundness	6
8 Inspection and testing	6
8.1 General	6
8.2 Sampling	7
8.3 Test units	7
8.4 Verification of chemical composition	7
8.5 Preparation of samples and test pieces	7
8.6 Test methods	7
8.7 Retests and resubmission for testing	7
8.8 Inspection documents	7
9 Marking	7
10 Disputes	8
11 Options	8
Annex A (normative) Location of test pieces	10
Annex B (informative) List of corresponding former designations	11
Annex C (informative) Minimum inside bend radii for cold forming	12

Foreword

This European Standard was prepared by the Technical Committee ECISS/TC 10 "Structural steels - Qualities" of which the secretariat is held by NNI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by March 1996, and conflicting national standards shall be withdrawn at the latest by March 1996.

According to the CEN/CENELEC Internal Regulations, the following countries are bound to implement this European Standard: Austria, Belgium, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland, United Kingdom.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 10149-2:1998

<https://standards.iteh.ai/catalog/standards/sist/d5532910-9c7d-4467-8cfd-23ebc9f2c97b/sist-en-10149-2-1998>

Page 4
EN 10149-2:1995

1 Scope

Part 2 of this European Standard, in addition to part 1, specifies requirements for flat products made of weldable, hot-rolled, high yield strength steels for cold forming.

The grades are given in table 1 (chemical composition) and table 2 (mechanical properties) and are supplied in the thermomechanically rolled delivery condition as given in 7.2.

The steels specified in this European Standard are applicable to hot-rolled flat products in the thickness range of 1,5 mm to 20 mm for the steels which have a specified minimum yield strength of 315 N/mm² up to and including 460 N/mm² and 1,5 mm to 16 mm for the steels which have a specified minimum yield strength of 500 N/mm² up to and including 700 N/mm².

2 Normative references

The normative references as given in EN 10149-1 shall apply.

3 Definitions

The definitions given in EN 10149-1 shall apply.

4 Information to be supplied by the purchaser

4.1 General

The information to be supplied by the purchaser shall be in accordance with EN 10149-1.

4.2 Options

The options given in EN 10149-1 and clause 11 shall apply.

5 Dimensions, mass and tolerances

5.1 Dimensions and tolerances

The dimensions and tolerances shall be in accordance with EN 10149-1.

5.2 Mass of steel

The calculated mass of steel shall be determined in accordance with EN 10149-1.

6 Classification and designation

6.1 Classification

6.1.1 Classification

The steel grades S315MC, S355MC, S420MC, S460MC, S500MC and S550MC of this European Standard are alloy quality steels and the steel grades S600MC, S650MC and S700MC of this European Standard are alloy special steels according to EN 10020.

6.1.2 Grades

The subdivision of steel grades shall comply with EN 10149-1.

6.2 Designation

The designation shall comply with EN 10149-1.

NOTE: For a list of corresponding former national designations and the former designation from EURONORM 149 (1980), see Annex B, table B.1.

ITeH STANDARD PREVIEW

(standards.iteh.ai)

7 Technical requirements

7.1 Steel manufacturing process

SIST EN 10149-2:1998
<https://standards.iteh.ai/catalog/standards/sist/d5532910-9c7d-4467-8cf4-33ebc972c97b/sist-en-10149-2-1998>

The steel manufacturing process shall be in accordance with EN 10149-1. See clause 11, option 1.

7.2 Delivery condition

The products shall be supplied in the thermomechanically rolled delivery condition.

The delivery condition of descaled surfaces shall be in accordance with EN 10149-1.

See clause 11, option 2.

7.3 Chemical composition

The requirements of EN 10149-1 shall apply.

The chemical composition determined by ladle analysis shall comply with the specified values of table 1.

See clause 11, option 3.

7.4 Mechanical properties

7.4.1 General

Under the inspection and testing conditions as specified in clause 8 and in the delivery condition as specified in 7.2 the mechanical properties shall comply with the values given in table 2.

Page 6
EN 10149-2:1995

7.4.2 Impact energy

If agreed at the time of the enquiry and order the verification of the impact energy value shall be carried out in accordance with EN 10149-1. See clause 11, option 5.

7.5 Technological properties

7.5.1 Weldability

Weldability shall be in accordance with EN 10149-1.

7.5.2 Formability

NOTE: Recommendations regarding hot and cold forming are laid down in ECSC IC 2.

7.5.2.1 Cold forming

Annex C contains indicative values for the inside bend radii for cold forming.

7.5.2.1.1 Flangeability

The products are suitable for flanging without cracking.

7.5.2.1.2 Roll forming

[SIST EN 10149-2:1998](https://standards.iteh.ai/catalog/standards/sist/d5532910-9c7d-4467-8cf4-3ebc97e07e11/sist-en-10149-2-1998)
<https://standards.iteh.ai/catalog/standards/sist/d5532910-9c7d-4467-8cf4-3ebc97e07e11/sist-en-10149-2-1998>

The suitability for roll forming shall be in accordance with EN 10149-1. See clause 11, option 6.

7.5.3 Other requirements

If agreed at the time of enquiry and order the grades S315MC, S355MC and S420MC of this European Standard shall be suitable for hot-dip zinc-coating and shall comply with the relevant product quality requirements. See clause 11, option 7.

7.6 Surface finish

The surface finish shall be in accordance with EN 10149-1. See clause 11, option 8.

7.7 Internal soundness

The internal soundness shall be in accordance with EN 10149-1. See clause 11, option 9.

8 Inspection and testing

8.1 General

The products shall be supplied in accordance with 8.1 of EN 10149-1. See clause 11, option 10.

8.2 Sampling

Sampling shall be in accordance with EN 10149-1.

8.3 Test units

The test unit shall be in accordance with EN 10149-1.

8.4 Verification of chemical composition

The verification of the chemical composition shall be in accordance with EN 10149-1.

See clause 11, option 4.

8.5 Preparation of samples and test pieces

The preparation of samples and test pieces shall be in accordance with EN 10149-1.

8.5.1 Preparation of samples

The following samples shall be taken from one sample product of each test unit:

- one sample in the longitudinal direction for tensile testing;
- one sample in the transverse direction for the bend test;
- one sample sufficient for one set of six impact test pieces (if an impact test is agreed at the time of the enquiry and order, see 7.4.2).

See clause 11, option 5.

(See Annex A).

8.6 Test methods

The test methods shall be in accordance with EN 10149-1.

8.7 Retests and resubmission for testing

The retests and resubmission for testing shall be in accordance with EN 10149-1.

8.8 Inspection documents

The inspection documents shall comply with EN 10149-1.

9 Marking

The marking shall comply with EN 10149-1.

See clause 11, option 11.