

INTERNATIONAL STANDARD

NORME INTERNATIONALE

Specifications for winding wires –
Part 51: Solderable polyurethane enamelled round copper wire, class 180
(standards.iteh.ai)

Spécifications pour types particuliers de fils de bobinage –
Partie 51: Fil brasable de section circulaire en cuivre émaillé avec polyuréthane,
classe 180

<https://standards.iteh.ai/catalog/standards/sist/006carbe-7as6-491b-9140-d794e0a688d2/iec-60317-51-2014>





THIS PUBLICATION IS COPYRIGHT PROTECTED

Copyright © 2014 IEC, Geneva, Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester. If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

Droits de reproduction réservés. Sauf indication contraire, aucune partie de cette publication ne peut être reproduite ni utilisée sous quelque forme que ce soit et par aucun procédé, électronique ou mécanique, y compris la photocopie et les microfilms, sans l'accord écrit de l'IEC ou du Comité national de l'IEC du pays du demandeur. Si vous avez des questions sur le copyright de l'IEC ou si vous désirez obtenir des droits supplémentaires sur cette publication, utilisez les coordonnées ci-après ou contactez le Comité national de l'IEC de votre pays de résidence.

IEC Central Office
3, rue de Varembé
CH-1211 Geneva 20
Switzerland

Tel.: +41 22 919 02 11
Fax: +41 22 919 03 00
info@iec.ch
www.iec.ch

About the IEC

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

About IEC publications

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigenda or an amendment might have been published.

IEC Catalogue - webstore.iec.ch/catalogue

The stand-alone application for consulting the entire bibliographical information on IEC International Standards, Technical Specifications, Technical Reports and other documents. Available for PC, Mac OS, Android Tablets and iPad.

Electropedia - www.electropedia.org

The world's leading online dictionary of electronic and electrical terms containing more than 30 000 terms and definitions in English and French, with equivalent terms in 14 additional languages. Also known as the International Electrotechnical Vocabulary (IEV) online.

IEC publications search - www.iec.ch/searchpub

The advanced search enables to find IEC publications by a variety of criteria (reference number, text, technical committee,...). It also gives information on projects, replaced and withdrawn publications.

IEC Glossary - std.iec.ch/glossary

More than 55 000 electrotechnical terminology entries in English and French extracted from the Terms and Definitions clause of IEC publications issued since 2002. Some entries have been collected from earlier publications of IEC TC 37, 77, 86 and CISPR.

IEC Just Published - webstore.iec.ch/justpublished

Stay up to date on all new IEC publications. Just Published details all new publications released. Available online and also once a month by email.

IEC Customer Service Centre - webstore.iec.ch/csc

If you wish to give us your feedback on this publication or need further assistance, please contact the Customer Service Centre: csc@iec.ch.

A propos de l'IEC

La Commission Electrotechnique Internationale (IEC) est la première organisation mondiale qui élabore et publie des Normes internationales pour tout ce qui a trait à l'électricité, à l'électronique et aux technologies apparentées.

A propos des publications IEC

Le contenu technique des publications IEC est constamment revu. Veuillez vous assurer que vous possédez l'édition la plus récente, un corrigendum ou amendement peut avoir été publié.

Catalogue IEC - webstore.iec.ch/catalogue

Application autonome pour consulter tous les renseignements bibliographiques sur les Normes internationales, Spécifications techniques, Rapports techniques et autres documents de l'IEC. Disponible pour PC, Mac OS, tablettes Android et iPad.

Electropedia - www.electropedia.org

Le premier dictionnaire en ligne de termes électroniques et électriques. Il contient plus de 30 000 termes et définitions en anglais et en français, ainsi que les termes équivalents dans 14 langues additionnelles. Egalement appelé Vocabulaire Electrotechnique International (IEV) en ligne.

Recherche de publications IEC - www.iec.ch/searchpub

La recherche avancée permet de trouver des publications IEC en utilisant différents critères (numéro de référence, texte, comité d'études,...). Elle donne aussi des informations sur les projets et les publications remplacées ou retirées.

Glossaire IEC - std.iec.ch/glossary

Plus de 55 000 entrées terminologiques électrotechniques, en anglais et en français, extraites des articles Termes et Définitions des publications IEC parues depuis 2002. Plus certaines entrées antérieures extraites des publications des CE 37, 77, 86 et CISPR de l'IEC.

IEC Just Published - webstore.iec.ch/justpublished

Restez informé sur les nouvelles publications IEC. Just Published détaille les nouvelles publications parues. Disponible en ligne et aussi une fois par mois par email.

Service Clients - webstore.iec.ch/csc

Si vous désirez nous donner des commentaires sur cette publication ou si vous avez des questions contactez-nous: csc@iec.ch.



IEC 60317-51

Edition 2.0 2014-02

INTERNATIONAL STANDARD

NORME INTERNATIONALE

Specifications for particular types of winding wires –
Part 51: Solderable polyurethane enamelled round copper wire, class 180
standards.iec.ch

Spécifications pour types particuliers de fils de bobinage –
Partie 51: Fil brasable de section circulaire en cuivre émaillé avec polyuréthane,
classe 180

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

COMMISSION
ELECTROTECHNIQUE
INTERNATIONALE

PRICE CODE
CODE PRIX

K

ICS 29.060.10

ISBN 978-2-8322-1419-0

Warning! Make sure that you obtained this publication from an authorized distributor.

Attention! Veuillez vous assurer que vous avez obtenu cette publication via un distributeur agréé.

CONTENTS

FOREWORD	3
INTRODUCTION	5
1 Scope	6
2 Normative references	6
3 Terms, definitions, general notes and appearance	6
3.1 Terms and definitions	6
3.2 General notes	6
3.2.1 Methods of test	6
3.2.2 Winding wire	6
3.3 Appearance	7
4 Dimensions	7
5 Electrical resistance	7
6 Elongation	7
7 Springiness	7
8 Flexibility and adherence	7
9 Heat shock	7
10 Cut-through	7
11 Resistance to abrasion (nominal conductor diameters from 0,250 mm up to and including 1,000 mm)	7
<i>iTeh STANDARD PREVIEW (standards.iteh.ai)</i>	
12 Resistance to solvents	8
13 Breakdown voltage	8
14 Continuity of insulation	8
15 Temperature index	8
16 Resistance to refrigerants	8
17 Solderability	9
17.1 General	9
17.2 Nominal conductor diameters up to and including 0,100 mm	9
17.3 Nominal conductor diameters over 0,100 mm	9
18 Heat or solvent bonding	9
19 Dielectric dissipation factor	9
20 Resistance to transformer oil	9
21 Loss of mass	9
23 Pin hole test	9
30 Packaging	9
Bibliography	10
Table 1 – Resistance to abrasion	8

INTERNATIONAL ELECTROTECHNICAL COMMISSION

**SPECIFICATIONS FOR PARTICULAR TYPES
OF WINDING WIRES –****Part 51: Solderable polyurethane enamelled round
copper wire, class 180****FOREWORD**

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

International Standard IEC 60317-51 has been prepared by IEC technical committee 55: Winding wires.

This second edition cancels and replaces the first edition published in 2001. This edition constitutes a technical revision.

This edition includes the following significant technical changes with respect to the previous edition:

- new 3.2.2 containing general notes on winding wire, formerly a part of the scope;
- new 3.3 containing requirements for appearance;
- revision to references to IEC 60317-0-1:2013 to clarify that their application is normative;
- New Clause 23, Pin hole test.

The text of this standard is based on the following documents:

CDV	Report on voting
55/1394/CDV	55/1456/RVC

Full information on the voting for the approval of this standard can be found in the report on voting indicated in the above table.

This publication has been drafted in accordance with the ISO/IEC Directives, Part 2.

This International standard is to be read in conjunction with the IEC 60317-0-1:2013.

A list of all parts in the IEC 60317 series, published under the general title *Specifications for particular types of winding wires*, can be found on the IEC website.

The numbering of clauses in this standard is not continuous from Clauses 20 and 30 in order to reserve space for possible future wire requirements prior to those for wire packaging.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[IEC 60317-51:2014](#)

<https://standards.iteh.ai/catalog/standards/sist/b06ea1bc-7a5e-491b-9140-d794e0a688d2/iec-60317-51-2014>

INTRODUCTION

This part of IEC 60317 is one of a series which deals with insulated wires used for windings in electrical equipment. The series has three groups describing:

- 1) Winding wires – Test methods (IEC 60851);
- 2) Specifications for particular types of winding wires (IEC 60317);
- 3) Packaging of winding wires (IEC 60264).

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[IEC 60317-51:2014](#)

<https://standards.iteh.ai/catalog/standards/sist/b06ea1bc-7a5e-491b-9140-d794e0a688d2/iec-60317-51-2014>

SPECIFICATIONS FOR PARTICULAR TYPES OF WINDING WIRES –

Part 51: Solderable polyurethane enamelled round copper wire, class 180

1 Scope

This part of IEC 60317 specifies the requirements of solderable enamelled round copper winding wire of class 180 with a sole coating based on polyurethane resin, which may be modified providing it retains the chemical identity of the original resin and meets all specified wire requirements.

NOTE A modified resin is a resin that has undergone a chemical change, or contains one or more additives to enhance certain performance or application characteristics.

The range of nominal conductor diameters covered by this standard is as follows:

- Grade 1: 0,018 mm up to and including 1,000 mm;
- Grade 2: 0,020 mm up to and including 1,000 mm.

iTeh STANDARD PREVIEW
The nominal conductor diameters are specified in Clause 4 of IEC 60317-0-1:2013.
(standards.iteh.ai)

2 Normative references

[IEC 60317-51:2014](#)

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60317-0-1:2013, *Specifications for particular types of winding wires – Part 0-1: General requirements – Enamelled round copper wire*

3 Terms, definitions, general notes and appearance

3.1 Terms and definitions

For the purposes of this document, the terms and definitions given in 3.1 of IEC 60317-0-1:2013 apply.

3.2 General notes

3.2.1 Methods of test

In case of inconsistencies between IEC 60317-0-1 and this standard, the latter shall prevail.

3.2.2 Winding wire

Class 180 is a thermal class that requires a minimum temperature index of 180 and a heat shock temperature of at least 200 °C.

The temperature in degrees Celsius corresponding to the temperature index is not necessarily that at which it is recommended that the wire be operated and this will depend on many factors, including the type of equipment involved.

3.3 Appearance

Subclause 3.3 of IEC 60317-0-1:2013 applies.

4 Dimensions

Clause 4 of IEC 60317-0-1:2013 applies.

5 Electrical resistance

Clause 5 of IEC 60317-0-1:2013 applies.

6 Elongation

Clause 6 of IEC 60317-0-1:2013 applies.

7 Springiness *iTeh STANDARD PREVIEW* *(standards.iteh.ai)*

8 Flexibility and adherence [IEC 60317-51:2014](#)

<https://standards.iteh.ai/catalog/standards/sist/b06ea1bc-7a5e-491b-9140-d794e0a688d2/iec-60317-51-2014>

Clause 8 of IEC 60317-0-1:2013 applies.

9 Heat shock

Clause 9 of IEC 60317-0-1:2013 applies. The minimum heat shock temperature shall be 200 °C.

10 Cut-through

No failure shall occur within 2 min at 230 °C.

11 Resistance to abrasion (nominal conductor diameters from 0,250 mm up to and including 1,000 mm)

The wire shall meet the requirements given in Table 1.

For intermediate nominal conductor diameters, the value of the next larger nominal conductor diameter applies.

Table 1 – Resistance to abrasion

Nominal conductor diameter mm	Grade 1		Grade 2	
	Minimum average force to failure N	Minimum force to failure of each measurement N	Minimum average force to failure N	Minimum force to failure of each measurement N
0,250	2,30	1,95	4,10	3,50
0,280	2,50	2,10	4,40	3,70
0,315	2,70	2,30	4,75	4,00
0,355	2,90	2,50	5,10	4,30
0,400	3,15	2,70	5,45	4,60
0,450	3,40	2,90	5,80	4,90
0,500	3,65	3,10	6,20	5,25
0,560	3,90	3,30	6,65	5,60
0,630	4,20	3,55	7,10	6,00
0,710	4,50	3,80	7,60	6,45
0,800	4,80	4,10	8,10	6,90
0,900	5,20	4,40	8,70	7,40
1,000	5,60	4,75	9,30	7,90

[IEC 60317-51:2014](#)**12 Resistance to solvents**<https://standards.itech.ai/catalog/standards/sist/b06ea1bc-7a5e-491b-9140-d794e0a688d2/iec-60317-51-2014>

Clause 12 of IEC 60317-0-1:2013 applies.

13 Breakdown voltage

Clause 13 of IEC 60317-0-1:2013 applies. The elevated temperature shall be 180 °C.

14 Continuity of insulation

Clause 14 of IEC 60317-0-1:2013 applies.

15 Temperature index

Clause 15 of IEC 60317-0-1:2013 applies. The minimum temperature index shall be 180.

16 Resistance to refrigerants

Test inappropriate.

17 Solderability

17.1 General

The temperature of the solder bath shall be (390 ± 5) °C. The surface of the tinned wire shall be smooth and free from holes and enamel residues.

17.2 Nominal conductor diameters up to and including 0,100 mm

The maximum immersion time shall be 3 s.

17.3 Nominal conductor diameters over 0,100 mm

The maximum immersion time (in seconds) shall be the following multiple of the nominal conductor diameter (in millimetres) with a minimum of 3 s.

Grade 1	Grade 2
8 s/mm	12 s/mm

18 Heat or solvent bonding

Test inappropriate.

iTeh STANDARD PREVIEW

19 Dielectric dissipation factor (standards.iteh.ai)

Test to be agreed between purchaser and supplier IEC 60317:2014

<https://standards.iteh.ai/catalog/standards/sist/b06ea1bc-7a5e-491b-9140-d794e0a688d2/iec-60317-51-2014>

20 Resistance to transformer oil

Test inappropriate.

21 Loss of mass

Test inappropriate.

23 Pin hole test

Clause 23 of IEC 60317-0-1:2013 applies.

30 Packaging

Clause 30 of IEC 60317-0-1:2013 applies.