

SLOVENSKI STANDARD
SIST EN 10025-4:2004

01-december-2004

BUXca Yý U
SIST EN 10113-1:1997

Jfc Yj U'Ub]nXY_]n' cbgfi _W'g_ l 'Y_Y'È("XY.'HY b] b]XcVUj b]dc[c'j'nU
 hYfa ca Y Ubg_c'cVXYUbUj U'UbUj Ufjj UXfcVbcnfbUU_cbgfi _W'g_U'Y'_U

Hot rolled products of structural steels - Part 4: Technical delivery conditions for thermomechanical rolled weldable fine grain structural steels

Warmgewalzte Erzeugnisse aus Baustählen - Teil 4: Technische Lieferbedingungen für thermomechanisch gewalzte schweißgeeignete Feinkornbaustähle

Produits laminés a chaud en aciers de construction Partie 4: Conditions techniques de livraison pour les aciers de construction soudables a grains fins obtenus par laminage thermomécanique

Ta slovenski standard je istoveten z: EN 10025-4:2004

ICS:

| | | |
|-----------|---------------------------------------|---------------------------------------|
| 77.140.10 | Jekla za toplotno obdelavo | Heat-treatable steels |
| 77.140.50 | Ú z aã\ ^} äã å^ äã][ã å^ ã | Flat steel products and semi-products |

SIST EN 10025-4:2004 en

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 10025-4:2004

<https://standards.iteh.ai/catalog/standards/sist/bb0b821d-0c97-4725-977e-22d4627e7e50/sist-en-10025-4-2004>

English version

Hot rolled products of structural steels - Part 4: Technical
delivery conditions for thermomechanical rolled weldable fine
grain structural steels

Produits laminés à chaud en aciers de construction - Partie
4: Conditions techniques de livraison pour les aciers de
construction soudables à grains fins obtenus par laminage
thermomécanique

Warmgewalzte Erzeugnisse aus Baustählen - Teil 4:
Technische Lieferbedingungen für thermomechanisch
gewalzte schweißgeeignete Feinkornbaustähle

This European Standard was approved by CEN on 1 April 2004.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Contents

Page

| | |
|---|----|
| Foreword..... | 4 |
| 1 Scope | 5 |
| 2 Normative references | 5 |
| 2.1 General standards | 5 |
| 2.2 Standards on dimensions and tolerances (see 7.7.1)..... | 6 |
| 2.3 Standards on testing | 6 |
| 3 Terms and definitions | 6 |
| 4 Classification and designation..... | 7 |
| 4.1 Classification..... | 7 |
| 4.1.1 Main quality classes | 7 |
| 4.1.2 Grades and qualities | 7 |
| 4.2 Designation | 7 |
| 5 Information to be supplied by the purchaser | 8 |
| 5.1 Mandatory information | 8 |
| 5.2 Options | 8 |
| 6 Manufacturing process..... | 8 |
| 6.1 Steel making process..... | 8 |
| 6.2 Grain structure..... | 8 |
| 6.3 Delivery conditions..... | 8 |
| 7 Requirements | 9 |
| 7.1 General..... | 9 |
| 7.2 Chemical composition | 9 |
| 7.3 Mechanical properties..... | 9 |
| 7.3.1 General..... | 9 |
| 7.3.2 Impact properties..... | 9 |
| 7.3.3 Improved deformation properties perpendicular to the surface | 10 |
| 7.4 Technological properties | 10 |
| 7.4.1 Weldability | 10 |
| 7.4.2 Formability..... | 10 |
| 7.4.3 Suitability for hot-dip zinc-coating..... | 11 |
| 7.5 Surface properties | 11 |
| 7.5.1 Strip | 11 |
| 7.5.2 Plates and wide flats | 11 |
| 7.5.3 Sections | 12 |
| 7.5.4 Bars and rods..... | 12 |
| 7.6 Internal soundness..... | 12 |
| 7.7 Dimensions, tolerances on dimensions and shape..... | 12 |
| 8 Inspection | 12 |
| 8.1 General..... | 12 |
| 8.2 Type of inspection and inspection document | 12 |
| 8.3 Frequency of testing | 13 |
| 8.3.1 Sampling | 13 |
| 8.3.2 Test units | 13 |
| 8.3.3 Verification of chemical composition..... | 13 |
| 8.4 Tests to be carried out for specific inspection..... | 13 |
| 9 Preparation of samples and test pieces..... | 13 |
| 9.1 Selection and preparation of samples for chemical analysis..... | 13 |
| 9.2 Location and orientation of samples and test pieces for mechanical tests..... | 14 |
| 9.2.1 General..... | 14 |

| | | |
|-----------------------|--|----|
| 9.2.2 | Preparation of samples | 14 |
| 9.2.3 | Preparation of test pieces..... | 14 |
| 9.2.4 | Impact test pieces..... | 14 |
| 9.3 | Identification of samples and test pieces | 14 |
| 10 | Test methods | 14 |
| 10.1 | Chemical analysis..... | 14 |
| 10.2 | Mechanical tests | 14 |
| 10.3 | Ultrasonic testing | 14 |
| 10.4 | Retests | 14 |
| 11 | Marking, labelling, packaging | 15 |
| 12 | Complaints | 15 |
| 13 | Options (see 5.2)..... | 15 |
| Annex A (informative) | List of corresponding former designations | 22 |
| Annex B (informative) | List of national standards which correspond with EURONORMS referenced .. | 23 |
| Bibliography | | 24 |

iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST EN 10025-4:2004](https://standards.iteh.ai/catalog/standards/sist/bb0b821d-0c97-4725-977e-22d4627e7e50/sist-en-10025-4-2004)

<https://standards.iteh.ai/catalog/standards/sist/bb0b821d-0c97-4725-977e-22d4627e7e50/sist-en-10025-4-2004>

Foreword

This document (EN 10025-4:2004) has been prepared by Technical Committee ECISS/TC 10 "Structural steels - Grades and qualities", the secretariat of which is held by NEN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by May 2005, and conflicting national standards shall be withdrawn at the latest by May 2005.

This document supersedes together with EN 10025-1:2004, EN 10113-1:1993, *Hot-rolled products in weldable fine grain structural steels - Part 1: General delivery conditions* and EN 10113-3:1993 *Hot-rolled products in weldable fine grain structural steels - Part 3: Delivery conditions for thermomechanical rolled steels*.

The titles of the other parts of this document are:

Part 1: General technical delivery conditions;

Part 2: Technical delivery conditions for non-alloy structural steels;

Part 3: Technical delivery conditions for normalized/normalized rolled weldable fine grain structural steels;

Part 5: Technical delivery conditions for structural steels with improved atmospheric corrosion resistance;

Part 6: Technical delivery conditions for flat products of high yield strength structural steels in the quenched and tempered condition.

SIST EN 10025-4:2004

This document has been prepared under Mandate M/120 given to CEN by the European Commission and the European Free Trade Association, and supports essential requirements of the EU Construction Products Directive (89/106/EEC). For relationship with the EU Construction Products Directive, see informative Annex ZA of EN 10025-1:2004.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

1 Scope

Part 4 of this document, in addition to Part 1, specifies requirements for flat and long products of hot rolled weldable fine grain structural steels in the thermomechanical rolled condition in the grades and qualities given in Tables 2 to 4 (chemical composition) and Tables 5 to 7 (mechanical properties) in thickness ≤ 120 mm for flat products and in thickness ≤ 150 mm for long products.

In addition to EN 10025-1 the steels specified in this document are especially intended for use in heavily loaded parts of welded structures such as, bridges, flood gates, storage tanks, water supply tanks, etc., for service at ambient and low temperatures.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

2.1 General standards

EN 1011-2, *Welding – Recommendations for welding of metallic materials - Part 2: Arc welding of ferritic steels.*

EN 10020, *Definition and classification of grades of steel.*

EN 10025-1:2004, *Hot rolled products of structural steels - Part 1: General technical delivery conditions.*

EN 10027-1, *Designation systems for steels - Part 1: Steel names, principal symbols.*

EN 10027-2, *Designation systems for steels - Part 2: Numerical system.*

EN 10163-1, *Delivery requirements for surface condition of hot-rolled steel plates, wide flats and sections – Part 1: General requirements.*

EN 10163-2, *Delivery requirements for surface condition of hot-rolled steel plates, wide flats and sections – Part 2: Plates and wide flats.*

EN 10163-3, *Delivery requirements for surface condition of hot-rolled steel plates, wide flats and sections – Part 3: Sections.*

EN 10164, *Steel products with improved deformation properties perpendicular to the surface of the product - Technical delivery conditions.*

EN 10221, *Surface quality classes for hot-rolled bars and rods - Technical delivery conditions.*

CR 10260, *Designation systems for steels - Additional symbols.*

2.2 Standards on dimensions and tolerances (see 7.7.1)

EN 10017, *Non-alloy steel rod for drawing and/or cold rolling – Dimensions and tolerances.*

EN 10024, *Hot rolled taper flange I sections - Tolerances on shape and dimensions.*

EN 10029, *Hot rolled steel plates 3 mm thick or above - Tolerances on dimensions, shape and mass.*

EN 10034, *Structural steel I and H sections - Tolerances on shape and dimensions.*

EN 10048, *Hot rolled narrow steel strip - Tolerances on dimensions and shape.*

EN 10051, *Continuously hot-rolled uncoated plate, sheet and strip of non-alloy and alloy steels - Tolerances on dimensions and shape.*

EN 10055, *Hot-rolled steel equal flange tees with radiused root and toes - Dimensions and tolerances on shape and dimensions.*

EN 10056-1, *Structural steel equal and unequal leg angles - Part 1: Dimensions.*

EN 10056-2, *Structural steel equal and unequal leg angles - Part 2: Tolerances on shape and dimensions.*

EN 10058, *Hot rolled flat steel bars for general purposes - Dimensions and tolerances on shape and dimensions.*

EN 10059, *Hot rolled square steel bars for general purposes - Dimensions and tolerances on shape and dimensions.*

EN 10060, *Hot rolled round steel bars for general purposes - Dimensions and tolerances on shape and dimensions.*

<https://standards.iteh.ai/catalog/standards/sist/bb0b821d-0c97-4725-977e-78c229e94146/en-10025-4:2004>

EN 10061, *Hot rolled hexagon steel bars for general purposes - Dimensions and tolerances on shape and dimensions.*

EN 10067, *Hot rolled bulb flats - Dimensions and tolerances on shape, dimensions and mass.*

EN 10162, *Cold rolled steel sections - Technical delivery conditions - Dimensional and cross-sectional tolerances.*

EN 10279, *Hot rolled steel channels - Tolerances on shape and dimensions.*

2.3 Standards on testing

EN 10160, *Ultrasonic testing of steel flat product of thickness equal to or greater than 6 mm (reflection method).*

EN 10306, *Iron and steel - Ultrasonic testing of H beams with parallel flanges and IPE beams.*

EN 10308, *Non-destructive testing - Ultrasonic testing of steel bars.*

EN ISO 643, *Steels – Micrographic determination of the apparent grain size (ISO 643:2003).*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in EN 10025-1:2004 and the following apply.

3.1**thermomechanical rolling**

rolling process in which the final deformation is carried out in a certain temperature range leading to a material condition with certain properties which cannot be achieved or repeated by heat treatment alone

NOTE 1 Subsequent heating above 580 °C may lower the strength values. If temperatures above 580 °C are needed reference should be made to the supplier.

NOTE 2 Thermomechanical rolling leading to the delivery condition M can include processes with an increasing cooling rate with or without tempering including self-tempering but excluding direct quenching and quenching and tempering.

NOTE 3 In some publications the word TMCP (Thermomechanical Control Process) is also used.

3.2**fine grained steels**

steels with fine grain structure with an equivalent index of ferritic grain size ≥ 6 determined in accordance with EN ISO 643

4 Classification and designation**4.1 Classification****4.1.1 Main quality classes**

All steel grades specified in this document shall be classified as alloy special steels according to EN 10020.

4.1.2 Grades and qualities

This document specifies four steel grades S275, S355, S420 and S460.

All the steel grades may be supplied in the following qualities as specified at the time of the enquiry and order:

- with specified minimum values of impact energy at temperatures not lower than -20 °C, designated as M;
- with specified minimum values of impact energy at temperatures not lower than -50 °C, designated as ML.

4.2 Designation

4.2.1 The designation shall be in accordance with EN 10025-1.

NOTE For a list of corresponding former designations and the former designations from EN 10113-3:1993 see Annex A, Table A.1.

4.2.2 The designation shall consist of:

- number of this document (EN 10025-4);
- steel name or the steel number; the steel name consisting of:
 - symbol S (for structural steel);
 - indication of the minimum specified yield strength for thickness ≤ 16 mm expressed in MPa¹⁾;

¹⁾ 1 MPa = 1 N/mm².

EN 10025-4:2004 (E)

- delivery condition M;
- capital letter L for the quality with specified minimum values of impact energy at temperatures not lower than -50 °C.

EXAMPLE Thermomechanical rolled structural steel (S) with a specified minimum yield strength at ambient temperature of 355 MPa¹), and with a specified minimum value of impact energy at -50 °C:

Steel EN 10025-4 - S355ML

or

Steel EN 10025-4 - 1.8834

5 Information to be supplied by the purchaser

5.1 Mandatory information

The information that shall be supplied by the purchaser at the time of the order is specified in EN 10025-1.

In addition to EN 10025-1 the following information shall be supplied by the purchaser at the time of the order:

- g) the type of inspection document (see 8.2).

5.2 Options

A number of options are specified in Clause 13. In the event that the purchaser does not indicate his wish to implement any of these options, the supplier shall supply in accordance with the basic specification.

6 Manufacturing process

6.1 Steel making process

The steel making process shall be in accordance with EN 10025-1. If specified at the time of the order the steel making process shall be reported to the purchaser.

See option 1.

6.2 Grain structure

The steels shall have a fine grain structure containing sufficient amounts of nitrogen binding elements (see Table 2).

6.3 Delivery conditions

The products shall be supplied in the thermomechanical rolled condition as defined in Clause 3.

7 Requirements

7.1 General

The following requirements apply when sampling, preparation of test pieces and testing specified in Clauses 8, 9 and 10 are carried out.

7.2 Chemical composition

7.2.1 The chemical composition determined by ladle analysis shall comply with the specified values of Table 2. On special request of the purchaser the manufacturer shall inform the purchaser at the time of the enquiry and order which of the alloying elements appropriate to the steel grade required will be deliberately added to the material to be delivered.

See option 29.

7.2.2 The upper limits applicable for the product analysis are given in Table 3. The manufacturer shall inform the purchaser at the time of the enquiry and order which of the alloying elements appropriate to the steel grade required will be deliberately added to the material to be delivered. The product analysis shall be carried out when specified at the time of the order.

See option 2.

7.2.3 The maximum carbon equivalent values based on the ladle analysis, given in Table 4 shall apply. For the carbon equivalent value formula see 7.2.3 of EN 10025-1:2004.

7.2.4 When products are supplied with a control on Si e.g. for hot-dip zinc-coating so that there could be a need to increase the content of other elements like C and Mn to achieve the required tensile properties, the maximum carbon equivalent values of Table 4 shall be increased as follows:

- for $Si \leq 0,030$ %, increase CEV by 0,02 %;
- for $Si \leq 0,25$ %, increase CEV by 0,01 %.

7.3 Mechanical properties

7.3.1 General

7.3.1.1 Under the inspection and testing conditions as specified in Clauses 8, 9 and 10 and in the delivery condition as specified in 6.3 the mechanical properties shall comply with the values given in Tables 5 to 7.

7.3.1.2 For flat products the nominal thickness applies. For long products of irregular section the nominal thickness of that part from which the samples are taken applies (see Annex A of EN 10025-1:2004).

7.3.2 Impact properties

7.3.2.1 The verification of the impact energy value shall be carried out in accordance with EN 10025-1.

Furthermore the verification of the impact energy value shall be carried out, unless otherwise agreed (see 7.3.2.2 and 7.3.2.3) with longitudinal test pieces for:

- M at -20 °C;
- ML at -50 °C.