



SLOVENSKI STANDARD

SIST EN 10111:1998

01-avgust-1998

Continuously hot-rolled low carbon steel sheet and strip for cold forming - Technical delivery conditions

Kontinuierlich warmgewalztes Band und Blech aus weichen Stählen zum Kaltumformen - Technische Lieferbedingungen

Bandes et tôles laminées a chaud en continu, en acier doux pour emboutissage ou pliage a froid - Conditions techniques de livraison

Ta slovenski standard je istoveten z: EN 10111:1998

ICS:

77.140.50 Flat steel products and semi-products

SIST EN 10111:1998

en

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 10111:1998

<https://standards.iteh.ai/catalog/standards/sist/c4f9a73d-2852-40a8-bbf9-b13442d7e728/sist-en-10111-1998>

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN 10111

February 1998

ICS 77.140.50

Descriptors: iron and steel products, hot rolled product, steels, cupping, folding, metal plates, steel strips, classifications, designation, delivery condition, chemical composition, mechanical properties, tests, marking

English version

Continuously hot-rolled low carbon steel sheet and strip for cold forming - Technical delivery conditions

Bandes et tôles laminées à chaud en continu, en acier doux pour emboutissage ou pliage à froid - Conditions techniques de livraison

Kontinuierlich warmgewalztes Band und Blech aus weichen Stählen zum Kaltumformen - Technische Lieferbedingungen

This European Standard was approved by CEN on 30 June 1996.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.

iTeh STANDARD PREVIEW
(standards.itech.ai)

SIST EN 10111:1998

<https://standards.itech.ai/catalog/standards/sist/c4f9a73d-2852-40a8-bb9-b13442d7e728/sist-en-10111-1998>



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Central Secretariat: rue de Stassart, 36 B-1050 Brussels

Page 2
EN 10111:1998

CONTENTS LIST

	Page
Foreword	3
1 Scope	4
2 Normative references	4
3 Classification of grades	4
4 Designation	5
5 Requirements	5
5.1 Steelmaking and manufacturing process	5
5.2 Method of deoxidation	5
5.3 Chemical composition	5
5.4 Delivery condition	5
5.5 Choice of properties	6
5.6 Mechanical properties	6
5.7 Surface appearance	6
5.8 Weldability	6
5.9 Tolerances on dimensions and shape	6
5.10 Suitability for surface coating	8
6 Tests	8
6.1 General	8
6.2 Inspection units	8
6.3 Number of tests	8
6.4 Sampling	8
6.5 Test method	9
6.6 Interpretation of results	9
6.7 Inspection documents	9
7 Marking	9
8 Packaging	10
9 Disputes after delivery	10
Annex A (informative) – Corresponding former steel designations	11
Annex B (informative) – Bibliography	12

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 10111:1998

https://standards.iteh.ai/en/standards/SIST-EN-10111-1998/2-40a8-bb9-b13442d7e728/sist-en-10111-1998

Foreword

This European Standard has been prepared by Technical Committee ECISS/TC 13 "Flat products for cold working - Qualities, dimensions, tolerances and specific tests", the secretariat of which is held by IBN/BIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by August 1998, and conflicting national standards shall be withdrawn at the latest by August 1998.

The European Committee for Iron and Steel Standardization (ECISS) charged ECISS/TC 13 (Secretariat : IBN) with preparing a European Standard EN 10111 to replace EURONORM 111-1977.

ECISS/TC 13 met on 1994-09-16 in Brussels and agreed on the text for publication as a European Standard. The following countries were represented in that meeting : France, Germany, Netherlands, Sweden and United Kingdom.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and the United Kingdom.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 10111:1998

<https://standards.iteh.ai/catalog/standards/sist/c4f9a73d-2852-40a8-bb9-b13442d7e728/sist-en-10111-1998>

1 SCOPE

This European standard specifies the grades of continuously hot rolled low carbon steel sheet and strip (in coils) for cold forming.

Depending on its actual width, strip is classified as :

- hot rolled wide strip if its width is greater than or equal to 600 mm;
- hot rolled slit wide strip, if its width is less than 600 mm.

For each grade, it specifies the chemical composition and the mechanical properties.

This European Standard is applicable to products of thickness not less than 1,5 mm and not exceeding 8 mm.

This European Standard is not applicable to products covered by other standards, such as :

- hot rolled products of non-alloy structural steels for general use (EN 10025);
- steel sheet for pressure purposes (EN 10028);
- steel sheet for welded gas cylinders (EN 10120);
- quenched and tempered steels (EN 10083-1 and EN 10083-2).

2 NORMATIVE REFERENCES

This European Standard incorporates by dated or undated reference provisions from other publications. These normative references are cited at the appropriate places in the text and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of any of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies.

EN 10002-1 - Metallic materials - Tensile testing - Part 1 : Method of test (at ambient temperature)

EN 10021 - Steel and iron products - General technical delivery requirements

EN 10027-1 - Designation systems for steels - Part 1 : Steel names, principal symbols

EN 10027-2 - Designation systems for steels - Part 2 : Numerical system

EN 10051 - Continuously hot-rolled uncoated plate, sheet and strip of non-alloy and alloy steels - Tolerances on dimensions and shape

EN 10079 - Definition of steel products

EN 10204 - Metallic products - Types of inspection documents

CR 10260 - Designation systems for steel - Additional symbols for steel names

EURONORM 6 - Bend test for steel

EURONORM 12 - Bend test on steel sheet and strip less than 3 mm thick

3 CLASSIFICATION OF GRADES

The choice of the steel grade and product type is left to the purchaser. For this choice, he may be advised by the manufacturer, but without any liability on the part of the latter, unless agreed at the time of ordering.

Hot rolled products are classified into four grades DD 11, DD 12, DD 13 and DD 14 defined by chemical composition, mechanical and forming characteristics (see table 1).

4 DESIGNATION

4.1 Steel symbols are attributed in accordance with EN 10027-1 and CR 10260; numerical designations are attributed in accordance with EN 10027-2.

NOTE : Annex A gives the correspondence with former national designations.

4.2 Products conforming to this draft European Standard shall be designated, in order, in the following way :

- a) Product designation (e.g. "strip", "sheet" or "slit strip cut longitudinally") in line with EN 10079;
- b) Number of this European Standard (EN 10111);
- c) Symbolic or numerical designation of the steel, shown in table 1.
Example : Strip EN 10111 - DD 13 or strip EN 10111 - 1.0335.

5 REQUIREMENTS

5.1 Steel-making and manufacturing process

Unless otherwise agreed at the time of ordering, the steel-making and manufacturing processes are left to the discretion of the manufacturer. The purchaser shall be informed of these processes, if he specifies it.

5.2 Method of deoxidation

For grade DD 11 the method of deoxidation shall be at the manufacturer's discretion. Grades DD 12, DD 13 and DD 14 shall be fully killed.

5.3 Chemical composition

Table 1 gives the permissible chemical composition limits in the cast.

Table 2 gives the permissible deviations for the product analysis.

5.4 Delivery condition

5.4.1 The products shall normally be delivered with their surface as rolled. By agreement at the time of ordering, the products may be delivered with descaled surface. When they are delivered as rolled, they are covered with a thin layer of scale of variable coloration.

The products may be supplied with a light skin-pass, either at the manufacturer's discretion or by agreement at the time of ordering.

5.4.2 The descaled products are normally delivered oiled. In this case, both surfaces are preserved by a layer of neutral non-drying oil, free of foreign bodies, and uniformly spread in such a way that under normal conditions of packaging, transportation, handling and storage the products will show no corrosion for up to three months.

The layer of oil shall be capable of being removed by alkaline solutions or normal solvents.

The choice of protective oils may be the subject of special agreement at the time of ordering.

If the conditions of transportation or storage are such that special protection against corrosion is required, the purchaser shall inform the manufacturer at the time of ordering.

If the purchaser does not require the surfaces to be oiled, this shall be clearly indicated at the time of ordering.

NOTE : If the order is for un-oiled products, the manufacturer is not responsible for the risk of rust.
The purchaser is also advised that there is a greater risk of the appearance of light scratches during handling, transportation and putting into application.

5.4.3 Descaled products may be supplied with trimmed edges upon agreement at the time of ordering (designation GK following EN 10051).

5.5 Choice of properties

The products covered by this standard correspond to the requirements of table 1.

Subject to special agreement, they may be supplied with special suitability for the production of a specific part. In this case, a maximum rejection percentage may be set by mutual agreement and acceptance on the basis of mechanical properties does not apply.

5.6 Mechanical properties

Table 1 gives the basic mechanical properties valid for the four grades.

The four grades correspond to the increasing formability in the order DD 11 to DD 14.

The characteristics indicated in table 1 are valid for the period specified in the same table 1, from the date on which the products are made available.

The date of availability shall be notified to the purchaser with reasonable prior notice compatible with the validity of the mechanical properties.

5.7 Surface appearance

The sheets shall not have any slivers, blow holes, seams, cracks or scratches which would adversely affect their use.

Pores, small pits, small marks, small scratches, kinks from pay-off reels and a slight coloration are permitted.

The defects shall not be of such an extent that they might run the risk of causing failure or damage to tooling or welding difficulties when in use.

The surface appearances of the unwound coil are assessed as for sheets. However, the percentage of surface defects is generally greater than when supplied in sheets. The maximum percentage of permissible rejections shall be fixed by special agreement at the time of ordering.

[SIST EN 10111:1998](https://standards.iteh.ai/catalog/standards/sist/c4f9a73d-2852-40a8-bb9-b13442d7e728/sist-en-10111-1998)

5.8 Weldability <https://standards.iteh.ai/catalog/standards/sist/c4f9a73d-2852-40a8-bb9-b13442d7e728/sist-en-10111-1998>

Suitability for normal welding processes is ensured. It is, however, desirable to state the welding procedure at the time of ordering but essential to do so in the case of gas welding.

For non-descaled products, the welding process shall take into account the presence of a layer of scale.

5.9 Tolerances on dimensions and shape

The tolerances on dimensions and shape are given in EN 10051.

Table 1 : Characteristics 1)

Designation In accordance with EN 10027-1 and IC 10	Designation in accordance with EN 10027-2	Method of deoxidation	Chemical composition (max) from ladle analysis ²⁾	Tensile properties ³⁾					Bend test radius ⁴⁾	Validity of me- chanical proper- ties
				R_d N/mm ²	R_m	Minimum elongation after fracture %		$L_0=5,65 \sqrt{S_0}$ $3 \leq e \leq 8$		
						$1,5 \leq e < 2$	$2 \leq e < 3$			
DD 11	1.0332	At the discretion of the manufacturer	C 0,12 Mn 0,60 P 0,045 S 0,045	170 - 360	170 - 340	23	24	28	1e	1 month
DD 12	1.0398	Fully killed	C 0,10 Mn 0,45 P 0,035 S 0,035	170 - 340	170 - 320	25	26	30	0	6 months
DD 13	1.0335	Fully killed	C 0,08 Mn 0,40 P 0,030 S 0,030	170 - 330	170 - 310	28	29	33	0	6 months
DD 14	1.0389	Fully killed	C 0,08 Mn 0,35 P 0,025 S 0,025	170 - 310	170 - 290	31	32	36	0	6 months

1) The mechanical characteristics relate only to hot rolled non-descaled or chemically descaled and oiled products, skin-passed or not.

2) Unless otherwise agreed at the time of ordering, nitrogen-fixing elements such as titanium and boron may be added at the discretion of the manufacturer.

3) As long as the width of the product permits, the test pieces for the tensile tests shall be taken perpendicular to the direction of rolling.

4) See EURONORM 6 and EURONORM 12.

1) The mechanical characteristics relate only to hot rolled non-descaled or chemically descaled and oiled products, skin-passed or not.

2) Unless otherwise agreed at the time of ordering, nitrogen-fixing elements such as titanium and boron may be added at the discretion of the manufacturer.

3) As long as the width of the product permits, the test pieces for the tensile tests shall be taken perpendicular to the direction of rolling.

4) See EURONORM 6 and EURONORM 12.