



## Standard Specification for Limestone for Dusting of Coal Mines<sup>1</sup>

This standard is issued under the fixed designation C 737; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

### 1. Scope

1.1 This specification covers limestone suitable for use as dust in coal mines to prevent coal dust explosions.

NOTE 1—In coal mine operations, limestone is dusted onto coal exposures in sufficient amount so that not less than 65 % of all loose dust shall be limestone. With such a concentration of limestone, explosions cannot initiate or be propagated from nearby gas explosions. The limestone must be substantially dry in order to dust satisfactorily.

### 2. Referenced Documents

#### 2.1 ASTM Standards:

C 25 Test Methods for Chemical Analysis of Limestone, Quicklime, and Hydrated Lime<sup>2</sup>

C 50 Methods for Sampling, Inspection, Packing, and Marking of Lime and Limestone Products<sup>2</sup>

C 110 Test Methods for Physical Testing of Quicklime, Hydrated Lime, and Limestone<sup>2</sup>

### 3. Chemical Composition

3.1 Limestone shall conform to the following as to chemical composition:

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee C-7 on Lime and is the direct responsibility of Subcommittee C07.03 on Industrial Uses.

Current edition approved June 10, 1997. Published June 1998. Originally published as C 737-73. Last previous edition C 737-92.

<sup>2</sup> *Annual Book of ASTM Standards*, Vol 04.01.

Moisture (at point of manufacture), max, %	0.5
Silica, free and combined, max, %	4.0

### 4. Physical Properties

4.1 Limestone for this application shall have the following fineness:

Passing a No. 20 (850- $\mu$ m) sieve, min, %	100
Passing a No. 200 (75- $\mu$ m) sieve, min, %	70

### 5. Test Methods

5.1 *Chemical Analysis*—The chemical analysis of the limestone shall be made in accordance with Test Methods C 25.

5.2 *Fineness*—The sieve analysis of limestone shall be determined in accordance with Test Methods C 110.

### 6. General Requirements

6.1 Either high calcium or dolomitic limestone may be furnished for this application.

### 7. Sampling, Inspection, etc.

7.1 The sampling, inspection, rejection, retesting, packing, and marking shall be conducted in accordance with Methods C 50.

### 8. Keywords

8.1 coal mines; dolomitic limestone; fineness; high calcium limestone; lime; limestone; limestone dust; mine explosions; moisture content; silica content

*The American Society for Testing and Materials takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, 100 Barr Harbor Drive, West Conshohocken, PA 19428.*

*This standard is copyrighted by ASTM, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (http://www.astm.org).*