



Designation: D 5467/D 5467M – 97^{e1}

Standard Test Method for Compressive Properties of Unidirectional Polymer Matrix Composite Materials Using a Sandwich Beam¹

This standard is issued under the fixed designation D 5467/D 5467M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

^{e1} NOTE—The designation of this standard was editorially corrected to be “combined” in September 2002, in accordance with Part H of ASTM’s *Form and Style for ASTM Standards*. Additionally, the inch-pound values were editorially placed in brackets instead of parentheses throughout, in accordance with Part H of ASTM’s *Form and Style*.

1. Scope

1.1 This test method covers the in-plane compressive properties of polymer matrix composite materials reinforced by high-modulus fibers in a sandwich beam configuration. The composite material forms are limited to continuous-fiber composites of unidirectional orientation. This test procedure introduces compressive load into a thin skin bonded to a thick honeycomb core with the compressive load transmitted into the sample by subjecting the beam to four-point bending.

1.2 This procedure is applicable primarily to laminates made from prepreg or similar product forms. Other product forms may require deviations from the test method.

1.3 The values stated in either SI units or inch-pound units are to be regarded separately as standard. Within the text the inch-pounds units are shown in brackets. The values stated in each system are not exact equivalents; therefore, each system must be used independently of the other. Combining values from the two systems may result in nonconformance with the standard.

NOTE 1—Additional procedures for determining compressive properties of polymer matrix composites may be found in Test Methods D 3410/D 3410M and D 695.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:

D 695 Test Method for Compressive Properties of Rigid Plastics²

- D 792 Test Methods for Density and Specific Gravity (Relative Density) of Plastics by Displacement²
- D 883 Terminology Relating to Plastics²
- D 2584 Test Method for Ignition Loss of Cured Reinforced Resins³
- D 2734 Test Method for Void Content of Reinforced Plastics³
- D 3171 Test Method for Constituent Content of Composite Materials⁴
- D 3410/D 3410M Test Method for Compressive Properties of Polymer Matrix Composite Materials with Unsupported Gage Section by Shear Loading⁴
- D 3878 Terminology for Composite Materials⁴
- D 5229/D 5229M Test Method for Moisture Absorption Properties and Equilibrium Conditioning of Polymer Matrix Composite Materials⁴
- E 4 Practices for Force Verification of Testing Machines⁵
- E 6 Terminology Relating to Methods of Mechanical Testing^{5-97/e1}
- E 111 Test Method for Young’s Modulus, Tangent Modulus, and Chord Modulus⁵
- E 122 Practice for Calculating Sample Size to Estimate, With a Specified Tolerable Error, the Average for a Characteristic of a Lot or Process⁶
- E 177 Practice for Use of the Terms Precision and Bias in ASTM Test Methods⁶
- E 251 Test Methods for Performance Characteristics of Metallic Bonded Resistance Strain Gages⁵
- E 456 Terminology Relating to Quality and Statistics⁶
- E 1237 Guide for Installing Bonded Resistance Strain Gages⁵
- E 1309 Guide for Identification of Fiber-Reinforced Polymer-Matrix Composite Materials in Databases⁴
- E 1434 Guide for Recording Mechanical Test Data of Fiber-Reinforced Composite Materials in Databases⁴

¹ This test method is under the jurisdiction of ASTM Committee D30 on Composite Materials and is the direct responsibility of Subcommittee D30.04 on Lamina and Laminate Test Methods.

Current edition approved Oct. 10, 1997. Published June 1998. Originally published as D 5467 – 93. Last previous edition D 5467 – 93.

² *Annual Book of ASTM Standards*, Vol 08.01.

³ *Annual Book of ASTM Standards*, Vol 08.02.

⁴ *Annual Book of ASTM Standards*, Vol 15.03.

⁵ *Annual Book of ASTM Standards*, Vol 03.01.

⁶ *Annual Book of ASTM Standards*, Vol 14.02.

E 1471 Guide for Identification of Fibers, Fillers, and Core Materials in Computerized Material Property Databases⁷

3. Terminology

3.1 *Definitions*—Terminology D 3878 defines terms relating to high-modulus fibers and their composites. Terminology D 883 defines terms relating to plastics. Terminology E 6 defines terms relating to mechanical testing. Terminology E 456 and Practice E 177 define terms relating to statistics. In the event of a conflict between terms, Terminology D 3878 shall have precedence over the other terminology standards.

3.2 *Definitions of Terms Specific to This Standard:*

3.2.1 *nominal value, n*—a value, existing in name only, assigned to a measurable property for the purpose of convenient designation. Tolerances may be applied to a nominal value to define an acceptable range for the property.

3.2.2 *orthotropic material, n*—a material with a property of interest that, at a given point, possesses three mutually perpendicular planes of symmetry defining the principal material coordinate system for that property.

3.2.3 *principal material coordinate system, n*—a coordinate system with axes that are normal to the planes of symmetry that exist within the material.

3.2.4 *reference coordinate system, n*—a coordinate system for laminated composites used to define ply orientations. One of the reference coordinate system axes (normally the Cartesian *x*-axis) is designated the reference axis, assigned a position, and the ply principal axis of each ply in the laminate

is referenced relative to the reference axis to define the ply orientation for that ply.

3.2.5 *specialty orthotropic, adj*—a description of an orthotropic material as viewed in its principal material coordinate system. In laminated composites, a specialty orthotropic laminate is a balanced and symmetric laminate of the $(0_i/90_j)_{ns}$ family as viewed from the reference coordinate system, such that the membrane-bending coupling terms of the stress-strain relation are zero.

3.2.6 *transition strain, $\epsilon^{transition}$, n*—the strain value at the mid-range of the transition region between the two essentially linear portions of a bilinear stress-strain or strain-strain curve (a transverse strain-longitudinal strain curve as used for determining Poisson's ratio).

3.3 *Symbols:*

3.3.1 *a*—distance between neutral axes of test and opposite facesheets.

3.3.2 *A*—cross-sectional area of test facesheet.

3.3.3 *CV*—sample coefficient of variation, in percent.

3.3.4 *E_o*—modulus of elasticity of the opposite facesheet in the test direction.

3.3.5 *E_f*—modulus of elasticity of the test facesheet in the test direction.

3.3.6 *F^{cu}*—ultimate compressive strength.

3.3.7 *G_{xz}*—through-thickness shear modulus of elasticity.

3.3.8 *h_c*—thickness of core.

3.3.9 *σ^c*—compressive normal stress.

4. Summary of Test Method

4.1 A sandwich beam composed of two facesheets separated by a relatively deep honeycomb core, as shown in Fig. 1, is

⁷ Annual Book of ASTM Standards, Vol 14.01.




FIG. 1 Longitudinal Compression Sandwich Beam Test Specimen

loaded in four-point bending. The main component of the compression test specimen is the face sheet that is loaded in compression during flexure, with the material direction of interest oriented along the length of the beam. The other facesheet is of a material and size carefully selected to preclude its influence on the test results. The ultimate compressive strength of the material is determined from the load at which the test facesheet of the sandwich beam fails in an acceptable compression failure mode. If the specimen strain is monitored with strain or deflection transducers then the stress-strain response of the material can be determined, from which can be derived the compressive modulus of elasticity for this configuration.

5. Significance and Use

5.1 This test method is designed to produce membrane compressive property data for material specifications, research and development, quality assurance, and structural design and analysis. Factors that influence the compressive response and should therefore be reported include the following: material, methods of material and specimen preparation, specimen conditioning, environment of testing, specimen alignment, speed of testing, time at reinforcement. Properties, in the test direction, that may be obtained from this test method include:

- 5.1.1 Ultimate compressive strength,
- 5.1.2 Ultimate compressive strain,
- 5.1.3 Compressive (linear or chord) modulus of elasticity, and
- 5.1.4 Transition strain.

6. Interferences

6.1 *Test Method Sensitivities*—Compressive strength for a single material system has been shown to differ when determined by different test methods. Such differences can be attributed to specimen alignment effects, specimen geometry effects, and fixture effects even though efforts have been made to minimize these effects.

6.2 *Material and Specimen Preparation*—Compressive modulus, and especially compressive strength, are sensitive to poor material fabrication practices, damage induced by improper coupon machining, and lack of control of fiber alignment. Fiber alignment relative to the specimen coordinate axis should be maintained as carefully as possible, although no standard procedure to insure this alignment exists. Procedures found satisfactory include the following: fracturing a cured unidirectional laminate near one edge parallel to the fiber direction to establish the [0] direction or laying in small filament count tows of contrasting color fiber (aramid in carbon laminates and carbon in aramid or glass laminates) parallel to the [0] direction either as part of the prepreg production or as part of panel fabrication.

6.3 *Calculation*—Stress equations are based on beam theory.

7. Apparatus

7.1 *Micrometers*—The micrometer(s) shall use a suitable size diameter ball-interface on irregular surfaces such as the bag-side of a laminate, and a flat anvil interface on machined

edges or very smooth tooled surfaces. The accuracy of the instruments shall be suitable for reading to within 1 % of the sample width and thickness. For typical specimen geometries, an instrument with an accuracy of $\pm 2.5 \mu\text{m}$ [± 0.0001 in.] is desirable for thickness measurement, while an instrument with an accuracy of $\pm 25 \mu\text{m}$ [± 0.001 in.] is desirable for width measurement.

7.2 *Compressive Fixture*—A fixture of four loading cylinders or cylindrical supports capable of loading the sandwich beam as shown in Fig. 1. The fixture shall be installed between the steel platens of the testing machine. To avoid local crushing or failure as a result of stress concentrations under the loading cylinders, the diameter of loading cylinders may be up to 1.5 times the sandwich thickness, and loading pads may be needed under the loading cylinders (see 11.6).

7.3 *Testing Machine*—The testing machine shall be in conformance with Practices E 4 and shall satisfy the following requirements:

7.3.1 *Testing Machine Heads*—The testing machine shall have two loading heads, with at least one movable along the testing axis.

7.3.2 *Drive Mechanism*—The testing machine drive mechanism shall be capable of imparting to the movable head a controlled displacement rate with respect to the stationary head. The displacement rate of the movable head shall be capable of being regulated as specified in 11.3.

7.3.3 *Load Indicator*—The testing machine load-sensing device shall be capable of indicating the total load being carried by the test specimen. This device shall be essentially free from inertia lag at the specified rate of testing and shall indicate the load with an accuracy over the load range(s) of interest of within ± 1 % of the indicated value, as specified by Practices E 4. The load range(s) of interest may be fairly low for modulus evaluation, much higher for strength evaluation, or both, as required.

NOTE 2—Obtaining precision load data over a large range of interest in the same test, such as when both elastic modulus and ultimate load are being determined, place extreme requirements on the load cell and its calibration. For some equipment, a special calibration may be required. For some combinations of material and load cell, simultaneous precision measurement of both elastic modulus and ultimate strength may not be possible, and measurement of modulus and strength may have to be performed in separate tests using a different load cell range for each test.

7.4 *Strain-Indicating Device*—Strain data, if required, shall be determined by means of strain gages.

7.4.1 *Bonded Resistance Strain Gages*—Strain gage selection is a compromise based on the procedure and the type of material to be tested. Strain gages should have an active grid length of 3 mm [0.125 in.] or less; (1.5 mm [0.06 in.] is preferable). Gage calibration certification shall comply with Test Methods E 251. Some guidelines on the use of strain gages on composites are presented below, with a general discussion on the subject in Footnote 8.⁸

7.4.1.1 Surface preparation of fiber-reinforced composites in accordance with Practice E 1237 can penetrate the matrix

⁸ Pendleton, R. P. and Tuttle, M. E., *Manual on Experimental Methods for Mechanical Testing of Composites*, Society for Experimental Mechanics, Bethel, CT, 1989.

material and cause damage to the reinforcing fibers, resulting in improper coupon failures. Reinforcing fibers shall not be exposed or damaged during the surface preparation process. Consult the strain gage manufacturer regarding surface preparation guidelines and recommended bonding agents for composites.

7.4.1.2 Select gages having larger resistances to reduce heating effects on low-conductivity materials. Resistances of 350 Ω or higher are preferred. Use the minimum possible gage excitation voltage consistent with the desired accuracy (1 to 2 V is recommended) to reduce further the power consumed by the gage. Heating of the coupon by the gage may affect the performance of the material directly, or it may affect the indicated strain as a result of a difference between the gage temperature compensation factor and the coefficient of thermal expansion of the coupon material.

7.4.1.3 Temperature compensation is recommended when testing at Standard Laboratory Atmosphere. Temperature compensation is required when testing in nonambient temperature environments. When appropriate, use a traveler coupon (dummy calibration coupon) with identical lay-up and strain gage orientations for thermal strain compensation.

7.4.1.4 Consider the transverse sensitivity of the selected strain gage. Consult the strain gage manufacturer for recommendations on transverse sensitivity corrections.

7.5 *Conditioning Chamber*—When conditioning materials in other than ambient laboratory environments, a temperature/vapor-level controlled environmental conditioning chamber is required that shall be capable of maintaining the required relative temperature to within ±3°C [±5°F] and the required relative vapor level to within ±5 %. Chamber conditions shall be monitored either on an automated continuous basis or on a manual basis at regular intervals.

7.6 *Environmental Test Chamber*—An environmental test chamber is required for test environments other than ambient testing laboratory conditions. This chamber shall be capable of maintaining the gage section of the test specimen within ±3°C [±5°F] of the required test temperature during the mechanical test. In addition, the chamber may have to be capable of maintaining environmental conditions such as fluid exposure or relative humidity during the test (see 11.4).

8. Sampling and Test Specimens

8.1 *Sampling*—Test at least five specimens per test condition unless valid results can be gained through the use of fewer specimens, such as in the case of a designed experiment. For

statistically significant data the procedures outlined in Practice E 122 should be consulted. The method of sampling shall be reported.

8.2 *Geometry*—The test specimen shall be a rectangular bonded beam as shown in Fig. 1, with a unidirectional composite test skin. Recommended facesheet and beam core geometry and material specifications for carbon reinforced [0]_{nT} and [90]_{nT} test coupons are provided in Table 1. The facesheets are bonded to the core using a structural adhesive as described in 8.3.1. If unacceptable failure modes for the carbon reinforced coupons occur, or if alternate reinforcement fibers are to be used (glass, aramid, boron, and so forth), then facesheet, beam core, and overall specimen geometry shall be designed to induce compressive failure of the test facesheet.

NOTE 3—If specimens are to undergo environmental conditioning to equilibrium, then another *traveler* coupon sized according to boundary conditions consistent with one-sided absorption shall be used to determine when equilibrium has been reached for the specimens being conditioned. Suggested approaches include using a facesheet two times the test facesheet thickness or using a facesheet of the same thickness as the test skin with foil masking one side.

8.3 *Specimen Preparation:*

8.3.1 *Panel Fabrication*—Individual test specimens may be fabricated by either preparing sandwich panels larger than the individual specimens and machining specimens from these panels or by bonding facesheets to beam cores that both have the final specimen dimensions before bonding. For either method, prepare the test facesheet by fabricating a unidirectional laminate, with the length of the panel sufficient to accommodate the final specimen length, and panel width large enough to allow the desired number of specimens. Prepare a second laminate for the opposite facesheet as recommended in Table 1 or modified as necessary to induce acceptable compressive failure of the test facesheet. Control of fiber alignment is important. Improper fiber alignment will reduce the measured properties. Erratic fiber alignment will also increase the coefficient of variation. Suggested methods of maintaining fiber alignment are discussed in 6.2. The panel preparation method used shall be reported. Bond the test facesheet laminate and opposite facesheet laminate to the beam core using a structural adhesive.

8.3.2 For preparation of test specimens from large sandwich panels, machine the sandwich beam panel into specimens of dimensions shown in Fig. 1 and Table 1. Care should be taken to avoid damaging the edge of the laminate since the compression strength is sensitive to edge damage. Milling of the

TABLE 1 Recommended Nominal Specifications for Carbon Tape Test Facesheets

Dimension	[0] mm [in.]	[90] mm [in.]
<i>h_f</i>	0.8 [0.03]	1.2 [0.048]
<i>h_c</i>	40 [1.5]	13 [0.5]
<i>h_o</i>	1.6 [0.06]	1.6 [0.063]
<i>l_m</i>	200 [8.0]	50 [2.0]
<i>w</i>	25 [1.0]	25 [1.0]
Materials		
Core material	3 to 4 mm [¹ / ₈ in.] hexagonal cell size Aluminum honeycomb, w/"L" axis in span direction	3 to 4 mm [¹ / ₈ in.] hexagonal cell size Aluminum honeycomb, w/"L" axis in span direction
Opposite facesheet	Same as test facesheet	2024 Aluminum
Core density	368 kg/m ³ [23 lb/ft ³]	130 kg/m ³ [8.1 lb/ft ³]