
Magnetni materiali - Metode ugotavljanja geometrijskih značilnosti elektropločevin in trakov

Magnetic materials - Methods of determination of the geometrical characteristics of electrical steel sheet and strip

Magnetische Werkstoffe - Verfahren zur Bestimmung der geometrischen Kenngrößen von Elektroblech und -band

Matériaux magnétiques - Méthodes de détermination des caractéristiques géométriques des tôles magnétiques en acier

[SIST EN 10251:1998](https://standards.iteh.ai/catalog/standards/sist/26a13c5a-e8e1-42a8-9949-17f955db9fa4/sist-en-10251-1998)

[https://standards.iteh.ai/catalog/standards/sist/26a13c5a-e8e1-42a8-9949-](https://standards.iteh.ai/catalog/standards/sist/26a13c5a-e8e1-42a8-9949-17f955db9fa4/sist-en-10251-1998)

[17f955db9fa4/sist-en-10251-1998](https://standards.iteh.ai/catalog/standards/sist/26a13c5a-e8e1-42a8-9949-17f955db9fa4/sist-en-10251-1998)

Ta slovenski standard je istoveten z: EN 10251:1997

ICS:

29.030	Magnetni materiali	Magnetic materials
77.140.50	Ploščati jekleni izdelki in polizdelki	Flat steel products and semi-products

SIST EN 10251:1998

en

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 10251:1998

<https://standards.iteh.ai/catalog/standards/sist/26a13c5a-e8e1-42a8-9949-17955db9fa4/sist-en-10251-1998>

EUROPEAN STANDARD

EN 10251

NORME EUROPÉENNE

EUROPÄISCHE NORM

January 1997

ICS 29.040.10; 77.140.50

Descriptors: metal plates, magnetic alloys, magnetic circuits, steels, tests, determination, geometric characteristics, definitions, flatness, straightness, curvature

English version

Magnetic materials - Methods of determination of the geometrical characteristics of electrical steel sheet and strip

Matériaux magnétiques - Méthodes de détermination des caractéristiques géométriques des tôles magnétiques en acier

Magnetische Werkstoffe - Verfahren zur Bestimmung der geometrischen Kenngrößen von Elektroblech und -band

This European Standard was approved by CEN on 1995-10-21. CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

The European Standards exist in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.

CEN

European Committee for Standardization
Comité Européen de Normalisation
Europäisches Komitee für Normung

Central Secretariat: rue de Stassart, 36 B-1050 Brussels

Contents

Foreword	3
1 Scope	4
2 Normative references	4
3 Definitions	4
4 Test methods	5
5 Test report	7

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN 10251:1998](#)

<https://standards.iteh.ai/catalog/standards/sist/26a13c5a-e8e1-42a8-9949-17f955db9fa4/sist-en-10251-1998>

Foreword

This European Standard has been prepared by Technical Committee ECISS/TC 24 "Electrical steel and strip qualities - Qualities, dimensions, tolerances and specific tests", the secretariat of which is held by AFNOR.

This European Standard is technically in accordance with CEI 404-9.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by July 1997, and conflicting national standards shall be withdrawn at the latest by July 1997.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard : Austria, Belgium, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and the United-Kingdom.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 10251:1998

<https://standards.iteh.ai/catalog/standards/sist/26a13c5a-e8e1-42a8-9949-17f955db9fa4/sist-en-10251-1998>

1 Scope

This European Standard is intended to define the test methods used for the determination of the following geometrical characteristics of electrical steel sheet and strip :

- flatness ;
- residual curvature ;
- edge camber ;
- deviation from the shearing line due to internal stresses ;
- burr height of cut edges.

This European Standard applies to electrical steel sheet and strip intended for the construction of magnetic circuits and corresponding to Clauses B2, C21 and C22 of IEC 404-1.

2 Normative references

This European Standard incorporates by dated or undated reference, provisions from other publications. These normative references are cited at the appropriate places in the text and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of any of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies.

IEC 404-1 Magnetic materials - Part 1 : Classification

3 Definitions

For the purpose of this European Standard, the following definitions apply :

3.1 flatness (wave factor) : Property of a sheet or length of strip which is characterized by the wave factor i.e. by the relation of the height of the wave to its length. (For examples of waves, see figure 1).

3.2 residual curvature : Permanent curvature in the direction of rolling of an unwound strip.

3.3 edge camber : Greatest distance between a longitudinal edge of the sheet and the line joining the two ends of the measured section corresponding to this edge (see figure 3).

3.4 deviation from the shearing line due to internal stresses : Greatest distance between corresponding points on the two cut edges of a sheet cut longitudinally (see figure 4).

3.5 burr height : Difference between the thicknesses measured respectively at the cut edge of the sheet and at a distance of 10 mm from this edge (see figure 5).

4 Test methods

4.1 Flatness

4.1.1 Test specimen

The test specimen shall consist of a sheet or a length of strip, the size of which is defined in the product standard.

4.1.2 Measuring procedure

The test specimen shall be placed on a surface table sufficiently large that the specimen does not overhang the edges. It shall then be lifted up on one edge and allowed to fall back. The height of the maximum wave (h) and the length of the wave (l) shall be measured with a rule graduated in millimetres (see figure 2).

4.2 Residual curvature

4.2.1 Test specimen

The test specimen shall consist of a sample 500 mm in length and of width equal to the delivered width of the sheet or strip. The axis of the test specimen shall be parallel to the direction of rolling of the sheet or strip.

4.2.2 Measuring procedure

The test shall consist of placing the test specimen vertically against a supporting plate. The top of the test specimen shall be held against the supporting plate over a height of 30 mm with its convex surface facing the plate. The distance (a) between the bottom edge of the test specimen and the supporting plate shall then be measured at the axis of the test specimen (see figure 6). The clamping force shall be sufficient to allow the full width of the test specimen to be in contact with the support.

(standards.iteh.ai)

4.3 Edge camber

[SIST EN 10251:1998](https://standards.iteh.ai/catalog/standards/sist/26a13c5a-e8e1-42a8-9949-17f955db9fa4/sist-en-10251-1998)

<https://standards.iteh.ai/catalog/standards/sist/26a13c5a-e8e1-42a8-9949-17f955db9fa4/sist-en-10251-1998>

4.3.1 Test specimen

The test specimen shall consist of a sheet or a length of strip, the size of which is defined in the product standard.

4.3.2 Measuring procedure

The test specimen shall be placed on a surface table. A rule shall be placed in contact with the extremities of the concave side and the maximum gap (e) between the edge and the rule shall be measured.

4.4 Deviation from the shearing line due to internal stresses

4.4.1 Test specimen

The test specimen shall consist of a sheet or a length of strip, the size of which is defined in the product standard.

4.4.2 Measuring procedure

The test specimen shall be split along the longitudinal axis. The two parts, neither of which shall be turned over, shall be weighted so that they remain flat. The two cut edges shall then be brought together again so as to give the smallest gap. The maximum distance (c) between the two cut edges shall be measured.

4.5 Burr height

4.5.1 Test specimen

The test specimen shall consist of a sheet or a length of strip, the size of which is defined in the product standard. The effective length for the measurement shall be 1 m.

4.5.2 Measuring procedure

The burr height shall be determined by using a linear measuring device such as a comparator.

The device shall have the following characteristics :

- resolution : 1 μm ;
- uncertainty : $\pm 2 \mu\text{m}$;
- axial movement of the sliding anvil shall be obtained without rotation ;
- dimension of the sliding anvil : 16 mm x 8 mm ;
- applied force on the sliding anvil : 4 N \pm 0,2 N.

The test specimen shall be held flat on a surface table. The linear measuring device shall be rigidly fixed on a stand so that the movement of the anvil is perpendicular to the table (see figure 7).

The surface of contact of the sliding anvil shall be parallel to the surface table. The verification of this parallelism can be made using a thickness of the sample. The difference in the distance from any point on the surface of the supporting table shall not exceed 2 μm . A three point adjusting surface table is necessary.

The test shall consist of measuring the thickness of the sheet at 10 mm from the cut edge (h_1) and the thickness of the cut edge (h_2), the sliding anvil having its larger dimension (16 mm) parallel to the cut edge (see figure 8).

A measurement shall be made every 50 mm, by moving the test specimen, the burr height being characterized by the mean value of the 20 measurements and by the indication of the maximum value obtained.

It is permissible to cut the test specimen, into lengths of at least 50 mm or multiples of 50 mm. If this is done, the cuts shall be made so that the burrs are on the same side of the sheet as the burr which is to be measured.

During the measurements, the temperature shall be constant.

5 Test report

The test report, when requested, shall contain the following as appropriate :

- reference to this European Standard ;
- type and designation of the magnetic steel sheet tested ;
- one or more of the following, depending on the requirements of the product standard :
 - 1) length (l) of wave in millimetres, to the nearest 10 mm, height (h) of wave in millimetres, to the nearest 1 mm and wave factor (w) in per cent to the nearest 0,1 % ;
 - 2) deviation (a) in millimetres characterizing the residual curvature, to the nearest 1 mm ;
 - 3) variation (c) from the shearing line in millimetres, to the nearest 0,1 mm ;
 - 4) distance (e) in millimetres characterizing the edge camber, to the nearest 0,1 mm ;
 - 5) arithmetic mean value and maximum value of burr height.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN 10251:1998](https://standards.iteh.ai/catalog/standards/sist/26a13c5a-e8e1-42a8-9949-17f955db9fa4/sist-en-10251-1998)

<https://standards.iteh.ai/catalog/standards/sist/26a13c5a-e8e1-42a8-9949-17f955db9fa4/sist-en-10251-1998>