



# SLOVENSKI STANDARD

## SIST EN 10208-1:1998

01-avgust-1998

---

### Jeklene cevi za cevovode za prenos plinastih in tekočih goriv - Tehnični dobavni pogoji - 1. del: Cevi razreda zahtevnosti A

Steel pipes for pipelines for combustible fluids - Technical delivery conditions - Part 1: Pipes of requirement class A

Stahlrohre für Rohrleitungen für brennbare Medien - Technische Lieferbedingungen - Teil 1: Rohre der Anforderungsklasse A

Tubes en acier pour conduites de fluides combustibles - Conditions techniques de livraison - Partie 1: Tubes de la classe de prescription A

<https://standards.iteh.ai/catalog/standards/sist/190bb5ef-87b2-4c11-ae9f-1373af7ab8a0/sist-en-10208-1-1998>

**Ta slovenski standard je istoveten z: EN 10208-1:1997**

---

#### **ICS:**

75.200	Oprema za skladiščenje nafte, naftnih proizvodov in zemeljskega plina	Petroleum products and natural gas handling equipment
77.140.75	Jeklene cevi in cevni profili za posebne namene	Steel pipes and tubes for specific use

**SIST EN 10208-1:1998**

**en**

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[SIST EN 10208-1:1998](#)

<https://standards.iteh.ai/catalog/standards/sist/190bb5ef-87b2-4c11-ae9f-1373afdab8a0/sist-en-10208-1-1998>

EUROPEAN STANDARD

EN 10208-1

NORME EUROPÉENNE

EUROPÄISCHE NORM

November 1997

ICS 23.040.10

Descriptors: metal tubes, steel tubes, welded tubes, pressure pipes, fluid pipelines, fuels, delivery, classifications, designation, manufacturing, chemical composition, mechanical properties, dimensions, dimensional tolerances, tests, inspection, marking

English version

## Steel pipes for pipelines for combustible fluids - Technical delivery conditions - Part 1: Pipes of requirement class A

Tubes en acier pour conduites de fluides combustibles -  
Conditions techniques de livraison - Partie 1: Tubes de la  
classe de prescription A

Stahlrohre für Rohrleitungen für brennbare Medien -  
Technische Lieferbedingungen - Teil 1: Rohre der  
Anforderungsklasse A

This European Standard was approved by CEN on 26 September 1997.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

Central Secretariat: rue de Stassart, 36 B-1050 Brussels

<u>Contents</u>		<u>Page</u>
FOREWORD		4
Introduction		5
1	Scope	6
2	Normative references	6
3	Definitions	10
3.1	General	10
3.2	Types of pipes and welds	10
3.3	Treatment condition	12
3.4	Imperfections and defects	13
3.5	Agreement	13
3.6	Margin symbols	13
4	Classification and designation	13
5	Information to be supplied by the purchaser	14
5.1	Mandatory information	14
5.2	Other information	14
5.3	Example of ordering	16
6	Manufacturing	17
6.1	General	17
6.2	Pipe manufacturing	17
6.3	Heat treatment condition	17
6.4	Sizing	19
6.5	Strip end welds	19
6.6	Jointers	19
7	Requirements	19
7.1	General	19
7.2	Chemical composition	20
7.3	Mechanical and technological properties	21
7.4	Weldability	21
7.5	Surface condition, imperfections and defects	23
7.6	Dimensions, masses and tolerances	24
7.6.1	Dimensions	24
7.6.2	Masses	26
7.6.3	Tolerances on the pipe	26
7.6.4	Finish of pipe ends	29
7.6.5	Tolerances of the weld seam	31
7.6.6	Mass tolerance	34

8	Inspection	34
8.1	Types of inspection and inspection documents	34
8.2	Non-specific and specific inspection and testing	36
8.2.1	Type and frequency of tests	36
8.2.2	Selection and preparation of samples and test pieces	36
8.2.3	Test methods	42
8.2.3.1	Chemical analysis (product analysis)	42
8.2.3.2	Tensile test	43
8.2.3.3	Bend test	44
8.2.3.4	Flattening test	44
8.2.3.5	Macrographic and metallographic examination	44
8.2.3.6	Hydrostatic test	44
8.2.3.7	Visual examination	46
8.2.3.8	Dimensional testing	46
8.2.3.9	Weighing	47
8.2.3.10	Non-destructive testing	47
8.2.4	Retests, sorting and reprocessing	47
9	Marking of the pipes	48
9.1	General marking	48
9.2	Special marking	49
10	Coating for temporary protection	49
Annex A	(informative) Correspondence with API steel grades	50
Annex B	(normative) Specification of welded jointers	51
Annex C	(normative) Treatment of imperfections and 52 defects disclosed by visual examination	
Annex D	(normative) Non-destructive testing	54
Annex E	(informative) Bibliography	62
Annex F	(informative) National A-deviations	63

## Foreword

This European Standard has been prepared by Technical Committee ECISS/TC 29 "Steel tubes and fittings for steel tubes" the secretariat of which is held by UNI.

This European Standard EN 10208-1 has been established by ECISS/TC 29/SC 2 "Steel tubes and fittings for steel tubes - Line pipe" in co-operation with ISO/TC 67/SC 1 "Material and equipment for petroleum and natural gas industries - Line pipe" which is responsible for the International Standard for line pipe ISO 3183-1 [1].

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by May 1998, and conflicting national standards shall be withdrawn at the latest by May 1998.

There are some principal differences between EN 10208-1 and ISO 3183-1 concerning

a) the concept:

This EN 10208-1 covers steel grades of low and medium strength level up to 360 N/mm<sup>2</sup> yield strength in a basic quality (see introduction).

ISO 3183-1 covers the full range of strength levels up to 555 N/mm<sup>2</sup> yield strength and provides, in addition to the general requirements which correspond in this case with those of the main part of ANSI/API 5L [2], for agreement at the time of enquiry and order, a series of supplementary requirements also taken from ANSI/API 5L.

b) formal items:

- normative references (see clause 2);
- this European Standard uses steel numbers in accordance with EN 10027-2 (see tables 2 and 4);
- this European Standard uses the standardized code numbers and terms of EURONORM 168 for the structure and the content of inspection documents.

Annex F contains national A-deviations specifying the restrictions for the application of this European Standard in Sweden.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and the United Kingdom.

## Introduction

In the preparation of this European Standard the competent committee was unanimous in seeking to avoid specifying the quality of line pipe to be used for a particular application. However, the committee recognized that there are several broad quality levels commonly used, and has differentiated between these quality levels as follows:

Firstly, the committee recognized the need to provide a basic quality level broadly similar to that specified in the main part of ANSI/API 5L [2]. This is designated quality level A and considered in this EN 10208-1.

Secondly, many purchasers impose requirements additional to the basic standard, for instance concerning toughness and non-destructive testing. This approach is common, for example, for transmission pipelines. Such enhanced requirements are addressed in requirement class B and considered in EN 10208-2.

Thirdly, there are certain particularly demanding applications where very stringent requirements on quality and testing are imposed. Such requirements are reflected in requirement class C and considered in EN 10208-3.

In this Part 1 of EN 10208 no impact properties are specified. The Charpy energy requirements in EN 10208-2 have been derived from established data in accordance with EPRG recommendations [3] to avoid long running shear fracture in pipelines transporting lean, dry natural gas. It is the responsibility of the designer to decide whether these energy requirements suffice for the intended application. For example, rich gas or two-phase fluids may require enhanced properties.

The selection of the requirement class depends on many factors. The properties of the fluid to be conveyed, the service conditions, design code and any statutory requirements should all be taken into consideration. Therefore this standard gives no detailed guidelines. It is the ultimate responsibility of the user to select the appropriate requirement class for the intended application.

NOTE: This European Standard combines a wide range of product types, dimensions and technical restrictions. In some areas of application, the absence of a single European pipeline design standard has resulted in differing national

regulations imposing conflicting requirements on the users, thus making technical harmonization difficult.

Consequently, it may be necessary to vary certain requirements of this European Standard to satisfy various national design codes. However, this European Standard shall be the basic reference document. Such amendments should be specified at the time of enquiry and order (see clause 5).

## 1 Scope

**1.1** This European Standard EN 10208-1 specifies the technical delivery conditions for unalloyed seamless and welded steel pipes. It includes quality and testing requirements lower than those specified in EN 10208-2 and applies for pipes which are normally used for the distribution of combustible fluids within the maximum allowable operating pressure given in the appropriate design code.

NOTE 1: Pipes according to EN 10208-1 are also applied for water piping in the oil and gas industries.

NOTE 2: This European Standard does not apply for cast steel pipe.

Other parts of this European Standard are:

- EN 10208-2 Steel pipes for pipelines for combustible fluids  
Technical delivery conditions  
Part 2: Pipes of requirement class B
- EN 10208-3 Steel pipes for pipelines for combustible fluids  
Technical delivery conditions  
Part 3: Pipes of requirement class C

**1.2** In addition to the requirements of this European Standard the general technical delivery conditions specified in EN 10021 apply.

## 2 Normative references

This European Standard incorporates by dated or undated reference, provisions from other publications. These normative references are cited at the appropriate places in the text and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of any of these publications apply to this Euro-



pean Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies.

The requirements of this European Standard rule when they differ from those in the standards and documents referred to below:

CR 10260	Designation systems for steel; Additional symbols for steel names (CEN Report)
EN 287-1	Approval testing of welders - Fusion welding - Part 1: Steels
EN 288-1	Specification and approval of welding procedures for metallic materials - Part 1: General rules for fusion welding
EN 288-2	Specification and approval of welding procedures for metallic materials - Part 2: Welding procedure specification for arc welding
EN 473	Qualification and certification of NDT personnel - General principles
EN 910	Welding - Welded butt joints in metallic materials - Bend test
EN 10002-1	Metallic materials - Tensile testing - Part 1: Method of test (at ambient temperature)
EN 10003-1	Metallic materials - Brinell hardness test - Part 1: Test method
EN 10020	Definition and classification of grades of steel
EN 10021	General technical delivery conditions for steel and iron products
EN 10027-1	Designation systems for steel, Part 1: Steel names, principal symbols
EN 10027-2	Designation systems for steel, Part 2: Numerical system
EN 10052	Vocabulary of heat treatment terms for ferrous products

EN 10079	Definition of steel products
EN 10109-1	Metallic materials - Hardness test - Part 1: Rockwell test (scales A, B, C, D, E, F, G, H, K) and Rockwell superficial test (scales 15N, 30N, 45N, 15T, 30T and 45T)
EN 10204	Metallic products - Types of inspection documents (includes amendment A1:1995)
EN 10233	Metallic materials - Tube - Flattening test
EN 10246-1	Non-destructive testing of steel tubes - Part 1: Automatic electromagnetic testing of seamless and welded (except submerged arc-welded) ferromagnetic steel tubes for verification of hydraulic leak-tightness
EN 10246-7	Non-destructive testing of steel tubes - Part 7: Automatic full peripheral ultrasonic testing of seamless and welded (except submerged arc-welded) steel tubes for the detection of longitudinal imperfections
EN ISO 9001	Quality systems - Model for quality assurance in design/development, production, installation and servicing (ISO 9001:1994)
EN ISO 9002	Quality systems - Model for quality assurance in production, installation and servicing (ISO 9002:1994)
ENV 10220	Seamless and welded steel tubes - Dimensions and masses per unit length
EURONORM 168 <sup>1)</sup>	Iron and steel products - Inspection documents - Contents
IC 2 <sup>2)</sup>	Weldable fine-grained structural steels; Recommendations for processing, in particular for welding

<sup>1)</sup> Until this EURONORM is transformed into an European Standard it can either be implemented or the corresponding national standard shall be agreed at the time of enquiry and order.

<sup>2)</sup> Information Circular of the European Committee for Iron and Steel Standardization (ECISS), published by the members of CEN

ISO 1027	Radiographic image quality indicators for non-destructive testing - Principles and identification
ISO 2566-1	Steel - Conversion of elongation values - Part 1: Carbon and low alloy steels
ISO 14284	Steel and iron - Sampling and preparation of samples for the determination of chemical composition
prEN 10246-3 <sup>3)</sup>	Non-destructive testing of steel tubes - Part 3: Automatic eddy current testing of seamless and welded (except submerged arc-welded) steel tubes for the detection of imperfections
prEN 10246-5 <sup>3)</sup>	Non-destructive testing of steel tubes - Part 5: Automatic full peripheral magnetic transducer/flux leakage testing of seamless and welded (except submerged arc-welded) ferromagnetic steel tubes for the detection of longitudinal imperfections
prEN 10246-8 <sup>3)</sup>	Non-destructive testing of steel tubes - Part 8: Automatic ultrasonic testing of the weld seam of electric welded steel tubes for the detection of longitudinal imperfections
prEN 10246-9 <sup>3)</sup>	Non-destructive testing of steel tubes - Part 9: Automatic ultrasonic testing of the weld seam of submerged arc-welded steel tubes for the detection of longitudinal and/or transverse imperfections
prEN 10246-10 <sup>3)</sup>	Non-destructive testing of steel tubes - Part 10: Radiographic testing of the weld seam of submerged arc-welded steel tubes for the detection of imperfections

---

<sup>3)</sup> In preparation; until this document is published as a European Standard a corresponding national standard should be agreed at the time of enquiry and order.

- prEN 10246-17<sup>3)</sup> Non-destructive testing of steel tubes - Part 17: Ultrasonic testing of tube ends of seamless and welded steel tubes for the detection of laminar imperfections
- prEN 10256<sup>3)</sup> Non-destructive testing of steel tubes - Qualification and competence of level 1 and level 2 NDT personnel
- prEN ISO 377<sup>3)</sup> Steel and steel products - Location of samples and test pieces for mechanical testing (ISO/DIS 377:1996)

### 3 Definitions

#### 3.1 General

For the purpose of this European Standard the definitions in 3.2 to 3.4 shall apply when additional to or differing from those given for the

- classification of steels in EN 10020;
- definition of steel products in EN 10079;
- heat treatment in EN 10052 and
- for types of sampling procedures, inspection and inspection documents in prEN ISO 377, EN 10021 and EN 10204.

SIST EN 10208-1:1998

#### 3.2 Types of pipes and welds

<https://standards.iteh.ai/catalog/standards/sist/190bb5ef-87b2-4c11-ae9f-1373afdab8a0/sist-en-10208-1-1998>

##### 3.2.1 Seamless (S) pipe

The tubular product is manufactured in a hot forming process which may be followed by sizing (see 6.4) or cold finishing (see 3.3.4) to produce the desired dimensions.

##### 3.2.2 Welded (W) pipe

###### 3.2.2.1 Electric welded (EW) pipe

The tubular product is manufactured by forming from strip and welding the abutting edges without addition of filler metal. The longitudinal seam is generated by current applied by induction or conduction.

---

<sup>3)</sup> In preparation; until this document is published as a European Standard a corresponding national standard should be agreed at the time of enquiry and order.

### 3.2.2.2 Continuous welded (BW) pipe

The tubular product is manufactured by forming from strip heated in a furnace and mechanically pressing the formed edges together, wherein successive coils of strip had been joined together to provide a continuous flow of steel for the welding mill. (This process implies a type of butt-welding.)

### 3.2.2.3 Submerged arc-welded (SAW) pipe

The tubular product is manufactured by forming from strip or plate and welding the abutting edges by addition of filler metal. The pipe having a longitudinal (SAWL) or helical (SAWH) seam is produced by the automatic submerged arc process (but see also 6.2). At least one pass is made on the inside and at least one pass on the outside of the pipe. An intermittent or continuous single pass tack weld made by the gas metal arc-welding process is permitted.

### 3.2.2.4 Combination gas metal arc and submerged arc-welded (COW) pipe

The tubular product is manufactured by forming from strip or plate and welding the abutting edges by addition of filler metal. The pipe having one longitudinal (COWL) or one helical (COWH) seam is produced by a combination of gas metal arc-welding and submerged arc welding. The gas metal arc-welding process is continuous and first, followed by the automatic submerged arc-welding process with at least one pass on the inside and at least one pass on the outside of the pipe.

### 3.2.3 Strip end weld

A weld that joins strip ends together.

### 3.2.4 Jointer

Two pieces of pipe joined together by a circumferential weld.

### 3.2.5 Pipe body

For welded pipe the entire pipe excluding the weld(s) and heat affected zone(s); for seamless pipe the entire pipe.

### 3.3 Treatment condition

#### 3.3.1 Normalizing forming

A forming process in which the final deformation is carried out within a certain temperature range leading to a material condition equivalent to that obtained after normalizing so that the specified values of the mechanical properties are retained even after normalizing.

The abbreviated form of this delivery condition is N.

#### 3.3.2 Thermomechanical forming

A forming process in which the final deformation is carried out in a certain temperature range leading to a material condition with certain properties which cannot be achieved or repeated by heat treatment alone. Subsequent heating above 580 °C may lower the strength values.

The abbreviated form of this delivery condition is M.

NOTE 1: Thermomechanical forming leading to the delivery condition M may include processes of increased cooling rates without or with tempering including self-tempering but excluding definitively direct quenching and quenching and tempering.

<https://standards.iteh.ai/catalog/standards/sist/190bb5ef-87b2-4c11-ae9f-1373affab8a0/sist-en-10208-1-1998>

NOTE 2: As a consequence of lower carbon content and carbon equivalent values material in the delivery condition M has improved weldability properties.

#### 3.3.3 Quenching and tempering

A heat treatment consisting of quench hardening followed by tempering. Quench hardening implies austenitization followed by cooling, under conditions such that austenite transforms more or less completely into martensite and possibly into bainite. Tempering implies heating to a specific temperature ( $< A_{c1}$ ) one or more times or holding at these temperatures, followed by cooling at an appropriate rate so that the structure is modified and the specified properties are achieved.

The abbreviated form of this delivery condition is Q.

### 3.3.4 Cold forming and cold finishing

In this context cold forming implies a process by which a flat product is formed to a pipe without heating. Cold finishing is a cold working operation (normally cold drawing) with a permanent strain greater than 1,5 %, which differentiates it from sizing operations specified in 6.4.

### 3.4 Imperfections and defects

**3.4.1** Imperfections are irregularities in the wall or on the pipe surfaces detectable by methods described in this European Standard. Imperfections with a size and/or population density that are within the acceptance criteria defined in this European Standard are considered to have no practical implication on the intended use of the product.

**3.4.2** Defects are imperfections with a size and/or population density that are greater than the acceptance criteria defined in this European Standard. Defects are considered to adversely affect or limit the intended use of the product.

### 3.5 Agreement

Unless otherwise indicated "by agreement" means "by agreement between manufacturer and purchaser at the time of enquiry and order".

**ITeH STANDARD PREVIEW**  
**(standards.iteh.ai)**

SIST EN 10208-1:1998  
<https://standards.iteh.ai/catalog/standards/sist/190bb5ef-87b2-4c11-ac9f-1373afdab8a0/sist-en-10208-1-1998>

### 3.6 Margin symbols

The following symbols are used in the margin of pages or tables for indicating optional delivery conditions:

- M Mandatory agreement (see 5.2.a);
- U Unless otherwise agreed left to the discretion of the manufacturer (see 5.2.b);
- O Optional agreement (see 5.2.c).

## 4 Classification and designation

### 4.1 Classification

The steels specified in this European Standard are non-alloy quality steels in accordance with EN 10020.