

---

**Varjene jeklene cevi za tlačne posode - Tehnični dobavni pogoji - 2. del: Električno varjene nelegirane in legirane jeklene cevi s specificiranimi lastnostmi za delo pri povišanih temperaturah**

Welded steel tubes for pressure purposes - Technical delivery conditions - Part 2: Electric welded non-alloy and alloy steel tubes with specified elevated temperature properties

**Geschweißte Stahlrohre für Druckbeanspruchungen - Technische Lieferbedingungen - Teil 2: Elektrisch geschweißte Rohre aus unlegierten und legierten Stählen mit festgelegten Eigenschaften bei erhöhten Temperaturen**

[SIST EN 10217-2:2003](https://standards.iteh.ai/catalog/standards/sist/a9b1ce15-9404-4eb3-b9ed-10217-2:2003)

<https://standards.iteh.ai/catalog/standards/sist/a9b1ce15-9404-4eb3-b9ed-10217-2:2003>

**Tubes soudés en acier pour service sous pression - Conditions techniques de livraison - Partie 2: Tubes soudés électriquement en acier non allié et allié avec caractéristiques spécifiées a température élevée**

**Ta slovenski standard je istoveten z: EN 10217-2:2002**

---

**ICS:**

23.020.30	Tlačne posode, plinske jeklenke	Pressure vessels, gas cylinders
77.140.75	Jeklene cevi in cevni profili za posebne namene	Steel pipes and tubes for specific use

**SIST EN 10217-2:2003**

**en**

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

SIST EN 10217-2:2003

<https://standards.iteh.ai/catalog/standards/sist/a9b1ce15-9404-4eb3-b9ed-fb32376551fa/sist-en-10217-2-2003>

EUROPEAN STANDARD  
NORME EUROPÉENNE  
EUROPÄISCHE NORM

**EN 10217-2**

May 2002

ICS 23.040.10; 77.140.75

English version

**Welded steel tubes for pressure purposes - Technical delivery conditions - Part 2: Electric welded non-alloy and alloy steel tubes with specified elevated temperature properties**

Tubes soudés en acier pour service sous pression -  
Conditions techniques de livraison - Partie 2: Tubes soudés  
électriquement en acier non allié et allié avec  
caractéristiques spécifiées à température élevée

Geschweißte Stahlrohre für Druckbeanspruchungen -  
Technische Lieferbedingungen - Teil 2: Elektrisch  
geschweißte Rohre aus unlegierten und legierten Stählen  
mit festgelegten Eigenschaften bei erhöhten Temperaturen

This European Standard was approved by CEN on 25 April 2002.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Malta, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

**Management Centre: rue de Stassart, 36 B-1050 Brussels**

## Contents

1	SCOPE .....	4
2	NORMATIVE REFERENCES .....	4
3	TERMS AND DEFINITIONS .....	5
4	SYMBOLS.....	5
5	CLASSIFICATION AND DESIGNATION .....	5
5.1	Classification .....	5
5.2	Designation .....	6
6	Information to be supplied by the purchaser .....	6
6.1	Mandatory information.....	6
6.2	Options .....	6
7	Manufacturing process .....	7
7.1	Steelmaking process.....	7
7.2	Deoxidation process .....	7
7.3	Tube manufacture and delivery conditions .....	7
8	requirements.....	8
8.1	General .....	8
8.2	Chemical composition .....	8
8.3	Mechanical properties.....	9
8.4	Appearance and internal soundness .....	12
8.5	Straightness.....	13
8.6	Preparation of ends.....	13
8.7	Dimensions, masses and tolerances .....	13
9	Inspection.....	17
9.1	Types of inspection.....	17
9.2	Inspection documents .....	17
9.3	Summary of inspection and testing .....	18
10	SAMPLING.....	19
10.1	Frequency of tests.....	19
10.2	Preparation of samples and test pieces.....	19
11	Test methods .....	20
11.1	Chemical analysis .....	20
11.2	Tensile test on base material .....	21
11.3	Transverse tensile test on the weld.....	21
11.4	Flattening test.....	21
11.5	Ring tensile test.....	21
11.6	Drift expanding test.....	22
11.7	Ring expanding test .....	22
11.8	Impact test.....	22
11.9	Leak tightness test .....	23
11.10	Dimensional inspection .....	23
11.11	Visual examination .....	24
11.12	Non-Destructive Testing.....	24
11.13	Material identification.....	24
11.14	Retests, sorting and reprocessing .....	24
12	MARKING.....	24
12.1	Marking to be applied.....	24
12.2	Additional marking .....	25
13	PROTECTION .....	25
	Annex ZA (informative).....	26
	Bibliography.....	27

## Foreword

This document (EN 10217-2:2002) has been prepared by Technical Committee ECISS/TC 29, "Steel tubes and fittings for steel tubes", the secretariat of which is held by UNI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by November 2002, and conflicting national standards shall be withdrawn at the latest by November 2002.

This document has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association, and supports essential requirements of EU Directive(s).

For relationship with EU Directive(s), see informative annex ZA, which is an integral part of this document.

Other parts of EN 10217 are:

- Part 1: Non-alloy steel tubes with specified room temperature properties
- Part 3: Alloy fine grain steel tubes.
- Part 4: Electric welded non-alloy steel tubes with specified low temperature properties
- Part 5: Submerged arc welded non-alloy and alloy steel tubes with specified elevated temperature properties.
- Part 6: Submerged arc welded non-alloy steel tubes with specified low temperature properties.
- Part 7: Stainless steel tubes.

ITEH STANDARD PREVIEW  
(standards.iteh.ai)

SIST EN 10217-2:2003

Another European Standard series covering tubes for pressure purposes is:

EN 10216: Seamless steel tubes for pressure purposes.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Malta, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and the United Kingdom.

**EN 10217-2:2002 (E)****1 SCOPE**

This Part of EN 10217 specifies the technical delivery conditions in two test categories of electric welded tubes of circular cross section, with specified elevated temperature properties, made of non-alloy and alloy steel.

**2 NORMATIVE REFERENCES**

This European Standard incorporates by date or undated reference, provisions from other publications. These normative references are cited at the appropriate places in the text and the publications are listed hereafter. For date references, subsequent amendments to or revisions of, any of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies (including amendments).

The requirements of this European Standard rule when they differ from those in the standards and documents referred to below:

EN 10002-1, *Metallic materials - Tensile testing - Part 1 : Method of test (at ambient temperature).*

EN 10002-5, *Metallic materials - Tensile testing - Part 5 : Method of testing at elevated temperature*

EN 10020, *Definitions and classification of grades of steel*

EN 10021, *General technical delivery requirements for steel and iron products*

EN 10027-1, *Designation systems for steels - Part 1 : Steel names, principle symbols.*

EN 10027-2, *Designation systems for steels - Part 2 : Numerical systems.*

EN 10045-1, *Metallic materials - Charpy impact test - Part 1 : Test method*

EN 10052, *Vocabulary of heat treatment terms for ferrous products*

EN 10204, *Metallic products - Types of inspection documents*

ENV 10220, *Seamless and welded steel tubes - Dimensions and masses per unit length*

EN 10233, *Metallic materials - Tubes - Flattening test*

EN 10234, *Metallic materials - Tubes - Drift expanding test*

EN 10236, *Metallic materials - Tubes - Ring expanding test*

EN 10237, *Metallic materials - Tubes - Ring tensile test*

EN 10246-1, *Non-Destructive Testing of steel tubes Part 1 : Automatic electromagnetic testing of seamless and welded (except submerged arc welded) ferromagnetic steel tubes for verification of hydraulic leak-tightness*

EN 10246-3, *Non-Destructive Testing of steel tubes - Part 3 : Automatic eddy current testing of seamless and welded (except submerged arc-welded) steel tubes for the detection of imperfections*

EN 10246-5, *Non-Destructive Testing of steel tubes – Part 5: Automatic full peripheral magnetic transducer/flux leakage testing of seamless and welded (except submerged arc-welded) ferromagnetic steel tubes for the detection of longitudinal imperfections*

EN 10246-6, *Non-Destructive Testing of steel tubes - Part 6 : Automatic full peripheral ultrasonic testing of seamless steel tubes for the detection of transverse imperfections*

EN 10246-7, *Non-Destructive Testing of steel tubes - Part 7 : Automatic full peripheral ultrasonic testing of seamless and welded (except submerged arc welded) steel tubes for the detection of longitudinal imperfections*

EN 10246-8, *Non-Destructive Testing of steel tubes – Part 8: Automatic ultrasonic testing of the weld seam of electric welded tubes for the detection of longitudinal imperfections*

EN 10246-14, *Non-Destructive Testing of steel tubes - Part 7 : Automatic ultrasonic testing of seamless and welded (except submerged arc welded) steel tubes for the detection of laminar imperfections*

EN 10256, *Non-Destructive Testing of steel tubes - Qualification and competence of level 1 and level 2 NDT personnel*

EN ISO 377, *Steel and steel products - Location and preparation of samples and test pieces for mechanical testing (ISO 377:1997)*

EN ISO 2566-1, *Steel - Conversion of elongation values – Part 1: Carbon and low-alloy steels (ISO 2566-1:1984)*

prEN 10266 <sup>1)</sup>, *Steel tubes, fittings and structural hollow sections - Symbols and definition of terms for use in product standards*

prEN 10168 <sup>1)</sup>, *Iron and steel products - Inspection documents - List of information and description*

ISO 14284, *Steel and iron - Sampling and preparation of samples for the determination of chemical composition*

CR 10260, *Designation systems for steel - Additional symbols*

CR 10261, *ECISS Information Circular IC 11 - Iron and steel - Review of available methods of chemical analysis.*

### 3 TERMS AND DEFINITIONS

For the purposes of this Part of EN 10217 the terms and definitions, given in EN 10020, EN 10021, EN 10052, prEN 10266 and the following apply:

#### 3.1

##### test category

classification that indicates the extent and level of inspection and testing.

SIST EN 10217-2:2003

<https://standards.iteh.ai/catalog/standards/sist/a9b1ce15-9404-4eb3-b9ed->

#### 3.2

##### employer

organisation for which a person works on a regular basis.

NOTE The employer may be either the tube manufacturer or supplier or a third party organisation providing Non-Destructive Testing (NDT) services.

### 4 SYMBOLS

For the purposes of this part of EN 10217, the symbols given in prEN 10266 and the following apply:

- C1, C2 category conformity indicators (see clauses 7.3.1 and 7.3.3.)
- TC test category.

1) In preparation; until this document is published as a European standard, a corresponding national standard should be agreed at the time of enquiry and order.

EN 10217-2:2002 (E)

## 5 CLASSIFICATION AND DESIGNATION

### 5.1 Classification

In accordance with the classification system in EN 10020, the steel grades P195GH, P235GH and P265GH are classified as non-alloy quality steels and the steel grade 16Mo3 is classified as an alloy special steel.

### 5.2 Designation

5.2.1 For the tubes covered by this Part of EN 10217 the steel designation consists of:

— the number of this Part of EN 10217;

plus either:

— the steel name in accordance with EN 10027-1 and CR 10260;

or:

— the steel number allocated in accordance with EN 10027-2.

5.2.1 The steel name of non alloy steel grades is designated by:

— the capital letter P for pressure purposes;

— the indication of the specified minimum yield strength at room temperature for thickness less than or equal to 16 mm, expressed in MPa (see Table 4);

— the symbols GH for elevated temperature. [SIST EN 10217-2:2003](https://standards.iteh.ai/catalog/standards/sist/a9b1ce15-9404-4eb3-b9ed-1603-10217-2-2003)

5.2.3 The steel name of alloy steel grade 16Mo3 is designated by the chemical composition (see Table 2).

## 6 Information to be supplied by the purchaser

### 6.1 Mandatory information

The following information shall be supplied by the purchaser at the time of enquiry and order:

- a) the quantity (mass or total length or number);
- b) the term "tube";
- c) the dimensions (outside diameter D and wall thickness T) (see Table 6);
- d) the designation of the steel grade in accordance with this Part of EN 10217 (see 5.2);
- e) the test category for non-alloy steel (see 9.3).

### 6.2 Options

A number of options are specified in this Part of EN 10217 and these are listed below. In the event that the purchaser does not indicate a wish to implement any of these options at the time of enquiry and order, the tubes shall be supplied in accordance with the basic specification (see 6.1).

- 1) Tube manufacturing route (see 7.3.2).
- 2) Restriction on copper and tin content (see Table 2).



- 3) Product analysis (see 8.2.2).
- 4) Impact testing (see 8.3.1).
- 5) Longitudinal impact testing at -10°C for non-alloy steel grades (see 8.3.1).
- 6) Tensile testing at elevated temperature (see 8.3.2).
- 7) Selection of leak-tightness test method (see 8.4.3.1).
- 8) Non-Destructive Testing for test category 2 tubers for the detection of transverse imperfections (see 8.4.3.2).
- 9) Non-Destructive Testing for test category 2 tubes for the detection of laminar imperfections (see 8.4.3.2).
- 10) Special end preparation (see 8.6).
- 11) Exact lengths (see 8.7.3).
- 12) The type of inspection document other than the standard document (see 9.2.1).
- 13) Transverse weld tensile test (see Table 9).
- 14) Test pressure for hydrostatic leak-tightness test (see 11.9.1).
- 15) Wall thickness measurement away from the ends (see 11.10).
- 16) Non-Destructive Testing method for the inspection of the weld seam (see 11.12.1)
- 17) Non-Destructive Testing method for the inspection of the tube body (see 11.12.2)
- 18) Additional marking (see 12.2).
- 19) Protection (see 13).

Examples of an order

500 m of electric welded tube with an outside diameter of 168,3 mm, a wall thickness of 4,5 mm in accordance with EN 10217-2, made of steel grade P265GH, test category 1, with a 3.1.C inspection certificate in accordance with EN 10204:

500 m - Tube - 168,3 x 4,5 - EN 10217-2 - P265GH - TC 1 - Option 12: 3.1.C

## 7 Manufacturing process

### 7.1 Steelmaking process

The steelmaking process is at the discretion of the manufacturer.

### 7.2 Deoxidation process

Steels shall be fully killed.

### 7.3 Tube manufacture and delivery conditions

**7.3.1** All NDT activities shall be carried out by qualified and competent level 1,2 and/or 3 personnel authorised to operate by the employer.

The qualification shall be in accordance with EN 10256 or, at least, an equivalent to it.

**EN 10217-2:2002 (E)**

It is recommended that the level 3 personnel be certified in accordance with EN 473 or, at least, an equivalent to it.

The operating authorisation issued by the employer shall be in accordance with a written procedure.

NDT operations shall be authorised by a level 3 NDT individual approved by the employer.

**NOTE** The definition of level 1,2 and 3 can be found in appropriate Standards, e.g. EN 473 and EN 10256.

For pressure equipment in categories III and IV (of Directive 97/23-EC) the personnel shall be approved by a recognised third-party organisation. Tubes not conforming to this requirement shall be marked "C 2", unless a requirement to mark "C1" (see 7.3.3) applies

**7.3.2** The tubes shall be manufactured by high frequency welding (HFW), minimum frequency 100kHz, by the manufacturing routes specified in Table 1.

Unless Option 1 is specified the manufacturing route is at the discretion of the manufacturer.

**Option 1:** *The manufacturing route is specified by the purchaser.*

The finished tubes shall not include welds used for joining together lengths of strip prior to forming.

**7.3.3** Welding shall be carried out by suitably qualified personnel in accordance with suitable operating procedures.

For pressure equipment in categories II, III, and IV, (of Directive 97/23 EC) the operating procedures and the personnel shall be approved by a competent third-party. Tubes not conforming to this requirement shall be marked "C 1".

**7.3.4** The delivery conditions of tubes covered by this Part of EN 10217 are shown in Table 1.

**Table 1 — Tube manufacturing route and delivery condition**

<https://standards.iteh.ai/catalog/standards/sist/a9b1ce15-9404-4eb3-b9ed-fb32376551fa/sist-en-10217-2-2003>

Route N°	Manufacturing routes		Delivery condition
	Starting material	Forming operation	
1	Normalising rolled strip	Cold formed (+welded)	Normalising weld zone or Normalising (entire tube)
2a	As (hot) rolled or Normalising rolled strip	Cold formed (+welded)	Normalising (entire tube)
2b		Cold formed (+welded) + hot stretch reduced	Normalising (entire tube)
2c		Cold formed (+ welded) + hot stretch reduced at a controlled temperature to give a normalised condition	Normalised rolled

## 8 requirements

### 8.1 General

When supplied in a delivery condition indicated in clause 7.3 and inspected in accordance with clauses 9, 10 and 11, the tubes shall conform to the requirements of this Part of EN 10217.

Tubes shall be suitable for hot and cold bending provided the bending is carried out in an appropriate manner.

In addition, the general technical delivery requirements specified in EN 10021 shall apply.

## 8.2 Chemical composition

### 8.2.1 Cast analysis

The cast analysis reported by the steel producer shall apply and conform to the requirements of Table 2.

**NOTE** When welding tubes produced in accordance with this Part of EN 10217, account should be taken of the fact that the behaviour of the steel during and after welding is dependent not only on the steel, but also on the applied heat treatment and the conditions of preparing for and carrying out the welding.

### 8.2.2 Product analysis

**Option 3:** *Product analysis for the tubes shall be supplied.*

Table 3 specifies the permissible deviations of the product analysis from the specified limits on cast analysis given in Table 2.

## 8.3 Mechanical properties

### 8.3.1 Mechanical properties at and below room temperature

The mechanical properties at and below room temperature of the tubes of this part of EN 10217 shall conform to the requirements in Table 4 and in clauses 11.4, 11.5, 11.6 and 11.7.

### 8.3.2 Proof strength at elevated temperature

The minimum proof strength  $R_{p0,2}$  values at elevated temperature are given in Table 5.

**Option 6:** *Proof strength  $R_{p0,2}$  shall be verified. The test temperature shall be agreed at the time of enquiry and order*

SIST EN 10217-2:2003

<https://standards.iteh.ai/catalog/standards/sist/a9b1ce15-9404-4eb3-b9ed-fb32376551fa/sist-en-10217-2-2003>