

# SLOVENSKI STANDARD **SIST EN 10255:2004**

01-november-2004

# BYY[]fUbY'Y\_`YbY'WYj]'nU'j UfYbY']b'j fYncj UbY'bUj cYj 'Ë'HY\ b] b]'XcVUj b] dc[ c1]

Non-Alloy steel tubes suitable for welding and threading - Technical delivery conditions

Rohre aus unlegiertem Stahl mit Eignung zum Schweißen und Gewindeschneiden -Technische Lieferbedingungen

# iTeh STANDARD PREVIEW

Tubes en acier non allié soudables et filetables - Conditions techniques de livraison

Ta slovenski standard je istoveten z STEN 10255:2004 https://standards.iteh.a/catalog/standards/sist/6988bal8-94

81881371f5e4/sist-en-10255-2004

ICS:

Železne in jeklene cevi 23.040.10 Iron and steel pipes

SIST EN 10255:2004 en

# iTeh STANDARD PREVIEW (standards.iteh.ai)

# SIST EN 10255:2004

https://standards.iteh.ai/catalog/standards/sist/6988baf8-94ae-4d5e-84e9-81881371f5e4/sist-en-10255-2004

# EUROPEAN STANDARD

# NORME EUROPÉENNE

**EUROPÄISCHE NORM** 

August 2004

EN 10255

ICS 23.040.10

#### **English version**

# Non-Alloy steel tubes suitable for welding and threading -Technical delivery conditions

Tubes en acier non allié soudables et filetables - Conditions techniques de livraison

Rohre aus unlegiertem Stahl mit Eignung zum Schweißen und Gewindeschneiden - Technische Lieferbedingungen

This European Standard was approved by CEN on 27 May 2004.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

#### SIST EN 10255:2004

https://standards.iteh.ai/catalog/standards/sist/6988baf8-94ae-4d5e-84e9-81881371f5e4/sist-en-10255-2004



EUROPEAN COMMITTEE FOR STANDARDIZATION COMITÉ EUROPÉEN DE NORMALISATION EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

# **Contents**

		page
Forewo	ord	4
1	Scope	5
2	Normative references	5
3	Terms and definitions	6
4	Classification and designation	6
5 5.1 5.2 5.3 5.3.1 5.3.2	Information to be supplied by the purchaser  Mandatory information  Options  Examples of ordering  By outside diameter and thickness  By thread size and series	6 6 7 7
6 6.1 6.2	Manufacturing process Steelmaking process Tube manufacturing process	
7 7.1 7.2 7.3 7.4	Delivery conditions (Standards.iteh.ai)  General Alternative finishes and protection of the tube ends: 2004 Suitability for hot dip galvanizing hai/catalog/standards/sist/6988ba/8-94ae-4d5e-84e9 Hot dip galvanized condition 81881371f5e4/sist-on-10255-2004	7 7 8
8 8.1 8.2 8.3 8.4	Requirements General Chemical composition and mechanical properties Appearance Dimensions, masses and tolerances	8 8 9
9 9.1 9.2 9.3 9.4 9.5 9.6 9.7	Inspection	11 12 12 12 12
10	Marking	13
11	Temporary protective coating	13
Annex	A (informative) Correlation between specified outside diameter, thread size, and nominal diameter	14
Annex B.1 B.2 B.3	B (normative) Types of tubes with wall thickness different from medium and heavy series  General	15 15
ZA.1	ZA (informative) Clauses of this European Standard addressing the provisions of the EC Construction Products Directive for applications covered by Mandate M 131	17
ZA.2 ZA.3	Procedure of attestation of conformity of pipes  Evaluation of Conformity	

ZA.4	Declaration of Conformity	19
	CE Marking and Labelling	
Riblion	uranhy	21

# iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN 10255:2004

https://standards.iteh.ai/catalog/standards/sist/6988baf8-94ae-4d5e-84e9-81881371f5e4/sist-en-10255-2004

EN 10255:2004 (E)

# **Foreword**

This document (EN 10255:2004) has been prepared by Technical Committee ECISS/TC 29 "Steel tubes and fittings for steel tubes", the secretariat of which is held by UNI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by February 2005, and conflicting national standards shall be withdrawn at the latest by May 2006.

This document has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association, and supports essential requirements of EU Directive(s).

For relationship with EU Directive(s), see informative Annex ZA, which is an integral part of this document.

This European Standard has been derived, with modifications, from ISO 65 "Carbon steel tube suitable for screwing in accordance with ISO 7/1".

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovakia, Slovakia, Sweden, Switzerland and United Kingdom.

(standards.iteh.ai)

<u>SIST EN 10255:2004</u> https://standards.iteh.ai/catalog/standards/sist/6988baf8-94ae-4d5e-84e9-81881371f5e4/sist-en-10255-2004

#### 1 Scope

This document specifies the requirements for circular non-alloy steel tubes suitable for welding and threading and provides a number of options for the finish of tube ends and coatings. This document covers tubes of specified outside diameter 10,2 mm to 165,1 mm (thread size 1/8 to 6) in two series, medium and heavy, and three types of designated thicknesses.

NOTE Tubes manufactured according to this document can be used for the conveyance of fluids as well as for other applications.

#### 2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

The requirements of this European Standard rule when they differ from those in the standards and documents referred to below:

EN 10002-1, Metallic materials: Tensile testing - Part 1: Method of test at ambient temperature

EN 10020, Definition and classification of grades of steel siteh.ai)

EN 10021, General technical delivery requirements for steel and iron products

https://standards.iteh.ai/catalog/standards/sist/6988baf8-94ae-4d5e-84e9-

EN 10027-1, Designation systems for steel Part 15 Steel names, principal symbols

EN 10027-2, Designation systems for steels - Part 2: Numerical system

EN 10204, Metallic products - Types of inspection documents

EN 10232, Metallic materials - Tube (in full section) - Bend test

EN 10233, Metallic materials - Tube - Flattening test

EN 10240, Internal and/or external protective coatings for steel tubes - Specification for hot dip galvanized coatings applied in automatic plants

EN 10241, Steel threaded pipe fittings

EN 10242, Threaded pipe fittings in malleable cast iron

EN 10246-1, Non destructive testing of steel tubes - Part 1: Automatic electromagnetic testing of seamless and welded (except submerged arc welded) ferromagnetic steel tubes for verification of hydraulic leak-tightness

EN 10226-1 Pipe threads where pressure-tight joints are made on the threads - Part 1: Taper external threads and parallel internal threads - Dimensions, tolerances and designation

prEN 10226-2, Pipe threads where pressure-tight joints are made on the threads - Part 2: Taper external threads and taper internal threads - Dimensions, tolerances and designation

EN 10266:2003, Steel tubes, fittings and structural hollow sections - Symbols and definitions of terms for use in product standards

#### EN 10255:2004 (E)

EN ISO 1461, Hot dip galvanized coatings on fabricated iron and steel articles - Specifications and test methods (ISO 1461:1999)

EN ISO 2566-1, Steel - Conversion of elongation values - Part 1: Carbon and low alloy steels (ISO 2566-1:1984)

#### 3 Terms and definitions

For the purposes of this document, the terms and definitions given in EN 10020:2000, EN 10021:1993, EN 10266:2003 and the following apply.

#### 3.1

#### Series and Types

designation used in conjunction with the diameter to define the thickness and the mass per unit length of the tube

#### 3.2

#### Bare tube

tube whose surface is as manufactured without subsequent coating

## 4 Classification and designation

The steel specified in this document is classified as a non-alloy quality steel in accordance with EN 10020.

The steel name S195 T has been established in accordance with EN 10027-1. R

The steel number 1.0026... has been established in accordance with EN 10027-2.

#### SIST EN 10255:2004

## 5 Information to be supplied by the purchaser is/sist/6988baf8-94ae-4d5e-84e9-

81881371f5e4/sist-en-10255-2004

#### 5.1 Mandatory information

The following information shall be supplied by the purchaser at the time of enquiry and order:

- a) Quantity (mass or total length or number of tubes);
- b) Seamless or Welded tube manufacturing process (S or W);
- c) The term "tube";
- d) The number of this European Standard (EN 10255);
- e) Specified outside diameter (D) in millimetres or thread size (R) (see Table 2 or Annex B);
- f) Wall thickness (T) in millimetres or series (M or H) (see Table 2) or type (L or L1 or L2) (see Annex B).

## 5.2 Options

A number of options are specified in this document and these are listed below. In the event that the purchaser does not indicate a wish to implement any of these options at the time of enquiry and order, the tubes shall be supplied in accordance with the basic specification (see 5.1).

- 1) Threaded ends (see 7.2);
- 2) Tube with socket (see 7.2);
- 3) Socket type to be specified (see 7.2);
- 4) Closed ends to prevent ingress of foreign matter (see 7.2);

- 5) Thread varnish or thread protection (see 7.2);
- 6) Suitable for galvanizing to EN ISO 1461, or to EN 10240 coating quality other than A.1 (see 7.3);
- 7) Suitable for galvanizing to EN 10240 coating quality A.1 (see 7.3);
- 8) Hot dip galvanized to EN ISO 1461 (see 7.4);
- 9) Hot dip galvanized to EN 10240, coating quality to be specified (see 7.4);
- 10) Delivery length (see 8.4.10);
- 11) Inspection document type 2.2 (see 9.2);
- 12) Temporary protective coating (see Clause 11).

#### 5.3 Examples of ordering

#### 5.3.1 By outside diameter and thickness

To order 6000 metres of seamless tubes in accordance with EN 10255, with 26.9 mm outside diameter, 2.6 mm wall thickness, galvanized according to EN 10240 - coating quality A.1, threaded.

EXAMPLE 6000 m - S tubes - 26,9 x 2,6 - EN 10255 - Options 1 and 9: A.1.

# iTeh STANDARD PREVIEW

## 5.3.2 By thread size and series

# (standards.iteh.ai)

To order 80 tonnes of welded tubes in accordance with EN 10255, with thread size 2, series medium, in standard length of 6,4 m with caps or plugs fitted to the ends  $_{\rm FN}$   $_{\rm 102552004}$ 

EXAMPLE 80 t – W tubes – 2 – M - EN 10255 - Options 4 and 10: 6.4 m.

#### 6 Manufacturing process

#### 6.1 Steelmaking process

The steelmaking process is at the discretion of the manufacturer. The steel shall be fully killed.

#### 6.2 Tube manufacturing process

The tubes shall be manufactured by a seamless (S) or longitudinally welded (W) process, as specified (see 5.1 b).

Cold formed tubes of Type L shall be heat treated (see B.2). The other series and types of tubes may be heat treated at the discretion of the manufacturer

Tubes shall not include welds used to join lengths of strip prior to forming the tube.

#### 7 Delivery conditions

#### 7.1 General

Unless otherwise specified (see 7.2 to 7.4) the tubes shall be supplied bare with plain ends. The tube ends shall be cut nominally square to the axis of the tube and shall be free from excessive burrs.

### 7.2 Alternative finishes and protection of the tube ends

Alternative types of end finish may be obtained by selecting from the following options:

- Option 1: Tube ends shall be supplied with external taper threads in accordance with EN 10226-1 / EN 10226-2.
- **Option 2:** Tube shall be supplied with one socket per tube. The socket shall be in accordance with EN 10241 or EN 10242 and unless Option 3 is requested the choice of standard and the socket type shall be at the discretion of the manufacturer. The purchaser shall be informed to which standard and of which type of socket is to be supplied.
- **Option 3:** The purchaser shall specify the standard, and which type of socket is to be supplied in accordance with Option 2.
- NOTE Purchasers who require tubes to be threaded and supplied with a socket should specify either Options 1 and 2 or Options 1 and 3.

Protection, to prevent ingress of foreign matter or physical damage or rusting of the threads, may be obtained by selecting from the following options:

- **Option 4:** One cap or plug fitted to each tube end to prevent ingress of foreign matter; the type is at the discretion of the manufacturer.
- **Option 5:** The tube shall be supplied with the thread varnished or with thread protection. The type of protection is at the discretion of the manufacturer.

#### 7.3 Suitability for hot dip galvanizing

- Option 6: The tubes shall be suitable for galvanizing to EN ISO 1461 or to EN 10240 coating quality A.2, A.3, B.1, B.2 or B.3.

  iTeh STANDARD PREVIEW
- **Option 7:** The tubes shall be suitable for galvanizing to EN 10240 coating quality A.1 (see 8.4.9). (Standards.iteh.al)

#### 7.4 Hot dip galvanized condition

SIST EN 10255:2004

- Option 8: The tubes shall be supplied galvanized according to EN ISO 1464 e-4d5e-84e9-81881371f5e4/sist-en-10255-2004
- **Option 9:** The tubes shall be supplied galvanized according to EN 10240; the coating quality shall be specified by the purchaser at the time of enquiry and order.

#### 8 Requirements

#### 8.1 General

The tubes when inspected in accordance with Clause 9 shall conform to the requirements of this document.

In addition to the requirements of this document, the general technical delivery requirements specified in EN 10021 shall apply.

# 8.2 Chemical composition and mechanical properties

**8.2.1** The chemical composition and the mechanical properties shall conform to the requirements of Table 1.

Steel Grade		Chemical composition %				Mechanical Properties		
						Upper Yield strength	Tensile strength	Elongation
Steel	Steel	С	Mn	Р	S	R <sub>eH</sub> min.	$R_{m}$	A min.
Name	Number max	max	max	max	max	(MPa)	(MPa)	%
S 195T	1.0026	0,20	1,40	0,035	0,030	195	320 to 520	20

NOTE The steel specified in this document is weldable, however when subsequently welding tubes produced according to this document account should be taken of the fact that the behaviour of the steel during and after welding is dependent not only on the steel but also on the conditions of preparing for and carrying out the welding.

**8.2.2** Tubes shall be suitable for cold bending and threading.

NOTE When bending tubes produced in accordance with this document, appropriate tooling should be correctly used.

#### 8.3 Appearance

# iTeh STANDARD PREVIEW

- **8.3.1** The tubes shall be free from such external and internal surface defects that can be detected by visual examination. (Standards.iten.al)
- **8.3.2** The internal and external surface finish of the tubes shall be typical of the manufacturing process and, where applicable, the heat treatment employed to The finish and surface condition shall be such that any surface imperfections or marks requiring dressing can be identified 1.10255-2004
- **8.3.3** It shall be permissible to dress, only by grinding or machining, surface imperfections provided that, after doing so, the tube thickness in the dressed area is not less than the specified minimum wall thickness. All dressed areas shall blend smoothly into the contour of the tube.
- **8.3.4** Surface imperfections which encroach on the specified minimum wall thickness shall be considered defects and tubes containing these shall be deemed not to conform to this document.

#### 8.4 Dimensions, masses and tolerances

**8.4.1** Specified outside diameters (D), wall thicknesses (T) and masses per unit length Medium and Heavy series tubes are listed in Table 2.