



Designation: F 22 – 02

Standard Test Method for Hydrophobic Surface Films by the Water-Break Test¹

This standard is issued under the fixed designation F 22; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers the detection of the presence of hydrophobic (nonwetting) films on surfaces and the presence of hydrophobic organic materials in processing ambients. When properly conducted, the test will enable detection of molecular layers of hydrophobic organic contaminants. On very rough or porous surfaces, the sensitivity of the test may be significantly decreased.

1.2 The values stated in SI units are to be regarded as the standard. The inch-pound values given in parentheses are for information only.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:

D 351 Classification for Natural Muscovite Block Mica and Thins Based on Visual Quality²

3. Terminology

3.1 Definitions:

3.1.1 *hydrophilic*—having a strong affinity for water, wettable.

3.1.2 *hydrophobic*—having little affinity for water, nonwetable.

4. Summary of Test Method

4.1 The water-break test is performed by withdrawing the surface to be tested, in a vertical position, from a container overflowing with water. The interpretation of the test is based upon the pattern of wetting. In the absence of hydrophobic films, the draining water layer will remain as a film over the surface. In areas where hydrophobic materials are present on the surface, the draining water layer will break up into a discontinuous film within one minute.

5. Significance and Use

5.1 The water-break test as described in this test method is nondestructive and may be used for control and evaluation of processes for the removal of hydrophobic contaminants. The test may also be used for the detection and control of hydrophobic contaminants in processing ambients. For this application, a surface free of hydrophobic films is exposed to the ambient and subsequently tested.

6. Interferences

6.1 Loss of sensitivity may result from either of the following factors:

6.1.1 The presence of hydrophilic substances on the surface to be tested, in the test equipment, or in the test materials, or

6.1.2 An unusually rough or porous surface condition.

7. Apparatus

7.1 *Overflow Container*, such as a glass beaker.

7.2 *Low Power Microscope*, (5 to 50 \times) and light source for observation of small piece parts.

8. Reagents and Materials

8.1 *Purity of Reagents*—Reagent grade chemicals shall be used in all tests. Unless otherwise indicated, it is intended that all reagents shall conform to the specifications of the Committee on Analytical Reagents of the American Chemical Society,³ where such specifications are available. Other grades may be used, provided it is first ascertained that the reagent is of sufficiently high purity to permit its use without lessening the accuracy of the determination.

8.2 *Purity of Water*—Deionized or distilled water is preferred. Water of higher ionic content may render the test destructive. The water used must be free of hydrophobic and hydrophilic substances.

NOTE 1—The freedom of the water from hydrophobic and hydrophilic contamination may be determined in accordance with Section 9.

8.3 *Acetone*.

¹ This test method is under the jurisdiction of ASTM Committee E21 on Space Simulation and Applications of Space Technology and is the direct responsibility of Subcommittee E21.05 on Contamination.

Current edition approved Oct. 10, 2002. Published November 2002. Originally published as F22 – 62 T. Last previous edition F22 – 65 (1998).

² *Annual Book of ASTM Standards*, Vol 10.01.

³ *Reagent Chemicals, American Chemical Society Specifications*, American Chemical Society, Washington, DC. For suggestions on the testing of reagents not listed by the American Chemical Society, see *Analar Standards for Laboratory Chemicals*, BDH Ltd., Poole, Dorset, U.K., and the *United States Pharmacopeia and National Formulary*, U.S. Pharmacopeial Convention, Inc. (USPC), Rockville, MD.