



SLOVENSKI STANDARD
SIST EN 10245-4:2003

01-november-2003

>Y_`YbUÿjWU]b`ÿ] b]`]nXY_]`È`Cf[Ubg_Y`dfYj`Y_Y`bU`Y_`Yb]`ÿjW]È` ("XY.`G`dc`Yglf]
dfYj`Y`YbUÿjWU]

Steel wire and wire products - Organic coatings on steel wire - Part 4: Polyester coated wire

Stahldraht und Drahterzeugnisse - Organische Beschichtungen auf Stahl-draht - Teil 4: Polyester-beschichteter Draht

Fils et produits tréfilés en acier - Revêtements organiques sur fils - Partie 4 : Fils a revêtement de polyester

STANDARD PREVIEW
(standards.iteh.ai)
<https://standards.iteh.ai/catalog/standards/sist/99ba54cf-32b3-4e68-a1d9-0b5a3efc8303/sist-en-10245-4-2003>

Ta slovenski standard je istoveten z: EN 10245-4:2003

ICS:

25.220.60	Organske prevleke	Organic coatings
77.140.65	Jeklene žice, jeklene vrvi in verige	Steel wire, wire ropes and link chains

SIST EN 10245-4:2003

en

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 10245-4:2003

<https://standards.iteh.ai/catalog/standards/sist/99ba54cf-32b3-4e68-a1d9-0b5a3efc8303/sist-en-10245-4-2003>

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN 10245-4

April 2003

ICS 25.220.60; 77.140.65

English version

Steel wire and wire products - Organic coatings on steel wire - Part 4: Polyester coated wire

Fils et produits tréfilés en acier - Revêtements organiques
sur fils - Partie 4: Fils à revêtement de polyester

Stahldraht und Drahterzeugnisse - Organische
Beschichtungen auf Stahl-draht - Teil 4: Polyester-
beschichteter Draht

This European Standard was approved by CEN on 28 February 2003.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Luxembourg, Malta, Netherlands, Norway, Portugal, Slovakia, Spain, Sweden, Switzerland and United Kingdom.

[SIST EN 10245-4:2003](https://standards.iteh.ai/catalog/standards/sist/99ba54cf-32b3-4e68-a1d9-0b5a3efc8303/sist-en-10245-4-2003)

<https://standards.iteh.ai/catalog/standards/sist/99ba54cf-32b3-4e68-a1d9-0b5a3efc8303/sist-en-10245-4-2003>



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Contents

Foreword.....	3
Introduction	4
1 Scope	5
2 Normative references	5
3 Terms and definitions.....	5
4 Methods of application of polyester coatings	6
5 Requirements and testing methods for polyester coating material	6
5.1 General.....	6
5.2 Composition and method of application	6
5.3 Consistency.....	6
5.4 Density	6
5.5 Hardness.....	7
5.6 Tensile strength	7
5.7 Elongation.....	7
6 Requirements and test methods for polyester coating on wire and wire products	7
6.1 General.....	7
6.2 Appearance.....	7
6.3 Colour.....	7
6.4 Gloss	7
6.5 Thickness.....	8
6.6 Elongation.....	8
6.7 Concentricity	8
6.8 Adherence.....	8
7 Performance requirements and tests for the polyester coating on the finished wire and wire products.....	9
7.1 General.....	9
7.2 Colour stability (accelerated weathering)	9
7.3 Kesternich test	9
7.4 Boiling water test	9
8 Retests	9
9 Inspection and quality assurance	10
Bibliography	11

Foreword

This document (EN 10245-4:2003) has been prepared by Technical Committee ECISS/TC 30 "Steel wire", the secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by October 2003, and conflicting national standards shall be withdrawn at the latest by October 2003.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Luxembourg, Malta, Netherlands, Norway, Portugal, Slovakia, Spain, Sweden, Switzerland and the United Kingdom.

iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN 10245-4:2003

<https://standards.iteh.ai/catalog/standards/sist/99ba54cf-32b3-4e68-a1d9-0b5a3efc8303/sist-en-10245-4-2003>

EN 10245-4:2003 (E)**Introduction**

This European Standard for Organic coatings for steel wire is in a number of parts; Part 1 covering the requirements of a general nature and applying also to coatings for which no specific requirements have been established in the subsequent parts of this standard.

The subsequent parts of this standard deal more specifically with clearly defined coatings or groups of coatings. These coatings may have their own particular methods of application and their individual requirements which are specified in these parts of this standard, in other standards or in manufacturers data sheets.

This standard is made up of the following parts:

Part 1: General rules

Part 2: PVC coated wire

Part 3: PE coated wire

Part 4: Polyester coated wire

In writing this series of standards consideration has been given to the nomenclature and transformation of organic materials as applied to steel wire. These organic coating materials may on application to wire and by their integration into the finished wire product change their characteristics and properties.

This standard specifies characteristics and tests not only for the organic coating but also for the coating materials both before and after their application to steel wire and wire products. In addition it specifies the requirements for performance tests and testing methods on organic coating material which have become an integral and permanent part of the finished wire product. Therefore it has proven not to be practical to put all requirements in one clause and all the tests in another one.

To aid continuity and in order to limit complexity following structure has been chosen for this standard.

Clause 5 deals with the characteristics and testing methods of organic coating material as supplied by the manufacturer for the purpose of its application to the wire. Tests described in this section are intended to be carried out by the organic coating material manufacturer or the applicator before the coating operation.

Clause 6 relates to the characteristics and testing methods for the "organic coating" when the organic coating material has been applied to and has become an integral part of the finished wire. Consequently tests are intended to be in the main carried out by the coating "applicator".

Clause 7 defines the Performance requirements and testing methods on the "organic coating" of the finished wire. When testing on the finished wire is not possible, tests will be carried out on "coated" panels.

1 Scope

Complementary to EN 10245-1, this document specifies the characteristics and requirements for steel wire and wire products coated with polyester.

It covers both thermoplastic and thermosetting polyester.

2 Normative references

This European Standard incorporates by dated and undated reference, provisions from other publications. The normative references are cited at the appropriate places in the text and the publications are listed hereafter. For date references, subsequent amendments to or revisions of any of the publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies (including amendments).

EN 10021, *General technical delivery requirements for steel and iron products*.

EN 10245-1:2001, *Steel wire and wire products — Organic coatings on steel wire – Part 1: General rules*.

EN ISO 527-3, *Plastics — Determination of tensile properties — Part 3: Test conditions for films and sheets (ISO 527-3:1995)*.

EN ISO 868, *Plastics and ebonite — Determination of indentation hardness by means of a durometer (Shore hardness) (ISO 868:1985)*.

EN ISO 2178, *Non-magnetic coatings on magnetic substrates — Measurement of coating thickness — Magnetic method (ISO 2178:1982)*.

EN ISO 2813, *Paints and varnishes - Determination of specular gloss of non-metallic paint films at 20°, 60° and 85° (ISO 2813:1994, including Technical Corrigendum 1:1997)*.

EN ISO 2815, *Paints and varnishes — Buchholz indentation test (ISO 2815:1973)*.

EN ISO 3231, *Paints and varnishes — Determination of resistance to humid atmospheres containing sulfur dioxide (ISO 3231:1993)*.

EN ISO 3668, *Paints and varnishes — Visual comparison of the colour of paints (ISO 3668:1998)*.

EN ISO 4892-1, *Plastics — Methods of exposure to laboratory light sources – Part 1: General guidance (ISO 4892-1:1999)*.

EN ISO 4892-2, *Plastics — Methods of exposure to laboratory light sources – Part 2: Xenon-arc sources (ISO 4892-2:1994)*.

ISO 1183, *Plastics — Methods for determining the density and relative density of non-cellular plastics*.

ISO 4582, *Plastics – Determination of changes in colour and variations in properties after exposure to daylight under glass, natural weathering or laboratory light sources*.

ISO 7724, *Paints and varnishes - Colorimetry (all parts)*

3 Terms and definitions

For the purposes of this European Standard the terms and definitions given in EN 10245-1:2001 and the following apply.

EN 10245-4:2003 (E)**3.1****polyester**

polyester is an organic material. It is the result of a polycondensation reaction of a polyhydroxy compound with di- or polycarbon acids. There are two main classes of polyester: the linear polyesters and the crosslinked polyesters. Linear polyesters generally are thermoplastic, whereas crosslinked polyester is thermosetting and is hard

3.2**PET**

one of the most commonly used linear polyesters is polyethyleneglycoltereftalate denominated by its abbreviation PET

NOTE PET is only the abbreviation of polyethyleneglycoltereftalate. The designation of other types of polyester by PET is not correct and is to be avoided.

4 Methods of application of polyester coatings

The most commonly used method for polyester coating on wire is by extrusion and for coating of wire products is by powder coating. The coating may be applied directly on the surface of the wire or wire product or after applying a primer. Where appropriate other methods may be used.

5 Requirements and testing methods for polyester coating material**5.1 General**

iTeh STANDARD PREVIEW

Unless otherwise specified the test methods for polyester coating material shall be in accordance with EN 10245-1.

5.2 Composition and method of application

<https://standards.iteh.ai/catalog/standards/sist/99ba54cf-32b3-4e68-a1d9-00b6e0009304/sist-en-10245-4-2003>

The coating material shall be free of lead (Pb), cadmium (Cd) and benzoin. Other requirements for the composition shall be agreed between manufacturer and applicator and shall take account of this method of application. However, the polyester coating material shall fulfil the requirements of this standard. The processing of the polyester coating material shall be at the manufacturer's discretion.

The requirements for the polyester intended for extrusion are those for PET. For other coating material other requirements may be agreed between the parties.

5.3 Consistency

The manufacturer shall ensure that the organic coating material composition and its characteristics shall remain constant from batch to batch and unchanged from that as agreed at the time of inquiry and ordering.

The manufacturer shall immediately notify the applicator of any subsequent change in the type and quantity of the constituent parts of the composition once this has been agreed between the two parties.

At the request of the specifier or purchaser the presence of certain elements may be limited. In any case, the compound composition shall be cadmium free.

5.4 Density

Unless otherwise agreed between the applicator and the coating material supplier the density of the coating material, when tested in accordance with ISO 1183, shall be in accordance with Table 1.

Where the apparent density of the supplied powder is specified, requirements and test methods shall be agreed between the parties.

5.5 Hardness

When measured in accordance with EN ISO 868 the Shore hardness D shall be in accordance with Table 1. If so agreed between the parties the Bucholtz hardness, when measured in accordance with EN ISO 2815, shall be in accordance with Table 1.

5.6 Tensile strength

When tested in accordance with EN ISO 527-3 the minimum tensile strength shall be in accordance with Table 1.

5.7 Elongation

When tested in accordance with EN ISO 527-3 the elongation shall be in accordance with Table 1.

Table 1 — Requirements and tests for the coating material

Characteristics	Requirements for		Test method
	thermoplastics materials	Thermosetting materials	
Density (kg/dm ³)	Neutral, uncoloured: 1,30 – 1,40 ^a	White: 1,50 – 1,70 ± 0,05 ^a Green: 1,45 – 1,65 ± 0,05	ISO 1183
Shore hardness D	Min. 76	not applicable	EN ISO 868
Bucholtz hardness	Not applicable	Min. 90	EN ISO 2815
Tensile strength MPa	Min. 55	not applicable	EN ISO 527-3
Elongation %	Min. 300	> 50	EN ISO 527-3

^a For other colours the density shall be by agreement.

SIST EN 10245-4:2003

<https://standards.iteh.ai/catalog/standards/sist/99ba54cf-32b3-4e68-a1d9-0b5a3efc8303/sist-en-10245-4-2003>

6 Requirements and test methods for polyester coating on wire and wire products

6.1 General

In addition to the general requirements of EN 10245-1, polyester coatings shall satisfy following requirements. The coating requirements are summarized in Table 2.

6.2 Appearance

Following examination by visual inspection with the naked eye, the surface of the polyester coating shall be smooth, shiny, free from irregularities and uniform in colour.

Small dents, not affecting subsequent use and resulting from contact with adjacent turns shall not constitute a cause for rejection.

6.3 Colour

When tested in accordance with the parts of ISO 7724 for colour comparison the polyester coating shall be in accordance with Table 2. When colour difference is evaluated in accordance with EN ISO 3668 the polyester coating shall be in accordance with Table 2.

6.4 Gloss

When tested in accordance with EN ISO 2813 the gloss of the polyester coating shall be in accordance with Table 2.