



Standard Guide for Selection, Design, and Installation of Thermoplastic Water-Pressure Piping Systems¹

This standard is issued under the fixed designation F 645; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This guide is intended for use in the selection, design, and installation of thermoplastic water systems for use outside buildings. For specific projects, a thorough review of this guide is recommended for the purpose of selecting specific materials, methods of joining, system design factor, and any special procedures deemed necessary to assure a satisfactory system.

1.2 It is recommended that governing codes and project specifications be consulted prior to the use of this guide. Nothing in this guide should be construed as recommending practices or systems at variance with governing codes and project specifications.

1.3 *Units*—The values stated in either SI units or inch-pound units are to be regarded separately as standard. Values in parentheses are for informational purposes only. The values in each system may not be exact equivalents, therefore, each system shall be used independently of the other. Combining values for the two systems may result in non-conformance with the standard. The pipe, fittings, and joining materials shall meet the requirements of one or more of the following component product standards listed in 1.3.1 to the extent applicable. Those pipe standards followed by (a) are outside diameter-controlled pipes. Those followed by (b) are inside diameter-controlled pipes.

1.3.1 *For poly(vinyl chloride) (PVC) plastic piping components:*

Title of Specification	ASTM Designation
Poly(Vinyl Chloride) (PVC) Plastic Pipe, Schedules 40, 80 and 120 (a)	D 1785
Poly(Vinyl Chloride) (PVC) Plastic Pipe (SDR-PR) (a)	D 2241
Threaded Poly(Vinyl Chloride) (PVC) Plastic Pipe Fittings, Schedule 80	D 2464
Poly(Vinyl Chloride) (PVC) Plastic Pipe Fittings, Schedule 40	D 2466
Socket-Type Poly(Vinyl Chloride) (PVC) Plastic Pipe Fittings, Schedule 80	D 2467

Solvent Cements for Poly(Vinyl Chloride) (PVC) Plastic Pipe and Fittings	D 2564
Bell-End Poly(Vinyl Chloride) (PVC) Pipe (a)	D 2672
Poly(Vinyl Chloride) (PVC) Plastic Tubing (a)	D 2740
Socket-Type Poly(Vinyl Chloride) (PVC) Plastic Line Couplings	D 3036
Joints for Plastic Pressure Pipes Using Flexible Elastomeric Seals	D 3139
Elastomeric Seals (Gaskets) for Joining Plastic Pipe	F 477
PVC and ABS Injected Solvent Cemented Plastic Pipe Joints	F 545

1.3.2 *For polyethylene (PE) plastic piping components:*

Title of Specification	ASTM Designation
Polyethylene (PE) Plastic Pipe, Schedule 40 (b)	D 2104
Polyethylene (PE) Plastic Pipe, (SDR-PR) (b)	D 2239
Polyethylene (PE) Plastic Pipe, Schedules 40 and 80, Based on Outside Diameter (a)	D 2447
Plastic Insert Fittings for Polyethylene (PE) Plastic Pipe	D 2609
Socket-Type Polyethylene Fittings for Outside Diameter-Controlled Polyethylene Pipe (a)	D 2683
Polyethylene (PE) Plastic Tubing (a)	D 2737
Polyethylene (PE) Plastic Pipe (SDR-PR) Based on Controlled Outside Diameter (a)	D 3035
Butt Heat Fusion Polyethylene (PE) Plastic Fittings for Polyethylene (PE) Plastic Pipe and Tubing	D 3261

1.3.3 *For poly(vinyl chloride) (PVC) and polyethylene (PE) Plastic Piping Components Issued By the American Water Works Association:*

C900 Poly(Vinyl Chloride) (PVC) Pressure Pipe, 4-inch through 12-inch, for Water (a)
C901 Polyethylene (PE) Pressure Pipe, Tubing and Fittings, ½-inch through 3-inch, for Water

1.3.4 Pipes with wall thicknesses less than 1.50 mm (0.06 in.) are not recommended.

1.4 *Other Joining Devices*—Joining devices other than those covered by the listed standards may be selected by the user on the basis of his own engineering evaluation and service experience.

1.5 *This standard does not purport to address all of the safety problems, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

¹ This guide is under the jurisdiction of ASTM Committee F17 on Plastic Piping Systems and is the direct responsibility of Subcommittee F17.61 on Water Systems. Current edition approved Sept. 10, 2002. Published November 2002. Originally published as F 645 – 80. Last previous edition F 645 – 95.

2. Referenced Documents

2.1 ASTM Standards:

- D 1600 Terminology for Abbreviated Terms Relating to Plastics²
- D 1785 Specification for Poly(Vinyl Chloride) (PVC) Plastic Pipe, Schedules 40, 80, and 120³
- D 2104 Specification for Polyethylene (PE) Plastic Pipe, Schedule 40³
- D 2239 Specification for Polyethylene (PE) Plastic Pipe (SIDR-PR) Based on Controlled Inside Diameter³
- D 2241 Specification for Poly(Vinyl Chloride) (PVC) Pressure-Rated Pipe (SDR Series)³
- D 2447 Specification for Polyethylene (PE) Plastic Pipe, Schedules 40 and 80 Based on Outside Diameter³
- D 2464 Specification for Threaded Poly(Vinyl Chloride) (PVC) Plastic Pipe Fittings, Schedule 80³
- D 2466 Specification for Poly(Vinyl Chloride) (PVC) Plastic Pipe Fittings, Schedule 40³
- D 2467 Specification for Socket-Type Poly(Vinyl Chloride) (PVC) Plastic Pipe Fittings, Schedule 80³
- D 2564 Specification for Solvent Cements for Poly(Vinyl Chloride) (PVC) Plastic Piping Systems³
- D 2672 Specification for Joints for IPS PVC Pipe Using Solvent Cement³
- D 2737 Specification for Polyethylene (PE) Plastic Tubing³
- D 2740 Specification for Poly(Vinyl Chloride) (PVC) Plastic Tubing³
- D 2749 Symbols for Dimensions of Plastic Pipe Fittings³
- D 2774 Practice for Underground Installation of Thermoplastic Pressure Piping³
- D 2855 Practice for Making Solvent-Cemented Joints With Poly(Vinyl Chloride) (PVC) Pipe and Fittings³
- D 3035 Specification for Polyethylene (PE) Plastic Pipe (SDR-PR) Based on Controlled Outside Diameter³
- D 3139 Specification for Joints for Plastic Pressure Pipes Using Flexible Elastomeric Seals³
- F 412 Terminology Relating to Plastic Piping Systems³
- F 477 Specification for Elastomeric Seals (Gaskets) for Joining Plastic Pipe³
- F 545 Specification for PVC and ABS Injected Solvent Cemented Plastic Pipe Joints³
- F 1498 Specification for Pipe Threads 60°³

2.2 American Water Works Association Standards⁴:

- C 651 Disinfecting Water Mains
- C 900 Poly(Vinyl Chloride) (PVC) Pressure Pipe, 4-Inch Through 12-Inch, for Water
- C 901 Polyethylene (PE) Pressure Pipe, Tubing and Fittings, 1/2-Inch Through 3-Inch, for Water

2.3 Plastics Pipe Institute Report:

- PPI-TR 4 HDB/SDB/PDB/MRS Listed Materials⁵

2.4 NSF Standards:

ANSI/NSF 14 for Plastic Piping Components and Related Materials⁶

ANSI/NSF61 for Drinking Water Systems Components—Health Effects⁶

3. Terminology

3.1 Definitions are in accordance with Terminology F 412 and abbreviations are in accordance with Terminology D 1600 and Symbols unless otherwise specified.

3.2 *relation between standard dimension ratio, hydrostatic design stress, and pressure rating*—the following expression is used in this guide to relate standard dimension ratio, hydrostatic design stress, and pressure rating:

$$2S/P = R - 1 \text{ or } 2 S/P = (D/t) - 1 \quad (1)$$

where:

S = hydrostatic design stress, MPa (or psi),

P = pressure rating, MPa (or psi),

D = average outside diameter, mm (or in.),

t = minimum wall thickness, mm (or in.), and

R = standard thermoplastic pipe dimension ratio also known as SDR or SIDR, whichever is applicable.

d = average inside diameter, mm (or in.)—substitute d for D in equations and change minus sign to plus.

4. Significance and Use

4.1 The requirements of this specification are intended to provide information to select, design and install thermoplastic, water-pressure piping systems for use outside buildings. Materials covered in this specification are Poly(Vinyl Chloride) (PVC) and Polyethylene (PE) plastic pipe fittings.

5. System Pressure Design

5.1 The maximum pressure ratings in Tables 1-9 make allowance for normal operating conditions, reasonable installation procedures, good handling, good jointing workmanship, operating temperatures below 27°C (80°F), and surges likely to be encountered at water flow velocities up to 5 ft/s (1.5 m/s). Tubing Sizes with pressure ratings less than 160 psi are listed in the tables. (Note 1).

NOTE 1—See Marking section and appendix of applicable pipe specification for marking pipe with pressure ratings lower than the maximum values given in Tables 1-9.

5.2 The maximum safe water velocity in a thermoplastic piping system depends on the specific details of the system and the operating conditions. In general, 5 ft/s (1.5 m/s) is considered to be safe. Higher velocities may be used in cases where the operating conditions can be controlled or a higher design factor than 2.0 is used, or both. The total pressure in the system at any time (operating plus surge or water hammer) due to surges or water hammers shall not exceed 150 % of the pressure rating of the system.

5.3 The maximum pressure ratings in Tables 1-9 make some allowance for surge and water hammer. However, when

² Annual Book of ASTM Standards, Vol 08.01.

³ Annual Book of ASTM Standards, Vol 08.04.

⁴ Available from American Water Works Association (AWWA), 1401 New York Ave., NW, Suite 640, Washington, DC 20005.

⁵ Available from Plastics Pipe Institute, 355 Lexington Ave., New York, NY 10017.

⁶ Available from NSF International, P.O. Box 130140, Ann Arbor, MI 48113-0140.

TABLE 1 Maximum Water Pressure Ratings at 23°C (73°F) for Schedule 40 PVC Plastic Pipe (Specification D 1785)

Nominal Pipe Size, in.	PVC 1120 PVC 1220 PVC 2120	Pressure Rating, psi ^A		
		PVC 2116	PVC 2110	PVC 2112
½	600	480	300	370
¾	480	390	240	300
1	450	360	220	280
1¼	370	290	180	230
1½	330	260	170	210
2	280	220	140	170
2½	300	240	150	190
3	260	210	130	160
3½	240	190	120	150
4	220	180	110	140
5	190	160	100	120
6	180	140	90	110
8	160	120	80	100
10	140	110	NPR ^B	90
12	130	110	NPR	80

^A These maximum pressure ratings apply only to unthreaded pipe. The industry recommends against the use of threaded PVC plastic pipe in Schedule 40 wall thickness in nominal pipe sizes 6 in. and smaller. See applicable ASTM standard for code designation, for example, PVC 1120. Pipe with pressure ratings less than 0.34 MPa (50 psi) is not recommended for use in pressure systems.

^B NPR = not pressure rated.

excessive surges and water hammer are likely to be encountered, extra allowance should be made or protective devices installed. The surge or water hammer resulting from rapid flow stoppage may be calculated by means of the following equation:

$$p = V \sqrt{\frac{4700}{\left(1 + \frac{300\,000d}{Et}\right)}} \quad (2)$$

where:

- p = peak water surge pressure, psi,
- E = modulus of elasticity of the pipe material, psi,
- d = inside diameter of the pipe, inclusive, in.,
- t = wall thickness, in., and
- V = water velocity, ft/s.

5.4 The pressure rating of properly solvent-cemented joints is the same as the pipe joined after reasonable time for cure of the joint. The pressure rating of well-made heat-fused joints is the same as the pipe joined, after the material in the joint has cooled to the pipe temperature.

5.5 PVC threaded pipe shall be pressure rated at 50 % of that of nonthreaded pipe (see Specification F 1498). Pipe with wall thicknesses less than those of Schedule 80 pipe shall not be threaded. PE pipe shall not be threaded.

5.6 Joints and the allied fittings made by means other than those covered above shall be pressure-rated by engineering evaluations and service experience by either the design engineer or user, or both. The recommendations of the manufacturers should also be considered (see Specification D 3139).

5.7 Allowance shall be made for operating conditions in which the water will be above 27°C (80°F) under normal service conditions. Hydrostatic design stresses for thermoplastic pipe materials are given in PPI-TR4, Recommended Hydrostatic Strengths and Design Stresses for Thermoplastic Pipe and Fittings Compounds, a report issued at intervals by the Plastics Pipe Institute.

5.8 In piping system design the selection of a design or safety factor depends on the operating conditions that will be encountered. It may be necessary to use pressure ratings lower than the pressure ratings listed in Tables 1-9 when the following are likely to be encountered: (1) surges or water hammer, (2) cyclic pressure oscillations, (3) air pockets, (4) quick-closing valves, (5) pumps with more capacity than the lines can deliver, (6) flow velocities more than 5 ft/s, and (7) similar factors or combinations of (1) through (6). This will result in using pipe and fittings with heavier walls. Consult manufacturers for specific recommendations. Operating temperatures above 23°C (73°F) will make the pipe more flexible and will lower both the short-term and long-term hydrostatic strengths; for a temperature of 38°C (100°F) a pressure rating of 80 % of the 23°C (73°F) values has been found to be adequate for most thermoplastic piping materials covered in current ASTM standards. The designer of the piping system shall use any additional design (safety) factors that are deemed necessary to cover any unusual or special conditions that may be encountered on a specific job. When long-term factors are translated to short-term pressure loadings, the corresponding short-term factors are 2 to 4 times greater, depending on the kind and type of plastic; for example, a 2.0 long-term factor for PVC 1120 gives a 4.0 short-term factor; a 2.0 long-term factor for PE 3306 gives a 5.0 short-term factor.

5.9 Pressure surges may adversely affect the long-term performance of system components and shall be kept to the absolute minimum practical. Where surges are anticipated due to the action of pressure regulating valves, pumps, and other operating equipment, the manufacturer shall be consulted for recommendations.

6. Joints and Connections

6.1 Plastic pipe, tubing, and fittings may be joined by the solvent-cement method, heat-fusion method, threading, elastomeric seals, or by means of other mechanical devices. Consult applicable ASTM practices. The method used shall be compatible with the materials being joined. The recommendations of the manufacturer shall be taken into consideration when determining which method and the details of the procedure to be used.

6.2 Joint Requirements:

6.2.1 Solvent-cement joints and heat-fusion joints shall be made in accordance with qualified procedures that have been established and proven by test to produce water-tight joints at least as strong as the pipe or tubing being joined.

6.2.2 Solvent-cement or heat-fusion joints shall not be made between different kinds of plastics.

6.2.3 Heat-fusion or mechanical joints shall be used when joining polyethylene pipe, tubing, or fittings.

6.2.4 Solvent-cement joints may be made between PVC pipe and PVC fittings.

6.2.5 Flanges or special joints may be used, provided that they are properly qualified and utilized by the design engineer or user, or both.

6.3 Solvent-Cement Joints:

6.3.1 Square-cut ends free of burrs are required for a proper socket joint.

TABLE 2 Maximum Water Pressure Ratings at 23°C (73°F) for Schedule 80 PVC Plastic Pipe (Specification D 1785)

Nominal Pipe Size in.	Pressure Rating, psi ^A							
	PVC 1120, PVC 1220 and PVC 2120		PVC 2116		PVC 2110		PVC 2112	
	Unthreaded	Threaded	Unthreaded	Threaded	Unthreaded	Threaded	Unthreaded	Threaded
1/4	850	420	680	340	420	210	530	260
3/4	690	340	550	280	340	170	430	210
1	630	320	500	250	320	160	390	200
1 1/4	520	260	420	210	260	130	320	160
1 1/2	470	240	380	190	240	120	290	150
2	400	200	320	160	200	100	250	130
2 1/2	420	210	340	170	210	110	260	130
3	370	190	300	150	190	90	230	120
3 1/2	350	170	280	140	170	90	220	110
4	320	160	260	130	160	80	200	100
5	290	140	230	120	140	NPR ^B	180	90
6	280	140	220	110	140	NPR	170	90
8	250	120	200	100	120	NPR	150	80
10	230	120	190	90	120	NPR	150	NPR
12	230	110	180	90	110	NPR	140	NPR

^A See applicable ASTM standard for code designation, for example, PVC 1120. Pressure ratings are lower at elevated temperatures. Pipe with pressure ratings less than 0.34 MPa (50 psi) is not recommended for use in pressure systems.

^B NPR, not pressure rated.

TABLE 3 Maximum Water Pressure Ratings at 23°C (73°F) for Schedule 120 PVC Plastic Pipe (Specification D 1785)

Nominal Pipe Size,	Pressure Rating, psi ^A							
	PVC 1120, PVC 1220 PVC 2120		PVC 2116		PVC 2110		PVC 2112	
	Unthreaded	Threaded	Unthreaded	Threaded	Unthreaded	Threaded	Unthreaded	Threaded
1/2	1010	510	810	410	510	250	630	320
3/4	770	390	620	310	390	190	480	240
1	720	360	570	290	360	180	450	220
1 1/4	600	300	480	240	300	150	370	190
1 1/2	540	270	430	210	270	130	340	170
2	470	240	380	190	240	120	290	150
2 1/2	470	230	370	190	230	120	290	150
3	440	220	360	180	220	110	280	140
3 1/2	380	190	310	150	190	100	240	120
4	430	220	340	170	220	110	270	130
5	400	200	320	160	200	100	250	120
6	370	190	300	150	190	90	230	120
8	380	180	290	140	180	90	230	110
10	370	180	290	140	180	90	230	110
12	340	170	270	140	170	80	210	110

^A See applicable ASTM standard for code designation, for example, PVC 1120. Pressure ratings are lower at elevated temperatures.

6.3.2 Proper fit between the pipe or tubing and mating socket or sleeve is essential to a good joint.

6.3.3 The mating surfaces shall be clean, dry, and free of materials that might be detrimental to the joint.

6.3.4 Solvent cements shall conform to Specification D 2564 or F 545 for making PVC joints.

6.3.5 A uniform coating of the solvent cement is required on both mating surfaces unless otherwise recommended by the manufacturer. Use a primer on PVC pipe. After the joint is made, excess cement shall be wiped from the outside of the joint. This paragraph is not applicable to joints made in accordance with Specification F 545.

6.3.6 The joint shall not be disturbed until it has properly set.

6.3.7 A solvent-cement joint shall not be heated to accelerate the setting of the cement.

6.3.8 For more detail on making PVC solvent-cement joints see Practice D 2855. For more detail on making joints by injecting solvent cement see Specification F 545.

6.4 Heat Fusion Joints:

6.4.1 Sound butt heat-fusion joints require the use of a jointing device that holds the heater element square to the machined ends of the piping, compresses the heated ends together, and holds the piping in proper alignment while the plastic hardens.