



# Standard Specification for Steel Castings, Martensitic Stainless and Alloy, for Pressure-Containing Parts, Suitable for High-Temperature Service<sup>1</sup>

This standard is issued under the fixed designation A 217/A 217M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the Department of Defense.*

## 1. Scope

1.1 This specification<sup>2</sup> covers martensitic stainless steel and alloy steel castings for valves, flanges, fittings, and other pressure-containing parts (Note 1) intended primarily for high-temperature and corrosive service (Note 2).

1.2 One grade of martensitic stainless steel and nine grades of ferritic alloy steel are covered. Selection will depend on design and service conditions, mechanical properties, and the high-temperature and corrosion-resistant characteristics (Note 3).

NOTE 1—Carbon steel castings for pressure-containing parts are covered by Specification A 216/A 216M. Low alloy quench-and-tempered grades equivalent to Specification A 217/A 217M grades may be found in both Specifications A 352/A 352M and A 487/A 487M.

NOTE 2—The grades covered by this specification represent materials that are generally suitable for assembly with other castings or wrought steel parts by fusion welding. It is not intended to imply that these grades possess equal degrees of weldability; therefore, it is the responsibility of the purchaser to establish for himself a suitable welding technique. Since these grades possess varying degrees of suitability for high-temperature and corrosion-resistant service, it is also the responsibility of the purchaser to determine which grade shall be furnished, due consideration being given to the requirements of the applicable construction codes.

NOTE 3—The committee formulating this specification has included nine grades of materials that are considered to represent basic types of ferritic alloy steels suitable for valves, flanges, fittings, and other pressure-containing parts. Additional alloy steels that may better fulfill certain types of service will be considered for inclusion in this specification by the committee as the need becomes apparent.

1.3 The values stated in either inch-pound units or SI units are to be regarded separately as standard. Within the text, the SI units are shown in brackets. The values stated in each system are not exact equivalents; therefore, each system must be used independently of the other. Combining values from the

two systems may result in nonconformance with the specification. Inch-pound units are applicable for material ordered to Specification A 217 and SI units for materials ordered to Specification A 217M.

## 2. Referenced Documents

### 2.1 ASTM Standards:

A 216/A 216M Specification for Steel Castings, Carbon, Suitable for Fusion Welding, for High-Temperature Service<sup>3</sup>

A 352/A 352M Specification for Steel Castings, Ferritic and Martensitic, for Pressure-Containing Parts, Suitable for Low-Temperature Service<sup>3</sup>

A 487/A 487M Specification for Steel Castings Suitable for Pressure Service<sup>3</sup>

A 488/A 488M Practice for Steel Castings, Welding, Qualifications of Procedures and Personnel<sup>3</sup>

A 703/A 703M Specification for Steel Castings, General Requirements, for Pressure-Containing Parts<sup>3</sup>

A 802/A 802M Practice for Steel Castings, Surface Acceptance Standards, Visual Examination<sup>3</sup>

E 165 Test Method for Liquid Penetrant Examination<sup>4</sup>

E 709 Guide for Magnetic Particle Examination<sup>4</sup>

## 3. General Conditions for Delivery

3.1 Material furnished to this specification shall conform to the requirements of Specification A 703/A 703M including any supplementary requirements that are indicated in the purchase order. Failure to comply with the general requirements of Specification A 703/A 703M constitutes nonconformance with this specification. In case of conflict between the requirements of this specification and Specification A 703/A 703M, this specification shall prevail.

## 4. Ordering Information

4.1 The inquiry and order should include or indicate the following:

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel, and Related Alloys and is the direct responsibility of Subcommittee A01.18 on Castings.

Current edition approved Mar. 10, 2002. Published May 2002. Originally published as A 217 – 39 T. Last previous edition A 217/A 217M – 01.

<sup>2</sup> For ASME Boiler and Pressure Vessel Code applications, see related Specification SA-217/SA 217M in Section II of that code.

<sup>3</sup> Annual Book of ASTM Standards, Vol 01.02.

<sup>4</sup> Annual Book of ASTM Standards, Vol 03.03.

4.1.1 A description of the casting by pattern number or drawing (dimensional tolerances shall be included on the casting drawing),

4.1.2 Grade of steel,

4.1.3 Options in the specification, and

4.1.4 The supplementary requirements desired including the standards of acceptance.

**5. Heat Treatment**

5.1 All castings shall receive a heat treatment proper to their design and chemical composition.

5.2 Castings shall be furnished in the normalized and tempered conditions; Grades WC1, WC4, WC5, WC6, and CA15 shall be tempered at 1100°F [595°C] min; Grades WC9, C5, C12, and WC11 shall be tempered at 1250°F [675°C] min; Grade C12A shall be tempered at 1350°F [730°C] min.

5.3 Heat treatment shall be performed after castings have been allowed to cool below the transformation range.

**6. Chemical Composition**

6.1 The steel shall conform to the requirements as to chemical composition prescribed in Table 1 (Note 4).

NOTE 4—The role of alloying elements in the development of Grade C12A has been extensively investigated. V and Cb contribute to precipitation strengthening by forming fine and coherent precipitation of M(C,N)X carbo-nitrides in the ferrite matrix. V also precipitates as VN during tempering or during creep. The two elements are more effective in combination. Therefore, the addition of strong nitride forming elements,

those with a stronger affinity for nitrogen than Cb and V, as deoxidation agents, interferes with these high-temperature strengthening mechanisms.<sup>5</sup>

**7. Tensile Requirements**

7.1 Steel used for the castings shall conform to the requirements as to tensile properties prescribed in Table 2.

**8. Quality**

8.1 The surface of the casting shall be examined visually and shall be free of adhering sand, scale, cracks, and hot tears. Other surface discontinuities shall meet the visual acceptance standards specified in the order. Practice A 802/A 802M or other visual standards may be used to define acceptable surface discontinuities and finish. Unacceptable visual surface discontinuities shall be removed and their removal verified by visual examination of the resultant cavities. When methods involving high temperature are used in the removal of discontinuities, castings shall be preheated to at least the minimum temperatures in Table 3.

8.2 When additional inspection is desired, Supplementary Requirements S4, S5, and S10 may be ordered.

8.3 The castings shall not be peened, plugged, or impregnated to stop leaks.

**9. Repair by Welding**

9.1 Repairs shall be made using procedures and welders qualified under Practice A 488/A 488M.

<sup>5</sup> Viswanathan, R. and Bakker, W. T., *Materials for Ultra Supercritical Fossil Power Plants*, EPRI, Palo Alto, CA: 2000. TR-114750.

**TABLE 1 Chemical Requirements**

NOTE—All values are maximum unless otherwise indicated.

Grade Identification Symbol	Composition, %									
	Carbon Molybdenum	Nickel Chromium Molybdenum	Nickel Chromium Molybdenum	Chromium Molybdenum	Chromium Molybdenum	Chromium Molybdenum	Chromium Molybdenum	Chromium Molybdenum	Chromium Molybdenum Vanadium	Chromium
	WC1	WC4	WC5	WC6	WC9	WC11	C5	C12	C12A (J84090)	CA15
Carbon	0.25	0.05–0.20	0.05–0.20	0.05–0.20	0.05–0.18	0.15–0.21	0.20	0.20	0.08–0.12	0.15
Manganese	0.50–0.80	0.50–0.80	0.40–0.70	0.50–0.80	0.40–0.70	0.50–0.80	0.40–0.70	0.35–0.65	0.30–0.60	1.00
Phosphorus	0.04	0.04	0.04	0.04	0.04	0.020	0.04	0.04	0.030	0.040
Sulfur	0.045	0.045	0.045	0.045	0.045	0.015	0.045	0.045	0.010	0.040
Silicon	0.60	0.60	0.60	0.60	0.60	0.30–0.60	0.75	1.00	0.20–0.50	1.50
Nickel	...	0.70–1.10	0.60–1.00	...	...	...	...	...	0.40	1.00
Chromium	...	0.50–0.80	0.50–0.90	1.00–1.50	2.00–2.75	1.00–1.50	4.00–6.50	8.00–10.00	8.0–9.5	11.5–14.0
Molybdenum	0.45–0.65	0.45–0.65	0.90–1.20	0.45–0.65	0.90–1.20	0.45–0.65	0.45–0.65	0.90–1.20	0.85–1.05	0.50
Columbium	...	...	...	...	...	...	...	...	0.060–0.10	...
Nitrogen	...	...	...	...	...	...	...	...	0.030–0.070	...
	Specified Residual Elements									
Aluminum	...	...	...	...	...	0.01	...	...	0.040	...
Copper	0.50	0.50	0.50	0.50	0.50	0.35	0.50	0.50	...	...
Nickel	0.50	...	...	0.50	0.50	0.50	0.50	0.50	...	...
Chromium	0.35	...	...	...	...	...	...	...	...	...
Tungsten	0.10	0.10	0.10	0.10	0.10	...	0.10	0.10	...	...
Vanadium	...	...	...	...	...	0.03	...	...	0.18–0.25	...
Total content of these residual elements	1.00	0.60	0.60	1.00	1.00	1.00	1.00	1.00	...	...