



Designation: B 775 – 02

# Standard Specification for General Requirements for Nickel and Nickel Alloy Welded Pipe<sup>1</sup>

This standard is issued under the fixed designation B 775; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope

1.1 This specification contains various requirements that, with the exception of Section 5 and Section 10, are mandatory requirements to the following ASTM nickel and nickel alloy, longitudinally welded piping specifications:<sup>2</sup>

Title of Specification	ASTM Designation <sup>2</sup>
Welded UNS N08020, N08024, and N08026 Alloy Pipe	B 464
Welded Nickel-Iron-Chromium Alloy Pipe	B 514
Welded Nickel-Chromium-Iron-Alloy (UNS N06600, UNS N06603, UNS N06025 and UNS N06045) Pipe	B 517
Welded Nickel and Nickel-Cobalt Alloy Pipe	B 619
UNS N08904, UNS N08925, and UNS N08926 Welded Pipe	B 673
UNS N08367 Welded Pipe	B 675
Nickel-Alloy (UNS N06625, N06219, and N08825) Welded Pipe	B 705
Ni-Cr-Mo-Co-W-Fe-Si Alloy (UNS N06333) Welded Pipe	B 723
Welded Nickel (UNS N02200/UNS N02201) and Nickel-Copper Alloy (UNS N04400) Pipe	B 725

1.2 One or more of the test requirements of Section 5 apply only if specifically stated in the product specification or in the purchase order.

1.3 In case of conflict between a requirement of the product specification and a requirement of this general specification, only the requirement of the product specification needs to be satisfied.

1.4 The values stated in inch-pound units are to be regarded as the standard. The values given in parentheses are for information only.

1.5 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to become familiar with all hazards including those identified in the appropriate Material Safety Data Sheet for this product/material as provided by the manufacturer, to establish appropriate safety and health practices, and determine the applicability of regulatory limitations prior to use.*

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee B02 on Nonferrous Metals and Alloys and is the direct responsibility of Subcommittee B02.07 on Refined Nickel and Cobalt and Their Alloys.

Current edition approved Oct. 10, 2002. Published December 2002. Originally published as B 775 – 87. Last previous edition B 775 – 01.

<sup>2</sup> *Annual Book of ASTM Standards*, Vol 02.04.

## 2. Referenced Documents

### 2.1 ASTM Standards:

B 880 Specification for General Requirements for Chemical Check Analysis Limits for Nickel, Nickel Alloys and Cobalt Alloys<sup>2</sup>

E 8 Test Methods for Tension Testing of Metallic Materials<sup>3</sup>

E 18 Test Methods for Rockwell Hardness and Rockwell Superficial Hardness of Metallic Materials<sup>3</sup>

E 29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications<sup>4</sup>

E 39 Test Methods for Chemical Analysis of Nickel<sup>5</sup>

E 76 Test Methods for Chemical Analysis of Nickel-Copper Alloys<sup>6</sup>

E 112 Test Methods for Determining the Average Grain Size<sup>3</sup>

E 213 Practice for Ultrasonic Examination of Metal Pipe and Tubing<sup>7</sup>

E 426 Practice for Electromagnetic (Eddy-Current) Examination of Seamless and Welded Tubular Products, Austenitic Stainless Steel and Similar Alloys<sup>7</sup>

E 571 Practice for Electromagnetic (Eddy-Current) Examination of Nickel and Nickel Alloy Tubular Products<sup>7</sup>

E 1473 Test Methods for Chemical Analysis of Nickel, Cobalt, and High-Temperature Alloys<sup>6</sup>

### 2.2 ANSI Standards:<sup>8</sup>

B 1.20.1 Pipe Threads

B 36.10 Welded and Seamless Wrought Steel Pipe

B 36.19 Stainless Steel Pipe

### 2.3 Other Documents:<sup>9</sup>

ASME Boiler and Pressure Vessel Code, Section IX - Welding and Brazing Qualifications

<sup>3</sup> *Annual Book of ASTM Standards*, Vol 03.01.

<sup>4</sup> *Annual Book of ASTM Standards*, Vol 14.02.

<sup>5</sup> Discontinued; see *1996 Annual Book of ASTM Standards*, Vol 03.05.

<sup>6</sup> *Annual Book of ASTM Standards*, Vol 03.05.

<sup>7</sup> *Annual Book of ASTM Standards*, Vol 03.03.

<sup>8</sup> Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036.

<sup>9</sup> Available from American Society of Mechanical Engineers (ASME), ASME International Headquarters, Three Park Ave., New York, NY 10016-5900.

### 3. Terminology

#### 3.1 Definitions:

3.1.1 *average diameter*—the average of the maximum and minimum outside diameters, as determined at any one cross section of the pipe.

3.1.2 *nominal wall*—a specified wall thickness with a plus or minus tolerance from the specified thickness.

3.1.3 *welded pipe*—a round hollow produced by forming flat stock and joining the single longitudinal seam by welding, and produced to the particular dimensions commercially known as pipe sizes (NPS).

### 4. Chemical Composition

4.1 In case of disagreement, the chemical composition shall be determined in accordance with the following methods:

UNS No. Prefixes	ASTM Method
N02	E 39
N04	E 76
N06, N08	E 1473

4.2 The ladle analysis of the material shall conform to the chemical requirements prescribed by the individual product specification.

4.3 The product (check) analysis of the material shall meet the requirements for the ladle analysis within the tolerance limits prescribed in Specification B 880.

### 5. Test Requirements

#### 5.1 Flattening Test:

5.1.1 A length of pipe not less than 4 in. (102 mm), shall be flattened under a load applied gradually at room temperature until the distance between the platens is five times the wall thickness. The weld shall be positioned 90° from the direction of the applied flattening force.

5.1.2 The flattened specimen shall not exhibit cracks.

5.1.3 Superficial ruptures resulting from surface imperfections shall not be a cause for rejection.

#### 5.2 Transverse Guided-Bend Weld Test:

5.2.1 For welded pipe made with weld filler and at the option of the manufacturer, the transverse guided bend weld test may be substituted in lieu of the flattening test. Two bend test specimens shall be taken transversely from pipe or the test specimens may be taken from a test plate of the same material and heat as the pipe, which is attached to the end of the cylinder and welded as a prolongation of the pipe longitudinal seam. Except as provided in 5.2.2, one shall be subject to a face guided bend test and a second to a root guided bend test. One specimen shall be bent with the inside surface of the pipe against the plunger and the other with the outside surface of the pipe against the plunger. Guided bend test specimens shall be prepared and tested in accordance with Section IX, Part QW, Paragraph QW 160 of the ASME Boiler and Pressure Vessel Code and shall be one of the types shown in QW 463.1 of that code.

5.2.2 For wall thicknesses over 3/8 in. (9.5 mm) but less than 3/4 in. (19 mm) side bend tests may be made instead of the face and root bend tests. For specified wall thicknesses 3/4 in. and over, both specimens shall be subjected to the side bend tests. Side bend specimens shall be bent so that one of the side surfaces becomes the convex surface of the bend specimen.

5.2.3 The bend test shall be acceptable if no cracks or other defects exceeding 1/8 in. (3 mm) in any direction be present in the weld metal or between the weld and the pipe or plate metal after bending. Cracks which originate along the edges of the specimen during testing, and that are less than 1/4 in. (6.5 mm) measured in any direction shall not be considered.

#### 5.3 Pressure (Leak Test):

5.3.1 *Hydrostatic*— Each pipe shall be tested by the manufacturer to an internal hydrostatic pressure of 1000 psi (6.9 MPa) provided that the fiber stress, calculated from the following equation, does not exceed the allowable fiber stress for the material:

$$P = 2St/D \quad (1)$$

where:

$P$  = hydrostatic test pressure, psi (MPa),

$S$  = allowable fiber stress, for material in the condition (temper) furnished as specified in the product specification ( $S$  is calculated as the lower of 2/3 of the specified minimum 0.2 % offset yield strength or 1/4 of the specified minimum ultimate strength for the material),

$t$  = minimum wall thickness permitted, in. (mm), including minus tolerance, if any, and

$D$  = nominal outside diameter of the pipe, in. (mm).

5.3.1.1 The test pressure must be held for a minimum of 5 s.

NOTE 1—Testing at a pressure greater than 1000 psi may be performed upon agreement between the purchaser and manufacturer provided that the allowable fiber stress is not exceeded.

5.3.2 *Pneumatic (Air Underwater Test)*—Each pipe shall be tested at a pressure of 150 psi (1.05 MPa). The test pressure shall be held for a minimum of 5 s. Visual examination is to be made when the material is submerged and under pressure. The full length of pipe must be examined for leaks.

5.3.3 If any pipe shows leaks during hydrostatic or pneumatic testing, it shall be rejected.

#### 5.4 Nondestructive Electric Test:

5.4.1 *Eddy Current Testing*—Testing shall be conducted in accordance with Practices E 426 or E 571. The eddy current examination reference in this specification has the capability of detecting significant discontinuities, especially of the short, abrupt type.

5.4.1.1 Unless otherwise specified by the purchaser, the calibration standard shall contain, at the option of the manufacturer, any one of the following discontinuities to establish a minimum sensitivity level for rejection. The discontinuity shall be placed in the weld if visible.

5.4.1.2 *Drill Hole*—A hole not larger than 0.031 in. (0.79 mm) diameter shall be drilled radially and completely through the wall, care being taken to avoid distortion of the material while drilling.

5.4.1.3 *Transverse Tangential Notch*—Using a round file or tool with a 1/4 in. (6 mm) diameter, a notch shall be filed or milled on the pipe outside diameter tangential to the surface and transverse to the longitudinal axis of the material. Said