

SLOVENSKI STANDARD SIST ISO 4589-2:1997

01-april-1997

Polimerni materiali - Določanje gorljivosti s kisikovim indeksom - 2. del: Preskus pri sobni temperaturi

Plastics -- Determination of burning behaviour by oxygen index -- Part 2: Ambient-temperature test

iTeh STANDARD PREVIEW

Plastiques -- Détermination du comportement au feu au moyen de l'indice d'oxygène --Partie 2: Essai à la température ambiante

SIST ISO 4589-2:1997

Ta slovenski standard je istoveten z de60a/sis/5a2bf8c1-8b15-4c88-b877-

ICS:

13.220.40	Sposobnost vžiga in obnašanje materialov in proizvodov pri gorenju	Ignitability and burning behaviour of materials and products
83.080.01	Polimerni materiali na splošno	Plastics in general

SIST ISO 4589-2:1997

en

SIST ISO 4589-2:1997

iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST ISO 4589-2:1997 https://standards.iteh.ai/catalog/standards/sist/5a2bf8c1-8b15-4c88-b877f25b1aeae60a/sist-iso-4589-2-1997 SIST ISO 4589-2:1997

INTERNATIONAL STANDARD

ISO 4589-2

First edition 1996-07-15

Plastics — Determination of burning behaviour by oxygen index —

Part 2: iTeh S Ambient-temperature test (standards.iteh.ai)

Plastiquesson <u>Détermination</u> du comportement au feu au moyen de https://standards.itel/indice.og/oxygènesist/5a2bf8c1-8b15-4c88-b877iPartie:2:/Essai à la température ambiante



Reference number ISO 4589-2:1996(E)

Page

Contents

1	Scope 1
2	Normative references1
3	Definition 2
4	Principle 2
5	Apparatus 2
6	Calibration of equipment 5
7	Preparation of test specimens
8	Procedure for determination of oxygen index
9	Calculations and expression of results 12
10	Procedure C — Comparison with a specified minimum value of the oxygen index (short procedure) 13
11	Test report iTen STANDARD PREVIEW
Anr	exes (standards.iteh.ai)
Α	Calibration of equipment
В	Calculation of oxygen concentrationrds.iteh.ai/catalog/standards/sist/5a2bfty1-8b15-4c88-b877-
C	Typical test results sheet
D	Results obtained by interlaboratory trials on type VI specimens 20

© ISO 1996

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

International Organization for Standardization Case Postale 56 • CH-1211 Genève 20 • Switzerland

Printed in Switzerland

SIST ISO 4589-2:1997

© ISO

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International iTeh ST Standard requires approval by at least 75 % of the member bodies casting a vote.

> SInternational Standard ISO 4589-2 was prepared by Technical Committee ISO/TC 61, Plastics, Subcommittee SC 4, Burning behaviour.

Together with parts 1 and 3 (see below), this part of ISO 4589 cancels and https://standards.iteh.acjilabos/stsgdard589t/5982t8 f25b1aeae60a/sist-iso-4589-2-19

1007

This revision has been prepared to introduce the following changes relative to the 1984 edition:

- a) to amplify the requirements for equipment calibration (see clause 6 and annex A):
- b) to reduce the permissible deviations for the gas flow rate through the chimney at 40 mm/s from \pm 10 mm/s to \pm 2 mm/s;
- c) to introduce a relatively short procedure, as procedure C, intended for use for comparison purposes, to determine whether or not the oxygen index of a material lies above a specified minimum value;
- d) to introduce a new specimen (form VI) and a corresponding procedure for testing of thin films. Precision data for the new procedure are given in an informative annex.

ISO 4589 consists of the following parts, under the general title Plastics — Determination of burning behaviour by oxygen index:

- Part 1: Guidance
- Part 2: Ambient-temperature test
- Part 3: Elevated-temperature test

Annexes A and B form an integral part of this part of ISO 4589. Annexes C and D are for information only.



iTeh This page intentionally left blank EVIEW (standards.iteh.ai)

SIST ISO 4589-2:1997 https://standards.iteh.ai/catalog/standards/sist/5a2bf8c1-8b15-4c88-b877f25b1aeae60a/sist-iso-4589-2-1997

Plastics — Determination of burning behaviour by oxygen index —

Part 2:

Ambient-temperature test

Scope 1

Results obtained in accordance with this part of This part of ISO 4589 specifies methods for deter-ISO 4589-2 must not be used to describe or appraise mining the minimum concentration of oxygen, in adthe fire hazard presented by a particular material or mixture with nitrogen, that will support combustion S.It shape under actual fire conditions, unless used as one of small vertical test specimens under specified test element of a fire risk assessment that takes into acconditions. The results are defined as oxygen lindex89-2:1 count all of the factors pertinent to the assessment values. https://standards.iteh.ai/catalog/standards/sist/ of the fire hazard of a particular application for the f25b1aeae60a/sist-iso-458material.

Methods are provided for testing materials that are self-supporting in the form of vertical bars or sheet up to 10,5 mm thick. These methods are suitable for solid, laminated or cellular materials characterized by an apparent density greater than 100 kg/m³. The methods may also be applicable to some cellular materials having an apparent density of less than 100 kg/m³. A method is provided for testing flexible sheet or film materials while supported vertically.

For comparative purposes, a procedure is provided for determining whether or not the oxygen index of a material lies above some specified minimum value.

Oxygen index results obtained using the methods described in this part of ISO 4589 can provide a sensitive measure of the burning characteristics of materials under certain controlled laboratory conditions, and hence may be useful for quality control purposes. The results obtained are dependent upon the shape, orientation and isolation of the test specimen and the conditions of ignition. For particular materials or applications, it may be necessary or appropriate to specify different test conditions. Results obtained from test specimens of differing thickness or by using different ignition procedures may not be comparable and no NOTES

fire conditions is implied.

1 It may not be possible to apply these methods satisfactorily to materials that exhibit high levels of shrinkage when heated, e.g. highly oriented thin film.

correlation with flammability behaviour under other

2 For assessing the flame propagation properties of cellular materials of density $< 100 \text{ kg/m}^3$, attention is drawn to the method of ISO 3582:1978, Cellular plastic and cellular rubber materials - Laboratory assessment of horizontal burning characteristics of small specimens subjected to a small flame, for testing horizontal burning characteristics.

2 Normative references

The following standards contain provisions which, through reference in this text, constitute provisions of this part of ISO 4589. At the time of publication, the editions indicated were valid. All standards are subject to revision, and parties to agreements based on this part of ISO 4589 are encouraged to investigate the possibility of applying the most recent editions of the standards indicated below. Members of IEC and ISO maintain registers of currently valid International Standards.

ISO 293:1986, *Plastics — Compression moulding test specimens of thermoplastic materials.*

ISO 294:1995, *Plastics* — *Injection moulding of test specimens of thermoplastic materials.*

ISO 295:1991, *Plastics — Compression moulding of test specimens of thermosetting materials.*

ISO 2818:1994, *Plastics* — *Preparation of test specimens by machining.*

ISO 2859-1:1989, Sampling procedures for inspection by attributes — Part 1: Sampling plans indexed by acceptable quality level (AQL) for lot-by-lot inspection.

ISO 2859-2:1985, Sampling procedures for inspection by attributes — Part 2: Sampling plans indexed by limiting quality (LQ) for isolated lot inspection.

ISO 3167:1993, *Plastics — Multipurpose test specimens.*

3 Definition

For the purposes of this part of ISO 4589, the follow dar ing definition applies.

5 Apparatus

5.1 Test chimney, consisting of a heat-resistant glass tube supported vertically on a base through which oxygen-containing gas mixtures can be introduced (see figures 1 and 2).

The preferred dimensions of the chimney are 450 mm minimum height and 95 mm minimum diameter.

The upper outlet shall be restricted as necessary by an overhead cap having an outlet small enough to produce an exhaust velocity of at least 90 mm/s from that outlet.

NOTE 3 A cap converging to an outlet of 40 mm diameter at a level at least 10 mm above the top of the cylindrical chimney has been found satisfactory.

Chimneys of other dimensions, with or without restricted outlets, may be used, if shown to give equivalent results. The bottom of the chimney, or the base upon which the chimney is supported, shall incorporate a device for distributing evenly the gas mixture entering the chimney. The preferred device comprises a suitable diffuser and a mixing chamber with metal foil. Other devices, such as radial manifolds, may be used, if shown to give equivalent results. A porous

3.1 oxygen index: The minimum sconcentration of osygen constrained below the level of the specoxygen, by volume percentage, in a mixture of oxygenc60a/sitrom fouling the gas entry and distribution paths.

and nitrogen introduced at 23 °C \pm 2 °C that will just support combustion of a material under specified test conditions.

4 Principle

A small test specimen is supported vertically in a mixture of oxygen and nitrogen flowing upwards through a transparent chimney. The upper end of the specimen is ignited and the subsequent burning behaviour of the specimen is observed to compare the period for which burning continues, or the length of specimen burnt, with specified limits for such burning. By testing a series of specimens in different oxygen concentrations, the minimum oxygen concentration is estimated (see 8.6).

Alternatively, for comparison with a specified minimum oxygen index value, three test specimens are tested using the relevant oxygen concentration, at least two of which are required to extinguish before any relevant burning criterion is exceeded. The chimney support may incorporate a levelling device and indicator, to facilitate vertical alignment of the chimney and a test specimen supported therein. A dark background may be provided to facilitate observation of flames within the chimney.

5.2 Test specimen holder, suitable for supporting a specimen vertically in the centre of the chimney.

For self-supporting materials, the specimen shall be held by a small clamp which is at least 15 mm away from the nearest point at which the specimen may burn before the extent-of-burning criterion is exceeded. For supported film or sheet test specimens, the specimen shall be supported by both vertical edges in a frame equivalent to that illustrated by figure 2, with reference marks at 20 mm and 100 mm below the top of the frame.

The profile of the holder and its support should preferably be smooth to minimize induction of turbulence in the rising flow gas.

1

2

3

ISO 4589-2:1996(E)









NOTE — The test specimen is held securely along both upright edges between forks made of stainless steel.

Figure 2 — Support frame for non-self-supporting test specimens

5.3 Gas supplies, comprising pressurized sources of oxygen and/or nitrogen not less than 98 % (*m/m*) pure and/or clean air [containing 20,9 % (*V/V*) oxygen], as appropriate.

The moisture content of the gas mixture entering the chimney shall be < 0,1 % (*m/m*), unless the results have been shown to be insensitive to higher moisture levels in the gas mixture. The gas supply system shall incorporate a drying device, or provision for monitor-

ing or sampling the gas supply for moisture content, unless the moisture content of the gas supplies is known to be acceptable.

The constituent gas supply lines shall be linked in a manner which thoroughly mixes the gases, before they enter the gas distribution device at the base of the chimney, so that the variation in oxygen concentration in the gas mixture rising in the chimney, below the level of the test specimen, is < 0.2 % (*V/V*).

NOTE 4 It should not be assumed that bottled oxygen or nitrogen will always contain < 0,1 % (*m/m*) of water; moisture contents of 0,003 % (*m/m*) to 0,01 % (*m/m*) are typical for commercial supplies as filled bottles of purity \ge 98 % (*m/m*), but as such bottled gases are depressurized to below about 1 MPa, the moisture content of the gas drawn off may rise above 0,1 % (*m/m*).

5.4 Gas measurement and control devices, suitable for measuring the concentration of oxygen in the gas mixture entering the chimney with an accuracy of \pm 0,5 % (*V/V*) of the mixture and for adjusting the concentration with a precision of \pm 0,1 % (*V/V*) of the mixture when the gas velocity through the chimney is 40 mm/s \pm 2 mm/s at 23 °C \pm 2 °C.

Means shall be provided for checking or ensuring that the temperature of the gas mixture entering the chimney is 23 °C \pm 2 °C. If this involves an internal probe, its position and profile shall be designed to minimize induction of turbulence within the chimney.

NOTE 5 Systems of measurement and control that have proved satisfactory include the following:

5.7 Fume extraction system, providing sufficient ventilation or exhaust to remove fumes or soot expelled from the chimney without disrupting the gas flow rate or temperatures in the chimney.

NOTE 6 If soot-generating materials are being tested, the glass chimney may require cleaning to maintain good visibility, and the gas inlets, or inlet screen, and temperature sensor (if fitted) may also require cleaning to function properly. Suitable precautions should be taken to protect personnel from noxious materials or burns during testing or cleaning operations.

5.8 Tool for preparing rolled film, consisting of a stainless-steel rod of 2 mm diameter, with a slit in one end (see figure 3).

6 Calibration of equipment

For compliance with this method, calibrate the equipment periodically in accordance with the instructions given in annex A so that the maximum interval between recalibration and use complies with the periods stated in table 1.

- a) needle valves on individual and mixed gas supply lines, D 7 Preparation of test specimens
 a) paramagnetic oxygen analyser that continuously samples the mixed gas, and a flowmeter to indicate S.119.1-Sampling
 when the gas flow through the chimney is within the required limits;
- b) calibrated orifices, gas pressure regulators and pressure gauges on the individual gas supply lines, lacae60a/sist-iso-458/evanty in accordance with the material specification,
- c) needle valves and calibrated flowmeters on the individual gas supply lines.

Systems b) and c) may require calibration after assembly to ensure that the cumulative errors of the component parts do not exceed the requirements of 5.4.

5.5 Flame igniter, comprising a tube that can be inserted into the chimney to apply to the test specimen a flame issuing from an outlet of $2 \text{ mm} \pm 1 \text{ mm}$ diameter at the end of the tube.

The flame fuel shall be propane, without premixed air. The fuel supply shall be adjusted so that the flame will project 16 mm \pm 4 mm vertically downwards from the outlet when the tube is vertical within the chimney and the flame is burning within the chimney atmosphere.

5.6 Timing device, capable of measuring periods up to 5 min with an accuracy of ± 0.5 s.

otherwise in accordance with ISO 2859-1 or ISO 2859-2, as applicable.

NOTE 7 For a material for which the oxygen index is known to within \pm 2, 15 test specimens may be sufficient. For materials of unknown oxygen index, or which exhibit erratic burning characteristics, between 15 and 30 test specimens may be required.

ltem	Maximum period
Gas system joints (as required by clause A.1 in annex A)	
a) for joints disturbed during use or clean- ing of the apparatus	lmmedi- ately
b) for undisturbed equipment	6 months
Cast PMMA sample	1 month
Gas flow rate controls	6 months
Oxygen concentration controls	6 months

Table 1 — Equipment calibration frequencies