



SLOVENSKI STANDARD

SIST-TS CEN/TS 13130-11:2005

01-april-2005

Materiali in predmeti v stiku z živilom - Plastične snovi, ki so predmet omejitve - Del 11: Določitev 11-aminoundecanojske kisline v živilskih simuliranih snoveh

Materials and articles in contact with foodstuffs - Plastics substances subject to limitation - Part 11: Determination of 11-aminoundecanoic acid in food simulants

iTeh STANDARD PREVIEW

Werkstoffe und Gegenstände (in Kontakt mit Lebensmitteln) - Substanzen in Kunststoffen, die Beschränkungen unterliegen - Teil 11: Bestimmung von 11-Aminoundecansäure in Prüflebensmitteln

[SIST-TS CEN/TS 13130-11:2005](https://standards.iteh.ai/catalog/standards/sist/9dfe078-20b1-4d99-a3ff-54f6f16b0586/sist-ts-cen-ts-13130-11-2005)

[https://standards.iteh.ai/catalog/standards/sist/9dfe078-20b1-4d99-a3ff-](https://standards.iteh.ai/catalog/standards/sist/9dfe078-20b1-4d99-a3ff-54f6f16b0586/sist-ts-cen-ts-13130-11-2005)

[54f6f16b0586/sist-ts-cen-ts-13130-11-2005](https://standards.iteh.ai/catalog/standards/sist/9dfe078-20b1-4d99-a3ff-54f6f16b0586/sist-ts-cen-ts-13130-11-2005)

Matériaux et objets en contact avec les denrées alimentaires - Matières plastiques et substances soumises a des limitations - Partie 11 : Détermination de l'acide 11-aminoundecanoïque dans les simulants d'aliments

Ta slovenski standard je istoveten z: CEN/TS 13130-11:2005

ICS:

67.250 Materiali in predmeti v stiku z živilom Materials and articles in contact with foodstuffs

SIST-TS CEN/TS 13130-11:2005

en,fr,de

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST-TS CEN/TS 13130-11:2005](#)

<https://standards.iteh.ai/catalog/standards/sist/9dfef078-20b1-4d99-a3ff-54ff16b0586/sist-ts-cen-ts-13130-11-2005>

TECHNICAL SPECIFICATION
 SPÉCIFICATION TECHNIQUE
 TECHNISCHE SPEZIFIKATION

CEN/TS 13130-11

February 2005

ICS 67.250

English version

**Materials and articles in contact with foodstuffs - Plastics
 substances subject to limitation - Part 11: Determination of 11-
 aminoundecanoic acid in food simulants**

Matériaux et objets en contact avec les denrées
 alimentaires - Matières plastiques et substances soumises
 à des limitations - Partie 11 : Détermination de l'acide 11-
 aminoundecanoïque dans les simulants d'aliments

Werkstoffe und Gegenstände in Kontakt mit Lebensmitteln
 - Substanzen in Kunststoffen, die Beschränkungen
 unterliegen - Teil 11: Bestimmung von 11-
 Aminoundecansäure in Prüflebensmitteln

This Technical Specification (CEN/TS) was approved by CEN on 16 December 2004 for provisional application.

The period of validity of this CEN/TS is limited initially to three years. After two years the members of CEN will be requested to submit their comments, particularly on the question whether the CEN/TS can be converted into a European Standard.

CEN members are required to announce the existence of this CEN/TS in the same way as for an EN and to make the CEN/TS available promptly at national level in an appropriate form. It is permissible to keep conflicting national standards in force (in parallel to the CEN/TS) until the final decision about the possible conversion of the CEN/TS into an EN is reached.

CEN members are the national standards bodies of Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

<https://standards.cen.eu/catalog/standards/sist/9dfef078-20b1-4d99-a3ff-5486f16b0586/sist-ts-cen-ts-13130-11-2005>



EUROPEAN COMMITTEE FOR STANDARDIZATION
 COMITÉ EUROPÉEN DE NORMALISATION
 EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Contents

	page
Foreword	3
Introduction.....	5
1 Scope	6
2 Normative references	6
3 Principle	6
4 Reagents	7
5 Apparatus	9
6 Samples	9
7 Procedure	11
8 Expression of results	12
9 Confirmation	14
10 Test report	14
Bibliography.....	15

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST-TS CEN/TS 13130-11:2005](https://standards.iteh.ai/catalog/standards/sist/9dfe078-20b1-4d99-a3ff-54f6f16b0586/sist-ts-cen-ts-13130-11-2005)

<https://standards.iteh.ai/catalog/standards/sist/9dfe078-20b1-4d99-a3ff-54f6f16b0586/sist-ts-cen-ts-13130-11-2005>

Foreword

This document (CEN/TS 13130-11:2005) has been prepared by Technical Committee CEN/TC 194 "Utensils in contact with food", the secretariat of which is held by BSI.

This part of EN 13130 has been prepared within the Standards, Measurement and Testing project, MAT1-CT92-0006, "Development of Methods of Analysis for Monomers" and has been prepared by Subcommittee (SC 1) of TC 194 "Utensils in contact with food" as one of a series of test methods for plastics materials and articles in contact with foodstuffs.

This standard is intended to support Directives 2002/72/EC [1], 89/109/EEC [2], 82/711/EEC [3] and its amendments 93/8/EEC [4] and 97/48/EC [5], and 85/572/EEC [6].

At the time of preparation and publication of this part of EN 13130 the European Union legislation relating to plastics materials and articles intended to come into contact with foodstuffs is incomplete. Further Directives and amendments to existing Directives are expected which could change the legislative requirements which this standard supports. It is therefore strongly recommended that users of this standard refer to the latest relevant published Directive(s) before commencement of a test or tests described in this standard.

This part of EN 13130 should be read in conjunction with EN 13130-1.

Further parts of EN 13130, under the general title *Materials and articles in contact with foodstuffs - Plastics substances subject to limitation*, have been prepared, and others are in preparation, concerned with the determination of specific migration from plastics materials into foodstuffs and food simulants and the determination of specific monomers and additives in plastics. The parts of EN 13130 are as follows.

[SIST-TS CEN/TS 13130-11:2005](#)

Part 1: *Guide to test methods for the specific migration of substances from plastics to foods and food simulants and the determination of substances in plastics and the selection of conditions of exposure to food simulants*

Part 2: *Determination of terephthalic acid in food simulants*

Part 3: *Determination of acrylonitrile in food and food simulants*

Part 4: *Determination of 1,3-butadiene in plastics*

Part 5: *Determination of vinylidene chloride in food simulants*

Part 6: *Determination of vinylidene chloride in plastics*

Part 7: *Determination of monoethylene glycol and diethylene glycol in food simulants*

Part 8: *Determination of isocyanates in plastics*

Part 9: *Determination of acetic acid, vinyl ester in food simulants*

Part 10: *Determination of acrylamide in food simulants*

Part 11: *Determination of 11-aminoundecanoic acid in food simulants*

Part 12: *Determination of 1,3-benzenedimethanamine in food simulants*

Part 13: *Determination of 2,2-bis(4-hydroxyphenyl)propane (Bisphenol A) in food simulants*

CEN/TS 13130-11:2005 (E)

Part 14: *Determination of 3,3-bis(3-methyl-4-hydroxyphenyl)-2-indoline in food simulants*

Part 15: *Determination of 1,3-butadiene in food simulants*

Part 16: *Determination of caprolactam and caprolactam salt in food simulants*

Part 17: *Determination of carbonyl chloride in plastics*

Part 18: *Determination of 1,2-dihydroxybenzene, 1,3-dihydroxybenzene, 1,4-dihydroxybenzene, 4,4'-dihydroxybenzophenone and 4,4'-dihydroxybiphenyl in food simulants*

Part 19: *Determination of dimethylaminoethanol in food simulants*

Part 20: *Determination of epichlorohydrin in plastics*

Part 21: *Determination of ethylenediamine and hexamethylenediamine in food simulants*

Part 22: *Determination of ethylene oxide and propylene oxide in plastics*

Part 23: *Determination of formaldehyde and hexamethylenetetramine in food simulants*

Part 24: *Determination of maleic acid and maleic anhydride in food simulants*

Part 25: *Determination of 4-methyl-pentene in food simulants*

Part 26: *Determination of 1-octene and tetrahydrofuran in food simulants*

Part 27: *Determination of 2,4,6-triamino-1,3,5-triazine in food simulants*

Part 28: *Determination of 1,1,1-trimethylolpropane in food simulants*

Parts 1 to 8 are European Standards. Parts 9 to 28 are Technical Specifications.

WARNING All chemicals are hazardous to health to a greater or lesser extent. It is beyond the scope of this Technical Specification to give instructions for the safe handling of all chemicals, that meet, in full, the legal obligations in all countries in which this Technical Specification may be followed. Therefore, specific warnings are not given and users of this Technical Specification should ensure that they meet all the necessary safety requirements in their own country.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to announce this CEN Technical Specification: Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

Introduction

11-aminoundecanoic acid, $C_{11}H_{23}O_2N$, PM/Ref. No 12788 is a monomer used in the manufacture of certain plastics materials and articles intended to come into contact with foodstuffs. After manufacture, residual acrylamide can remain in the polymer and may migrate into foodstuffs coming into contact with that product.

This analytical method should be used in conjunction with EN 13130-1, which describes the procedures to be applied prior to the determination of 11-aminoundecanoic acid in food simulants.

NOTE Although the method is applicable to olive oil, it should be taken into account that 11-aminoundecanoic acid is unstable in olive oil during storage. Therefore the method should only be applied in case of short exposure periods with olive oil. Alternatively iso-octane could be used as a substitute fatty food simulant.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST-TS CEN/TS 13130-11:2005](https://standards.iteh.ai/catalog/standards/sist/9dfef078-20b1-4d99-a3ff-54f6f16b0586/sist-ts-cen-ts-13130-11-2005)

<https://standards.iteh.ai/catalog/standards/sist/9dfef078-20b1-4d99-a3ff-54f6f16b0586/sist-ts-cen-ts-13130-11-2005>

CEN/TS 13130-11:2005 (E)**1 Scope**

This document, part of EN 13130, specifies a method for the determination of 11-aminoundecanoic acid in the food simulants water, 3 % w/v aqueous acetic acid, 15 % v/v aqueous ethanol, olive oil and iso-octane. The level of 11-aminoundecanoic acid determined is expressed as milligrams per kilogram of food simulant.

The method is appropriate for the quantitative determination of 11-amino-undecanoic acid in approximate analyte concentration range of 0,5 mg/kg to 10 mg/kg of food simulants.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 13130-1:2004, *Materials and articles in contact with foodstuffs – Plastics substances subject to limitation – Part 1: Guide to test methods for the specific migration of substances from plastics to foods and food simulants and the determination of substances in plastics and the selection of conditions of exposure to food simulants.*

iTeh STANDARD PREVIEW
(standards.iteh.ai)

3 Principle

The level of 11-aminoundecanoic acid in food simulants is determined by preparing a derivative of 11-aminoundecanoic acid with a fluorescent component. The derivative is subsequently determined by high performance liquid chromatography (HPLC) and fluorescence detection. Quantification is achieved using the calibration curve method.

NOTE A method for confirmation of the presence of 11-aminoundecanoic acid has not yet been established.

4 Reagents

NOTE All reagents should be of recognized analytical quality unless otherwise stated.

4.1 Analyte

11-aminoundecanoic acid, $C_{11}H_{23}O_2N$, molecular weight 201, purity greater than 99 %.

NOTE The monomer is stable for a long period at room temperature if protected from light.

4.2 Chemicals

4.2.1 Acetic acid, glacial

4.2.2 Acetic acid, 96 %

4.2.3 Acetone

4.2.4 di-Sodium tetraborate-10-hydrate, $Na_2B_4O_7 \cdot 10 \cdot H_2O$

4.2.5 Boric acid

4.2.6 Fluorescamine, 4-phenylspiro-[furan 2-(3), 1-phthalan]-3,3-dione

4.2.7 Iso-octane

4.2.8 Methanol

<https://standards.iteh.ai/catalog/standards/sist/9dfe078-20b1-4d99-a3ff-54f6f16b0586/sist-ts-cen-ts-13130-11-2005>

4.2.9 Nitrogen

4.2.10 Phosphoric acid 85 %

4.2.11 Sodium dihydrogen phosphate monohydrate

4.2.12 Sodium hydroxide

4.2.13 Water deionized (HPLC quality)

4.3 Solutions

4.3.1 Stock solution of 11-aminoundecanoic acid in water (1,25 mg/ml)

Weigh to the nearest 0,1 mg approximately 60 mg of 11-aminoundecanoic acid in a 50 ml volumetric flask. Dissolve the 11-aminoundecanoic acid in the smallest possible volume, approximately 1 ml, of 96 % acetic acid (4.2.2) and fill the conical flask up to the mark with water (4.2.13).

Calculate the actual concentration in milligrams 11-aminoundecanoic acid per millilitre of solution.

Repeat the procedure to obtain a second stock solution.