

SLOVENSKI STANDARD SIST-TS CEN/TS 13130-23:2005

01-april-2005

A UhYf]U]']b'dfYXa Yh]'j 'gh]_i 'n'ÿ]j]`]'!'Gbcj]'j 'dc`]a Yfb]\ 'a UhYf]U]\ ž_UhYf]\ _cbWYbhfUV]/U'^Y'ca Y^YbU'!'&' "XY'.'8c`c Yj Ub^Y'Zcfa UXY\]XU']b \ Y_gUa Yh]`YbhYhfUa]bU'j 'a cXY'b]\ 'fUnhcd]bU\ 'nU'ÿ]j]`U

Materials and articles in contact with foodstuffs - Plastics substances subject to limitation - Part 23: Determination of formaldehyde and hexamethylenetetramine in food simulants iTeh STANDARD PREVIEW

Werkstoffe und Gegenstände in Kontakt mit Lebensmitteln - Substanzen in Kunststoffen, die Beschränkungen unterliegen - Teil 23: Bestimmung von Formaldehyd und Hexamethylentetramin in Prüflebensmittelns 13130-23:2005

https://standards.iteh.ai/catalog/standards/sist/cff2740b-d293-424e-8267-0feb97899b4e/sist-ts-cen-ts-13130-23-2005

Matériaux et objets en contact avec les denrées alimentaires - Substances dans les matieres plastiques soumises a des limitations - Partie 23 : Détermination du formaldéhyde et de l'hexaméthylenetétramine dans les simulants d'aliments

Ta slovenski standard je istoveten z: CEN/TS 13130-23:2005

ICS:

67.250 Materiali in predmeti v stiku z Materials and articles in živili contact with foodstuffs

SIST-TS CEN/TS 13130-23:2005

en,fr,de

iTeh STANDARD PREVIEW (standards.iteh.ai)

<u>SIST-TS CEN/TS 13130-23:2005</u> https://standards.iteh.ai/catalog/standards/sist/cff2740b-d293-424e-8267-0feb97899b4e/sist-ts-cen-ts-13130-23-2005

SIST-TS CEN/TS 13130-23:2005

TECHNICAL SPECIFICATION SPÉCIFICATION TECHNIQUE TECHNISCHE SPEZIFIKATION

CEN/TS 13130-23

February 2005

ICS 67.250

English version

Materials and articles in contact with foodstuffs - Plastics substances subject to limitation - Part 23: Determination of formaldehyde and hexamethylenetetramine in food simulants

Matériaux et objets en contact avec les denrées alimentaires - Substances dans les matières plastiques soumises à des limitations - Partie 23 : Détermination du formaldéhyde et de l'hexaméthylènetétramine dans les simulants d'aliments Werkstoffe und Gegenstände in Kontakt mit Lebensmitteln - Substanzen in Kunststoffen, die Beschränkungen unterliegen - Teil 23: Bestimmung von Formaldehyd und Hexamethylentetramin in Prüflebensmitteln

This Technical Specification (CEN/TS) was approved by CEN on 16 December 2004 for provisional application.

The period of validity of this CEN/TS is limited initially to three years. After two years the members of CEN will be requested to submit their comments, particularly on the question whether the CEN/TS can be converted into a European Standard.

CEN members are required to announce the existence of this CEN/TS in the same way as for an EN and to make the CEN/TS available promptly at national level in an appropriate form. It is permissible to keep conflicting national standards in force (in parallel to the CEN/TS) until the final decision about the possible conversion of the CEN/TS into an EN is reached.

CEN members are the national standards bodies of Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION COMITÉ EUROPÉEN DE NORMALISATION EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Ref. No. CEN/TS 13130-23:2005: E

SIST-TS CEN/TS 13130-23:2005

CEN/TS 13130-23:2005 (E)

Contents

page

Foreword		3
Introduction		5
1	Scope	6
2	Normative references	6
3	Principle	6
4	Reagents	6
5	Apparatus	8
6	Samples	9
7	Procedure	10
8	Precision	12
9	Confirmation	13
10	Test report ITeh STANDARD PREVIEW	15
Bibliog	graphy	16

SIST-TS CEN/TS 13130-23:2005 https://standards.iteh.ai/catalog/standards/sist/cff2740b-d293-424e-8267-0feb97899b4e/sist-ts-cen-ts-13130-23-2005

Foreword

This document (CEN/TS 13130-23:2005) has been prepared by Technical Committee CEN/TC 194 "Utensils in contact with food", the secretariat of which is held by BSI.

This part of EN 13130 has been prepared within the Standards, Measurement and Testing project, MAT1-CT92-0006, "*Development of Methods of Analysis for Monomers*" and has been prepared by Subcommittee (SC 1) of TC 194 "Utensils in contact with food" as one of a series of test methods for plastics materials and articles in contact with foodstuffs.

This standard is intended to support Directives 2002/72/EC [1], 89/109/EEC [2], 82/711/EEC [3] and its amendments 93/8/EEC [4] and 97/48/EC [5], and 85/572/EEC [6].

At the time of preparation and publication of this part of EN 13130 the European Union legislation relating to plastics materials and articles intended to come into contact with foodstuffs is incomplete. Further Directives and amendments to existing Directives are expected which could change the legislative requirements which this standard supports. It is therefore strongly recommended that users of this standard refer to the latest relevant published Directive(s) before commencement of a test or tests described in this standard.

This part of EN 13130 should be read in conjunction with EN 13130-1.

Further parts of EN 13130, under the general title *Materials and articles in contact with foodstuffs - Plastics substances subject to limitation*, have been prepared, and others are in preparation, concerned with the determination of specific migration from plastics materials into foodstuffs and food simulants and the determination of specific monomers and additives in plastics. The parts of EN 13130 are as follows.

Part 1: Guide to test methods for the specific migration of substances from plastics to foods and food simulants and the determination of substances in plastics and the selection of conditions of exposure to food simulants

- Part 2: Determination of terephthalic acid in food simulants
- Part 3: Determination of acrylonitrile in food and food simulants
- Part 4: Determination of 1,3-butadiene in plastics
- Part 5: Determination of vinylidene chloride in food simulants
- Part 6: Determination of vinylidene chloride in plastics
- Part 7: Determination of monoethylene glycol and diethylene glycol in food simulants
- Part 8: Determination of isocyanates in plastics
- Part 9: Determination of acetic acid, vinyl ester in food simulants
- Part 10: Determination of acrylamide in food simulants
- Part 11: Determination of 11-aminoundecanoic acid in food simulants
- Part 12: Determination of 1,3-benzenedimethanamine in food simulants
- Part 13: Determination of 2,2-bis(4-hydroxyphenyl)propane (Bisphenol A) in food simulants

SIST-TS CEN/TS 13130-23:2005

CEN/TS 13130-23:2005 (E)

Part 14: Determination of 3,3-bis(3-methyl-4-hydroxyphenyl)-2-indoline in food simulants

Part 15: Determination of 1,3-butadiene in food simulants

Part 16: Determination of caprolactam and caprolactam salt in food simulants

Part 17: Determination of carbonyl chloride in plastics

Part 18: Determination of 1,2-dihydroxybenzene, 1,3-dihydroxybenzene, 1,4-dihydroxybenzene, 4,4'-dihydroxybenzophenone and 4,4'dihydroxybiphenyl in food simulants

Part 19: Determination of dimethylaminoethanol in food simulants

Part 20: Determination of epichlorohydrin in plastics

Part 21: Determination of ethylenediamine and hexamethylenediamine in food simulants

Part 22: Determination of ethylene oxide and propylene oxide in plastics

Part 23: Determination of formaldehyde and hexamethylenetetramine in food simulants

Part 24: Determination of maleic acid and maleic anhydride in food simulants

Part 25: Determination of 4-methyl-pentene in food simulants

Part 26: Determination of 1-octene and tetrahydrofuran in food simulants R VIR W

Part 27: Determination of 2,4,6-triamino-1,3,5-triazine in food simulants 21)

Part 28: Determination of 1,1,1-trimethylolpropane in food simulants

Parts 1 to 8 are European Standards. Parts 9 to 28 are Technical Specifications.

WARNING All chemicals are hazardous to health to a greater or lesser extent. It is beyond the scope of this Technical Specification to give instructions for the safe handling of all chemicals, that meet, in full, the legal obligations in all countries in which this Technical Specification may be followed. Therefore, specific warnings are not given and users of this Technical Specification should ensure that they meet all the necessary safety requirements in their own country.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to announce this CEN Technical Specification: Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

Introduction

Formaldehyde, CH₂O, PM/Ref. No 17260, and hexamethylenetetramine, $C_6H_{12}N_4$, PM/Ref. No 18670, are monomers used in the manufacture of certain plastics materials and articles intended to come into contact with foodstuffs. After manufacture residual formaldehyde or residual hexamethylenetetramine (HMTA) can remain in the finished product and may migrate into foodstuffs coming into contact with that product.

Since migration of HMTA is limited as formaldehyde, this method allows the determination of formaldehyde, liberated from HMTA, in food simulants water, 3 % w/v aqueous acetic acid, 15 % v/v aqueous ethanol and rectified olive oil.

The chemical conversion of HMTA to formaldehyde is as follows:

 $C_6H_{12}N_4 + 6 H_2O \rightarrow 6 CH_2O + 4 NH_3$

The method allows the determination of HMTA and formaldehyde at the same time.

The method has been pre-validated by collaborative trial with two laboratories. The confirmation procedure was found to be quantitative. In collaborative trials with three laboratories comparable results using the chromotropic acid method and the acetyl acetone method were found for the detection limits, repeatability, recovery and migration of formaldehyde. Therefore the method of determination and the confirmation procedure are interchangeable.

(standards.iteh.ai)

SIST-TS CEN/TS 13130-23:2005 https://standards.iteh.ai/catalog/standards/sist/cff2740b-d293-424e-8267-0feb97899b4e/sist-ts-cen-ts-13130-23-2005

1 Scope

This document, part of EN 13130, specifies an analytical procedure for the chemical conversion of HMTA to formaldehyde and the determination of formaldehyde in food simulants water, 3 % w/v aqueous acetic acid, 15 % v/v aqueous ethanol and rectified olive oil.

The method is appropriate for the quantitative determination of formaldehyde in approximate analyte concentration range of 3,0 mg to 30 mg formaldehyde per kilogram of food simulant, which corresponds to 2,3 mg to 23,3 mg hexamethylenetetramine per kilogram of food simulant.

NOTE The method should also be applicable to other aqueous food simulants as well as to other fatty food simulants e.g. sunflower oil, corn oil or a mixture of synthetic triglycerides.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 13130-1:2004, Materials and articles in contact with foodstuffs – Plastics substances subject to limitation – Part 1: Guide to test methods for the specific migration of substances from plastics to foods and food simulants and the determination of substances in plastics and the selection of conditions of exposure to food simulants.

(standards.iteh.ai)

3 Principle SIST-TS CEN/TS 13130-23:2005 https://standards.iteh.ai/catalog/standards/sist/cff2740b-d293-424e-8267-

HMTA is treated with acid and heated to release formaldehydets-13130-23-2005

Formaldehyde in food simulant is determined by spectrophotometry. Formaldehyde reacts with chromotropic acid in the presence of sulfuric acid. This solution is measured in a spectrophotometer at the wavelength of 574 nm, with cells of an optical path length of 10 mm. Quantification is achieved using an external standard.

Confirmation of formaldehyde is carried out by spectrophotometer. Formaldehyde reacts with pentane-2,4-dione in the presence of ammonium acetate to form 3,5-diacetyl-1,4-dihydrolutidine. The absorption of this extract is measured at 410 nm, with a spectrophotometer with cells of an optical path length of 10 mm.

NOTE The confirmation procedure is also a quantitative method and can therefore be used as the method of determination. In that case the method with chromotropic acid should be used as the confirmation procedure.

4 Reagents

NOTE All reagents should be of recognized analytical quality unless otherwise stated.

4.1 Analyte

Formaldehyde solution, CH_2O, minimum 37 % (w/v), stabilized with approximately 10 % methanol.

4.2 Chemicals

- 4.2.1 Water, deionised.
- 4.2.2 Acetic acid, glacial 100 %.
- 4.2.3 Ethanol, absolute.
- 4.2.4 Olive oil, rectified (according to Directive 93/8/EEC)

4.2.5 Chromotropic acid disodium salt (dihydrate), 4,5-dihydroxy-2,7-naphthalene-disulfonic acid, $C_{10}H_6Na_2O_8S_2.2H_2O.$

- **4.2.6** Sulfuric acid, density 1,84 g/cm³.
- 4.2.7 Acetone
- 4.2.8 Starch, soluble

90 % Acetone

- 4.2.9 n-pentane
- 4.3 Solutions

4.3.1

iTeh STANDARD PREVIEW

(standards.iteh.ai) Measure 900 ml of acetone (4.2.7) and make up with water (4.2.1) to 1 000 ml.

SIST-TS CEN/TS 13130-23:2005

4.3.2 Stock solutions of formal dehyde in water containing approximately 1,5 mg formal dehyde per millilitre 0feb97899b4e/sist-ts-cen-ts-13130-23-2005

Weigh to the nearest 1 mg approximately 0,8 g formaldehyde solution (4.1.1) into a 200 ml volumetric flask and make up to the mark with water (4.2.1).

Determine the strength of this solution as follows.

Pipette 10,0 ml formaldehyde stock solution into a beaker, add 25,0 ml of a 0,05 mol standard iodine solution (4.3.5) and 10,0 ml of 1 mol sodium hydroxide solution (4.3.6) to the beaker. Allow to stand for 5 min. Acidify with 11,0 ml of 1 mol hydrochloric acid (4.3.7) and determine the excess iodine by titration with a 0,1 mol standard sodium thiosulfate solution (4.3.8) using 0,1 ml of the starch solution (4.3.12) as indicator.

Make a blank test on the corresponding amount of standard iodine solution.

1 ml of 0,1 N iodine consumed is equivalent to 1,5 mg formaldehyde.

Calculate the concentration in mg formaldehyde per millilitre of solution.

Repeat the procedure to obtain a second stock solution.

Store the formaldehyde stock solution for up to 3 months in a refrigerator.

4.3.3 Stock solution of formaldehyde in 90 % acetone containing approximately 1 mg formaldehyde per millilitre

Weigh to the nearest 1 mg approximately 0,3 g formaldehyde solution (4.1.1) into a 100 ml volumetric flask and make up to the mark with 90 % acetone (4.3.1).