



Standard Specification for Metallic Mechanical Fittings for Use on Outside Diameter Controlled Thermoplastic Gas Distribution Pipe and Tubing¹

This standard is issued under the fixed designation F 1948; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

^{e1} NOTE—Section 10 was editorially updated in December 2002.

1. Scope

1.1 This specification covers requirements and test methods for the qualification of metallic mechanical fittings for use with outside diameter controlled thermoplastic gas distribution pipe and tubing as specified in Specification D 2513.

1.2 The test methods described are not intended to be routine quality control tests.

1.3 This specification covers the types of mechanical fittings described in 3.3.

1.4 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units which are provided for information only and not considered standard.

1.5 The following safety hazards caveat pertains only to the test method portion, Section 7, of this specification. *This standard may involve hazardous material, operations and equipment. This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

1.6 The text of this standard references notes and footnotes which provide explanatory material. These notes and footnotes (excluding those in tables and figures), shall not be considered as requirements of the standard.

2. Referenced Documents

2.1 ASTM Standards:

- D 638 Test Method for Tensile Property of Plastics²
- D 1598 Test Methods for Time-To-Failure of Plastic Pipe Under Constant Internal Pressure³
- D 1600 Abbreviations of Terms Relating to Plastics²
- D 2513 Specification for Thermoplastic Gas Pressure Pipe, Tubing and Fittings³
- D 2837 Method for Obtaining Hydrostatic Design Basis for

Thermoplastic Pipe Materials³

F 412 Definitions of Terms Relating to Plastic Piping Systems³

F 1588 Test Method for Constant Tensile Load Test³

2.2 ASME Standard:

ASME B 31.8 Gas Transmission and Distribution Piping Systems⁴

2.3 Federal Specification:

OPS Part 192 Title 49, Code of Federal Regulations⁵

2.4 Other Document:

PPI TR-4 Recommended Hydrostatic Strengths and Design Stresses for Thermoplastic Pipe and Fitting Compounds⁶

3. Terminology

3.1 Definitions are in accordance with Definitions F 412 unless otherwise specified. Abbreviations are in accordance with Abbreviations D 1600 unless otherwise specified.

3.1.1 The gas industry terminology used in this specification is in accordance with ASME/ANSI B31.8 or United States CFR 49 Part 192 unless otherwise indicated.

3.1.2 The term “pipe” used herein refers to both pipe and tubing unless specifically stated otherwise. The term “fitting” refers to a mechanical connecting device as described in 3.2.5 and 3.2.7.

3.2 Definitions:

3.2.1 *Category 1 mechanical fitting, n*—fitting for assembling pipe, which includes a compression zone(s) to provide for pressure integrity, leak tightness, and resistance to end loads sufficient to cause no less than 25 % elongation of the piping, as described in this standard.

3.2.2 *Category 2 mechanical fitting, n*—fitting for assembling pipe, which includes a compression zone(s) to provide for pressure integrity and leak tightness; Category 2 fittings do not provide for resistance to end loads.

¹ This specification is under the jurisdiction of ASTM Committee F-17 on Plastic Piping Systems, and is the direct responsibility of Subcommittee F17.60 on Gas. Current edition approved April 10, 1999. Published July 1999.

² *Annual Book of ASTM Standards*, Vol 08.01.

³ *Annual Book of ASTM Standards*, Vol 08.04.

⁴ Available from the American Society of Mechanical Engineers, Three Park Ave., New York, NY, 10016-5900.

⁵ Available from the Office of Pipeline Safety, Research and Special Programs Administration, U.S. Department of Transportation, 400 Seventh Street, S.W., Washington, DC, 20006-1301.

⁶ Available from the Plastics Pipe Institute, 1801 K Street N.W., Suite 600K, Washington, DC, 20006-1301.

3.2.3 *Category 3 mechanical fitting, n*—fitting for assembling pipe, which includes a compression zone(s) for pressure integrity, leak tightness, and resistance to end loads; the nominal size of the fitting shall be 4 and larger in diameter.

3.2.3.1 *Discussion*—Resistance to end loads shall be equal to or greater than the maximum thermal stress that would be produced by a temperature change of 100°F (55°C) (for formula, see Annex A1).

3.2.4 *joint, n*—the location at which two or more pieces of pipe, or a pipe and a fitting, are connected (an installed coupling has two joints).

3.2.5 *joint, mechanical, n*—a connection between piping components employing physical force to develop a seal or produce alignment.

3.2.6 *maximum allowable operating pressure, MAOP, n*—of the fuel gas piping system, in psig, as determined in accordance with US DOT CFR, Title 49, Part 192.121, and as represented in the following:

$$MAOP = P = 2 \times S / (R - 1) \times f \quad (1)$$

where:

S = the pipe material's HDB as published in PPI TR 4,

R = the pipe's dimension ratio determined by dividing the pipe's specified nominal outside diameter by the pipe's specified nominal wall thickness, and

f = design (derating) factor for thermoplastic fuel gas piping as set by the authority having jurisdiction. In the United States, the design factor is cited in CFR, Title 49, Part 192.121.

3.2.7 *mechanical fitting, n*—fitting for making a mechanical joint to provide for pressure integrity, leak tightness, and, depending on category, as defined in this standard, resistance to end loads.

3.3 Types of Mechanical Fittings:

3.3.1 *clamped insert fitting, n*—mechanical fitting used to make a mechanical joint that utilizes external clamps, or other mechanical devices, to form a pressure seal between the reinforcing tubular stiffener and the surface of the pipe.

3.3.2 *compression fitting, n*—mechanical fitting used to make a mechanical joint by compressing either externally, internally, or radially to form a pressure seal between the fitting and the surface of the pipe.

3.3.3 *compression gasket fitting, n*—mechanical fitting used to make a mechanical joint that utilizes a compression nut, tightening ring, bolts, or any other device to compress gasketing onto the surface of the pipe to form a pressure seal.

3.3.4 *stab-type fitting, n*—mechanical fitting used to make a mechanical joint in which a seal is achieved by radial compression of a gasket between the outside diameter (OD) of the pipe and the inside diameter (ID) of the fitting.

4. Material

4.1 The physical properties of each material used to produce the fitting shall be available from the fitting manufacturer upon request.

4.2 Specifications outlining the physical and chemical properties of all fitting materials shall be available from the fitting manufacturer upon request.

NOTE 1—Materials in long-term contact with natural gas of line quality and LP gas vapor should be demonstrated to not adversely effect the performance of the fitting.

NOTE 2—Materials should have a demonstrated resistance to environmental stress cracking when exposed, under stress, to chemical compounds encountered in or external to gas piping systems, and a demonstrated resistance to bacteriological decomposition. Such compounds include, but are not limited to, ice thawing chemicals, fertilizers, insecticides, herbicides, leak detection fluids, acids, bases and antifreeze solutions used to thaw frozen lines.

5. Dimensions

5.1 The dimensions and tolerances shall be determined by the manufacturer.

6. Qualification Requirements

6.1 *General*—Unless otherwise specified, each nominal size of fitting shall be tested. Testing the fitting with the thickest wall pipe for which the fitting is designed qualifies that type of fitting for use with pipe of lesser wall thickness.

6.1.1 Mechanical joint qualification shall be performed on assembled joints using the fitting manufacturer's joining procedure. All mechanical fittings offered by the manufacturer shall be capable of meeting the requirements of this standard when connecting thermoplastic piping materials complying with Specification D 2513. It is not the intent of this standard to require the testing of all fitting configurations (that is, tees, elbows, etc.) but each joint design in each size.

6.1.2 All mechanical fittings described in 3.3 shall have an internal pipe reinforcing tubular stiffener that extends at least under the seal and gripping device (where used).

6.2 Performance Requirements:

6.2.1 *Tensile Strength*—The pipe joint shall accommodate the tensile loads, when tested in accordance with 7.2.

6.2.1.1 *Category 1*—The joint shall provide resistance to a force on the pipe joint equal to or greater than that which will cause no less than 25 % elongation of the pipe, or which causes the pipe to fail outside the joint area when tested in accordance with 7.2.

6.2.1.2 *Category 2*—Joint design that only provides a seal. A mechanical joint designed for this category excludes any provisions in the design of the joint to resist axial pullout forces; therefore, tensile tests are not required.

6.2.1.3 *Category 3*—Joint of nominal pipe size 4 and larger in diameter shall provide resistance to a force on the pipe joint equal to or greater than the maximum thermal stress that would be produced by a temperature change of 100°F (55°C) (for formula, see Annex A1).

NOTE 3—Category 3 has a manufacturer's rated pipe end restraint less than the value required to yield the pipe as outlined in 6.2.1.1 (Category 1).

6.2.1.4 Joint restraint capabilities less than as defined in 6.2.2.1 and 6.2.2.3 shall constitute failure of the test.

6.2.2 *Temperature Cycling Test*—The mechanical joint shall provide a pressure seal after 10 cycles of the temperature cycling test when tested in accordance with 7.3.

6.2.3 *Constant Tensile Load Test*—The joint shall not fail by leakage or pullout when loaded to an axial tensile stress of 1320 psi (9101 kPa) and tested in accordance with 7.4.