
Tekstilije - Metode za določevanje nekaterih aromatskih aminov, izvirajočih iz azo barvil - 1. del: Zaznavanje prisotnosti določenih azo barvil, dostopnih brez ekstrahiranja vlaken

Textiles - Methods for the determination of certain aromatic amines derived from azo colorants - Part 1: Detection of the use of certain azo colorants accessible without extraction

Textilien - Verfahren für die Bestimmung bestimmter aromatischer Amine aus Azofarbstoffen - Teil 1: Verwendungsnachweis bestimmter Azofarbstoffe ohne vorherige Extraktion

Textiles - Méthodes de détermination de certaines amines aromatiques dérivées de colorants azoïques - Partie 1: Détection de l'utilisation de certains colorants azoïques accessibles sans extraction

Ta slovenski standard je istoveten z: EN 14362-1:2003

ICS:

59.080.01 Tekstilije na splošno Textiles in general

SIST EN 14362-1:2003

en

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 14362-1:2003

<https://standards.iteh.ai/catalog/standards/sist/99646b89-cef1-4655-b5a7-8deedaeaedcc/sist-en-14362-1-2003>

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN 14362-1

October 2003

ICS 59.080.30

English version

Textiles - Methods for the determination of certain aromatic amines derived from azo colorants - Part 1: Detection of the use of certain azo colorants accessible without extraction

Textiles - Méthodes de détermination de certaines amines aromatiques dérivées de colorants azoïques - Partie 1: Détection de l'utilisation de certains colorants azoïques accessibles sans extraction

Textilien - Verfahren für die Bestimmung bestimmter aromatischer Amine aus Azofarbstoffen - Teil 1: Verwendungsnachweis bestimmter Azofarbstoffe ohne vorherige Extraktion

This European Standard was approved by CEN on 1 September 2003.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Luxembourg, Malta, Netherlands, Norway, Portugal, Slovakia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Contents

Page

Foreword	3
1 Scope	4
2 Normative references	4
3 General	4
4 Principle	5
5 Safety precautions	6
6 Reagents	6
7 Apparatus	7
8 Procedure	7
9 Evaluation	9
10 Test report	9
Annex A (informative) Chromatographic analyses	10
Annex B (normative) Calculation	15
Annex C (informative) Reliability of the method	16
Annex D (informative) Assessment guide - Interpretation of analytical results	17

[SIST EN 14362-1:2003](https://standards.itech.ai/catalog/standards/sist/99646b89-cef1-4655-b5a7-8deedaeaedcc/sist-en-14362-1-2003)

<https://standards.itech.ai/catalog/standards/sist/99646b89-cef1-4655-b5a7-8deedaeaedcc/sist-en-14362-1-2003>

Foreword

This document (EN 14362-1:2003) has been prepared by Technical Committee CEN/TC 248 "Textiles and textile products", the secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by April 2004, and conflicting national standards shall be withdrawn at the latest by April 2004.

Annexes A, C and D are informative. Annex B is normative.

This European Standard calls for the use of substances and/or procedures that may be injurious to health if appropriate precautions are not observed. It refers only to technical suitability and does not absolve the user from legal obligations relating to health and safety at any stage.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Luxembourg, Malta, Netherlands, Norway, Portugal, Slovakia, Spain, Sweden, Switzerland and the United Kingdom.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 14362-1:2003

<https://standards.iteh.ai/catalog/standards/sist/99646b89-cef1-4655-b5a7-8deedaeaedcc/sist-en-14362-1-2003>

EN 14362-1:2003 (E)**1 Scope**

This part of EN 14362 describes a procedure to detect the use of certain azo colorants that may not be used in the manufacture or treatment of certain commodities made of textile fibres and that are accessible to reducing agent without extraction, particularly textiles made of cellulose and protein fibres (e.g. cotton, viscose, wool, silk).

For the extraction test method see EN 14362-2 *Detection of the use of certain azo colorants accessible by extracting the fibres*.

For certain fibre blends both parts of this standard may need to be applied.

2 Normative references

This European Standard incorporates by dated or undated reference, provisions from other publications. These normative references are cited at the appropriate places in the text and the publications are listed hereafter. For dated references subsequent amendments to, or revisions of, any of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies (including amendments).

EN ISO 3696, *Water for analytical laboratory use - Specification and test methods (ISO 3696:1987)*

ISO 4787, *Laboratory glassware - Volumetric glassware - Methods for use and testing of capacity*

[SIST EN 14362-1:2003](https://standards.iteh.ai/catalog/standards/sist/99646b89-cef1-4655-b5a7-8deedaeedcc/sist-en-14362-1-2003)

<https://standards.iteh.ai/catalog/standards/sist/99646b89-cef1-4655-b5a7-8deedaeedcc/sist-en-14362-1-2003>

3 General

Certain azo colorants may release, by reductive cleavage of azo group(s), one or more of the following aromatic amines, which are proscribed under Directive 2002/61/EC.

Table 1 – Aromatic amines proscribed under Directive 2002/61/EC.

No.	CAS number	Index number	EC number	Substances
1	92-67-1	612-072-00-6	202-177-1	biphenyl-4-ylamine 4-aminobiphenyl xenylamine
2	92-87-5	612-042-00-2	202-199-1	benzidine
3	95-69-2		202-441-6	4-chloro-o-toluidine
4	91-59-8	612-022-00-3	202-080-4	2-naphthylamine
5*	97-56-3	611-006-00-3	202-591-2	o-aminoazotoluene 4-amino-2',3-dimethylazobenzene 4-o-tolylazo-o-toluidine
6*	99-55-8		202-765-8	5-nitro-o-toluidine

7	106-47-8	612-137-00-9	203-401-0	4-chloroaniline
8	615-05-4		210-406-1	4-methoxy-m-phenylenediamine
9	101-77-9	612-051-00-1	202-974-4	4,4'-methylenedianiline 4,4'-diaminodiphenylmethane
10	91-94-1	612-068-00-4	202-109-0	3,3'-dichlorobenzidine 3,3'-dichlorobiphenyl-4,4'-ylenediamine
11	119-90-4	612-036-00-X	204-355-4	3,3'-dimethoxybenzidine o-dianisidine
12	119-93-7	612-041-00-7	204-358-0	3,3'-dimethylbenzidine 4,4'-bi-o-toluidine
13	838-88-0	612-085-00-7	212-658-8	4,4'-methylenedi-o-toluidine
14	120-71-8		204-419-1	6-methoxy-m-toluidine p-cresidine
15	101-14-4	612-078-00-9	202-918-9	4,4'-methylene-bis-(2-chloro-aniline) 2,2'-dichloro-4,4'-methylene-dianiline
16	101-80-4		202-977-0	4,4'-oxydianiline
17	139-65-1		205-370-9	4,4'-thiodianiline
18	95-53-4	612-091-00-X	202-429-0	o-toluidine 2-aminotoluene
19	95-80-7	612-099-00-3	202-453-1	4-methyl-m-phenylenediamine
20	137-17-7		205-282-0	2,4,5-trimethylaniline
21	90-04-0	612-035-00-4	201-963-1	o-anisidine 2-methoxyaniline
22**	60-09-3	611-008-00-4	200-453-6	4-aminoazobenzene

*The CAS-numbers 97-56-3 (No. 5) and 99-55-8 (No. 6) are further reduced to CAS-numbers 95-53-4 (No. 18) and 95-80-7 (No. 19).

**Azo colorants that are able to form 4-aminoazobenzene, generate under the condition of this method aniline and 1,4-phenylenediamine. The presence of these colorants cannot be reliably ascertained without additional information, e.g. the chemical structure of the colorant used.

4 Principle

The textile sample is treated with sodium dithionite in a citrate-buffered aqueous solution (pH = 6) at 70 °C in a closed vessel. The amines released in the process are transferred to a t-butyl methyl ether phase by means of liquid-liquid extraction using diatomaceous earth columns. The t-butyl methyl ether extract is then concentrated and the residue is taken up in either methanol or another solvent appropriate for the detection and determination of amines using chromatography.

EN 14362-1:2003 (E)

If the amines are detected by one chromatographic method, then confirmation shall be made using one or more alternative methods.

5 Safety precautions

5.1 General

WARNING The substances [amines] listed in Table 1 are classified as substances known to be or suspected to be human carcinogens.

Any handling and disposal of these substances shall be in strict accordance with the appropriate national health and safety regulations.

5.2 It is the user's responsibility to use safe and proper techniques in handling materials in this test method. Consult manufacturers for specific details such as material safety data sheets and other recommendations.

5.3 Good laboratory practice should be followed. Wear safety glasses in all laboratory areas and a single-use dust respirator while handling powder colorants.

5.4 Users should comply with any national and local safety regulations.

6 Reagents

6.1 General

Unless otherwise specified, analytical grade chemicals have to be used.

6.2 methanol

6.3 ethyl acetate

6.4 t-butyl methyl ether

6.5 citrate/sodium hydroxide buffer solution, pH = 6, $c = 0,06 \text{ mol/l}^1$

6.6 aqueous sodium dithionite solution, $\rho = 200 \text{ mg/ml}^2$, freshly (daily) prepared

6.7 diatomaceous earth

6.8 amine substances - amines 1 to 4, 7 to 21 (as specified in Table 1), and aniline and 1,4-phenylenediamine- all of highest available defined purity standard.

6.9 standard solutions

6.9.1 calibration solution of amines (see 6.7) $\rho = 15,0 \text{ } \mu\text{g}$ of each amine per millilitre of an appropriate solvent

¹⁾ c is citrate concentration

²⁾ ρ is mass concentration

6.9.2 an appropriate mixture of internal standards in solution, $\rho = 10,0 \mu\text{g}$ of each IS/ml of the appropriate IS solvent

NOTE	IS1:	naphthalene-d8, CAS No.: 1146-65-2
	IS2:	2,4,5-trichloroaniline, CAS No.: 636-30-6
	IS3:	4-aminoquinaldine, CAS No.: 6628-04-2
	IS4:	anthracene-d10, CAS No.: 1719-06-8

6.9.3 solution of amine (see 6.8) for checking the experimental procedure, $\rho = 30,0 \mu\text{g}$ of each amine per millilitre methanol

6.10 grade 3 water, complying with EN ISO 3696.

7 Apparatus

7.1 reaction vessel (20 ml to 50 ml) of heat-resistant glass, with tight closure

7.2 heating source that generates $(70 \pm 2) ^\circ\text{C}$

7.3 glass or polypropylene column, inside diameter 25 to 30 mm, length 140 to 150 mm, packed with 20 g of diatomaceous earth (6.7), fitted with glass fibre filter at the outlet. The diatomaceous earth columns are either bought pre-packed and used as is, or 20 g of diatomaceous earth can be packed into a glass or polypropylene column of the dimensions given.

7.4 vacuum rotary evaporator with water bath
<https://standards.iteh.ai/catalog/standards/sist/99646b89-cef1-4655-b5a7-8deedacaedc9/sist-en-14362-1-2003>

7.5 pipettes 10 ml, 5 ml, 2 ml, 1 ml of class 1 complying with ISO 4787

7.6 chromatographic equipment selected from the following:

7.6.1 thin layer chromatography (TLC) or high performance thin layer chromatography (HPTLC) equipment, including relevant detection

7.6.2 high performance liquid chromatography (HPLC) with gradient elution and diode array detector (DAD) or mass selective detector (MSD)

7.6.3 gas chromatography (GC) with flame ionisation detector (FID) or mass selective detector (MSD)

7.6.4 capillary electrophoresis (CE) with DAD

NOTE A description of the equipment is given in annex A.

8 Procedure

8.1 Preparation of test specimens

Textile material is cut in an appropriate manner. For analysis, 1,00 g of test material is weighed into the reaction vessel (7.1).