



Designation: E 2241 – 02

Standard Test Method for Assessing the Current-Voltage Cycling Stability at Room Temperature of Absorptive Electrochromic Coatings on Sealed Insulating Glass Units¹

This standard is issued under the fixed designation E 2241; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 The test described is a method for the accelerated aging and monitoring of the time-dependent performance of electrochromic windows (ECW). Cross sections of typical electrochromic windows have three to five-layers of coatings that include one to three active layers sandwiched between two transparent conducting electrodes (TCEs, see Section 3). Examples of the cross-sectional arrangements can be found in “Evaluation Criteria and Test Methods for Electrochromic Windows.”² (For acronyms used in this standard, see [Appendix X1](#), section [X1.1](#)).

1.2 The test method is applicable only for layered (one or more active coatings between the TCEs) absorptive electrochromic coatings on sealed insulating glass (IG) units fabricated for vision glass (superstrate and substrate) areas for use in buildings, such as glass doors, windows, skylights, and exterior wall systems. The layers used for electrochromically changing the optical properties may be inorganic or organic materials between the superstrate and substrate.

1.3 The electrochromic coatings used in this test method will be subsequently exposed (see Test Methods [E 2141](#)) to solar radiation and deployed to control the amount of radiation by absorption and reflection and thus, limit the solar heat gain and amount of solar radiation that is transmitted into the building.

1.4 The test method is not applicable to other chromogenic devices, for example, photochromic and thermochromic devices.

1.5 The test method is not applicable to electrochromic windows that are constructed from superstrate or substrate materials other than glass.

1.6 The test method referenced herein is a laboratory test conducted under specified conditions. This test is intended to simulate and, possibly, to also accelerate actual in-service use

of the electrochromic windows. Results from this test cannot be used to predict the performance with time of in-service units unless actual corresponding in-service tests have been conducted and appropriate analyses have been conducted to show how performance can be predicted from the accelerated aging tests.

1.7 The values stated in metric (SI) units are to be regarded as the standard.

1.8 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*

2.1.1 For additional useful standards related to this standard, see [Appendix X1](#), section [X1.2](#).

[C 168](#) Terminology Relating to Building Materials³

[C 1048](#) Specification for Heat-Treated Flat Glass-Kind HS, Kind FT Coated and Uncoated Glass⁴

[C 1199](#) Test Method for Measuring the Steady State Thermal Transmittance of Fenestration Systems Using Hot Box Methods⁵

[E 632](#) Practice to Aid Prediction of Service Life of Building Components and Materials⁵

[E 903](#) Test Method for Solar Absorptance, Reflectance, and Transmittance of Materials Using Integrating Spheres⁶

[E 1423](#) Practice for Determining the Steady State Thermal Transmittance of Fenestration Systems⁷

[E 2094](#) Practice for Evaluating the Service Lifetime of Chromogenic Glazings⁸

[E 2141](#) Test Methods for Assessing the Durability of Absorptive Electrochromic Coatings on Sealed Insulating Glass Units⁸

¹ This test method is under the jurisdiction of ASTM Committee E06 on Performance of Buildings and is the direct responsibility of Subcommittee E06.22 on Durability Performance of Building Constructions.

Current edition approved Oct. 10, 2002. Published December 2002.

² Czanderna, A. W., and Lampert, C. M., “Evaluation Criteria and Test Methods for Electrochromic Windows,” SERI/PR-255-3537, July 1990, Golden, CO; Solar Energy Research Institute.

³ *Annual Book of ASTM Standards*, Vol 04.06.

⁴ *Annual Book of ASTM Standards*, Vol 15.02.

⁵ *Annual Book of ASTM Standards*, Vol 14.04.

⁶ *Annual Book of ASTM Standards*, Vol 12.02.

⁷ *Annual Book of ASTM Standards*, Vol 04.11.

⁸ *Annual Book of ASTM Standards*, Vol 04.12.



E 2188 Test Method for Insulating Glass Unit Performance⁸
G 113 Terminology Relating to Natural and Artificial
Weathering Tests of Non-Metallic Materials⁵

2.2 Canadian Standard:

CAN/CGSB 12.8 Insulating Glass Units

3. Terminology

3.1 *Definitions*—Refer to terminology in Terminology C 168, Practice E 632, and Terminology G 113 for descriptions of general terms.

3.2 *Definitions of Terms Specific to This Standard*:

3.2.1 *accelerated aging test*—an aging test in which the rate of degradation of building components or materials is intentionally accelerated from that expected in actual service.

3.2.2 *bleached state*—a descriptor for an ECW when no ions reside in the electrochromic layer or after ions have been removed (or inserted, depending on the type of material) from the electrochromic layer(s) and if applicable, the maximum number of ions have been returned to the counterelectrode layer to restore the photopic optical specular transmittance in the bleached state (τ_b) from that of the photopic optical specular transmittance in the colored state (τ_c).

3.2.3 *colored state*—a descriptor for an ECW after ions have been inserted (or removed, depending on the type of material) into the electrochromic layer and, if applicable, removed from the counterelectrode layer to reduce the photopic optical specular transmittance (of wavelengths from 400 to 730 nm) from that in the bleached state (τ_b).

3.2.4 *durability*—the capability of maintaining the serviceability of a product, component, assembly or construction over a specified time.

3.2.5 *electrochromic coating*—the multilayered materials that include the electrochromic layers, other layers, and transparent conducting oxide layers required for altering the optical properties of the coating.

3.2.6 *electrochromic layer(s)*—the material(s) in an ECW that alter its optical properties in response to the insertion or removal of ions, for example, Li^+ or H^+ .

3.2.7 *electrochromic window (ECW)*—a window consisting of several layers of electrochromic and attendant materials, which are able to alter their optical properties in response to a change in an applied electric field. The changeable optical properties include transmittance, reflectance, and absorptance.

3.2.8 *ion conducting layer*—the material in an ECW through which ions are transported between the electrochromic layer and the ion storage layer and electron transport is minimized.

3.2.9 *ion storage layer or counter electrode layer*—the material in an ECW that serves as a reservoir for ions that can be inserted into the electrochromic layer.

3.2.10 *performance parameters*—the photopic transmittance ratio (PTR), of at least 5:1 ($\text{PTR} = \tau_b/\tau_c$) between the bleached (for example, τ_b of 60 to 70 %) and colored (for example, τ_c of 12 to 14 %) states; coloring and bleaching times of a few minutes; switching with applied voltages from ~1 to 3 V; and open-circuit memory of a few hours, for example, contemporary ECWs typically have open circuit memories of 6 to 24 h.

3.2.11 *serviceability*—the capability of a building product, component, assembly or construction to perform the function(s) for which it was designed and constructed.

3.2.12 *service life*—of a building component or material, the period of time after installation during which all properties exceed minimum acceptable values when routinely maintained.

3.3 For additional useful definitions for terminology used in this standard, see Appendix X1, section X1.3.

4. Significance and Use

4.1 This test method is intended to provide a means for evaluating the current-voltage cycling stability at ca. 22°C of ECWs as described in 1.2.^{2,9} (See Appendix X1, sections X1.4-X1.7.)

5. Background

5.1 Observations and measurements have shown that some of the performance parameters of ECWs have a tendency to deteriorate over time. In selecting the materials, device design, and glazing for any application, the ability of the glazing to perform over time is an indication of that glazing's durability. The ability of the product to perform over time, at or better than specified requirements, is an indication of the service life of the glazings (see Practice E 2094). While these two indicators are related, the purpose of this standard test method is to assess the current-voltage cycling stability at ca. 22°C of ECWs.

5.2 ECWs perform a number of important functions in a building envelope including: minimizing the solar energy heat gain; providing for passive solar energy gain; controlling a variable visual connection with the outside world; enhancing human comfort (heat gain), security, ventilation, illumination, and glare control; providing for architectural expression, and (possibly) improving acoustical performance. Some of these functions may deteriorate in performance over time. Solar heat gain through an ECW is decreased because of two principal processes. Energy from the visible part of the spectrum is absorbed by an ECW in the colored state. In addition, infrared radiation is either absorbed by the ECW materials or is reflected by the transparent conducting oxide layers that are used for applying the coloring or bleaching potentials across the other layers in the ECW.

5.3 It is possible, but difficult, to predict the time-dependent performance of ECWs from accelerated aging tests because of the reasons listed below. Users of this document should be aware of these limitations when reviewing published performance results and their connection to durability.

5.3.1 The degradation mechanisms of ECW materials or glazings, or both, are complex. In some cases, however, these mechanisms may be determined and quantified.

5.3.2 The external factors that affect the performance of ECWs are numerous and may be difficult to quantify. However,

⁹ Czanderna, A. W., Benson, D. K., Jorgensen, G. J., Zhang, J.-G., Tracy, C. E., and Deb, S. K., "Durability Issues and Service Lifetime Prediction of Electrochromic Windows for Buildings Applications," NREL/TP-510-22702, May 1997, National Renewable Energy Laboratory, Golden, CO; Solar Energy Materials and Solar Cells, 56, 1999, pp. 419-436.