



Designation: D 1508 – 02^{ε1}

Standard Test Method for Carbon Black, Pelleted Fines and Attrition¹

This standard is issued under the fixed designation D 1508; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

^{ε1} NOTE—Section 7.1.4 was editorially updated in December 2002.

1. Scope

1.1 This test method covers the determination of the fines and attrition of pelleted carbon black.

1.2 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*

D 1511 Test Method for Carbon Black—Pellet Size Distribution²

D 1799 Practice for Carbon Black—Sampling Packaged Shipments²

D 1900 Practice for Carbon Black—Sampling Bulk Shipments²

D 4483 Practice for Determining Precision for Test Method Standards in the Rubber and Carbon Black Industries²

D 5817 Pelleted Carbon Black—Practice for Reducing and Blending Gross Samples of Carbon Black²

E 11 Specification for Wire Cloth and Sieves for Testing Purposes³

3. Summary of Test Method

3.1 *Method A, Fines*—A sample of carbon black is placed on a 125- μm sieve and shaken in a mechanical or vibratory sieve shaker for 5 min. The pellets, pellet fragments, dust, and unpelleted black that pass through the sieve are defined as carbon black fines. The fines are expressed in percent.

3.2 *Method B, Attrition*—The same test sample is shaken for an additional 15 min to determine the amount of pellet degradation or attrition created during this additional shake interval. The attrition is expressed in percent.

¹ This practice is under the jurisdiction of ASTM Committee D24 on Carbon Black and is the direct responsibility of Subcommittee D24.51 on Carbon Black Pellet Properties.

Current edition approved Nov. 10, 2002. Published December 2002. Originally approved in 1957. Last previous edition approved in 2001 as D 1508–01.

² *Annual Book of ASTM Standards*, Vol 09.01.

³ *Annual Book of ASTM Standards*, Vol 14.02.

4. Significance and Use

4.1 *Method A, Fines*—The fines content of carbon black is related to the bulk flowability, dustiness, and, in some instances, the level of dispersion. Due to the many other variables that influence dispersion and handling, the significance of fines content must be determined by the user.

4.2 *Method B, Attrition*—By comparing the percent fines and attrition, an indication can be obtained of pellet stability and the amount of fines that may be created by pellet degradation in conveying, handling or transit.

5. Apparatus

5.1 *Mechanical or Vibratory Sieve Shaker*.⁴

5.2 *Sieves*, six 125- μm (U.S. Standard No. 120) having a 200-mm (8-in.) diameter and 25-mm (1-in.) height, or equivalent, conforming to Specification E 11.

5.3 *Sieve Separator Receivers*, five required.

5.4 *Sieve Cover*.

5.5 *Bottom Receiver Pan*.

5.6 *Riffle Sample Splitter*.

5.7 *Small Scoop or Large Spoon*.

5.8 *Balance, 0.1-g sensitivity*.

6. Sampling

6.1 Samples shall be taken in accordance with Practice D 1799 or Test Method D 1900.

6.2 Practice D 5817 shall be used for reduction and blending of samples.

7. Procedure

7.1 *Method A, Fines and Method B, Attrition:*

7.1.1 Stack up to six sets of sieves and receivers with a receiver beneath each sieve.

7.1.2 Weigh 25.0 g portions, being careful to dip approximately 25 g of black from the riffle splitter.

⁴ A Ro–Tap sieve shaker is satisfactory for this purpose. For a description of this apparatus refer to Test Method D 1511. The Fritsche Analysette 3 Pro vibratory sieve shaker has also been found suitable for this purpose (variable amplitude at 3600 vpm) and is available from Gilson Company, P.O. Box 200, Lewis Center, OH 43035–0200, website: www.globalgilson.com.