

# INTERNATIONAL STANDARD



Optical fibres – **iTeh STANDARD PREVIEW**  
Part 2-30: Product specifications – Sectional specification for category A3  
multimode fibres  
(standards.iteh.ai)

[IEC 60793-2-30:2015](#)

<https://standards.iteh.ai/catalog/standards/sist/a66f8815-be44-4445-b4e6-fe251bf25ddb/iec-60793-2-30-2015>



**THIS PUBLICATION IS COPYRIGHT PROTECTED**  
**Copyright © 2015 IEC, Geneva, Switzerland**

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester. If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

IEC Central Office  
3, rue de Varembe  
CH-1211 Geneva 20  
Switzerland

Tel.: +41 22 919 02 11  
Fax: +41 22 919 03 00  
[info@iec.ch](mailto:info@iec.ch)  
[www.iec.ch](http://www.iec.ch)

**About the IEC**

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

**About IEC publications**

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigenda or an amendment might have been published.

**IEC Catalogue - [webstore.iec.ch/catalogue](http://webstore.iec.ch/catalogue)**

The stand-alone application for consulting the entire bibliographical information on IEC International Standards, Technical Specifications, Technical Reports and other documents. Available for PC, Mac OS, Android Tablets and iPad.

**Electropedia - [www.electropedia.org](http://www.electropedia.org)**

The world's leading online dictionary of electronic and electrical terms containing more than 30 000 terms and definitions in English and French, with equivalent terms in 15 additional languages. Also known as the International Electrotechnical Vocabulary (IEV) online.

**IEC publications search - [www.iec.ch/searchpub](http://www.iec.ch/searchpub)**

The advanced search enables to find IEC publications by a variety of criteria (reference number, text, technical committee,...). It also gives information on projects, replaced and withdrawn publications.

**IEC Glossary - [std.iec.ch/glossary](http://std.iec.ch/glossary)**

More than 60 000 electrotechnical terminology entries in English and French extracted from the Terms and Definitions clause of IEC publications issued since 2002. Some entries have been collected from earlier publications of IEC TC 37, 77, 86 and CISPR.

**IEC Just Published - [webstore.iec.ch/justpublished](http://webstore.iec.ch/justpublished)**

Stay up to date on all new IEC publications. Just Published details all new publications released. Available online and also once a month by email.

**IEC Customer Service Centre - [webstore.iec.ch/csc](http://webstore.iec.ch/csc)**

If you wish to give us your feedback on this publication or need further assistance, please contact the Customer Service Centre: [csc@iec.ch](mailto:csc@iec.ch).

INTERNATIONAL STANDARDS PREVIEW  
(standards.iec.ch)  
Tel: +41 22 919 2300  
https://standards.iec.ch/catalog/standards  
fe251bf25ddb/iec-60793-2-30-2015

# INTERNATIONAL STANDARD



---

**Optical fibres – iTeh STANDARD PREVIEW**  
**Part 2-30: Product specifications – Sectional specification for category A3**  
**multimode fibres**  
(standards.itih.ai)

[IEC 60793-2-30:2015](https://standards.itih.ai/catalog/standards/sist/a66f8815-be44-4445-b4e6-fe251bf25ddb/iec-60793-2-30-2015)

[https://standards.itih.ai/catalog/standards/sist/a66f8815-be44-4445-b4e6-  
fe251bf25ddb/iec-60793-2-30-2015](https://standards.itih.ai/catalog/standards/sist/a66f8815-be44-4445-b4e6-fe251bf25ddb/iec-60793-2-30-2015)

INTERNATIONAL  
ELECTROTECHNICAL  
COMMISSION

---

ICS 33.180.10

ISBN 978-2-8322-2772-5

**Warning! Make sure that you obtained this publication from an authorized distributor.**

## CONTENTS

FOREWORD.....	4
1 Scope.....	6
2 Normative references.....	6
3 Specifications.....	7
3.1 General.....	7
3.2 Dimensional requirements.....	7
3.3 Mechanical requirements.....	8
3.4 Transmission requirements.....	8
3.5 Environmental requirements.....	9
Annex A (normative) Specifications for sub-category A3a multimode fibres.....	10
A.1 General.....	10
A.2 Dimensional requirements.....	10
A.3 Mechanical requirements.....	10
A.4 Transmission requirements.....	10
A.5 Environmental requirements.....	11
Annex B (normative) Specifications for sub-category A3b multimode fibres.....	12
B.1 General.....	12
B.2 Dimensional requirements.....	12
B.3 Mechanical requirements.....	12
B.4 Transmission requirements.....	12
B.5 Environmental requirements.....	13
Annex C (normative) Specifications for sub-category A3c multimode fibres.....	14
C.1 General.....	14
C.2 Dimensional requirements.....	14
C.3 Mechanical requirements.....	14
C.4 Transmission requirements.....	14
C.5 Environmental requirements.....	15
Annex D (normative) Specifications for sub-category A3d multimode fibres.....	17
D.1 General.....	17
D.2 Dimensional requirements.....	17
D.3 Mechanical requirements.....	17
D.4 Transmission requirements.....	17
D.5 Environmental requirements.....	18
Annex E (normative) Specifications for sub-category A3e multimode fibres.....	20
E.1 General.....	20
E.2 Dimensional requirements.....	20
E.3 Mechanical requirements.....	20
E.4 Transmission requirements.....	20
E.5 Environmental requirements.....	21
Annex F (normative) Specifications for sub-category A3f multimode fibres.....	23
F.1 General.....	23
F.2 Dimensional requirements.....	23
F.3 Mechanical requirements.....	23
F.4 Transmission requirements.....	23
F.5 Environmental requirements.....	24
Annex G (normative) Specifications for sub-category A3g multimode fibres.....	26

G.1	General.....	26
G.2	Dimensional requirements .....	26
G.3	Mechanical requirements.....	26
G.4	Transmission requirements.....	26
G.5	Environmental requirements .....	27
Table 1	– Relevant dimensional attributes and measurement methods .....	7
Table 2	– Dimensional requirements common to all category A3 fibres.....	8
Table 3	– Additional dimensional attributes required for each sub-category .....	8
Table 4	– Relevant mechanical attributes and test methods .....	8
Table 5	– Mechanical requirements to be specified for each sub-category.....	8
Table 6	– Relevant transmission attributes and measurement methods .....	9
Table 7	– Additional transmission attributes required for each sub-category .....	9
Table 8	– Relevant environmental attributes and test methods.....	9
Table A.1	– Dimensional requirements specific to A3a fibres .....	10
Table A.2	– Mechanical requirements specific to A3a fibres .....	10
Table A.3	– Transmission requirements specific to A3a fibres .....	11
Table B.1	– Dimensional requirements specific to A3b fibres .....	12
Table B.2	– Mechanical requirements specific to A3b fibres .....	12
Table B.3	– Transmission requirements specific to A3b fibres.....	13
Table C.1	– Dimensional requirements specific to A3c fibres .....	14
Table C.2	– Mechanical requirements specific to A3c fibres.....	14
Table C.3	– Transmission requirements specific to A3c fibres .....	15
Table C.4	– Environmental exposure tests.....	15
Table C.5	– Attributes measured .....	16
Table D.1	– Dimensional requirements specific to A3d fibres .....	17
Table D.2	– Mechanical requirements specific to A3d fibres.....	17
Table D.3	– Transmission requirements specific to A3d fibres.....	18
Table D.4	– Environmental exposure tests.....	18
Table D.5	– Attributes measured .....	19
Table E.1	– Dimensional requirements specific to A3e fibres .....	20
Table E.2	– Mechanical requirements specific to A3e fibres .....	20
Table E.3	– Transmission requirements specific to A3e fibres .....	21
Table E.4	– Environmental exposure tests.....	21
Table E.5	– Attributes measured .....	22
Table F.1	– Dimensional requirements specific to A3f fibres .....	23
Table F.2	– Mechanical requirements specific to A3f fibres .....	23
Table F.3	– Transmission requirements specific to A3f fibres .....	24
Table F.4	– Environmental exposure tests .....	24
Table F.5	– Attributes measured .....	25
Table G.1	– Dimensional requirements specific to A3g fibres .....	26
Table G.2	– Mechanical requirements specific to A3g fibres.....	26
Table G.3	– Transmission requirements specific to A3g fibres.....	27
Table G.4	– Environmental exposure tests .....	27
Table G.5	– Attributes measured .....	28

## INTERNATIONAL ELECTROTECHNICAL COMMISSION

## OPTICAL FIBRES –

**Part 2-30: Product specifications –  
Sectional specification for category A3 multimode fibres**

## FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

International Standard IEC 60793-2-30 has been prepared by subcommittee 86A: Fibres and cables, of IEC technical committee 86: Fibre optics.

This fourth edition cancels and replaces the third edition published in 2012 and constitutes a technical revision.

This edition includes the following significant technical changes with respect to the previous edition:

- specified test specimen length and measurement details for core diameter and  $NA_{ff}$  measurements have been added.
- two new sub-categories have been added
- $NA_{th}$  is replaced by  $NA_{ff}$

The text of this standard is based on the following documents:

FDIS	Report on voting
86A/1661/FDIS	86A/1662/RVD

Full information on the voting for the approval of this standard can be found in the report on voting indicated in the above table.

This publication has been drafted in accordance with the ISO/IEC Directives, Part 2.

A list of all parts of the IEC 60793 series can be found, under the general title *Optical fibres*, on the IEC website.

The committee has decided that the contents of this publication will remain unchanged until the stability date indicated on the IEC web site under "<http://webstore.iec.ch>" in the data related to the specific publication. At this date, the publication will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

A bilingual version of this publication may be issued at a later date.

**ITeCh STANDARD PREVIEW**  
**(standards.iteh.ai)**

**IMPORTANT – The 'colour inside' logo on the cover page of this publication indicates that it contains colours which are considered to be useful for the correct understanding of its contents. Users should therefore print this document using a colour printer.**

## OPTICAL FIBRES –

### Part 2-30: Product specifications – Sectional specification for category A3 multimode fibres

#### 1 Scope

This part of IEC 60793-2 is applicable to sub-categories A3a, A3b, A3c, A3d, A3e, A3f and A3g. These fibres are used or can be incorporated in different information transmission equipment, other applications employing similar light transmitting techniques as well as fibre optic cables.

Three types of requirements apply to these fibres:

- general requirements, as defined in IEC 60793-2;
- specific requirements common to the category A3 multimode fibres covered in this standard and which are given in Clause 3;
- particular requirements applicable to the individual sub-categories or specific applications (e.g. automotive or industrial applications), which are defined in the normative sub-category annexes.

**ITeh STANDARD PREVIEW**

#### 2 Normative references (standards.iteh.ai)

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60793-1-20, *Optical fibres – Part 1-20: Measurement methods and test procedures – Fibre geometry*

IEC 60793-1-21, *Optical fibres – Part 1-21: Measurement methods and test procedures – Coating geometry*

IEC 60793-1-22, *Optical fibres – Part 1-22: Measurement methods and test procedures – Length measurement*

IEC 60793-1-30, *Optical fibres – Part 1-30: Measurement methods and test procedures – Fibre proof test*

IEC 60793-1-31, *Optical fibres – Part 1-31: Measurement methods and test procedures – Tensile strength*

IEC 60793-1-40, *Optical fibres – Part 1-40: Measurement methods and test procedures – Attenuation*

IEC 60793-1-41, *Optical fibres – Part 1-41: Measurement methods and test procedures – Bandwidth*

IEC 60793-1-43, *Optical fibres – Part 1-43: Measurement methods and test procedures – Numerical aperture*



IEC 60793-1-46, *Optical fibres – Part 1-46: Measurement methods and test procedures – Monitoring of changes in optical transmittance*

IEC 60793-1-50, *Optical fibres – Part 1-50: Measurement methods and test procedures – Damp heat (steady state) tests*

IEC 60793-1-51, *Optical fibres – Part 1-51: Measurement methods and test procedures – Dry heat (steady state) tests*

IEC 60793-1-52, *Optical fibres – Part 1-52: Measurement methods and test procedures – Change of temperature tests*

IEC 60793-2, *Optical fibres –Part 2: Product specifications – General*

IEC TR 62048:2014, *Optical fibres – Reliability – Power law theory*

### 3 Specifications

#### 3.1 General

The fibre shall consist of a glass core and a plastic cladding in accordance with the definition in IEC 60793-2. For sub-categories A3f and A3g, a glass inner cladding between core and cladding is present.

#### 3.2 Dimensional requirements

Relevant dimensional attributes and measurement methods are given in Table 1.

Dimensional requirements common to all sub-categories are indicated in Table 2.

Table 3 lists additional dimensional attributes that shall be specified for each sub-category.

**Table 1 – Relevant dimensional attributes and measurement methods**

Attributes	Measurement methods
Core diameter <sup>a</sup>	IEC 60793-1-20
Core non-circularity	IEC 60793-1-20
Inner glass cladding <sup>b</sup>	IEC 60793-1-20
Cladding diameter	IEC 60793-1-20
Core-cladding concentricity error	IEC 60793-1-20
Coating diameter	IEC 60793-1-21
Fibre length	IEC 60793-1-22
<sup>a</sup> Core diameter is specified at 850 nm ± 10 nm with a test specimen length of 2,0 m ± 0,2 m and a threshold value $k_{CORE}$ which is defined in each sub-category (see IEC 60793-1-20:2001, Method B).	
<sup>b</sup> Only relevant for sub-categories A3f and A3g	

**Table 2 – Dimensional requirements common to all category A3 fibres**

Attributes	Unit	Limits
Fibre length	km	<sup>a</sup>
<sup>a</sup> Length requirements vary and should be agreed between supplier and customer.		

**Table 3 – Additional dimensional attributes required for each sub-category**

Attributes
Core diameter
Core non-circularity
Inner glass cladding <sup>a</sup>
Cladding diameter
Core-cladding concentricity error
Coating diameter
<sup>a</sup> Only relevant for sub-categories A3f and A3g

**3.3 Mechanical requirements**

Relevant mechanical attributes and test methods are given in Table 4.

Requirements to be specified for each sub-category are listed in Table 5.

**Table 4 – Relevant mechanical attributes and test methods**

Attributes	Test methods
Tensile strength	IEC 60793-1-31 (0,5 m specimen length) Strain rate 3 %/min to 5 %/min
Proof test	IEC 60793-1-30

**Table 5 – Mechanical requirements to be specified for each sub-category**

Attribute	Unit
Proof stress level	GPa

**3.4 Transmission requirements**

Relevant transmission attributes and measurement methods are given in Table 6.

Additional attributes required in the sub-categories are listed in Table 7.

**Table 6 – Relevant transmission attributes and measurement methods**

Attributes	Measurement methods
Attenuation coefficient <sup>a</sup>	IEC 60793-1-40
Modal bandwidth <sup>a</sup>	IEC 60793-1-41
Numerical aperture (NA <sub>ff</sub> ) <sup>a,b</sup>	IEC 60793-1-43
Change of optical transmission	IEC 60793-1-46
<sup>a</sup> When measuring attenuation, modal bandwidth and numerical aperture, the appropriate launching conditions should be applied as specified in the corresponding measurement methods (IEC 60793-1-40, IEC 60793-1-41 and IEC 60793-1-43).	
<sup>b</sup> Numerical aperture (NA <sub>ff</sub> ) is specified at 850 nm with a test specimen length of 2,0 m ± 0,2 m, and a threshold value, k <sub>NA</sub> defined in each sub-category.	

**Table 7 – Additional transmission attributes required for each sub-category**

Attributes
Attenuation coefficient
Modal bandwidth
Numerical aperture

### 3.5 Environmental requirements

Relevant environmental attributes and test methods are given in Table 8.

**Table 8 – Relevant environmental attributes and test methods**

Attributes	Test methods
Damp heat tests	IEC 60793-1-50
Dry heat tests	IEC 60793-1-51
Change of temperature tests	IEC 60793-1-52

## Annex A (normative)

### Specifications for sub-category A3a multimode fibres

#### A.1 General

Clauses A.2 to A.5 contain particular requirements applicable to A3a fibres. Common requirements, repeated here for ease of reference from the sectional specification, are noted by an entry in the “Reference” column.

#### A.2 Dimensional requirements

Table A.1 contains dimensional requirements specific to A3a fibres.

**Table A.1 – Dimensional requirements specific to A3a fibres**

Attributes	Unit	Limits	Reference
Core diameter <sup>a</sup>	µm	200 ± 8	3.2 Table 1
Core non-circularity	%	≤ 6	3.2
Cladding diameter	µm	300 ± 30	3.2
Core-cladding concentricity error	µm	≤ 20	3.2
Coating diameter	µm	900 ± 50	3.2
Fibre length	km	See 3.2	3.2
<sup>a</sup> Using $k_{CORE}$ of 0,5			

#### A.3 Mechanical requirements

Table A.2 contains mechanical requirements specific to A3a fibres.

**Table A.2 – Mechanical requirements specific to A3a fibres**

Attribute	Unit	Limit	Reference
Proof stress level	GPa	≥ 0,345	3.3
NOTE The normative proof test stress value of 0,345 GPa equals about 0,5 % strain or about 11,7 N force (for the largest allowed core diameter). For the relation between these different units, see IEC TR 62048:2014, 7.4.			

#### A.4 Transmission requirements

Table A.3 contains transmission requirements specific to A3a fibres.